Paints and varnishes — Determination of resistance to liquids —

Part 4: Spotting methods

The European Standard EN ISO 2812-4:2007 has the status of a British Standard

ICS 87.040



National foreword

This British Standard was published by BSI. It is the UK implementation of EN ISO 2812-4:2007. This standard, together with BS EN ISO 2812-1:2007 and BS EN ISO 2812-3:2007, supersedes BS EN ISO 2812-1:1995, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/10, Test methods for paints.

A list of organizations represented on STI/10 can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2007

 \odot BSI 2007

ISBN 978 0 580 50474 7

Amendments issued since publication

Amd. No.	Date	Comments

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN ISO 2812-4

January 2007

ICS 87.040

English Version

Paints and varnishes - Determination of resistance to liquids - Part 4: Spotting methods (ISO 2812-4:2007)

Peintures et vernis - Détermination de la résistance aux liquides - Partie 4: Méthodes à la tache (ISO 2812-4:2007)

Beschichtungsstoffe - Bestimmung der Beständigkeit gegen Flüssigkeiten - Teil 4: Tropf-/Fleckverfahren (ISO 2812-4:2007)

This European Standard was approved by CEN on 23 December 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This document (EN ISO 2812-4:2007) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2007, and conflicting national standards shall be withdrawn at the latest by July 2007.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of ISO 2812-4:2007 has been approved by CEN as EN ISO 2812-4:2007 without any modifications.

INTERNATIONAL STANDARD

ISO 2812-4

First edition 2007-01-15

Paints and varnishes — Determination of resistance to liquids —

Part 4: Spotting methods

Peintures et vernis — Détermination de la résistance aux liquides — Partie 4: Méthodes à la tache



Contents		Page
Fore	eword	
1	Scope	
2	Normative references	1
3	Principle	
4	Apparatus	2
5	Test substances	
6	Sampling	2
7	Test panels	2
8	Procedure	2
9	Evaluation	3
10	Precision	3
11	Test report	4
Anno	ex A (informative) Examples of test substances	
	liography	

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2812-4 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

ISO 2812 consists of the following parts, under the general title *Paints and varnishes* — *Determination of resistance to liquids*:

- Part 1: Immersion in liquids other than water
- Part 2: Water immersion method
- Part 3: Method using an absorbent medium
- Part 4: Spotting methods
- Part 5: Temperature-gradient oven method

Paints and varnishes — Determination of resistance to liquids —

Part 4: **Spotting methods**

1 Scope

This part of ISO 2812 specifies spotting methods for determining the resistance of an individual layer or multilayer system of coating materials to the effects of liquids or paste-like products.

These methods enable the testers to determine the effects of the test substance on the coating and, if necessary, to assess the damage to the substrate.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1513, Paints and varnishes — Examination and preparation of samples for testing

ISO 1514, Paints and varnishes — Standard panels for testing

ISO 2808, Paints and varnishes — Determination of film thickness

ISO 3270, Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing

ISO 4628-1, Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 1: General introduction and designation system

ISO 4628-2, Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 2: Assessment of degree of blistering

ISO 15528, Paints, varnishes and raw materials for paints and varnishes — Sampling

3 Principle

A coated test panel is exposed to a test substance using the spotting method. The effects of the exposures are assessed in accordance with agreed criteria.

4 Apparatus

Ordinary laboratory equipment and the following apparatus.

- **4.1 Pipette**, suitable for applying approximately 0,1 ml droplets of test substance.
- **4.2 Burette**, 50 ml, for applying test substances.
- **4.3 Petri dishes** with 60 mm diameter and 20 mm rim.

5 Test substances

One or more test substances, as agreed between interested parties, shall be used. Examples of test substances are given in Annex A.

6 Sampling

Take a representative sample of the coating material to be tested, in accordance with ISO 15528.

Pretest each sample in accordance with ISO 1513 and prepare it for further testing (see 7.2).

7 Test panels

7.1 Substrate

Unless otherwise agreed, use test panels conforming to the requirements of ISO 1514, with dimensions of approximately $150 \text{ mm} \times 100 \text{ mm}$ and a thickness of 0.7 mm to 1.0 mm.

7.2 Preparation and coating

Prepare each test panel as described in ISO 1514 and then coat it by the specified application method with the product or system under test. Dry (or stove) and age (if applicable) each coated test panel for the specified time under specified conditions.

7.3 Coating thickness

Determine the dry film thickness of the coating, in micrometres, using one of the non-destructive methods specified in ISO 2808.

8 Procedure

8.1 Conditioning of the test panels

Immediately before testing, condition the test panels for at least 16 h under standard conditions as specified in ISO 3270, i.e. (23 ± 2) °C and (50 ± 5) % relative humidity.

8.2 Test conditions

Carry out the test at the standard temperature specified in ISO 3270, i.e. (23 \pm 2) °C.

8.3 Determination

8.3.1 Method A — Horizontal test panel

Perform the test in duplicate.

Place the test panel horizontally. When using liquid test substances, apply them to the test panel with a pipette, making sure that the droplets do not touch one another and that the distance to the edges of the panel is at least 12 mm. Then immediately cover the test areas with the Petri dishes.

When using highly viscous or paste-like test substances, apply about 0,5 cm³ of each substance to the test panel and cover the areas with Petri dishes.

The test duration shall be agreed between the interested parties and should reflect the end use of the coating.

8.3.2 Method B — Inclined test panel

Perform the test in duplicate.

Place the test panel in a collecting vessel at an angle of 30° to the horizontal. With the burette, and at intervals of 1 s to 2 s, apply droplets of the liquid test substance to the upper section of the test panel, close to the centre of the panel, over a period of 10 min. The substance will flow down the test panel into the collecting vessel.

9 Evaluation

After the test period has expired, wipe the test panel with dry cotton wool. Clean off any dried residue of aqueous test substances under running water, and clean off the dried residue of any other test substances with a solvent that does not attack the coating.

Evaluate only the area which has been in direct contact with the test substance.

Immediately assess the test panel for blistering as specified in ISO 4628-2 and in comparison with the non-exposed areas of the panel. Rate any visible alterations as specified in ISO 4628-1.

Unless otherwise agreed, reassess the exposed areas after 24 h.

Further tests on the exposed and non-exposed areas of the test panel may be performed (e.g., cross-cut test, hardness test, etc.) to determine the changes resulting from the effects of the test substances.

If the substrate of the test piece is to be examined for visible alterations, remove the coating using the specified procedure.

If the results of the evaluation of the duplicate determinations differ significantly, repeat the determination, again in duplicate.

Report the results of all determinations, including any repeat determinations.

10 Precision

No details are currently available for the repeatability limit (r) and reproducibility limit (R).

11 Test report

The test report shall contain at least the following information:

- a) all information necessary for identification of the coating tested, including the manufacturer, trade name, batch number, etc;
- b) a reference to this International Standard (ISO 2812-4:2006);
- c) details of the test panels, including:
 - 1) the material (including thickness) and surface pretreatment of the substrate;
 - 2) the application method for applying the sample coating to the substrate, including the drying time and drying conditions for all layers; where applicable, ageing conditions before the test;
 - the dry film thickness of the coating, in micrometres, including the measuring method chosen in ISO 2808;
- d) the method used (A or B), including:
 - 1) the specification of the test substances;
 - 2) the duration of the test;
 - the temperature;
- e) result(s) of the assessment, as indicated in Clause 9;
- f) the name of the person who conducted the test;
- g) any deviations from the procedure specified;
- h) any unusual features (anomalies) observed during the test;
- i) the date of the test.

Annex A (informative)

Examples of test substances

A.1 General

A range of fuels and chemicals that are typically used as test substances for automotive coatings is given in A.2, A.3 and A.4. Other test liquids may be used for testing both automotive and other coatings.

Use only analytical grade chemicals.

A.2 Fuels and operating fluids for the automotive industry

- **A.2.1 FAM test substance**, conforming to the requirements of DIN 51604-1, DIN 51604-2 or DIN 51604-3.
- **A.2.2 Diesel fuel**, conforming to the requirements of EN 590.
- **A.2.3** Premium gasoline, conforming to the requirements of EN 228.
- **A.2.4 Bio-diesel**, conforming to the requirements of EN 14214.
- A.2.5 Engine oil.
- A.2.6 Hypoid gearbox oil.
- A.2.7 Hydraulic oil.
- A.2.8 Automatic transmission oil.
- A.2.9 Brake fluid.
- A.2.10 Radiator anti-freeze.
- A.2.11 Body sealing compound.
- A.2.12 Cavity sealing compound.
- A.2.13 Windscreen-washer fluid.
- A.2.14 Cold cleaner.

A.3 Laboratory chemicals

- A.3.1 Ethanol.
- A.3.2 Isopropanol.
- **A.3.3** Sodium hydroxide solution, with a mass fraction of 5 % sodium hydroxide.
- A.3.4 Hydrochloric acid solution, with a mass fraction of 10 % hydrochloric acid.

- **A.3.5** Sulfurous acid solution, with a mass fraction of 6 % sulfurous acid.
- **A.3.6** Sulfuric acid solution, with a mass fraction of 10 % sulfuric acid.
- **A.3.7** Sulfuric acid solution, with a mass fraction of 36 % sulfuric acid.
- **A.3.8** Water, conforming to the requirements of Grade 3 of ISO 3696.

A.4 Biological substances

A.4.1 Resin, consisting of:

— rosin 50 % (mass fraction)

— pine oil 50 % (mass fraction).

A.4.2 Fall-out test substance, consisting of:

e.g. formic acid47 % (mass fraction)

— tannic acid 24 % (mass fraction)

— albumin 5 % (mass fraction)

— honey 24 % (mass fraction).

A.4.3 Gum arabic, e.g. acacia gum.

A.4.4 Rosin.

A.4.5 Simulated bird droppings: pancreatin, 1:1 diluted with water of grade 3 in accordance with ISO 3696.

Pancreatin may be ground in a mortar, if agreed between the interested parties. If the pancreatin is ground, this shall be stated in the test report.

Bibliography

- [1] ISO 3696, Water for analytical laboratory use Specification and test methods
- [2] EN 228, Automotive fuels Unleaded petrol Requirements and test methods
- [3] EN 590, Automotive fuels Diesel Requirements and test methods
- [4] EN 14214, Automotive fuels Fatty acid methyl esters (FAME) for diesel engines Requirements and test methods
- [5] DIN 51604-1, FAM testing fluid for polymer materials; composition and requirements
- [6] DIN 51604-2, Methanolic FAM testing fluid for polymer materials; composition and requirements
- [7] DIN 51604-3, Methanolic lower layer FAM testing fluid for polymer materials; composition and requirements

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at http://www.bsi-global.com.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.

Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.

Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at http://www.bsi-global.com/bsonline.

Further information about BSI is available on the BSI website at http://www.bsi-global.com.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means—electronic, photocopying, recording or otherwise—without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.

BSI 389 Chiswick High Road London W4 4AL