

Extenders for paints Specifications and methods of test —

Part 2: Barytes (natural barium sulfate)

The European Standard EN ISO 3262-2:1998 has the status of a
British Standard

ICS 87.060.10

National foreword

This British Standard is the English language version of EN ISO 3262-2:1998. It is identical with ISO 3262-2:1998. Together with the other Parts of BS EN ISO 3262, it will supersede BS 1795:1976 which is declared obsolescent.

The UK participation in its preparation was entrusted to Technical Committee STI/1, Pigments, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

Attention is drawn to the fact that CEN and CENELEC standards normally include an annex which lists normative references to international publications with their corresponding European publications. The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled "International Standards Correspondence Index", or by using the "Find" facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, the EN ISO title page, page 2, the ISO title page, pages ii to iv, pages 1 to 4, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard, having been prepared under the direction of the Sector Board for Materials and Chemicals, was published under the authority of the Standards Board and comes into effect on 15 September 1998

© BSI 04-1999

ISBN 0 580 30494 9

Contents

	Page
National foreword	Inside front cover
Foreword	2
Foreword	iii
Text of ISO 3262-2	1

ICS 87.060.10

Descriptors: See ISO document

English version

Extenders for paints — Specifications and methods of test — Part 2: Baryte (natural barium sulfate)

(ISO 3262-2:1998)

Matières de charge pour peintures —
Spécifications et méthodes d'essai —
Partie 2: Barytine (sulfate de baryum naturel)
(ISO 3262-2:1998)

Füllstoffe für Beschichtungsstoffe —
Anforderungen und Prüfverfahren —
Teil 2: Schwerspat (natürliches Bariumsulfat)
(ISO 3262-2:1998)

This European Standard was approved by CEN on 21 June 1998.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

Foreword

The text of the International Standard ISO 3262-2:1998 has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 298 "Pigments and extenders", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 1999, and conflicting national standards shall be withdrawn at the latest by January 1999.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 3262-2:1998 has been approved by CEN as a European Standard without any modification.

NOTE Normative references to International Standards are listed in Annex ZA (normative).

INTERNATIONAL
STANDARD

ISO
3262-2

First edition
1998-07-01

**Extenders for paints — Specifications and
methods of test —**

**Part 2:
Barytes (natural barium sulfate)**

*Matières de charge pour peintures — Spécifications et méthodes d'essai —
Partie 2: Barytine (sulfate de baryum naturel)*



Contents

	Page
Foreword	iii
1 Scope	1
2 Normative references	1
3 Definition	1
4 Requirements and test methods	1
5 Sampling	1
6 Determination of BaSO ₄ content	1
7 Determination of matter soluble in hydrochloric acid	3
8 Test report	4
Annex ZA (normative) Normative references to international publications with their relevant European publications	Inside back cover
Table 1 — Essential requirements	1
Table 2 — Conditional requirements	2

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 3262-2 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 2, *Pigments and extenders*.

Together with the other parts (see below), this part of ISO 3262 cancels and replaces ISO 3262:1975, which has been technically revised. Part 1 comprises the definition of the term extender and a number of test methods that are applicable to most extenders, whilst part 2 and the following parts specify requirements and, where appropriate, particular test methods for individual extenders.

At present, the following parts of ISO 3262 are published or in preparation, under the general title *Extenders for paints — Specifications and methods of test*:

- *Part 1: Introduction and general test methods;*
- *Part 2: Barytes (natural barium sulfate);*
- *Part 3: Blanc fixe;*
- *Part 4: Whiting;*
- *Part 5: Natural crystalline calcium carbonate;*
- *Part 6: Precipitated calcium carbonate;*
- *Part 7: Dolomite;*
- *Part 8: Natural clay;*
- *Part 9: Calcined clay;*
- *Part 10: Natural talc/chlorite in lamellar form;*
- *Part 11: Natural talc, in lamellar form, containing carbonates;*
- *Part 12: Muscovite-type mica;*
- *Part 13: Natural quartz (ground);*
- *Part 14: Cristobalite;*
- *Part 15: Vitreous silica;*
- *Part 16: Aluminium hydroxides;*
- *Part 17: Precipitated calcium silicate;*
- *Part 18: Precipitated sodium aluminium silicate;*
- *Part 19: Precipitated silica;*
- *Part 20: Fumed silica;*
- *Part 21: Silica sand (unground natural quartz);*
- *Part 22: Diatomaceous earth (kieselguhr).*

Descriptors: Paints, extenders, barium sulphate, specifications, materials specifications, tests.

1 Scope

This part of ISO 3262 specifies requirements and corresponding methods of test for baryte (natural barium sulfate).

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 3262. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 3262 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 787-2:1981, *General methods of test for pigments and extenders — Part 2: Determination of matter volatile at 105 °C.*

ISO 787-3:1979, *General methods of test for pigments and extenders — Part 3: Determination of matter soluble in water — Hot extraction method.*

ISO 787-7:1981, *General methods of test for pigments and extenders — Part 7: Determination of residue on sieve — Water method — Manual procedure.*

ISO 787-9:1981, *General methods of test for pigments and extenders — Part 9: Determination of pH value of an aqueous suspension.*

ISO 787-14:1973, *General methods of test for pigments — Part 14: Determination of resistivity of aqueous extract.*

ISO 842:1984, *Raw materials for paints and varnishes — Sampling.*

ISO 3262-1:1997, *Extendors for paints — Specifications and methods of test — Part 1: Introduction and general test methods.*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods.*

ISO 4793:1980, *Laboratory sintered (fritted) filters — Porosity grading, classification and designation.*

3 Definition

For the purposes of this part of ISO 3262, the following definition applies:

3.1

barytes

naturally occurring barium sulfate, BaSO₄

4 Requirements and test methods

For barytes complying with this part of ISO 3262, the essential requirements are specified in Table 1 and the conditional requirements are listed in Table 2.

5 Sampling

Take a representative sample of the product to be tested, as described in ISO 842.

6 Determination of BaSO₄ content¹⁾

6.1 General

For barytes, the acid-insoluble barium, calculated as barium sulfate, is taken as the BaSO₄ content.

6.2 Reagents

Use only reagents of recognized analytical grade and only water of at least grade 3 purity as defined in ISO 3696.

6.2.1 Hydrochloric acid, concentrated, approximately 37 % (m/m), $\rho \approx 1,19$ g/ml.

6.2.2 Hydrochloric acid, diluted 1 + 3.

Add 1 part by volume of concentrated hydrochloric acid (**6.2.1**) to 3 parts by volume of water.

Table 1 — Essential requirements

Characteristic	Unit	Requirement		Test method
		Grade A	Grade B	
BaSO ₄ content, min.	% (m/m)	90	80	See clause 6
Residue on 45 µm sieve, max.	% (m/m)	0,5	See Table 2	ISO 787-7
Matter volatile at 105 °C, max.	% (m/m)	0,5		ISO 787-2 ^a
Loss on ignition, max.	% (m/m)	1	See Table 2	ISO 3262-1
Matter soluble in water, max.				ISO 787-3
pH value of aqueous suspension		6 to 10		ISO 787-9
^a By agreement between the interested parties, test portions other than 10 g may be used.				

¹⁾ This determination includes strontium sulfate.

Table 2 — Conditional requirements

Characteristic	Unit	Requirement		Test method
		Grade A	Grade B	
Residue on 45 µm sieve	% (m/m)	See Table 1	To be agreed between the interested parties	ISO 787-7
Particle size distribution (instrumental method)	% (m/m)	To be agreed between the interested parties ^a		
Colour		To be agreed between the interested parties		ISO 3262-1
Lightness				To be agreed between the interested parties ^b
Loss on ignition	% (m/m)	See Table 1	To be agreed between the interested parties	ISO 3262-1
Matter soluble in water				ISO 787-3
Resistivity of aqueous extract	Ω m	To be agreed between the interested parties		ISO 787-14
Matter soluble in hydrochloric acid	% (m/m)			See clause 7

^a A general description of a sedimentation method using X-ray absorption is given in EN 725-5:1996, *Advanced technical ceramics — Methods of test for ceramic powders — Part 5: Determination of the particle size distribution*.

^b Test method in preparation.

6.2.3 Hydrochloric acid, diluted 1 + 100.

Add 1 part by volume of concentrated hydrochloric acid (6.2.1) to 100 parts by volume of water.

6.2.4 Sulfuric acid, diluted 1 + 9.

Add 1 part by volume of concentrated sulfuric acid [approximately 96 % (m/m), $\rho \approx 1,84$ g/ml] slowly to 9 parts by volume of water.

6.2.5 Ammonia solution, diluted 1 + 3.

Add 1 part by volume of concentrated ammonia solution [approximately 32 % (m/m), $\rho \approx 0,880$ g/ml] to 3 parts by volume of water.

6.2.6 Bromine water, saturated solution.**6.2.7 Sodium carbonate solution**, 10 g/l.

Dissolve 1 g of anhydrous sodium carbonate in 100 ml of water.

6.2.8 Hydroxylammonium chloride solution, 50 g/l.**6.2.9 Fusion mixture**

Mix equal parts by mass of sodium carbonate and potassium carbonate.

6.3 Apparatus

Use ordinary laboratory apparatus and glassware, together with the following:

6.3.1 Platinum crucible, with lid.

6.3.2 Sintered-silica filter crucible, pore size index P 16 (pore diameter 10 µm to 16 µm) as defined in ISO 4793.

6.3.3 Air oven, capable of being maintained at (105 ± 2) °C.

6.3.4 Muffle furnace.**6.4 Procedure**

Weigh, to the nearest 1 mg, approximately 1 g (m_0) of the test sample, previously dried in accordance with ISO 787-2, into a 400 ml beaker. Add 100 ml of 1 + 100 hydrochloric acid (6.2.3) and allow to stand for 1 h at room temperature, with occasional stirring. Filter through a 125 mm fine-textured ashless filter paper and wash once with 10 ml of hot water.

Transfer the filter paper to the platinum crucible (6.3.1), dry and ignite. Add 5 g of the fusion mixture (6.2.9), mix well, and then place a further 1 g of the fusion mixture on top of the mixture in the crucible.

Heat the crucible, fitted with its lid, at bright-red heat (800 °C to 900 °C) for 15 min. Then allow the crucible and lid to cool.

Measure 100 ml of hot water into a 600 ml beaker (A) and place into it the crucible and lid. Heat gently for 15 min to extract the melt, then, using clean nickel or other suitable tongs, remove the crucible and lid. Rinse the crucible and lid and tongs with water into the beaker. Remove any white residue from the crucible with a rubber-tipped glass stirring rod and rinse again with water.

Measure 95 ml of water and 5 ml of concentrated hydrochloric acid (6.2.1) into a second 600 ml beaker (B) and put the crucible and lid into it.

Allow the aqueous fusion extract in beaker A to settle on a warm surface for 30 min. Decant the hot solution through a 125 mm fine-textured ashless filter paper. Wash the precipitate three times by decantation, using 10 ml portions of hot sodium carbonate solution (6.2.7) and transfer to the filter paper. Repeat the washing three times with 5 ml portions of sodium carbonate solution and discard the washings.

Remove the crucible and lid from the acid solution in beaker B and wash down with water into the beaker. Transfer this solution to beaker A, in which the melt was extracted, and add to it the filter paper and residue. Cover the beaker with a watch glass, boil for 5 min and then filter through a 125 mm filter paper into beaker B, which originally contained the acid solution. Wash the filter papers thoroughly six times with 10 ml portions of hot water.

Transfer the filter papers to the platinum crucible and dry, then ignite at dull-red heat (650 °C to 700 °C) and add 2 g of the fusion mixture (6.2.9) to the crucible. Heat the crucible and lid at bright-red heat for 15 min. Allow the crucible and lid to cool.

Measure 50 ml of hot water into beaker A and place into it the crucible and lid. Heat gently for 15 min to extract the melt. Filter through a 125 mm filter paper. Wash twice with 5 ml portions of sodium carbonate solution (6.2.7) and discard the washings.

Add to beaker A (which still contains the crucible and lid), 20 ml of 1 + 3 hydrochloric acid (6.2.2) and 50 ml of hot water. Filter this solution through the filter paper, and collect the filtrate in beaker B, which contained the original acid extract. Wash six times with 5 ml portions of hot water. Dilute the filtrate with water to approximately 300 ml.

Boil the solution in beaker B to remove carbon dioxide and then add bromine water (6.2.6) until a yellow colour appears. Add ammonia solution (6.2.5) in slight excess and boil to precipitate the hydroxides of iron, aluminium and manganese. Filter the precipitate on a fast filter paper and wash three times with hot ammonia solution (6.2.5), collecting the filtrate and washings in a 400 ml beaker.

Dissolve the precipitate in another beaker with approximately 8 ml of 1 + 3 hydrochloric acid (6.2.2) and 12 ml of water to which a few drops of hydroxylammonium chloride solution (6.2.8) have been added. Dilute this solution to 50 ml, add bromine water (6.2.6) until a yellow colour appears and then add ammonia solution (6.2.5) in slight excess. Filter and wash the precipitate as described above. Add the first and second filtrates to beaker B and acidify the whole with 1 + 3 hydrochloric acid (6.2.2) against methyl orange, adding approximately 4 ml of acid in excess.

Heat the acid extract to boiling. Stir and add slowly 20 ml of hot dilute sulfuric acid (6.2.4). Allow the covered beaker to stand on a warm surface for 3 h.

Filter through a sintered-silica filter crucible (6.3.2) which has been previously dried in the air oven (6.3.3) at (105 ± 2) °C, cooled in a desiccator and weighed. Wash four times with 10 ml portions of hot water. Dry in the air oven at (105 ± 2) °C for 15 min and heat in the muffle furnace (6.3.4) at a temperature of 500 °C to 600 °C to constant mass. Allow to cool in a desiccator and weigh the precipitate to the nearest 0,1 mg (m_1).

Alternatively, the precipitate may be filtered on a filter paper, placed in a platinum crucible, dried and ignited before cooling in the desiccator.

6.5 Expression of results

Calculate the barium compound content $w(\text{BaSO}_4)$, expressed as a percentage by mass of barium sulfate, using the equation

$$w(\text{BaSO}_4) = \frac{m_1}{m_0} \times 100$$

where

m_0 is the mass, in grams, of the test portion;

m_1 is the mass, in grams, of the precipitate.

7 Determination of matter soluble in hydrochloric acid

7.1 Reagents

During the analysis, use only reagents of recognized analytical grade and only water of at least grade 3 purity as defined in ISO 3696.

7.1.1 Hydrochloric acid, approximately 25 % (m/m), $\rho \approx 1,125$ g/ml.

7.2 Apparatus

Use ordinary laboratory apparatus and glassware, together with the following:

7.2.1 Membrane filter, pore size 0,8 μm .

7.2.2 *Air oven*, capable of being maintained at $(105 \pm 2) ^\circ\text{C}$.

7.3 Procedure

Weigh, to the nearest 0,1 mg, approximately 10 g (m_0) of the test sample into a 600 ml beaker.

Add 50 ml of water and, carefully, approximately 50 ml of hydrochloric acid (7.1.1). Cover the beaker with a watch glass and boil the solution for 15 min.

Dry the membrane filter (7.2.1) in the air oven (7.2.2) at $(105 \pm 2) ^\circ\text{C}$ to constant mass, cool in a desiccator to room temperature and weigh it to the nearest 0,1 mg (m_1). Then filter the solution through it. Wash the residue on the filter eight times with hot distilled water. Dry the residue on the filter in the air oven at $(105 \pm 2) ^\circ\text{C}$ for about 1 h. Allow to cool in a desiccator to room temperature and weigh to the nearest 0,1 mg (m_2).

7.4 Expression of results

Calculate the matter soluble in hydrochloric acid $w(\text{MS}_{\text{HCl}})$, expressed as a percentage by mass, using the equation

$$w(\text{MS}_{\text{HCl}}) = 100 - \left(\frac{m_2 - m_1}{m_0} \times 100 \right)$$

where

m_0 is the mass, in grams, of the test portion;

m_1 is the mass, in grams, of the dried membrane filter;

m_2 is the mass, in grams, of the dried membrane filter plus the residue.

8 Test report

The test report shall contain at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this part of ISO 3262 (ISO 3262-2);
- c) the results of the tests and whether or not the product complies with the relevant specification limits;
- d) any deviation from the test methods specified;
- e) the dates of the tests.

Annex ZA (normative)**Normative references to international publications with their relevant European publications**

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN</u>	<u>Year</u>
ISO 787-2	1981	General methods of test for pigments and extenders — Part 2: Determination of matter volatile at 105 degrees C	EN ISO 787-2	1995
ISO 787-3	1979	General methods of test for pigments and extenders — Part 3: Determination of matter soluble in water — Hot extraction method	EN ISO 787-3	1995
ISO 787-9	1981	General methods of test for pigments and extenders — Part 9: Determination of pH value of aqueous suspension	EN ISO 787-9	1995
ISO 3262-1	1997	Extenders for paints — Specifications and methods of test — Part 1: Introduction and general test methods	EN ISO 3262-1	1998
ISO 3696	1987	Water for analytical laboratory use — Specification and test methods	EN ISO 3696	1995

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.