

Extenders for paints — Specifications and methods of test —

Part 22: Flux-calcined kieselguhr

The European Standard EN ISO 3262-22:2001 has the status of a British Standard

ICS 87.060.10

National foreword

This British Standard is the official English language version of EN ISO 3262-22:2001. It is identical with ISO 3262-22:2001.

The UK participation in its preparation was entrusted to Technical Committee STI/1, Pigments, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled “International Standards Correspondence Index”, or by using the “Find” facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, EN ISO foreword, ISO title page, pages ii to iv, pages 1 to 4, the Annex ZA page and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard, having been prepared under the direction of the Sector Policy and Strategy Committee for Materials and Chemicals, was published under the authority of the Standards Policy and Strategy Committee on 21 December 2001

© BSI 21 December 2001

ICS 87.060.10

English version

Extenders for paints - Specifications and methods of test - Part 22: Flux-calcined kieselguhr (ISO 3262-22:2001)

Matières de charge pour peintures - Spécifications et
méthodes d'essai - Partie 22: Kieselguhr, flux-calciné (ISO
3262-22:2001)

Füllstoffe für Beschichtungsstoffe - Anforderungen und
Prüfverfahren - Teil 22: Kieselgur, fluxcalciniert (ISO 3262-
22:2001)

This European Standard was approved by CEN on 15 October 2001.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of the International Standard ISO 3262-22:2001 has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 298 "Pigments and extenders", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2002, and conflicting national standards shall be withdrawn at the latest by April 2002.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 3262-22:2001 was approved by CEN as a European Standard without any modification.

NOTE Normative references to International Standards are listed in annex ZA (normative).

INTERNATIONAL
STANDARD

ISO
3262-22

First edition
2001-10-15

**Extenders for paints — Specifications and
methods of test —**

Part 22:

Flux-calcined kieselguhr

Matières de charge pour peintures — Spécifications et méthodes d'essai —

Partie 22: Kieselguhr, flux-calciné



Reference number
ISO 3262-22:2001(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 3262 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 3262-22 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 2, *Pigments and extenders*.

Together with the other parts (see below), this part of ISO 3262 cancels and replaces ISO 3262:1975, which has been technically revised. Part 1 comprises the definition of the term extender and a number of test methods that are applicable to most extenders, whilst part 2 and the following parts specify requirements and, where appropriate, particular test methods for individual extenders.

ISO 3262 consists of the following parts, under the general title *Extenders for paints — Specifications and methods of test*:

- *Part 1: Introduction and general test methods*
- *Part 2: Barytes (natural barium sulfate)*
- *Part 3: Blanc fixe*
- *Part 4: Whiting*
- *Part 5: Natural crystalline calcium carbonate*
- *Part 6: Precipitated calcium carbonate*
- *Part 7: Dolomite*
- *Part 8: Natural clay*
- *Part 9: Calcined clay*
- *Part 10: Natural talc/chlorite in lamellar form*
- *Part 11: Natural talc, in lamellar form, containing carbonates*
- *Part 12: Muscovite-type mica*
- *Part 13: Natural quartz (ground)*
- *Part 14: Cristobalite*
- *Part 15: Vitreous silica*
- *Part 16: Aluminium hydroxides*
- *Part 17: Precipitated calcium silicate*
- *Part 18: Precipitated sodium aluminium silicate*

EN ISO 3262-22:2001

- *Part 19: Precipitated silica*
- *Part 20: Fumed silica*
- *Part 21: Silica sand (unground natural quartz)*
- *Part 22: Flux-calcined kieselguhr*

Extenders for paints — Specifications and methods of test —

Part 22:

Flux-calcined kieselguhr

1 Scope

This part of ISO 3262 specifies requirements and corresponding methods of test for flux-calcined kieselguhr.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 3262. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 3262 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 787-2:1981, *General methods of test for pigments and extenders — Part 2: Determination of matter volatile at 150 °C*

ISO 787-3:2000, *General methods of test for pigments and extenders — Part 3: Determination of matter soluble in water — Hot extraction method*

ISO 787-5:1980, *General methods of test for pigments and extenders — Part 5: Determination of oil absorption value*

ISO 787-7:1981, *General methods of test for pigments and extenders — Part 7: Determination of residue on sieve — Water method — Manual procedure*

ISO 787-9:1981, *General methods of test for pigments and extenders — Part 9: Determination of pH value of an aqueous suspension*

ISO 3262-1:1997, *Extenders for paints — Specifications and methods of test — Part 1: Introduction and general test methods*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*

ISO 5794-1:1994, *Rubber compounding ingredients — Silica, precipitated, hydrated — Part 1: Non-rubber tests*

ISO 15528:2000, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Term and definition

For the purposes of this part of ISO 3262, the following term and definition apply.

3.1

flux-calcined kieselguhr

siliceous material of diatomaceous origin

NOTE Flux-calcined kieselguhr is produced by adding soda ash or salt to the siliceous material and heating to 1 148 °C. The loss on ignition is then up to 3 % Na₂O and K₂O. Flux calcining converts the iron oxide to a colourless glassy phase and produces a white rather than pink diatomaceous earth.

4 Requirements and test methods

For flux-calcined kieselguhr complying with this part of ISO 3262 the essential requirements are specified in Table 1 and the conditional requirements are listed in Table 2.

Table 1 — Essential requirements

Characteristic	Unit	Requirement		Test method
		Grade		
		A	B	
Silica content, SiO ₂ , min.	% by mass	85		See clause 6
Loss on ignition, max.	% by mass	0,5		ISO 3262-1
pH-value of aqueous suspension		7,0 to 10,5		ISO 787-9
Matter soluble in water, max.	% by mass	1,0		ISO 787-3
Matter volatile at 105 °C, max.	% by mass	0,5		ISO 787-2
Residue on sieve, max. 63 µm 45 µm	% by mass	1	0	ISO 787-7
		10	0,1	
Specific surface area	m ² /g	max. 3	min. 3	ISO 5794-1
Oil absorption value	g/100 g	120 to 200	90 to 140	ISO 787-5

Table 2 — Conditional requirements

Characteristic	Unit	Requirement	Test method
Lightness		To be agreed between the interested parties	To be agreed between the interested parties ^a
^a Test method in preparation.			

5 Sampling

Take a representative sample of the product to be tested, as described in ISO 15528.

6 Determination of silica content

6.1 Reagents

Use only reagents of recognized analytical grade and only water of at least grade 3 purity as defined in ISO 3696.

6.1.1 Sulfuric acid, diluted 1 + 1.

Add 1 part by volume of concentrated sulfuric acid, approximately 96 % by mass, $\rho \approx 1,84$ g/ml, slowly to 1 part by volume of water.

6.1.2 Hydrofluoric acid, concentrated, approximately 40 % by mass, $\rho \approx 1,13$ g/ml.

6.2 Apparatus

Use ordinary laboratory apparatus and glassware, together with the following:

6.2.1 Platinum dish.

6.2.2 Muffle furnace, capable of being maintained at up to $(1\ 000 \pm 25)$ °C.

6.3 Procedure

6.3.1 Number of determinations

Carry out the determination in duplicate.

6.3.2 Test portion

Weigh, to the nearest 1 mg, approximately 2 g of the sample (see clause 5), previously dried at 105 °C in accordance with ISO 787-2, into the tared platinum dish (6.2.1).

6.3.3 Determination

Ignite the test portion in the platinum dish in the muffle furnace (6.2.2) at $(1\ 000 \pm 25)$ °C to constant mass (m_1) and allow to cool in a desiccator containing phosphorus pentoxide.

Add approximately 1 ml of sulfuric acid (6.1.1). Heat the platinum dish gently until fuming ceases and then continue the heating at 900 °C for 15 min in the muffle furnace. Remove from the furnace, cool in the desiccator and weigh (m_2).

Add to the residue in the platinum dish (6.2.1) 5 ml of hydrofluoric acid (6.1.2) and evaporate to a syrup, taking care to avoid loss by spitting. Cool the platinum dish and wash the sides down with small quantities of water. Then add a further 2 ml of hydrofluoric acid and evaporate to dryness. Heat the residue on a hot-plate until white fumes are no longer evolved, then ignite in the muffle furnace at 900 °C for 15 min. Remove the dish from the furnace, allow to cool in the desiccator and weigh (m_3).

6.4 Expression of results

Calculate the silica content, $w(\text{SiO}_2)$, expressed as a percentage by mass, using the equation:

$$w(\text{SiO}_2) = \frac{(m_2 - m_3)}{m_1} \times 100$$

where

m_1 is the mass, in grams, of the test portion after ignition;

m_2 is the mass, in grams, after treatment with sulfuric acid and igniting;

m_3 is the mass, in grams, after treatment with hydrofluoric acid and igniting.

Calculate the mean of the two determinations and report the result to the nearest 0,1 %.

7 Test report

The test report shall contain at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this part of ISO 3262 (ISO 3262-22);
- c) the results of the tests and whether or not the product complies with the relevant specification limits;
- d) any deviation from the test methods specified;
- e) the dates of the tests.

Annex ZA (normative)

Normative references to International Publications with their relevant European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

NOTE Where an International Publication has been modified by common modifications, indicated by (mod.), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
ISO 787-2	1981	General methods of test for pigments and extenders — Part 2: Determination of matter volatile at 105 °C	EN ISO 787-2	1995
ISO 787-3	1979	General methods of test for pigments and extenders — Part 3: Determination of matter soluble in water — Hot extraction method	EN ISO 787-3	1995
ISO 787-5	1980	General methods of test for pigments and extenders — Part 5: Determination of oil absorption value	EN ISO 787-5	1995
ISO 787-9	1981	General methods of test for pigments and extenders — Part 9: Determination of pH value of an aqueous suspension	EN ISO 787-9	1995
ISO 3262-1	1997	Extenders for paints – Specifications and methods of test — Part 1: Introduction and general test methods	EN ISO 3262-1	1998
ISO 3696	1987	Water for analytical laboratory use — Specifications and test methods	EN ISO 3696	1995
ISO 15528	2000	Paints, varnishes and raw materials for paints and varnishes — Sampling	EN ISO 15528	2000

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.