

Hardmetals — Determination of transverse rupture strength (ISO 3327:2009)

ICS 77.040.10; 77.160

National foreword

This British Standard is the UK implementation of EN ISO 3327:2009. It supersedes BS EN 23327:1993 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/65, Sintered metal components.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2009

© BSI 2009

ISBN 978 0 580 56453 6

Amendments/corrigenda issued since publication

Date	Comments

EUROPEAN STANDARD

EN ISO 3327

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2009

ICS 77.160; 77.040.10

Supersedes EN 23327:1993

English Version

Hardmetals - Determination of transverse rupture strength (ISO 3327:2009)

Métaux-durs - Détermination de la résistance à la flexion
(ISO 3327:2009)

Hartmetalle - Bestimmung der Biegebruchfestigkeit (ISO 3327:2009)

This European Standard was approved by CEN on 16 April 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 3327:2009) has been prepared by Technical Committee ISO/TC 119 "Powder metallurgy" in collaboration with Technical Committee CEN/SS M11 "Powder metallurgy" the secretariat of which is held by CMC.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2009, and conflicting national standards shall be withdrawn at the latest by November 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 23327:1993.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 3327:2009 has been approved by CEN as a EN ISO 3327:2009 without any modification.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 3327 was prepared by Technical Committee ISO/TC 119, *Powder metallurgy*, Subcommittee SC 4, *Sampling and testing methods for hardmetals*.

This third edition cancels and replaces the second edition (ISO 3327:1982), which has been technically revised.

Hardmetals — Determination of transverse rupture strength

1 Scope

This International Standard specifies a method for the determination of the transverse rupture strength of hardmetals.

This method is applicable to hardmetals of negligible ductility. If it is used for hardmetals showing significant plastic deformation before breaking, incorrect results may be obtained. In such cases, the method may be used for comparison purposes only.

2 Symbols and designations

For the purposes of this document, the symbols, designations and units given in Table 1 apply.

Table 1 — Symbols and designations

Symbol	Designation	Unit
F	Force required to fracture the test piece	N
l	Distance between supports	mm
b	Width of test piece perpendicular to its height	mm
h	Height of test piece parallel to the direction of application of the test force	mm
k	Correction factor to compensate for the chamfer	—
R_a	Surface roughness	μm
R_{bm}	Transverse rupture strength	N/mm^2
d	Diameter of test piece (if a cylindrical test piece is used)	mm

3 Principle

Breaking a test piece lying freely on two supports by application of a force at the midpoint of the span, under conditions of short-term static application of the force.

4 Apparatus

4.1 Device for applying a force, capable of applying a uniformly increasing force with an accuracy of 1 % or better.

4.2 Three cylinders (rollers), of which two are freely lying support cylinders with a fixed distance between them and one is a freely lying force cylinder. The three cylinders shall be of equal diameter between 3,2 mm and 6 mm.

Alternatively, the force may be applied by a ball having a diameter of 10 mm. Loading of the test piece can only be made via three cylinders if a cylindrical test piece is used. Consequently, a ball is only applicable for test pieces having plane surfaces.

The support cylinders and the force cylinder or ball shall be made of tungsten carbide hardmetal which will not be visibly deformed by the applied force. The surface roughness R_a of the cylinders and the ball shall not be greater than 0,63 μm .

The support cylinders shall be mounted parallel, with a span between them of 30 mm \pm 0,5 mm for Type A test pieces and 14,5 mm \pm 0,5 mm for Type B or Type C test pieces. The measurement of the span used for the calculation shall be made to an accuracy of 0,1 mm for Type B or Type C test pieces and to an accuracy of 0,2 mm for Type A test pieces.

The mounting of the cylinders shall be such as to minimize deviations from parallelism of the support cylinders.

4.3 A suitable protective guard, surrounding the fixture for safety.

5 Test pieces

5.1 The test pieces shall be of rectangular (Type A or B) or cylindrical (Type C) cross-section and shall have the dimensions shown in Table 2.

Table 2 — Dimensions of test pieces

Dimensions in millimetres

Type	Length	Width/Diameter	Height
A	35 \pm 1	5 \pm 0,25	5 \pm 0,25
B	20 \pm 1	6,5 \pm 0,25	5,25 \pm 0,25
C	25 \pm 5	3,3 \pm 0,5	—

NOTE In general, Type B test pieces give strength values which are about 10 % to 20 % higher than those obtained using Type A test pieces, depending on the material tested and provided that they have the same surface conditions. The repeatability is similar for all types of test piece. Type C test pieces give strength values which are about 5 % – 10 % higher than Type B specimens whereas the increase of the strength values are material related.

5.2 The test pieces shall be ground on the four faces which are parallel to the length with a free-cutting diamond wheel, preferably resin bonded, using copious quantities of coolant. No pass shall exceed 0,01 mm and all grinding marks shall be parallel to the length. The amount taken off each face shall be not less than 0,1 mm and the surface roughness shall be $R_a \leq 0,4 \mu\text{m}$. The four long edges shall be chamfered to 0,15 mm to 0,2 mm at an angle of 45° and all grinding marks shall be parallel to the length. Type C test pieces shall be centreless ground to a surface roughness $R_a \leq 0,4 \mu\text{m}$.

5.3 It is also permitted to use test pieces in the as-sintered condition. Such test pieces shall have a chamfer of 0,4 mm to 0,5 mm at an angle of 45°, made before sintering to avoid flash. Bend strength results from as-sintered test pieces are generally significantly lower than those for ground test pieces.

Surface preparation is an important variable and should be standardized to ensure that consistent results are obtained.

5.4 The deviation from parallelism of opposite longitudinal sides, in both the longitudinal and transverse directions, shall not exceed 0,05 mm for each 10 mm length for as-sintered test pieces and 0,01 mm for each 10 mm length for ground test pieces. For round test pieces, opposite sides shall be parallel within 0,015 mm.

5.5 Width and height measurements used for calculation of the results shall be carried out at the middle of the test pieces to the nearest 0,01 mm.

5.6 The test pieces shall be free from visual surface cracks and structural defects.

6 Procedure

6.1 Place a test piece flat and centrally on the support cylinders so that its length is perpendicular to the lengths of the support cylinders. In the case of a Type B test piece, place its width on the support cylinders.

6.2 Bring the force cylinder or ball gradually into contact with the test piece.

The deviation of the line or the point of application of the force from the middle of the span shall not exceed 0,5 mm for Type A test pieces and 0,2 mm for Type B test pieces.

6.3 Increase the stress in the test piece at a uniform rate not exceeding 200 N/(mm²·s).

NOTE This corresponds to a force increasing at a maximum rate of 1 600 N/s for Type B and Type C test pieces and 600 N/s for Type A test pieces.

7 Expression of results

7.1 The transverse rupture strength R_{bm} , expressed in newtons per square millimetre, is given by the equation:

$$R_{bm} = \frac{3 \cdot k \cdot F \cdot l}{2 \cdot b \cdot h^2}$$

for rectangular test pieces.

Values of the chamfer correction factor, k , are given in Table 3.

Table 3 — Values of chamfer correction factor, k

Test piece type	Chamfer mm	Correction factor k
A	0,4 to 0,5	1,03
A	0,15 to 0,2	1,00
B	0,4 to 0,5	1,02
B	0,15 to 0,2	1,00

The transverse rupture strength R_{bm} , expressed in newtons per square millimetre, is given by the equation:

$$R_{bm} = \frac{8 \cdot F \cdot l}{\pi \cdot d^3}$$

for cylindrical test pieces.

NOTE The equation for calculating the transverse rupture strength does not take into account the effect of any plastic deformation that might occur.

7.2 Report the arithmetical mean of at least five transverse rupture strength determinations, round to the nearest 10 N/mm².

8 Test report

Since the test piece geometry and surface preparation can significantly affect the values of transverse rupture strength, it is important that the test report shall include the following information:

- a) a reference to this International Standard;
 - b) all details necessary for identification of the test sample;
 - c) the type of test piece and the method of preparation of its surface;
 - d) the method of applying the force;
 - e) the result obtained. The following additional subscripts shall be added to the symbol indicating transverse rupture strength, to indicate the surface condition, i.e. sintered (S) or ground (G):
 - for Type A test pieces: A30S or A30G,
 - for Type B test pieces: B15S or B15G,
 - for Type C test pieces: C15S or C15G
- EXAMPLES R_{bm30} (A30S), R_{bm30} (A30G);
- f) all operations not specified in this International Standard, or regarded as optional;
 - g) details of any occurrence which may have affected the result.

Bibliography

- [1] ROEBUCK, B. VAMAS Report No. 22, June 1996 (ISSN 1016-2186), B. *Bend Strength Measurements for Hardmetals, Part 1 Rationale and Results*
- [2] ROEBUCK, B. *Effect of Test Piece Geometry on the Bend Strength of Hardmetals*, 14th Int. Plansee Seminar '97, Reutte, Austria, V2, pp. 352-365
- [3] VAMAS Report, Part 2, *Analysis*, No. 24, 1997 (ISSN 1016-2186)

BSI - British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001 Email: orders@bsigroup.com You may also buy directly using a debit/credit card from the BSI Shop on the Website <http://www.bsigroup.com/shop>

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact Information Centre. Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048 Email: info@bsigroup.com

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001 Email: membership@bsigroup.com

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsigroup.com/BSOL>

Further information about BSI is available on the BSI website at <http://www.bsigroup.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright and Licensing Manager. Tel: +44 (0)20 8996 7070 Email: copyright@bsigroup.com