

*Incorporating
Amendment No. 1 to
BS ISO 3673-1:1996
(renumbers the BS ISO
as BS EN ISO
3673-1:2000)*

Plastics — Epoxy resins

Part 1: Designation

The European Standard EN ISO 3673-1:1999 has the status of a
British Standard

ICS 83.080.10

National foreword

This British Standard is the English language version of EN ISO 3673-1:1999, which is identical to ISO 3673-1:1996.

The UK participation in its preparation was entrusted to Technical Committee PRI/42, Fibre reinforced thermosetting plastics and prepregs, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Change of identifier

Wherever BS ISO 3673-1:1996 appears in this standard, it should be read as EN ISO 3673-1:1999.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled "International Standards Correspondence Index", or by using the "Find" facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, the EN ISO foreword, the ISO title page, page ii, pages 1 to 4, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments
10743	February 2000	Implements the European Standard

This British Standard, having been prepared under the direction of the Sector Board for Materials and Chemicals, was published under the authority of the Standards Board and comes into effect on 15 May 1997

© BSI 02-2000

ISBN 0 580 27292 3

ICS 83.080.10

English version

Plastics - Epoxy resins - Part 1: Designation (ISO 3673-1:1996)

Plastiques - Résines époxydes - Partie 1: Désignation (ISO
3673-1:1996)

Kunststoffe - Epoxidharze - Teil 1: Einstufung (ISO 3673-
1:1996)

This European Standard was approved by CEN on 2 July 1999.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of the International Standard from Technical Committee ISO/TC 61 "Plastics" of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2000, and conflicting national standards shall be withdrawn at the latest by February 2000.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 3673-1:1996 has been approved by CEN as a European Standard without any modification.

NOTE: Normative references to International Standards are listed in annex ZA (normative).

INTERNATIONAL STANDARD

ISO
3673-1

Second edition
1996-12-15

Plastics — Epoxy resins —

Part 1: Designation

Plastiques — Résines époxydes —

Partie 1: Désignation



Reference number
ISO 3673-1:1996(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 3673-1 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee 12, *Thermosetting materials*.

This second edition cancels and replaces the first edition (ISO 3673-1:1980), of which it constitutes a minor (editorial) revision.

ISO 3673 consists of the following parts, under the general title *Plastics — Epoxy resins*:

- *Part 1: Designation*
- *Part 2: Preparation of test specimens and determination of properties*

Plastics – Epoxy resins – Part 1: Designation

1 Scope

This part of ISO 3673 specifies a method of designation for epoxy resins.

The objective of this designation method is to allocate to each commercial product a group of digits, called the "designation", giving in a coded form certain information on the product: chemical base, approximate values of main properties and the nature of modifiers, solvents or additives.

Thus, all products having similar characteristics and therefore likely to have the same uses will have the same designation, so aiding users in their choice, provided that manufacturers quote the designation in their data sheets.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 3673. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 3673 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 1183: 1987, *Plastics — Method for determining the density and relative density of non-cellular plastics.*

ISO 1675: 1985, *Plastics — Liquid resins — Determination of density by the pycnometer method.*

ISO 3001:—¹⁾, *Plastics — Epoxy compounds — Determination of epoxy equivalent.*

ISO 3219: 1993, *Plastics — Polymers/resins in the liquid state or as emulsions or dispersions — Determination of viscosity using a rotational viscometer with defined shear rate.*

3 Designation system

Epoxy resins shall be designated by the symbol "EP" for epoxide, followed by a group of five digits (corresponding to principal properties), followed by a space, followed by three digits (corresponding to secondary properties) as follows:

- each digit, except the first two digits which shall be taken together, shall correspond to one of the properties given in table 1,
- the position (I and II, III, IV, etc.) of each digit in the group shall indicate the property to which it refers,
- each digit for a property shall indicate the class (1, 2, 3 etc.) corresponding to a certain range of values of the property, as given in table 1.

NOTE 1 Not every combination of property classification will be achievable in practice. Note also that the designation of a material will not correspond, except by chance, with a horizontal row.

NOTE 2 The value of each property in positions III, IV and VI to be taken into consideration in defining the class to which a product belongs is the mean value found in manufacture and normally given in data sheets.

¹⁾ To be published. (Revision of ISO 3001:1978)

Because of inevitable variations in manufacturing conditions, a product supposedly belonging to a given class for one property incidentally may fall, in some cases:

- in the adjacent lower class if the mean value of this property is near the lower limit of the designation class;
- in the adjacent upper class if the mean value is near the upper limit.

4 Designation of an epoxy resin

In accordance with the designation system described in clause 3, an epoxy resin shall be designated by a group of five digits followed by a group of three digits, the two groups being separated by a space.

The first group of five digits refers to the principal properties and the final three digits to the secondary properties.

If one of the properties, usually designated by a digit indicating the class, is not specified, a small " x " shall be inserted at the appropriate place in the designation.

EXAMPLE An epoxy resin designated by EP 03361 3xx is a resin based on an aliphatic glycidyl ether (or ester), viscosity between 1 Pa·s and 5 Pa·s, epoxy equivalent between 291 g/mol et 525 g/mol, without any modifiers, density between 1,15 g/cm³ and 1,19 g/cm³, without any indication for additives and without any special indications.

NOTE 3 The designation does not exempt the manufacturer from giving in his literature the actual values of the designated properties, together with manufacturing and measurement tolerances.

5 Special properties

These properties shall not be included in the designation but shall be given, if necessary, in actual values only, and reference made to the relevant International Standards for the test methods.

Examples of such properties are electrical properties and optical properties, both of which will be the subjects of future International Standards.

Table 1 — Characteristics of epoxy resins

Designation order number	I and II	III	IV	V	VI	VII	VIII
Characteristic	Principal properties				Secondary properties		
	Chemical base ¹⁾	Viscosity at 23 °C and shear rate of 1 s ⁻¹	Epoxy equivalent	Organic modifiers or solvents	Density at 23 °C	Additives ²⁾	Special indications ²⁾
Units	—	Pa.s (= 10 P)	g/mol	—	g/cm ³	—	—
Method Class	—	ISO 3219	ISO 3001	—	ISO 1675 ISO 1183	—	—
x	Not designated (ND)	ND	ND	ND	ND	ND	ND
1	Bisphenol A/ glycidyl ethers	≤0,25	≤115	None	<1,10	None	Material with specified burning characteristics ³⁾
2	Aromatic glycidyl ethers (or esters)	>0,25 to 1	116 to 150	Reactive agent	1,10 to 1,14	Fillers	Content of hydrolysable chlorine below 0,2 %
3	Aliphatic glycidyl ethers (or esters)	>1 to 5	151 to 175	Non-reactive agent	1,15 to 1,19	Colorants (organic or inorganic)	Low tendency to crystallize
4	Cycloaliphatic glycidyl ethers (or esters)	>5 but fluid	176 to 210	Organic solvent	1,20 to 1,29	Fillers and colorants	Water-soluble
5	Epoxy-cycloolefins	Semi-solid	211 to 290	Reactive agent and organic solvent	1,30 to 1,39	Emulsifying agents	Heat-resistant
6	Epoxy-novolac	Solid	291 to 525	Non-reactive agent and organic solvent	1,40 to 1,59	—	—
7	Halogenated epoxides	Thixotropic	526 to 1 025	—	1,60 to 1,80	—	—
8	Other glycidic nitrogenous compounds	—	1 026 to 2 050	—	>1,80	—	—
9	Heterocyclic compounds	—	>2 050	—	—	—	—
10	Epoxy-olefins	—	—	—	—	—	—
11	Bisphenol glycidyl ethers other than class 1	—	—	—	—	—	—

1) The chemical basis shall be indicated by two digits:

- class x is written xx
- class 1 is written 01
- class 2 is written 02 etc.
- class 11 is written 11

For a mixture with equal proportions of two resins of different chemical base, the symbol "xx" (not designated) may be used.

2) The most important one shall be indicated, if there are several additives or special indications.

3) For a complete assessment of the fire performance of a material, information is required on at least the following properties:

- ignitability
- combustibility
- flammability
- heat release
- smoke release
- noxious-gas release

Annex ZA (normative)**Normative references to international publications
with their relevant European publications**

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN</u>	<u>Year</u>
ISO 1675	1985	Plastics - Liquid resins - Determination of density by the pycnometer method	EN ISO 1675	1998
ISO 3001	1999	Plastics - Epoxy compounds - Determination of epoxy equivalent	EN ISO 3001	1999
ISO 3219	1993	Plastics - Polymers/resins in the liquid state or as emulsions or dispersions - Determination of viscosity using a rotational viscometer with defined shear rate	EN ISO 3219	1994

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.