

Leather — Chemical tests — Determination of matter soluble in dichloromethane and free fatty acid content

ICS 59.140.30

National foreword

This British Standard is the UK implementation of EN ISO 4048:2008. It supersedes BS EN ISO 4048:1998 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear, leather and coated fabrics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 May 2008

© BSI 2008

ISBN 978 0 580 57418 4

Amendments/corrigenda issued since publication

Date	Comments

English Version

Leather - Chemical tests - Determination of matter soluble in dichloromethane and free fatty acid content (ISO 4048:2008)

Cuir - Essais chimiques - Dosage des matières solubles dans le dichlorométhane et des acides gras libres (ISO 4048:2008)

Leder - Chemische Prüfungen - Bestimmung der in Dichlormethan löslichen Substanzen und des freien Fettsäuregehalts (ISO 4048:2008)

This European Standard was approved by CEN on 3 February 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This document (EN ISO 4048:2008) has been prepared by Technical Committee CEN/TC 289 "Leather", the secretariat of which is held by UNI in collaboration with Technical Committee ISO/TC IULTCS "International Union of Leather Technologists and Chemists Societies".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2008, and conflicting national standards shall be withdrawn at the latest by August 2008.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 4048:1998.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4048/IUC 4 was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, in collaboration with the Chemical Tests Commission of the International Union of Leather Technologists and Chemists Societies (IUC Commission, IULTCS), in accordance with the Agreement on technical co-operation between ISO and CEN (Vienna Agreement). It is based on IUC 4 originally published in *J. Soc. Leather Trades Chemists*, 49, p. 10, 1965, and declared an official method of the IULTCS in 1965.

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for sampling and the testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

This second edition cancels and replaces the first edition (ISO 4048:1977), which has been technically revised.

.....

Leather — Chemical tests — Determination of matter soluble in dichloromethane and free fatty acid content

1 Scope

This International Standard specifies a method for the determination of the substances in leather which are soluble in dichloromethane. This method is applicable to all types of leather.

Not all fatty and similar substances can be extracted from leather with organic solvents; they may be in part soluble and partly bound to the leather. On the other hand, the solvent can dissolve non-fatty substances, e.g. sulfur and impregnants, both of which cause difficulty in the determination of the acid value and saponification value of the fat.

This International Standard includes two techniques for extraction of the fatty substances: 1) extraction using the Soxhlet apparatus; and 2) extraction using a pressurized extraction system.

As the extraction is frequently done in conjunction with determination of the free fatty acid content of the leather, a suitable procedure for determination of the free fatty acids extracted by this method is included.

The apparatus and technique described in this method are also suitable for the extraction by solvents other than dichloromethane (although the temperature conditions may need to be varied for high pressure extraction).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 4044, *Leather — Chemical tests — Preparation of chemical test samples*

ISO 4098, *Leather — Chemical tests — Determination of water-soluble matter, water-soluble inorganic matter and water-soluble organic matter*

ISO 4684, *Leather — Chemical tests — Determination of volatile matter*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

extractable substances

fats and other soluble matter which can be extracted from leather with dichloromethane

3.2

free fatty acid content

fatty acid content of the extractable substances as determined by this method and expressed as oleic acid

4 Principle

The prepared leather is extracted with dichloromethane. The solvent is evaporated from the extract which is then dried at 102 °C. Subsequent analysis can then be performed on the resulting extract to determine the free fatty acid content of the leather.

5 Reagents

During analysis, use only reagents of a recognized analytical grade.

5.1 Determination of substances soluble in dichloromethane.

5.1.1 Dichloromethane, boiling point 38 °C to 40 °C, freshly distilled and kept in a dark flask over calcium oxide. Dichloromethane that has been allowed to stand for a long time should be tested as follows for the presence of any hydrochloric acid which may have formed.

- Shake 10 ml of dichloromethane with 1 ml of 0,1 mol/l silver nitrate solution.
- If the silver nitrate solution becomes turbid, the dichloromethane should be redistilled and kept in a dark flask over calcium oxide.

WARNING — Dichloromethane has toxic properties and should be used with caution. The supplier's handling instructions should be followed.

5.2 Determination of free fatty acid content of the leather.

5.2.1 Mixed solvent, a mixture of equal volumes of diethyl ether and 95 % (volume fraction) ethanol, neutralized with 0,1 mol/l sodium hydroxide (phenolphthalein is used as the indicator).

If, for any purpose, other solvents are used, the solvent or solvents used shall be stated in the test report.

5.2.2 Sodium hydroxide, 0,1 mol/l standard solution.

5.2.3 Phenolphthalein indicator solution, 10 g/l prepared in 95 % (volume fraction) ethanol.

In determinations on dark coloured solutions, observation of the end point of the titration may be facilitated either by the substitution of thymolphthalein or alkali blue 6B for phenolphthalein. Alternatively, 1 ml of a 0,1 % solution of methylene blue can be added to each 100 ml of the phenolphthalein solution before titration. Phenolphthalein should be used as the preferred option if possible.

NOTE Dichloromethane which has been used for this analysis can be recovered and reused after distillation.

6 Apparatus

6.1 Soxhlet extraction apparatus, including an extraction flask of suitable capacity and a condenser, or **pressurized extraction system**, including extraction flask of suitable capacity.

6.2 Filter paper thimbles, of suitable sizes, or suitable **glass filter bells**.

6.3 Oven, capable of being maintained at (102 ± 2) °C.

6.4 Analytical balance, capable of weighing to an accuracy of 0,1 mg.

6.5 Desiccator, suitable for cooling the extraction vessels.

6.6 Glass wool or cotton wad.

If a cotton wad is used, this shall be pre-extracted in dichloromethane (5.1.1).

7 Sampling and preparation of the samples

If possible, sample in accordance with ISO 2418. If sampling in accordance to ISO 2418 is not possible, then details about sampling shall be given in the test report. Grind the leather in accordance with ISO 4044.

Samples shall be analysed in duplicate.

8 Procedure

8.1 General

Weigh accurately using the analytical balance (6.4) ($10 \pm 0,1$) g of the prepared sample and press evenly into the filter paper thimble or glass bell (6.2). Cover the leather with a thin layer of glass wool or cotton wad (6.6).

Dry the extraction flask (see 6.1) with four glass beads in it by heating for 30 min at (102 ± 2) °C. Weigh after cooling in a desiccator (6.5).

NOTE If determination of free fatty acids is not being carried out, boiling chips may be used as an alternative to glass beads.

Two techniques for extraction of the fatty substances are described: 1) extraction using the Soxhlet apparatus (see 8.2); and 2) extraction using a pressurized extraction system (see 8.3). In the case of dispute, the Soxhlet extraction shall be used.

8.2 Extraction using the Soxhlet apparatus

8.2.1 Place the sample prepared in 8.1 into the extraction apparatus and begin continuous extraction with the dichloromethane (see 8.2.2); then after at least 30 changes of solvent, distil the dichloromethane from the flask containing the extract (see 8.2.3).

Dry the extract for 4 h in the oven (6.3), maintained at (102 ± 2) °C (if drops of water are visible before drying, add 1 ml to 2 ml of ethanol). Weigh after cooling for 30 min in a desiccator.

Repeat the drying, cooling and weighing operations, but with drying periods of 1 h, until either the further loss in mass does not exceed 0,01 g, or the total drying time equals 8 h (see 8.2.3).

8.2.2 Dichloromethane (5.1.1) can also dissolve non-fatty materials from the leather, for example sulfur. (The presence of sulfur is recognizable by a yellow precipitate in the flask.) As sulfur causes difficulty, it can be removed in the following way.

- Dissolve the extract in the smallest possible quantity of diethyl ether and filter through a little cotton wad (6.6) into a previously weighed flask.
- After thoroughly washing out the cotton wad filter with ether, remove the ether from the extract in the flask by distillation over a hot water bath from which any flame has previously been removed.
- If the sulfur should precipitate again, repeat the procedure.
- After the diethyl ether has been distilled off, dry the flask and residue and weigh.

8.2.3 The extract may be used for analysis, for example to determine acid and saponification values of the fats, or to determine the free fatty acid content of the leather.

NOTE After removal of the solvent, the extracted leather can be used for determination of water soluble substances in accordance with ISO 4098.

8.3 Extraction using a pressurized extraction system

Place the sample prepared in 8.1 above in the extraction apparatus, and fill with dichloromethane as appropriate. The sample should be boiled at 180 °C for 40 min. Following this, sufficient dichloromethane should be distilled from the flask containing the extract to ensure that the extraction thimble is clear of the solvent. Extraction should then continue for a further 40 min with the distilled dichloromethane percolating through the leather sample and collecting in the extraction vessel below. Finally, the remainder of the dichloromethane should be distilled from the flask containing the extract (see 8.2.2 and 8.2.3).

Dry the extract for 4 h in the oven (6.3), maintained at (102 ± 2) °C (if drops of water are visible before drying, add 1 ml to 2 ml of ethanol). Weigh after cooling for 30 min in a desiccator.

Repeat the drying, cooling and weighing operations, but with drying periods of 1 h until either the further loss in mass does not exceed 0,01 g, or the total drying time equals 8 h (see 8.2.3).

8.4 Determination of free fatty acid content

To the flask containing the weighed extract obtained from 8.2 or 8.3, add 40 ml of mixed solvent (5.2.1). Add 0,5 ml of phenolphthalein indicator solution (5.2.3) to the flask.

Dissolve the extract completely by rotating the flask, warming if necessary. Cool, and rapidly titrate the solution with 0,1 mol/l sodium hydroxide solution (5.2.2), shaking vigorously during the titration, until a slight but definite colour change, persisting for 15 s, shows that the end point has been reached.

9 Expression of results

9.1 Calculation

The matter extractable in dichloromethane is given, as a percentage by mass on dry matter, by the formula:

$$\frac{m_1}{m_0} \times 100 \times F$$

where

m_0 is the mass, in grams, of the test sample;

m_1 is the mass, in grams, of the extract;

and

$$F = \frac{100}{100 - w}$$

where w is the mass fraction of the volatile matter (based on ISO 4684), in percent.

The free fatty acid content, expressed as oleic acid, $C_{18}H_{34}O_2$, is given, as a percentage by mass, by the formula:

$$\frac{V}{m_0} \times 2,82 \times F$$

where

V is the volume, in millilitres, of the 0,1 mol/l sodium hydroxide solution used in the titration;

m_0 is the mass, in grams, of the test sample;

and 1 ml of 0,1 mol/l sodium hydroxide (5.2.2) will titrate 0,028 2 g of oleic acid.

9.2 Repeatability

The results of duplicate determinations carried out by the same operator in the same laboratory should not differ by more than 0,2 %, calculated on the original mass of the leather.

9.3 Reproducibility

The results of two determinations carried out by different operators in different laboratories on the same sample should not differ by more than 0,5 %, calculated on the original mass of the leather.

10 Test report

The test report shall include the following details:

- a) reference to this International Standard (ISO 4048);
- b) complete identification of the sample;
- c) the characteristics of the solvent(s) used;
- d) the mean value of the results obtained, to one decimal place;
- e) details of any deviations from the test procedure or circumstances that may have affected the results;
- f) details of the extraction procedure used.

Annex A (informative)

Comparison on five leather samples

A comparison has been carried out on five leather samples to determine if differences are observed between the pressurized extraction system and standard Soxhlet extraction.

Results are illustrated in Table A.1 and are an average of triplicate analysis.

Table A.1 — Comparison data on five different leather samples

Sample	Soxhlet		Pressurized solvent extraction	
	Grease removed %	Standard deviation	Grease removed %	Standard deviation
Tan	5,4	0,2	5,3	0,2
Beige	3,3	0,1	3,2	0,3
Light blue	10,0	0,2	9,4	0,1
Dark blue	12,3	0,2	12,0	0,2
Black	9,6	0,1	9,1	0,2

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.

BSI
389 Chiswick High Road
London
W4 4AL