

BS EN ISO 4629-2:2016



BSI Standards Publication

Binders for paints and varnishes — Determination of hydroxyl value

Part 2: Titrimetric method using a catalyst
(ISO 4629-2:2016)

National foreword

This British Standard is the UK implementation of EN ISO 4629-2:2016.

The UK participation in its preparation was entrusted to Technical Committee STI/3, Paints, media and related products.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 88348 4

ICS 87.060.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2016.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN ISO 4629-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2016

ICS 87.060.20

English Version

Binders for paints and varnishes - Determination of
hydroxyl value - Part 2: Titrimetric method using a catalyst
(ISO 4629-2:2016)

Liants pour peintures et vernis - Détermination de
l'indice d'hydroxyle - Partie 2: Méthode titrimétrique
utilisant un catalyseur (ISO 4629-2:2016)

Bindemittel für Beschichtungsstoffe - Bestimmung der
Hydroxylzahl - Teil 2: Verfahren mit Katalysator (ISO
4629-2:2016)

This European Standard was approved by CEN on 19 May 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 4629-2:2016) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2016, and conflicting national standards shall be withdrawn at the latest by December 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 4629-2:2016 has been approved by CEN as EN ISO 4629-2:2016 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	2
6 Apparatus	2
7 Sampling	3
8 Procedure	3
8.1 Number of determinations.....	3
8.2 Test portion.....	3
8.3 Determination.....	3
8.4 Blank test.....	4
8.5 Determination of acid value.....	4
9 Expression of results	4
10 Precision	4
10.1 Repeatability.....	4
10.2 Reproducibility.....	4
11 Test report	5
Bibliography	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 35, *Paints and varnishes*, Subcommittee SC 10, *Test methods for binders for paints and varnishes*.

ISO 4629 consists of the following parts, under the general title *Binders for paints and varnishes — Determination of hydroxyl value*:

- *Part 1: Titrimetric method without using a catalyst*
- *Part 2: Titrimetric method using a catalyst*

Introduction

There are several different methods standardized for determining the hydroxyl value of resins. The classic method using pyridine without a catalyst is specified in ISO 4629-1. The advantages of the method using a catalyst are the following:

- the solvents used are less hazardous to health;
- the solvent consumption is lower;
- the method is faster due to shorter reaction times;
- the end point of the titration is easier to see;
- polyols are more readily soluble.

Binders for paints and varnishes — Determination of hydroxyl value —

Part 2: Titrimetric method using a catalyst

1 Scope

This part of ISO 4629 specifies a titrimetric method for determining the hydroxyl value of resins, binders for paints and varnishes, primary alcohols, glycols and fats. Whether it can be applied for hydro carboxylic acids, phenolic hydroxyl groups, polyols such as trimethyl propane and substances containing aromatic groups have been activated for Friedel-Crafts acylation shall be decided on case-to-case basis.

Under the right conditions, the method is also applicable for determining the hydroxyl value of castor oil and its derivatives.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 660, *Animal and vegetable fats and oils — Determination of acid value and acidity*

ISO 2114:2000, *Plastics (polyester resins) and paints and varnishes (binders) — Determination of partial acid value and total acid value*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 4618, *Paints and varnishes — Terms and definitions*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

3.1

hydroxyl value

number of milligrams of potassium hydroxide (KOH) corresponding to hydroxyl groups that have been acetylated under specified test conditions in 1 g of the product tested

[SOURCE: ISO 4629-1:2016, 3.1]

4 Principle

The hydroxyl groups in polyols are acetylated with acetic anhydride. The excess acetic anhydride is titrated with alcoholic potassium hydroxide solution.

5 Reagents

During the analysis, use only reagents of recognized analytical grade and only water of at least grade 3 purity as specified in ISO 3696.

5.1 N-Methylpyrrolidone (NMP).

NOTE Commission chemists' workgroup validate methodologies using less dangerous substances such as dioxolane and other hetero cycles.

5.2 Potassium hydroxide solution, $c = 0,5$ mol/l in methanol.

Ethanol may also be used if the product to be tested is soluble in ethanol.

5.2.1 Preparation

Weigh, to the nearest 0,05 g, 28 g of potassium hydroxide, dissolve in the minimum quantity of water in a 1 000 ml one-mark flask, dilute to the mark with methanol and mix well.

5.2.2 Standardization

Weigh, to the nearest 0,01 g, 2,5 g of potassium hydrogen phthalate, previously dried at about 120 °C to constant mass and allowed to cool in a desiccator, into a 250 ml flask. Add 150 ml freshly boiled and cooled water and swirl until dissolved.

Titrate the potassium hydroxide solution prepared in [5.2.1](#), using phenolphthalein solution as indication, until a red coloration that remains for at least 10 s appears.

Calculate the actual concentration, c , in moles of hydroxyl ions (OH⁻) per litre, of the potassium hydroxide solution using [Formula \(1\)](#):

$$c = \frac{m}{V} \cdot \frac{1\,000}{204,22} \quad (1)$$

where

m is the mass, in grams, of potassium hydrogen phthalate taken;

V is the volume, in millilitres, of potassium hydroxide solution used for the titration;

204,22 is the relative molecular mass, in grams per mole, of potassium hydrogen phthalate.

5.3 Methyl ethyl ketone (MEK).

5.4 Demineralized water.

5.5 Acetylating reagent, make up a 10 % solution of acetic anhydride in NMP ([5.1](#)).

5.6 Catalyst solution, make up a 1 % (by mass) solution of 4-N-dimethylaminopyridine in NMP ([5.1](#)).

5.7 Indicator solution, make up a 1 % (by mass) solution of either thymolphthalein or 0,05 % (by mass) solution of phenolphthalein in NMP ([5.1](#)).

6 Apparatus

Ordinary laboratory equipment and glassware, together with the following.

- 6.1 Automatic titrator.
- 6.2 Analytical balance.
- 6.3 250 ml conical flask with ground joint.
- 6.4 50 ml motorized piston burette.
- 6.5 Hot plate.
- 6.6 Magnetic stirrer.

7 Sampling

Take a representative sample of the product to be tested, as specified in ISO 15528.

8 Procedure

8.1 Number of determinations

Carry out the determination in triplicate by titrating the sample potentiometrically or using a colour indicator.

8.2 Test portion

The initial sample mass required for the determination depends on the expected hydroxyl value and shall be calculated using [Formula \(2\)](#):

$$m = \frac{300}{HV_e} \quad (2)$$

where

m is the initial sample mass, in grams;

HV_e is the expected hydroxyl value, in milligrams of KOH per gram, of the product.

Weigh, to the nearest 1 mg, the test portion into the 250 ml conical flask ([6.3](#)).

8.3 Determination

Add 30 ml of catalyst solution ([5.6](#)) and 10 ml of acetylating reagent ([5.5](#)). Close the flask with the stopper and dissolve the sample by stirring and, if necessary, by heating the mixture. Then, while stirring continuously on the magnetic stirrer ([6.6](#)), allow the reaction to take place for at least 15 min at ambient temperature (23 ± 2) °C.

All products containing secondary OH-groups require a reaction time of at least 60 min, and that is also found to be the case for polyols containing secondary OH-groups.

Stop the reaction by adding 3 ml of demineralized water ([5.4](#)) and stir for a further 12 min.

All products containing secondary OH-groups require a hydrolysis time of at least 30 min.

Remove the flask from the stirrer, rinse the stopper and wall with methyl ethyl ketone ([5.3](#)), add two to three drops of indicator solution ([5.7](#)) and titrate with potassium hydroxide solution ([5.2](#)) until the colourless solution becomes blue (thymolphthalein) or pink (phenolphthalein).

8.4 Blank test

Carry out a blank test, following the same procedure, but omitting the test portion.

It shall be redetermined on a daily basis.

NOTE The value for the blank is around 40 ml.

8.5 Determination of acid value

Determine the acid value of the sample separately as specified in ISO 2114:2000, Method A. For determination of the acid value of animal and vegetable fats and oils, ISO 660 may be used.

9 Expression of results

Calculate the hydroxyl value, HV, in milligrams of KOH per gram, of the product using [Formula \(3\)](#):

$$HV = \frac{(V_0 - V_1) \cdot c \cdot 56,1}{m} + AV \quad (3)$$

where

- V_0 is the volume, in millilitres, of potassium hydroxide solution ([5.2](#)) required for the blank test ([8.4](#));
- V_1 is the volume, in millilitres, of potassium hydroxide solution ([5.2](#)) required for the determination ([8.3](#));
- c is the actual concentration, in moles per litre, of the potassium hydroxide solution ([5.2](#));
- 56,1 is the factor for the conversion of millilitres of potassium hydroxide, $c(\text{KOH}) = 1 \text{ mol/l}$, to milligrams of potassium hydroxide;
- m is the mass, in grams, of the test portion ([8.2](#));
- AV is the acid value ([8.5](#)), in milligrams of KOH per gram, of the product.

Report as the final result the hydroxyl value (individual values and mean) to the nearest 1 mg KOH/g.

10 Precision

10.1 Repeatability

Two determinations made consequently on the same day under repeatability conditions with different masses of the final sample shall not differ by more than 0,84 mg KOH/g for hydroxyl values less than 20 and not more than 1,72 mg KOH/g for hydroxyl values between 20 and 200.

10.2 Reproducibility

Two determinations made with the same sample under reproducibility conditions shall not differ by more than 1,36 mg KOH/g for hydroxyl values less than 20 and not more than 3,28 mg KOH/g for hydroxyl values between 20 and 200.

11 Test report

The test report shall contain at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this part of ISO 4629, i.e. ISO 4629-2;
- c) the result of the test as indicated in [Clause 9](#);
- d) the acetylation time;
- e) the type of titration: in the presence of a colour indicator (thymolphthalein or phenolphthalein) or potentiometric;
- f) any deviation from the test method specified;
- g) any unusual features (anomalies) observed during the test;
- h) the date of the test.

Bibliography

- [1] ISO 4629-1:2016, *Binders for paints and varnishes — Determination of hydroxyl value — Part 1: Titrimetric method without using a catalyst*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK