

BS EN ISO 5089:2016



BSI Standards Publication

# Textiles — Preparation of laboratory test samples and test specimens for chemical testing (ISO 5089:1977)

**National foreword**

This British Standard is the UK implementation of EN ISO 5089:2016. It is identical to ISO 5089:1977.

The UK participation in its preparation was entrusted to Technical Committee TCI/80, Chemical testing of textiles.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.  
Published by BSI Standards Limited 2016

ISBN 978 0 580 92496 5

ICS 59.080.01

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2016.

**Amendments/corrigenda issued since publication**

Date	Text affected
------	---------------

---

EUROPEAN STANDARD

**EN ISO 5089**

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2016

---

ICS 59.080.01

English Version

## Textiles - Preparation of laboratory test samples and test specimens for chemical testing (ISO 5089:1977)

Textiles - Préparation des échantillons réduits de laboratoire et des éprouvettes en vue des essais chimiques (ISO 5089:1977)

Textilien - Vorbereitung von Laborproben und Messproben zur chemischen Prüfung (ISO 5089:1977)

This European Standard was approved by CEN on 12 June 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

## **European foreword**

The text of ISO 5089:1977 has been prepared by Technical Committee ISO/TC 38 “Textiles” of the International Organization for Standardization (ISO) and has been taken over as EN ISO 5089:2016 by Technical Committee CEN/TC 248 “Textiles and textile products” the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2017, and conflicting national standards shall be withdrawn at the latest by January 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

### **Endorsement notice**

The text of ISO 5089:1977 has been approved by CEN as EN ISO 5089:2016 without any modification.

# Textiles — Preparation of laboratory test samples and test specimens for chemical testing

## 0 INTRODUCTION

In the methods given in this International Standard, the laboratory test samples are obtained by the combination of numerous small portions each drawn from a different part of the laboratory bulk sample. Therefore, any results obtained on test specimens from these samples will estimate the mean level in the laboratory bulk sample but will not indicate the variability of level from portion to portion of the laboratory bulk sample. Consequently it is appropriate to use this method in cases where it is desired to estimate the bulk composition, for example the proportions of different fibres in a blend, but it is not appropriate in cases where variability is important, for example in the determination of pH where the local value is significant, or in the determination of fungicides, where a high value in one area of the material does not compensate for a low value elsewhere. Nor may it be appropriate for use in determination of commercial mass values.

## 1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies methods of obtaining laboratory test samples of textile materials from laboratory bulk samples taken from a bulk source, and gives general directions for the preparation of test specimens of convenient size for chemical tests.

No provision for sampling from the bulk source is described since it is assumed that the laboratory bulk sample has been selected by a suitable procedure and is representative of the bulk source.

## 2 DEFINITIONS

**2.1 bulk source :** That quantity of material which is to be judged on the basis of one series of test results. This may comprise, for example, all the material in one delivery of cloth; all the cloth woven from a particular beam; a consignment of yarn; a bale or a group of bales of raw fibre.

**2.2 laboratory bulk sample :** That portion of the bulk source taken to be representative of the whole. The size and nature of the laboratory bulk sample should be sufficient to overcome adequately the variability of the bulk source and to facilitate ease of handling in the laboratory.

**2.3 laboratory test sample :** That portion of the laboratory bulk sample from which specimens are taken for testing. The size and nature of the laboratory test sample should be sufficient to overcome adequately the variability of the laboratory bulk sample.

**2.4 test specimen :** The portion of material required to give an individual test result.

## 3 PRINCIPLE

The laboratory test sample is taken so that it is representative of the laboratory bulk sample. The test specimens are taken from the laboratory test sample in such a way that each of them is representative of the laboratory test sample.

## 4 SAMPLING FROM LOOSE FIBRES

### 4.1 Non-oriented fibres

If the laboratory bulk sample consists of less than 5 kg of loose fibre, spread it out in an even layer. Obtain the laboratory test sample by taking at random a minimum of 100 tufts of approximately equal size, the total mass sufficient to give a laboratory test sample of required size.

If the laboratory bulk sample is greater than 5 kg, divide it into a number of equal portions, and take an equal number of tufts of suitable mass from each portion such that the total number from all portions exceeds 100.

Pretreat the laboratory test sample if required by the test method to be used. From the laboratory test sample remove at random, using forceps, small tufts of approximately equal mass to give a test specimen of the mass required.

### 4.2 Oriented fibres (card webs, slivers, rovings)

From randomly selected parts of the laboratory bulk sample cut not less than ten cross-sections each of mass approximately 1,0 g. After applying pretreatment if necessary, lay the cross-sections together and obtain the test specimen by cutting through them so as to take a portion of each of the ten lengths.

## 5 SAMPLING YARN

### 5.1 Yarn in packages or in hanks

If the number of packages in the laboratory bulk sample is 25 or less, sample all the packages. If the number exceeds 25, take 25 packages at random. If the linear density of the yarn, expressed in tex, is  $t$ , and the number of packages taken from the laboratory bulk sample is  $n$ , the length of yarn from each package to give a 10 g laboratory test sample is

$$\frac{10^6}{n t} \text{ cm}$$

If  $n t$  is high, for example more than 2 000, wind a heavier skein and cut it across in two places to make a tow of suitable mass.

Withdraw the appropriate continuous lengths from each package either by winding skeins of the same number of turns on a wrap reel<sup>1)</sup>, or by some other means. Unite the lengths side by side either as a single skein or as a tow to form the laboratory test sample, ensuring that there are equal lengths from each package in the skein or tow. Pre-treat the laboratory test sample if required by a suitable method and ensure that the ends of any sample in the form of tow are securely tied before treatment.

Take specimens of the appropriate mass from the laboratory test sample by cutting a bunch of threads of equal length from the skein or tow and comprising all the threads in it, ensuring that test specimens are taken from a place remote from the tie bands.

### 5.2 Yarn on warp

Take the laboratory test sample by cutting a length from the end of the warp, not less than 20 cm long and comprising all the yarns in the warp except the selvedge yarns, which are rejected. Tie the bunch of threads together near one end. If the sample is too large for any required pretreatment divide it into two or more portions, each tied together for pretreatment, and reunite the portions after the pretreatment of each separately.

Take a test specimen by cutting a suitable length from the laboratory test sample from the end remote from the tie band, and comprising all the threads in the warp. For warp of  $N$  threads of tex  $t$ , the length of a specimen of mass 1 g is

$$\frac{10^5}{N t} \text{ cm}$$

## 6 SAMPLING FABRIC

### 6.1 From a laboratory bulk sample consisting of a single cutting up to 1 m in length

Cut a diagonal strip from corner to corner and remove the selvages. For a laboratory test sample of  $X$  g the area of the strip required is

$$\frac{X 10^4}{M} \text{ cm}^2$$

where  $M$  is the mass of the cloth in grams per square metre.

This area divided by the length of the diagonal in centimetres will give the required width of strip in centimetres.

After subjecting the strip to any pretreatment, cut it across its length into four equal lengths and superimpose them. Take test specimens from any part of the layered material by cutting through all the layers in such a way that each specimen comprises an equal length from each layer.

### 6.2 From a laboratory bulk sample consisting of a single cutting more than 1 m in length

Take two full-width cuttings, one from each end of the laboratory bulk sample and not more than 1 m long. Cut both into two equal portions by a cut parallel to the warp direction and mark the right-hand and left-hand halves of each. Put the right-hand half of one cutting to the left-hand half of the other, with the cut edges together, and cut a diagonal strip from the lower corner of one cutting to the upper corner of the other, after removing the selvages. Proceed as in 6.1, treating the two half-width diagonal strips as if they were a full-width continuous strip.

### 6.3 From a laboratory bulk sample consisting of several cuttings

Treat each cutting separately as described in 6.1 or 6.2 and give results for each cutting in the test report.

### 6.4 From a fabric with a design arising from the distribution of threads

Ensure, if possible, that there is an integral number of complete repeats of the design in the laboratory bulk sample and proceed as in 6.1 unless the laboratory bulk sample so obtained is more than 1 m in length, in which case proceed as in 6.2. Where the pattern repeat is large

1) If the packages can be mounted in a convenient creel a number can be wound simultaneously.

and/or asymmetric, the entire strip should be cut into small fragments, thoroughly mixed and then sampled by the procedure indicated in 4.1.

Where the laboratory bulk sample does not contain at least one complete repeat of the design, report this under 8b).

## **7 SAMPLING MADE-UP ARTICLES**

The laboratory bulk sample normally consists of a complete made-up article or a representative part of such an article.

Determine whether all parts of the article are of similar composition; if so, treat the whole article as a laboratory bulk sample, and take a laboratory test sample representative of the laboratory bulk sample.

If parts of the article are of different composition, separate the parts and treat each as the laboratory bulk sample and take a laboratory test sample representative of the laboratory bulk sample.

## **8 TEST REPORT**

The test report shall include the following information :

- a) a statement that the material was sampled in accordance with this International Standard;
- b) the size of the laboratory bulk sample (see also 6.4);
- c) the size of the laboratory test sample;
- d) the size of the test specimen.







# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

## Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

## Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com).

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Useful Contacts

### Customer Services

**Tel:** +44 345 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 345 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)

### BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK