

Leather — Chemical determination of chromic oxide content —

Part 1: Quantification by titration

The European Standard EN ISO 5398-1:2007 has the status of a
British Standard

ICS 59.140.30

National foreword

This British Standard is the UK implementation of EN ISO 5398-1:2007.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear, leather and coated fabrics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 December 2007

© BSI 2007

ISBN 978 0 580 55574 9

Amendments issued since publication

Amd. No.	Date	Comments

English Version

**Leather - Chemical determination of chromic oxide content - Part
1: Quantification by titration (ISO 5398-1:2007)**

Cuir - Dosage chimique de l'oxyde de chrome - Partie 1:
Quantification par titrage (ISO 5398-1:2007)

Leder - Chemische Bestimmung des Chromoxidgehalts -
Teil 1: Bestimmung durch Titration (ISO 5398-1:2007)

This European Standard was approved by CEN on 28 July 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This document (EN ISO 5398-1:2007) has been prepared by Technical Committee CEN/TC 289 "Leather", the secretariat of which is held by UNI, in collaboration with the International Union of Leather Technologists and Chemists Societies (IULTCS).

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2008, and conflicting national standards shall be withdrawn at the latest by February 2008.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

INTERNATIONAL
STANDARD

ISO
5398-1

IULTCS/IUC
8:1

First edition
2007-08-01

**Leather — Chemical determination of
chromic oxide content —**

Part 1:
Quantification by titration

*Cuir — Dosage chimique de l'oxyde de chrome —
Partie 1: Quantification par titrage*



Reference number
ISO 5398-1:2007(E)
IULTCS/IUC 8:1:2007(E)

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle.....	1
5 Sampling and sample preparation.....	2
6 Reagents.....	2
6.1 Wet oxidation method	2
6.2 Alkaline fusion method	2
6.3 Iodometric titration	2
7 Apparatus	2
8 Methods	3
8.1 Preparation of analytical solution.....	3
8.2 Measurement of the aqueous solution.....	3
9 Calculation and expression of results.....	4
9.1 General.....	4
9.2 Repeatability.....	4
10 Test report	4
Annex A (informative) Determination of water and other volatile matter	5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

This part of ISO 5398 was prepared by the Chemical Tests Commission of the International Union of Leather Technologists and Chemists Societies (IUC Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the agreement on technical co-operation between ISO and CEN (Vienna Agreement). It is based on IUC 8 originally published in *J. Soc. Leather Trades Chemists* **49**, p. 17, (1965) and declared an official method of the IULTCS in 1965.

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

ISO 5398 consists of the following parts, under the general title *Leather — Chemical determination of chromic oxide content*:

- *Part 1: Quantification by titration*
- *Part 2: Quantification by colorimetric determination*
- *Part 3: Quantification by atomic absorption spectrometry*
- *Part 4: Quantification by inductively coupled plasma – optical emission spectrometer (ICP-OES)*

Introduction

ISO 5398 has been split into four parts, each describing methods suitable for the determination of the chromic oxide content in leather. The different techniques have been described to reflect the variations in industrial practice compared with the more sensitive analytical equipment available for test laboratories. Variations also exist in the range of chromic oxide that the methods are deemed suitable to quantify.

ISO 5398-1 describes a traditional technique applied in industry that does not require the use of advanced analytical equipment.

Leather — Chemical determination of chromic oxide content —

Part 1: Quantification by titration

1 Scope

This part of ISO 5398 describes a method for the determination of chromium in aqueous solution obtained from leather. This is an analysis for total chromium in leather; it is not compound specific or specific to its oxidation state.

This method describes the determination of chrome by iodometric titration and is to be applicable to chromium-tanned leathers which are expected to have chromic oxide contents in excess of 0,3 %. Two different methods are described as alternatives for obtaining chromium in a suitable solution. It is appropriate to use either method.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*

ISO 4044, *Leather — Chemical tests — Preparation of chemical test samples*

ISO 4047, *Leather — Determination of sulphated total ash and sulphated water-insoluble ash*

ISO 4684, *Leather — Chemical tests — Determination of volatile matter*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

chromic oxide content

amount of chromium in leather, determined by this method and reported as chromic oxide

NOTE The chromic oxide content is expressed in percentage by mass, based on dry matter.

4 Principle

The chromium present in the leather is solubilized in the hexavalent state followed by analysis of the solution by iodometric titration.

5 Sampling and sample preparation

If possible, sample in accordance with ISO 2418 and grind leather in accordance with ISO 4044. If sampling in accordance with ISO 2418 is not possible (as in the case of leathers from finished products like shoes, garments), details about sampling shall be given together with the test report.

Weigh accurately the ground leather to the nearest 0,001 g. (Suggested masses are full chrome leather 1 g, semi-chrome leather 2 g, leather with low chrome content 2 g to 5 g.) From every leather, a minimum of two determinations shall be made.

6 Reagents

Unless otherwise stated, only analytical grade chemicals are to be used. The water shall be grade 3 in accordance with ISO 3696:1987. All solutions are aqueous solutions.

6.1 Wet oxidation method

6.1.1 Nitric acid, 70 %.

6.1.2 Sulfuric acid, concentrated (98 %), and **perchloric acid** (60 % to 70 %), mixed together in the ratio of 1:3 by volume.

6.1.3 Orthophosphoric acid, 90 %.

6.2 Alkaline fusion method

6.2.1 Fusion mixture, consisting of equal masses of **sodium carbonate** (Na_2CO_3), **potassium carbonate** (K_2CO_3) and **sodium tetraborate** ($\text{Na}_2\text{B}_4\text{O}_7$).

6.2.2 Hydrochloric acid, concentrated (37 %).

6.3 Iodometric titration

6.3.1 Potassium iodide solution, freshly prepared, 100 g/l.

6.3.2 Sodium thiosulfate, 0,1 mol/l standardized solution in water.

6.3.3 Starch indicator solution, 10 g/l (or soluble starch powder).

7 Apparatus

Usual laboratory apparatus is required and, in particular, the following.

7.1 Conical flask, 500 ml, with ground glass stopper.

7.2 Crucible, glazed porcelain or platinum (required for alkaline fusion method only).

7.3 Burette, 50 ml.

7.4 Filtration device, using simple paper, glass fibre (GFC) or membrane type filters.

7.5 Antibumping granules (or similar) (wet oxidation method).

8 Methods

8.1 Preparation of analytical solution

8.1.1 Wet oxidation method

WARNING — It is imperative that nitric acid is added first because of the possible explosive reaction of perchloric acid with leather.

Accurately weigh a mass of leather (see Clause 5) into the conical flask (7.1). Add 10 ml of nitric acid (6.1.1) and allow to stand for 2 min. Add 15 ml of mixed sulfuric/perchloric acids (6.1.2) and a few antibumping granules (7.5). Place a funnel or splash bulb in the neck of the flask and heat to boiling on a wire gauze over a moderate flame. As soon as the reaction mixture begins to turn orange, lower the flame. After a complete change of colour, heat gently for at least 2 min. Allow to cool in air for 5 min and dilute to approximately 200 ml. Boil for 10 min to eliminate any chlorine. Allow to cool and add 5 ml of orthophosphoric acid (6.1.3) to mask any iron.

The use of a sulfuric/perchloric acid mixture is preferred to the use of the individual acids as it prevents the accidental use of perchloric acid alone.

In the case of incomplete oxidation (i.e. the solution does not change to an orange colour), it is permissible to add further mixed sulfuric/perchloric acid to the sample.

8.1.2 Alkaline fusion method

Ash the accurately weighed sample of leather (see Clause 5) in accordance with ISO 4047. In the crucible (7.2) containing the leather ash, carefully add 5 g of fusion mixture (6.2.1) and mix well using a platinum wire or thin glass rod. Start by heating the crucible gently on an open flame, then heat more fiercely for approximately 30 min. (A muffle furnace operating at $750\text{ }^{\circ}\text{C} \pm 50\text{ }^{\circ}\text{C}$ for at least 30 min may be used to heat the melt). After cooling, place the crucible in a beaker containing 100 ml to 150 ml of boiling water and continue to heat the water until the fusion mixture has completely dissolved. Filter (7.4) the solution obtained into the conical flask (7.1). Thoroughly wash the beaker, crucible and filter with hot water collecting the washings in the flask. Carefully add at least 10 ml hydrochloric acid to the flask and allow to cool down to room temperature.

8.2 Measurement of the aqueous solution

Add to the solution obtained from 8.1.1 or 8.1.2 20 ml of potassium iodide solution (6.3.1), stopper the flask and leave to stand for 10 min in the dark. Titrate with 0,1 mol/l sodium thiosulfate solution (6.3.2) until the solution in the flask is either light green or blue using 5 ml of starch indicator solution (6.3.3) (or a small quantity of starch powder), added towards the end of titration. Note the millilitres of thiosulfate solution used.

If starch solution is used, it should either be freshly prepared or should have been prepared with the addition of a little mercuric iodide to preserve the solution for several months.

If the titre is in excess of 50 ml, the analysis should be repeated using either smaller sample size or with appropriate dilution of the solution obtained from 8.1.1 or 8.1.2.

9 Calculation and expression of results

9.1 General

Calculate the following percentage.

The percentage by mass on dry matter, w_{Cr} , of chromic oxide, Cr_2O_3 , in the leather is given by the equation

$$w_{Cr} = \frac{V_1 \times 0,002\ 53 \times 100 \times F}{m_0}$$

where

V_1 is the volume, in millilitres (ml), of 0,1 mol/l thiosulfate solution used for the titration;

m_0 is the mass of the original leather sample, in grams (g);

F is the factor to correct to 0 % volatile matter; it is calculated as follows:

$$F = \frac{100}{100 - w_W}$$

where w_W is the volatile matter content, based on ISO 4684, in percentage by mass.

NOTE 1 ml of exactly 0,1 mol/l thiosulfate solution is equivalent to 0,002 53 g Cr_2O_3 .

It is also permissible, if required, to quote the results based on the dry, degreased mass of the sample.

9.2 Repeatability

The results of the duplicate determination should not differ by more than 0,1 % calculated on the original mass of the leather.

10 Test report

The test report shall include the following:

- a) a reference to this part of ISO 5398 (ISO 5398-1:2007);
- b) a description of the leather;
- c) a reference to the method used for sample preparation, type of digestion and measurement;
- d) the volatile matter content of the leather, in percentage;
- e) the results obtained based on dry sample mass to one decimal place in percentage;
- f) details of any deviations from the described procedures.

Annex A
(informative)

Determination of water and other volatile matter

The volatile matter content of leathers is determined according to ISO 4684. The volatile matter content of the leather is determined from a sample of ground leather prepared for the chromium determination. Wet leathers are dried before the determination of the volatile matter content according to ISO 4684. The loss in mass during initial drying is added to the loss in mass after drying according to ISO 4684.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.

BSI
389 Chiswick High Road
London
W4 4AL