

BS EN ISO 6224:2011



BSI Standards Publication

Thermoplastics hoses, textile-reinforced, for general-purpose water applications — Specification (ISO 6224:2011)

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 6224:2011. It supersedes BS EN ISO 6224:2008 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/66/-/1, Rubber and plastics tubing, hoses and hose assemblies - Industrial, chemical and petrochemical applications.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2011

ISBN 978 0 580 65919 5

ICS 23.040.70

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2011.

Amendments issued since publication

Date	Text affected
------	---------------

English Version

**Thermoplastics hoses, textile-reinforced, for general-purpose
water applications - Specification (ISO 6224:2011)**

Tuyaux en matières thermoplastiques à armature textile
d'usage général pour l'eau - Spécifications (ISO 6224:2011)

Kunststoffschläuche mit Textileinlage für allgemeine
Anwendungen mit Wasser - Anforderung (ISO 6224:2011)

This European Standard was approved by CEN on 30 September 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 6224:2011) has been prepared by Technical Committee ISO/TC 45 "Rubber and rubber products" in collaboration with Technical Committee CEN/TC 218 "Rubber and plastics hoses and hose assemblies" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2012, and conflicting national standards shall be withdrawn at the latest by April 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 6224:2008.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 6224:2011 has been approved by CEN as a EN ISO 6224:2011 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	2
5 Materials and construction	2
6 Dimensions	2
6.1 Inside diameters and tolerances on inside diameter	2
6.2 Concentricity	3
6.3 Tolerance on length	3
6.4 Minimum wall thickness	3
7 Physical properties	3
7.1 Thermoplastic materials	3
7.2 Finished hoses	4
8 Type, routine and production testing	4
9 Test certificate/report	4
10 Marking	5
11 Recommendations for packaging and storage	5
Annex A (normative) Type testing and routine testing	6
Annex B (informative) Recommended tests for production testing	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 6224 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Hoses (rubber and plastics)*.

This fourth edition cancels and replaces the third edition (ISO 6224:2005), which has been technically revised. The main changes are as follows:

- Table 1 includes four additional inside diameters (4 mm, 6 mm, 8 mm and 9 mm) for each type of hose;
- in Table 3, the requirement for the minimum adhesion between components has been raised from 1,5 kN/m to 2,0 kN/m;
- annexes giving schedules for type, routine and production testing have been added.

Thermoplastics hoses, textile-reinforced, for general-purpose water applications — Specification

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This standard does not purport to address all the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate health and safety practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard specifies the requirements for general-purpose textile-reinforced thermoplastics water-discharge hoses.

Three types of hose are specified according to their operating duty requirements, i.e. their ambient and water temperature ranges:

- ambient temperatures: $-10\text{ }^{\circ}\text{C}$ to $+60\text{ }^{\circ}\text{C}$;
- water temperature during operation: $0\text{ }^{\circ}\text{C}$ to $+60\text{ }^{\circ}\text{C}$.

NOTE At water temperatures above $23\text{ }^{\circ}\text{C}$ and particularly above $40\text{ }^{\circ}\text{C}$, the maximum working pressure will be reduced.

These hoses are not intended to be used for conveyance of potable (drinking) water, for washing-machine inlets, as fire-fighting hoses, for special agricultural machines or as gardening hoses for the consumer market.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3, *Preferred numbers — Series of preferred numbers*

ISO 176:2005, *Plastics — Determination of loss of plasticizers — Activated carbon method*

ISO 188:2011, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 1307, *Rubber and plastics hoses — Hose sizes, minimum and maximum inside diameters, and tolerances on cut-to-length hoses*

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies*

ISO 8033, *Rubber and plastics hoses — Determination of adhesion between components*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 8331, *Rubber and plastics hoses and hose assemblies — Guidelines for selection, storage, use and maintenance*

ISO 10619-1:—¹⁾, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 1: Bending tests at ambient temperature*

1) To be published. (Revision of ISO 1746:1998)

ISO 10619-2:—²⁾, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 2: Bending tests at sub-ambient temperatures*

ISO 30013:2011, *Rubber and plastics hoses — Methods of exposure to laboratory light sources — Determination of changes in colour, appearance and other physical properties*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

4 Classification

Hoses are designated as one of the following types, depending on their pressure rating:

- Type 1: Low pressure — Designed for a maximum working pressure of 0,6 MPa (6 bar) at 23 °C and 0,36 MPa (3,6 bar) at 60 °C.
- Type 2: Medium pressure — Designed for a maximum working pressure of 1,0 MPa (10 bar) at 23 °C and 0,65 MPa (6,5 bar) at 60 °C.
- Type 3: High pressure — Designed for a maximum working pressure of 2,5 MPa (25 bar) at 23 °C and 1,6 MPa (16 bar) at 60 °C.

5 Materials and construction

The hose shall consist of:

- a flexible thermoplastic lining;
- a reinforcement of natural or synthetic textile, applied by any suitable technique;
- a flexible thermoplastic cover.

The lining and the cover shall be of uniform thickness, concentric, fully gelled and free from visible cracks, porosity, foreign inclusions and other defects. The cover may have a smooth or fluted finish.

6 Dimensions

6.1 Inside diameters and tolerances on inside diameter

When measured in accordance with ISO 4671, the inside diameter and its tolerances shall conform to the values specified in Table 1.

2) To be published. (Revision of ISO 4672:1997)

Table 1 — Inside diameters, tolerances and minimum wall thicknesses

Inside diameter mm	Tolerance on inside diameter mm	Minimum wall thickness mm		
		Type 1	Type 2	Type 3
4	±0,50	2,00	2,00	2,50
6	±0,50	2,00	2,00	2,50
8	±0,60	2,00	2,00	2,80
9	±0,60	2,00	2,00	2,80
10	±0,75	2,00	2,00	2,80
12,5	±0,75	2,00	2,50	3,00
16	±0,75	2,00	2,80	3,00
19	±0,75	2,20	3,00	3,50
25	±1,25	2,70	3,50	4,00
32	±1,25	3,40	4,00	—
38	±1,50	4,00	4,50	—
50	±1,50	5,00	5,50	—

NOTE 1 For smaller or larger diameters, it is recommended that values be chosen from the R10 series of preferred numbers (see ISO 3), with tolerances as specified in ISO 1307.

NOTE 2 For intermediate diameters, it is recommended that values be chosen from the R20 series of preferred numbers (see ISO 3).

6.2 Concentricity

When determined in accordance with ISO 4671, the concentricity, based on a total indicator reading between the inside diameter and the outside surface of the cover, shall be no greater than 1,0 mm.

6.3 Tolerance on length

When measured in accordance with ISO 4671, the tolerance on cut lengths shall be as specified in ISO 1307.

6.4 Minimum wall thickness

When measured in accordance with ISO 4671, the minimum wall thickness of the hose shall conform to the values specified in Table 1. If the cover is fluted, the depth of the flutes shall not be greater than 50 % of the cover thickness.

7 Physical properties

7.1 Thermoplastic materials

When measured by the methods listed in Table 2, the physical properties of the materials used for the lining and cover shall conform to the values specified in Table 2.

Tests shall be carried out on test pieces taken either from the hose or from separately gelled sheets, 2 mm in thickness.

Table 2 — Physical properties of thermoplastic materials

Property	Requirements		Test method
	Lining	Cover	
Minimum tensile strength	10,0 MPa	10,0 MPa	ISO 527-2 (dumb-bell test piece)
Minimum elongation at break	250 %	250 %	ISO 527-2 (dumb-bell test piece)
Resistance to ageing:			
Change in tensile strength from original value (max.)	±15 %	±15 %	ISO 188:2011 (3 days at 70 °C ± 1 °C), method A or B; ISO 527-2 (dumb-bell test piece)
Change in elongation at break from original value (max.)	±25 %	±25 %	
Loss in mass on heating (max.)	4 %	4 %	ISO 176:2005, method B

7.2 Finished hoses

When tested at 23 °C (standard laboratory temperature) and at 60 °C by the appropriate method specified in ISO 1402, the physical properties of finished hoses shall conform to the values specified in Table 3.

8 Type, routine and production testing

Type tests are those tests carried out to determine that the hose design and method of manufacture meet the full requirements of this International Standard.

Routine tests are those tests carried out on every manufactured length of finished hose.

The type tests and routine tests which shall be carried out are given in Annex A.

Production tests are those tests carried out on each batch. The tests recommended for production testing are given in Annex B, which is for guidance only.

9 Test certificate/report

When requested by the purchaser, the manufacturer or supplier shall provide a test certificate or test report with each length of hose or batch of hoses supplied to the purchaser.

Table 3 — Physical properties of finished hoses

Property	Requirements						Test method
	Type 1		Type 2		Type 3		
	MPa	bar	MPa	bar	MPa	bar	
Proof pressure at 23 °C	0,9	9	1,5	15	5,0	50	ISO 1402
Minimum burst pressure at 23 °C	1,8	18	3,0	30	10,0	100	ISO 1402
Proof pressure at 60 °C	0,55	5,5	0,975	9,75	2,5	25	ISO 1402
Minimum burst pressure at 60 °C	1,1	11	1,95	19,5	5,0	50	ISO 1402
Change in length at maximum working pressure at 23 °C	±8 %						ISO 1402
Adhesion between components	2,0 kN/m (min.)						ISO 8033
UV resistance (xenon-arc lamp)	The cover shall show no cracking or change in colour which would cause the hose to be unserviceable. When comparing the test pieces with the grey scale, the minimum acceptable degree of contrast shall be as determined between the interested parties.						ISO 30013:2011, method A
Flexibility at 23 °C	<i>T/D</i> not less than 0,8						ISO 10619-1:—, method A1
Low-temperature flexibility	No cracks shall be detected and the hose shall pass the proof pressure test specified above at 23 °C.						ISO 10619-2:—, method B, at -10 °C ± 2 °C

10 Marking

The hose shall be continuously and durably marked with the following minimum information:

- the manufacturer's name or identification, e.g. MAN;
- the number and year of publication of this International Standard, i.e. ISO 6224:2011;
- the hose type, e.g. type 1;
- the inside diameter, in millimetres, e.g. 25;
- the maximum working pressure, in megapascals and in bars, or in either, with the units indicated, e.g. 0,6 MPa;
- the quarter and the last two digits of the year of manufacture, e.g. 2Q11.

EXAMPLE MAN/ISO 6224:2011/type 1/25/0,6 MPa/2Q11.

11 Recommendations for packaging and storage

These are given in ISO 8331.

Annex A (normative)

Type testing and routine testing

Table A.1 gives the tests to be carried out for type tests and routine tests as defined in Clause 8.

Table A.1 — Type tests and routine tests

Dimension/property under test (with reference to relevant subclause)	Type testing	Routine testing
Inside diameter and tolerances (6.1)	X ^a	X
Concentricity (6.2)	X	X
Tolerance on length (6.3)	X	X
Minimum wall thickness (6.4)	X	X
Minimum tensile strength and minimum elongation at break (7.1)	X	N.A. ^b
Resistance to ageing:		
Change in tensile strength from original value (max.) (7.1)	X	N.A.
Change in elongation at break from original value (max.) (7.1)		
Loss in mass on heating (max.) (7.1)	X	N.A.
Proof pressure at 23 °C (7.2)	X	X
Minimum burst pressure at 23 °C (7.2)	X	N.A.
Proof pressure at 60 °C (7.2)	X	N.A.
Minimum burst pressure at 60 °C (7.2)	X	N.A.
Change in length at maximum working pressure at 23 °C (7.2)	X	N.A.
Adhesion between components (7.2)	X	N.A.
UV resistance (xenon-arc lamp) (7.2)	X	N.A.
Flexibility at 23 °C (7.2)	X	N.A.
Low-temperature flexibility (7.2)	X	N.A.
^a X = test required. ^b N.A. = not applicable.		

Annex B (informative)

Recommended tests for production testing

Table B.1 gives the tests recommended for production testing. Production tests are carried out on a hose or a sample of hose from each batch manufactured.

A batch is defined as, at the most, either 30 000 m of hose or 10 000 kg of lining and/or cover compound (plastic).

Table B.1 — Recommended tests for production testing

Dimension/property under test (with reference to relevant subclause)	Production testing
Inside diameter and tolerances (6.1)	X ^a
Concentricity (6.2)	X
Tolerance on length (6.3)	X
Minimum wall thickness (6.4)	X
Minimum tensile strength and minimum elongation at break (7.1)	N.A. ^b
Resistance to ageing: Change in tensile strength from original value (max.) (7.1) Change in elongation at break from original value (max.) (7.1)	N.A.
Loss in mass on heating (max.) (7.1)	N.A.
Proof pressure at 23 °C (7.2)	X
Minimum burst pressure at 23 °C (7.2)	X
Proof pressure at 60 °C (7.2)	N.A.
Minimum burst pressure at 60 °C (7.2)	N.A.
Change in length at maximum working pressure at 23 °C (7.2)	N.A.
Adhesion between components (7.2)	X
UV resistance (xenon-arc lamp) (7.2)	N.A.
Flexibility at 23 °C (7.2)	N.A.
Low-temperature flexibility (7.2)	N.A.
^a X = test required. ^b N.A. = not applicable.	

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™