

Binders for paints and varnishes — Alkyd resins —

Part 2: Determination of phthalic anhydride content

The European Standard EN ISO 6744-2:2004 has the status of a
British Standard

ICS 87.060.20

National foreword

This British Standard is the official English language version of EN ISO 6744-2:2004. It is identical with ISO 6744-2:1999.

The UK participation in its preparation was entrusted to Technical Committee STI/3, Paint media and related products, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, the EN ISO foreword page, the ISO title page, pages ii and iii, a blank page, pages 1 to 4, the Annex ZA page and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments
10884 Corrigendum No. 1	December 2000	Correction to identifier
15239	14 July 2004	Implementation of the European Standard

This British Standard, having been prepared under the direction of the Sector Committee for Materials and Chemicals, was published under the authority of the Standards Committee on 14 July 2004

© BSI 14 July 2004

ICS 87.060.20

English version

Binders for paints and varnishes - Alkyd resins - Part 2:
Determination of phthalic anhydride content (ISO 6744-2:1999)

Liants pour peintures et vernis - Résines alkydes - Partie 2:
Détermination de la teneur en anhydride phtalique (ISO
6744-2:1999)

Bindemittel für Beschichtungsstoffe - Alkydharze - Teil 2:
Bestimmung des Gehaltes an Phthalsäureanhydrid (ISO
6744-2:1999)

This European Standard was approved by CEN on 8 April 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of ISO 6744-2:1999 has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 6744-2:2004 by Technical Committee CEN/TC 139 "Paints and varnishes", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2004, and conflicting national standards shall be withdrawn at the latest by November 2004.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of ISO 6744-2:1999 has been approved by CEN as EN ISO 6744-2:2004 without any modifications.

NOTE Normative references to International Standards are listed in Annex ZA (normative).

INTERNATIONAL
STANDARD

ISO
6744-2

First edition
1999-12-01

**Binders for paints and varnishes — Alkyd
resins —**

Part 2:
**Determination of phthalic anhydride
content**

Liants pour peintures et vernis — Résines alkydes —

Partie 2: Détermination de la teneur en anhydride phtalique



Reference number
ISO 6744-2:1999(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 6744 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 6744-2 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 10, *Test methods for binders for paints and varnishes*.

Together with the other parts (see below), this part of ISO 6744 cancels and replaces ISO 6744:1984, which has been technically revised.

ISO 6744 consists of the following parts, under the general title *Binders for paints and varnishes — Alkyd resins*:

- *Part 1: General methods of test*
- *Part 2: Determination of phthalic anhydride content*
- *Part 3: Determination of unsaponifiable matter content*
- *Part 4: Determination of fatty acid content*

Binders for paints and varnishes — Alkyd resins —

Part 2:

Determination of phthalic anhydride content

1 Scope

This part of ISO 6744 specifies a method for determining the phthalic anhydride content of alkyd resins.

It is only applicable to those alkyd resins which contain only orthophthalic acid as the polybasic acid. It is not applicable to modified alkyd resins (see 3.2 of ISO 6744-1:1999) or to resins containing benzoic acid.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 6744. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 6744 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 3681:1996, *Binders for paints and varnishes — Determination of saponification value — Titrimetric method.*

ISO 3696:1987, *Water for analytical laboratory use — Specification and methods of test.*

ISO 6744-1:1999, *Binders for paints and varnishes — Alkyd resins — Part 1: General methods of test.*

ISO 6744-3:1999, *Binders for paints and varnishes — Alkyd resins — Part 3: Determination of unsaponifiable matter content.*

ISO 6744-4:1999, *Binders for paints and varnishes — Alkyd resins — Part 4: Determination of fatty acid content.*

ISO 15528:—¹⁾, *Paints, varnishes and raw materials for paints and varnishes — Sampling.*

3 Principle

A test portion is saponified with potassium hydroxide solution. The potassium phthalate precipitate which forms is filtered, dried and weighed. The filtrate is reserved for the subsequent determinations of unsaponifiable matter and fatty acid contents.

1) To be published. (Revision of ISO 842:1984 and ISO 1512:1991)

4 Reagents

During the analysis, use only reagents of recognized analytical grade and only water of at least grade 3 purity as defined in ISO 3696.

4.1 Toluene.

4.2 Solvent mixture, consisting of 1 part by volume of toluene and 1 part by volume of absolute ethanol. Alternatively, a mixture of 1 part by volume of diethyl ether and 1 part by volume of absolute ethanol may be used.

4.3 Potassium hydroxide, approximately 28 g/l solution in absolute ethanol, clear and free from sediment.

5 Apparatus

Ordinary laboratory apparatus and glassware, together with the following:

5.1 Conical flask, of capacity about 250 ml, with ground-glass joint.

5.2 Reflux condenser, with ground-glass joint, fitting on the conical flask (5.1) and the drying tube (5.3).

5.3 Drying tube, filled with anhydrous calcium chloride, fitting on the reflux condenser (5.2).

5.4 Hotplate, fitted with a magnetic stirrer.

5.5 Sintered-glass filter crucible, diameter of the plate 30 mm, pore diameter 15 μm to 40 μm .

5.6 Desiccator, containing silica gel as the desiccant.

5.7 Weighing bottle.

5.8 Drying oven, capable of being maintained at approximately 140 °C.

6 Sampling

Take a representative sample of the product to be tested, as described in ISO 15528.

7 Procedure

7.1 Number of determinations

Carry out the determination in duplicate.

7.2 Test portion

Weigh, to the nearest 1 mg, a mass (m_0) of the resin or the resin solution containing not more than 2 g of fatty acid (see ISO 6744-4) into the conical flask (5.1).

NOTE The mass of resin to be taken will normally be 3 g to 5 g.

7.3 Determination

Dissolve the test portion (see 7.2) in 10 ml of toluene (4.1) in the conical flask. Add 100 ml of potassium hydroxide solution (4.3), fit the reflux condenser (5.2) on to the conical flask and fit the drying tube (5.3) on to the condenser.

Heat the contents of the flask to boiling and maintain at the boiling point under reflux for 2 h, while stirring (see note). Allow the flask to cool to ambient temperature, rinse the condenser with some solvent and filter the solution through the weighed sintered-glass filter crucible (5.5). Reserve the filtrate for the determination of the unsaponifiable matter in accordance with ISO 6744-3. Wash the potassium phthalate precipitate as rapidly as possible several times with solvent mixture (4.2). Make sure that the precipitate is continuously covered with the solvent mixture and only becomes exposed after the final washing. Afterwards, the precipitate may be placed in an oven maintained at 100 °C for 1 min to 2 min to facilitate evaporation of the solvents. Dry the precipitate in the desiccator (5.6) under vacuum until the difference between the results of two consecutive weighings is not greater than 0,1 %, calculated on the basis of the lower value. Weigh the precipitate to the nearest 1 mg (m_1).

As the precipitate is hygroscopic, transfer the crucible and the precipitate immediately after drying to the weighing bottle (5.7). Close the weighing bottle and weigh the precipitate to the nearest 1 mg. Dry the precipitate in the drying oven (5.8) at approximately 140 °C until the difference between the results of two consecutive weighings is not greater than 0,1 %, calculated on the basis of the lower value. Weigh the residue to the nearest 1 mg (m_2).

NOTE Normally, saponification is complete after 2 h. The completeness of saponification can be checked by determining the saponification value under more severe conditions which can be achieved by the use of a longer saponification time, a more concentrated potassium hydroxide solution or a higher-boiling alcohol as solvent (see ISO 3681).

8 Expression of results

Calculate the phthalic anhydride content w_p , expressed as a percentage by mass, by the equations

$$w_p = \frac{m_1 \times 51,4}{m_0} \quad (1)$$

and

$$w_p = \frac{m_2 \times 61,1}{m_0} \quad (2)$$

where

m_0 is the mass, in grams, of the test portion (see note to 7.2);

m_1 is the mass, in grams, of the precipitate after drying in vacuum at ambient temperature (potassium phthalate monoethanolate);

m_2 is the mass, in grams, of the residue after drying at 140 °C (ethanol-free potassium phthalate);

51,4 is a factor to convert the mass of potassium phthalate monoethanolate to that of phthalic anhydride;

61,1 is a factor to convert the mass of anhydrous potassium phthalate to that of phthalic anhydride.

Calculate the average of the two values and report this average value.

NOTE If the difference between the results calculated by the two equations is greater than 2 % absolute, the method specified in this part of ISO 6744 is not suitable for the alkyd resin under test (see footnote c to Table 1 of ISO 6744-1:1999).

The phthalic anhydride content shall be calculated on the basis of the resin or, for resin solutions, on the basis of the non-volatile matter content of the solution.

9 Test report

The test report shall contain at least the following information:

- a) a reference to this part of ISO 6744 (ISO 6744-2);
- b) all details necessary to identify the product tested;
- c) the result of the test, as indicated in clause 8;
- d) any deviation from the test method specified;
- e) the date of the test.

Annex ZA (normative)

Normative references to international publications with their relevant European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

NOTE Where an International Publication has been modified by common modifications, indicated by (mod.), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN</u>	<u>Year</u>
ISO 3681	1996	Binders for paints and varnishes - Determination of saponification value - Titrimetric method	EN ISO 3681	1998
ISO 3696	1987	Water for analytical laboratory use - Specification and test methods	EN ISO 3696	1995
ISO 15528	2000	Paints, varnishes and raw materials for paints and varnishes - Sampling	EN ISO 15528	2000

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.