

BS EN ISO 7625:2012



BSI Standards Publication

**Sintered metal materials,
excluding hardmetals —
Preparation of samples for
chemical analysis for
determination of carbon
content**

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 7625:2012. It supersedes BS EN ISO 7625:2010 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/65, Sintered metal components.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012

Published by BSI Standards Limited 2012

ISBN 978 0 580 75120 2

ICS 77.160

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 December 2012.

Amendments issued since publication

Amd. No.	Date	Text affected
----------	------	---------------

EUROPEAN STANDARD

EN ISO 7625

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2012

ICS 77.160

Supersedes EN ISO 7625:2010

English Version

Sintered metal materials, excluding hardmetals - Preparation of samples for chemical analysis for determination of carbon content (ISO 7625:2012)

Matériaux métalliques frittés, à l'exclusion des métaux-durs
- Préparation des échantillons pour analyse chimique en
vue du dosage du carbone (ISO 7625:2012)

Sintermetalle, ausgenommen Hartmetalle - Vorbereitung
von Proben für die chemische Analyse zur Bestimmung
des Kohlenstoffgehaltes (ISO 7625:2012)

This European Standard was approved by CEN on 1 December 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
---------------	---

Foreword

This document (EN ISO 7625:2012) has been prepared by Technical Committee ISO/TC 119 "Powder metallurgy".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2013, and conflicting national standards shall be withdrawn at the latest by May 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 7625:2010.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 7625:2012 has been approved by CEN as a EN ISO 7625:2012 without any modification.

Introduction

The chemical analysis of sintered metal materials, excluding hardmetals, is carried out as it would be for solid metals, by using existing standard methods. However, as these sintered materials very often contain carbonaceous constituents, the correct determination of carbon content (free or total) requires that certain precautions be taken when preparing the sample for analysis from components.

Samples prepared in accordance with this International Standard may also be suitable for chemical analysis for other elements.

Sintered metal materials, excluding hardmetals — Preparation of samples for chemical analysis for determination of carbon content

1 Scope

This International Standard specifies methods for preparing a sample from one or more sintered parts to be analysed for free or total carbon content. Combined carbon is determined as the difference between total and free carbon. This standard covers the preparation of samples for the determination of carbon by a chemical method, i.e. combustion in oxygen and measurement of the carbon dioxide produced, in accordance with ISO 437. It does not cover the preparation of samples for carbon determination by physical methods, such as metallography or spectroscopy.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 437, *Steel and cast iron — Determination of total carbon content — Combustion gravimetric method*

ISO 2738, *Sintered metal materials, excluding hardmetals — Permeable sintered metal materials — Determination of density, oil content, and open porosity*

3 Principle

Eliminate any impregnated or surface carbon using the procedures in Clause 5. Prepare samples for analysis by fragmentation or machining, taking care not to lose any free carbon.

4 Materials

This International Standard applies to parts in which carbon is uniformly distributed and present in the forms shown in Table 1. It does not apply to parts in which the carbon is not uniformly distributed throughout the part, including those parts with carburized or decarburized surfaces.

In instances where the carbon is not uniformly distributed, for example a case-hardened part, the method of selecting the sample should be agreed upon between the supplier and the purchaser.

The presence of carbonaceous materials in the pores or on the surface of the part to be analysed interferes with the determination of carbon, see Table 2.

Table 1 — Forms of carbon that can be determined by chemical analysis

Form of carbon	Typical materials	Comments
Combined carbon (as carbides or in solid solution)	Carbon-containing steels and super-alloys	Determined as the difference between total and free carbon
Free carbon	Bronze and steel containing graphite; material impregnated with a graphite-containing liquid	Determined by combustion of the residue of selective dissolution of the metal in the sample.
Total carbon		Determined by direct combustion of the sample

**Table 2 — Origins of carbonaceous material
and feasibility of carbon determination by chemical methods**

Carbonaceous material	Origin	Feasibility
1 Liquid or semi-liquid organic substances on the surface or in the pores	Sizing lubricant, quenching oil, impregnating lubricant, cutting fluid, grease	Carbon determination is possible only when these organic substances are totally eliminated by the method described in Clause 5
2 Waxes and wax-like substances	Sizing lubricant, corrosion protective	
3 Deposits of carbon on the parts	Sintering, heat treatment	
4 Solid organic substances, for example, plastics materials on the surface or in the pores	Sealant material	In general, it is not possible to eliminate these substances, and determination of carbon is not possible

5 Procedure

5.1 Removal of interfering carbonaceous material

5.1.1 General

Carbonaceous materials (see Table 2) that affect the carbon determination shall be removed from the part or parts to be analysed as specified in 5.1.2 and 5.1.3.

5.1.2 Impregnated organic substances in the pores or on the surface (see Cases 1 and 2 in Table 2) shall be removed by Soxhlet degreasing with an appropriate solvent, in accordance with ISO 2738. The solvent used shall be stated.

NOTE When the impregnated liquid contains fine carbon particles, for example colloidal graphite, it is possible that not all of these particles are removed by Soxhlet degreasing. In such a case, the determination of free carbon and total carbon is invalid. Nevertheless, the calculation of combined carbon is still valid if the free carbon and total carbon are determined on the same part or parts after degreasing.

5.1.3 Surface deposits of carbon (see Case 3 in Table 2) shall be removed by mechanical treatment.

5.2 Final preparation

The sample for analysis shall consist of small fragments of a size appropriate to the analysis method to be used, prepared by one of the following methods:

- crushing in a mortar made of a material which does not alter the sample composition;
- drilling, milling or turning. Such machining shall be performed dry by using hardmetal or ceramic tools. Care shall be taken to avoid overheating, oxidation and contamination of the fragments. Where drilling is used, the part shall be drilled through completely and the distribution of drilling holes shall be uniform over the whole surface of the part. If the part is too thick, the holes shall be drilled to the middle from both faces of the part.

Where crushed or machined fragments contain fine particles (for example free graphite), care shall be taken not to lose these particles during handling.

Where segregation is expected to be a problem, the entire sample should be analysed after being divided into a suitable number of test portions. The carbon content is then calculated as the average of the results from each portion.

In general, a sufficient quantity of fragments, representative of the part or parts, shall be prepared. The samples for analysis shall be kept in a container that is tightly sealed, in order to avoid contamination.

6 Precision

When the degreasing is carried out according to ISO 2738 as stated in 5.1.2, the carbon content after oil removal can be considered suspect if the repeatability is greater than 5 % and the reproducibility is greater than 10 % at the 95 % confidence level.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™