

Coating powders — Part 11: Inclined- plane flow test (ISO 8130-11:1997)

ICS 87.040

National foreword

This British Standard is the UK implementation of BS EN ISO 8130-11:2010. It is identical to ISO 8130-11:1997. It supersedes BS 3900-J11:1997 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/10, Test methods for paints.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard, having been prepared under the direction of the Sector Board for, Materials and Chemicals, was published under the authority of the Standards Board and comes into effect on 15 September 1997

© BSI 2011

ISBN 978 0 580 72118 2

Amendments/corrigenda issued since publication

Date	Comments
30 April 2011	This corrigendum renumbers BS 3900-J11:1997 as BS EN ISO 8130-11:2010

EUROPEAN STANDARD

EN ISO 8130-11

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2010

ICS 87.040

English Version

Coating powders - Part 11: Inclined-plane flow test (ISO 8130-11:1997)

Poudres pour revêtement - Partie 11: Essai d'écoulement sur plan incliné (ISO 8130-11:1997)

Pulverlacke - Teil 11: Prüfung des Fließverhaltens auf einer geeigneten Platte (ISO 8130-11:1997)

This European Standard was approved by CEN on 16 October 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

The text of ISO 8130-11:1997 has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 8130-11:2010 by Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2011, and conflicting national standards shall be withdrawn at the latest by May 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 8130-11:1997 has been approved by CEN as a EN ISO 8130-11:2010 without any modification.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	1
5 Sampling	1
6 Procedure	1
7 Expression of results	2
8 Precision	2
9 Test report	2

Descriptors: Paints, coatings, powdery materials, tests, determination, gravity flow.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 8130-11 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

ISO 8130 consists of the following parts, under the general title *Coating powders*:

- *Part 1: Determination of particle size distribution by sieving;*
- *Part 2: Determination of density by gas comparison pyknometer (referee method);*
- *Part 3: Determination of density by liquid displacement pyknometer;*
- *Part 4: Calculation of lower explosion limit;*
- *Part 5: Determination of flow properties of a powder/air mixture;*
- *Part 6: Determination of gel time of thermosetting coating powders at a given temperature;*
- *Part 7: Determination of loss of mass on stoving;*
- *Part 8: Assessment of the storage stability of thermosetting powders;*
- *Part 9: Sampling;*
- *Part 10: Determination of deposition efficiency;*
- *Part 11: Inclined-plane flow test;*
- *Part 12: Determination of compatibility.*

1 Scope

This Part of ISO 8130 is one of a series of standards dealing with the sampling and testing of paints, varnishes and related products.

It specifies a method for determining the flow characteristics of a fused thermosetting coating powder down a plane inclined at a set angle to the horizontal.

The result of the test described in this Part of ISO 8130 gives an indication of the degree of melt flow that may occur during the curing of the coating powder. This characteristic contributes to the coherence of the coating, to its surface appearance and to the degree of coverage over sharp edges.

The test acts as a useful method for checking for batch to batch variation in the behaviour of a given coating powder. Correlation between the results from coating powders of differing composition is not to be expected.

This method is unlikely to yield meaningful results with coating powders which have gel times of less than one minute at the test temperature when characterised according to ISO 8130-6.

2 Normative references

The following standards contain provisions which, through reference to this text, constitute provisions of this Part of ISO 8130. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 8130-2:1992, *Coating powders — Part 2: Determination of density by gas comparison pycnometer (referee method)*.

ISO 8130-3:1992, *Coating powders — Part 3: Determination of density by liquid displacement pycnometer*.

ISO 8130-6:1992, *Coating powders — Part 6: Gel time of thermosetting coating powders at a given temperature*.

ISO 8130-9:1992, *Coating powders — Part 9: Sampling*.

3 Principle

The thermosetting coating powder is pressed into a pellet of standard size which is allowed to melt and flow down a heated inclined plate. The extent of flow is measured.

4 Apparatus

4.1 Fan-assisted air circulation oven, capable of maintaining temperatures up to 250 °C. The circulation fan shall be capable of being turned on and off as required.

4.2 Glass plates, of suitable dimensions to undertake the test.

NOTE 1 Photographic float-glass plates have been found to be suitable.

As an alternative metal plates may be used. However, these will need to be closely defined with respect to their composition and surface finish. The plates shall be sufficiently rigid so as not to flex during the test. The details of the metal plates shall be included in the test report (clause 9).

4.3 Plate assembly, of suitable metal, that fits inside the oven (4.1). The assembly shall be capable of carrying one or more of the plates (4.2) in a horizontal position and at an angle of $(65 \pm 1)^\circ$ to the horizontal when moved by a lever projecting through the side of the oven.

4.4 Balance, capable of measuring to 10 mg.

4.5 Steel pellet-moulding press, together with a knockout rod, to make pellets of $(12,5 \pm 0,05)$ mm in diameter and $(6,5 \pm 0,2)$ mm thick.

4.6 Steel rule, graduated in mm.

4.7 Polytetrafluoroethylene, (PTFE) release aerosol spray

5 Sampling

Take a representative sample of the product under test as described in ISO 8130-9.

6 Procedure

Carry out the determination in duplicate.

6.1 Weigh in the balance (4.4) to an accuracy of 10 mg a mass of the product under test equivalent in grams to half of the density of the coating powder in accordance with ISO 8130-2 or ISO 8130-3. By means of the pellet press (4.5) compact the pellet into a disc $(6,5 \pm 0,2)$ mm thick and push the pellet out of the mould with the knockout rod. Weigh the pellet to confirm that its mass is correct to 10 mg.

If there is a delay between the commencement of the test and the preparation of the pellet, protect it against moisture absorption by storage in a desiccator or a sealed bag.

6.2 Unless otherwise agreed the temperature of the test shall be the recommended stoving temperature. In the absence of this information a temperature of (180 ± 2) °C shall be used.

6.3 Spray the uppermost side of the glass plate(s) (4.2) with the PTFE release material (4.7) and allow to air dry.

The use of PTFE release material is in order to facilitate the removal of the sample so that the glass test plate may be reused and to ensure that a uniform surface is obtained. This procedure may be considered inappropriate when metal plates are used. It may be omitted on agreement between interested parties in which case this shall be indicated in the test report (clause 9).

6.4 Place the plate(s) in the plate assembly (4.3) in a horizontal position.

6.5 Place the plate assembly and plate(s) into the oven set at the appropriate temperature (see clause 6.2) and allow the assembly to preheat for a minimum period of 15 minutes with the fan on.

NOTE 2 It may be more convenient to maintain the plate assembly in the oven and carefully load the plate(s) in situ.

6.6 At the end of the preheat period turn off the circulation fan and open the door of the oven. Place the pellet(s) towards the end of the plate(s) which will be uppermost when tilted. Close the door of the oven and restart the fan. This operation shall take no longer than 15 s to perform. After a further 15 s since closing the oven door operate the plate assembly to bring the plate(s) to $(65 \pm 1)^\circ$ to the horizontal. Allow the plate(s) to remain in this position for 15 minutes. At the end of this period remove the plate(s) from the oven and allow to cool to room temperature in a horizontal position.

6.7 Using the steel rule (4.6) measure the total length of the flowed pellet in mm. This is most conveniently undertaken with glass plates by viewing from the reverse side. Record the measurement to the nearest 0,5 mm.

7 Expression of results

Calculate the pellet flow by deducting the original diameter of the pellet (12,5 mm) from the total flow as measured in clause 6.7.

If the two determinations differ by more than 5 % based on the lower figure, repeat the procedure described in clause 6.

Calculate the average of two valid determinations and report to the nearest 0,5 mm.

8 Precision

The precision of the method, as obtained by statistical examination of interlaboratory test results, is as follows:

8.1 Repeatability (r)

The value below which the absolute difference between two single test results, each the mean of duplicates, obtained on identical material by one operator in one laboratory within a short interval of time using the standardized test method, may be expected to lie with a 95 % probability is 5 %.

9 Test report

The test report should contain at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this part of ISO 8130 (ISO 8130-11);
- c) the test temperature;
- d) weight of sample;
- e) results of the test (individual values and mean value);
- f) whether a metal plate was used and a description of its surface finish and composition (sub-clause 4.2);
- g) whether a PTFE pre-treatment of the plate was used (sub-clause 6.3);
- h) any deviation from the test method specified;
- i) the date of the test.

BSI - British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001 Email: orders@bsigroup.com You may also buy directly using a debit/credit card from the BSI Shop on the Website <http://www.bsigroup.com/shop>

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact Information Centre. Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048 Email: info@bsigroup.com

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001 Email: membership@bsigroup.com

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsigroup.com/BSOL>

Further information about BSI is available on the BSI website at <http://www.bsigroup.com>

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright and Licensing Manager. Tel: +44 (0)20 8996 7070 Email: copyright@bsigroup.com