



BSI Standards Publication

Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness

Part 2: Laboratory determination of chloride
on cleaned surfaces (ISO 8502-2:2017)

National foreword

This British Standard is the UK implementation of EN ISO 8502-2:2017. It supersedes BS EN ISO 8502-2:2005 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/21, Paint systems and surface preparation for metallic substrates.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2017.
Published by BSI Standards Limited 2017

ISBN 978 0 580 76073 0

ICS 25.220.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 28 February 2017.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN ISO 8502-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2017

ICS 25.220.10

Supersedes EN ISO 8502-2:2005

English Version

**Preparation of steel substrates before application of paints
and related products - Tests for the assessment of surface
cleanliness - Part 2: Laboratory determination of chloride
on cleaned surfaces (ISO 8502-2:2017)**

Préparation des subjectiles d'acier avant application de
peintures et de produits assimilés - Essais pour
apprécier la propreté d'une surface - Partie 2:
Recherche en laboratoire des chlorures sur les surfaces
nettoyées (ISO 8502-2:2017)

Vorbereitung von Stahloberflächen vor dem Auftragen
von Beschichtungsstoffen - Prüfungen zum Beurteilen
der Oberflächenreinheit - Teil 2: Laborbestimmung von
Chlorid auf gereinigten Oberflächen (ISO 8502-2:2017)

This European Standard was approved by CEN on 19 September 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 8502-2:2017) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2017, and conflicting national standards shall be withdrawn at the latest by August 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 8502-2:2005.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 8502-2:2017 has been approved by CEN as EN ISO 8502-2:2017 without any modification.

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reagents and materials	1
5 Apparatus	2
6 Procedure	2
7 Expression of results	3
8 Test report	3
Annex A (informative) Determination of chloride by coulometric titration	5
Bibliography	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 12, *Preparation of steel substrates before application of paints and related products*.

This third edition cancels and replaces the second edition (ISO 8502-2:2005), which has been technically revised with the following changes:

- a) the analysis method has been deleted;
- b) a selection of analysis methods from other standards have been added;
- c) the coulometric method has been added and briefly described in an informative annex;
- d) the formula in [Clause 7](#) has been replaced by [Formula \(1\)](#) transforming chloride concentration in a solution to amount of chloride on the surface;
- e) the document has been editorially revised.

ISO 8502 consists of the following parts, under the general title *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness*:

- *Part 2: Laboratory determination of chloride on cleaned surfaces*
- *Part 3: Assessment of dust on steel surfaces prepared for painting (pressure-sensitive tape method)*
- *Part 4: Guidance on the estimation of the probability of condensation prior to paint application*
- *Part 5: Measurement of chloride on steel surfaces prepared for painting (ion detection tube method)*
- *Part 6: Extraction of soluble contaminants for analysis — The Bresle method*
- *Part 9: Field method for the conductometric determination of water-soluble salts*
- *Part 11: Field method for the turbidimetric determination of water-soluble sulfate*
- *Part 12: Field method for the titrimetric determination of water-soluble ferrous ions*

Introduction

The performance of protective coatings of paint and related products applied to steel is significantly affected by the state of the steel surface immediately prior to painting. The principal factors that are known to influence this performance are as follows:

- a) presence of rust and mill scale;
- b) presence of surface contaminants, including salts, dust, oils and greases;
- c) surface profile.

The ISO 8501, ISO 8502 and ISO 8503 series of International Standards have been prepared to provide methods of assessing these factors, while the ISO 8504 series provides guidance on the preparation methods that are available for cleaning steel substrates, indicating the capabilities of each in attaining specified levels of cleanliness.

These series of International Standards do not contain recommendations for the protective coating systems to be applied to the steel surface. Neither do they contain recommendations for the surface quality requirements for specific situations even though surface quality can have a direct influence on the choice of protective coating to be applied and on its performance. Such recommendations are found in other documents such as national standards and codes of practice. It will be necessary for the users of these International Standards to ensure that the qualities specified are

- compatible and appropriate both for the environmental conditions to which the steel will be exposed and for the protective coating system to be used, and
- within the capability of the cleaning procedure specified.

The four series of International Standards referred to above deal with the following aspects of preparation of steel substrates before application of paints and related products:

- ISO 8501 on visual assessment of surface cleanliness;
- ISO 8502 on tests for the assessment of surface cleanliness;
- ISO 8503 on surface roughness characteristics of blast-cleaned steel substrates;
- ISO 8504 on surface preparation methods.

Each of these International Standards is in turn divided into separate parts. This part of ISO 8502 describes a method for the assessment of chloride-containing salts that are readily soluble in water and are present on a steel surface. Rusted steel substrates, particularly of rust grades C or D (see ISO 8501-1), even when blast cleaned to preparation grade Sa 3 (see ISO 8501-1) can still be contaminated by soluble salts and corrosion products. These compounds are almost colourless and are localized at the lowest point of the rust pits. If they are not removed prior to painting, chemical reactions can result in large accumulations of rust that destroy the adhesion between the substrate and the applied protective coating. Even if the salt is readily soluble in water, it is often impossible to remove it completely from the surface by a simple washing such as that described in this procedure. The method does not therefore determine the total amount of chloride on the surface but gives an indication of the cleanliness level of the surface. Prolonging the washing time should remove a larger proportion of the salt.

Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness —

Part 2: Laboratory determination of chloride on cleaned surfaces

1 Scope

This part of ISO 8502 describes a method for the determination of chloride-containing salts that are readily soluble in water and are present on a steel surface. The method is also applicable to previously coated surfaces. This part of ISO 8502 includes a method, applicable in the field or in the laboratory, for washing off the surface while several methods are referred to for chloride analyses.

NOTE 1 ISO 8502-5 describes a field test for the determination of chloride on a surface.

NOTE 2 The precision of the method is limited by both the accuracy of the selected method of analyses and by uncertainties in the sampling procedure. The extraction method might not take all the water soluble material off the surface due to

- soluble material hiding in crevices, under folds of metal or at the bottom of pits, and
- soluble material hiding under corrosion layers, passivation layers, inhibitors, oil, grease, or other non-visible thin films as these boundary layers can prevent contact with the underlying salt for its removal.

NOTE 3 The performance of a paint system is affected by the amount of soluble chloride remaining on the surface. The acceptable level of this contamination is related to the service conditions. For further information regarding levels of water-soluble salt contamination, see ISO/TR 15235.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

3 Principle

A defined area of the steel surface is washed with a known volume of water and assessment of chloride concentration in the wash water is then carried out using instrumental methods.

4 Reagents and materials

During the analysis, use only reagents of recognized analytical grade.

4.1 Water, conforming to the requirements of grade 3 of ISO 3696.

4.2 Chalk, essentially chloride-free, **or other suitable means for marking the test area**.

4.3 Absorbent cotton pads (cotton wool), of mass 1 g to 1,5 g.

5 Apparatus

- 5.1 **Ruler.**
- 5.2 **Metal spatula or knife.**
- 5.3 **Gloves**, of plastics material.
- 5.4 **Beakers**, of capacity 250 ml.
- 5.5 **Small glass rod.**
- 5.6 **Filter funnel.**
- 5.7 **Filter paper**, approximately 120 mm diameter.
- 5.8 **Measuring cylinder**, of capacity 50 ml.
- 5.9 **Volumetric flasks**, of capacities 50 ml, 100 ml and 1 000 ml.
- 5.10 **Volumetric pipettes**, of capacities 1 ml and 20 ml.

6 Procedure

6.1 Washing of the surface

Carry out the test at least in duplicate. During the swabbing procedure, prevent accidental contamination of the wash water by using, for example, clean plastics gloves (5.3) each time.

Mark out a test area measuring approximately 25 000 mm² (for example, 250 mm × 100 mm) using the ruler (5.1) and chalk or other suitable means (4.2). Record the actual area in square millimetres.

Mark two beakers (5.4) A and B. Pour 45 ml of water (4.1) into beaker A, using the measuring cylinder (5.8). Soak an absorbent cotton pad (4.3) in the water and thoroughly swab the test area with the pad. Do not allow water to drip from the pad or run off the test area. Remove the water from the surface with the absorbent cotton pad and squeeze the washings into beaker B.

In the case of bare steel, scrape the surface with the metal spatula or knife (5.2) until bright metal is exposed and is of sufficient size to conduct a representative surface retrieval or replicates the surface condition specified immediately prior to coating.

Repeat the swabbing procedure with several portions of water until all the water in beaker A has been used. If the cotton pad becomes worn out, use a fresh one and keep the used absorbent cotton pads. The swabbing procedure should take at least 10 min.

Filter the washings, using the filter paper (5.7) and the filter funnel (5.6) and collect the filtrate in the volumetric flask of capacity 50 ml (5.9). Wash the used absorbent cotton pads and the filter paper with small portions of water (total 5 ml), using beaker B and the small glass rod (5.5). Squeeze the pads and collect the washings in the flask. Fill up to the mark with water.

NOTE An alternative method for sampling is described in ISO 8502-6.

6.2 Wash-water analysis

For the assessment of chloride concentration in the wash-water, different methods can be used depending on equipment available and accuracy required. Some examples are as follows:

- ion chromatography (ISO 10304-1);
- detection method of the ion detection tube method (ISO 8502-5);
- ion selective electrode (ISO 9517);
- coulometric titration, see [Annex A](#).

NOTE Both the ion detection tube method (ISO 8502-5) and the ion selective electrode (ISO 9517) require conditioning of the wash-water before analyses.

If all salts present in the wash-water are considered to be containing the anion chloride, conductivity measurement can be used and converted to an assumed non-specific result using ISO 8502-9.

Other methods than those listed above might be appropriate. The measurement uncertainty of the method used shall always be taken into account and reported.

Titration including mercury or chromate containing substances should be avoided due to health and environmental hazards

7 Expression of results

Calculate the amount of chloride per unit surface area, $\rho_A(\text{Cl})$, expressed in milligrams per square metre, using [Formula \(1\)](#):

$$\rho_A(\text{Cl}) = \frac{c \times V \cdot 10^3}{A} \quad (1)$$

where

c is the chloride concentration in the wash-water, expressed in milligrams per litre;

A is the surface area washed, expressed in square millimetres.

V is the sampling volume of water, expressed in millilitres (50 ml used in the procedure of [6.1](#)).

Dilution, e.g. by adding acid or ion strength adjustor or from adding a small amount of the sample to a larger volume of buffer solution (required for the ion detection tube, the ion selective electrode and for the coulometric titration methods, respectively), shall be taken into account when calculating the volume to be used in [Formula \(1\)](#).

8 Test report

The test report shall contain at least the following information:

- a) all details necessary to identify the surface tested, including details of shape and attitude (e.g. horizontal, vertical, at an angle);
- b) a reference to this part of ISO 8502, i.e. ISO 8502-2;
- c) the method used for assessing the chloride concentration in the wash-water;
- d) the results of the test, including the results of all individual determinations and their mean, expressed as indicated in [Clause 7](#);

- e) any deviations from the test method specified;
- f) any unusual features (anomalies) observed during the test;
- g) date(s) of the test.

Annex A (informative)

Determination of chloride by coulometric titration

Principle for the method: A current is passed between a cathode and a silver-containing anode placed in a buffer solution to which a portion of a reference solution with known chloride contents is added followed by the sample. The chloride ions will react with the produced silver ions forming a precipitate. The end point can be detected by changes in solution conductivity due to the presence of excess silver ions in solution or by potential changes.

Accuracy of the method is dependent on the system used for controlling current and the end point, the buffer solution and electrodes used (affecting the current efficiency and solubility of species formed), the accuracy of the reference solution, the difference in chloride concentration between the reference and the sample and the use of the instrumentation.

If commercial instruments are used, it is vital to follow the instrument manual, using proper buffer solutions etc.

Bibliography

- [1] ISO 9517, *Iron ores — Determination of water-soluble chloride — Ion-selective electrode method*
- [2] ISO 10304-1, *Water quality — Determination of dissolved anions by liquid chromatography of ions — Part 1: Determination of bromide, chloride, fluoride, nitrate, nitrite, phosphate and sulfate*
- [3] ISO 8502-5, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 5: Measurement of chloride on steel surfaces prepared for painting (ion detection tube method)*
- [4] ISO 8502-6, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 6: Extraction of soluble contaminants for analysis — The Bresle method*
- [5] ISO 8502-9, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 9: Field method for the conductometric determination of water-soluble salts*
- [6] ISO/TR 15235, *Preparation of steel substrates before application of paints and related products — Collected information on the effect of levels of water-soluble salt contamination*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK