

# Plastics — Polybutene-1 (PB-1) moulding and extrusion materials

**Part 2: Preparation of test specimens  
and determination of properties (ISO  
8986-2:2009)**

ICS 83.080.20

## National foreword

This British Standard is the UK implementation of EN ISO 8986-2:2009. It supersedes BS EN ISO 8986-2:1996 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/82, Thermoplastic materials.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 December 2009

© BSI 2009

ISBN 978 0 580 60084 5

### Amendments/corrigenda issued since publication

Date	Comments

English Version

Plastics - Polybutene-1 (PB-1) moulding and extrusion materials  
- Part 2: Preparation of test specimens and determination of  
properties (ISO 8986-2:2009)

Plastiques - Matériaux à base de polybutène-1 (PB-1) pour  
moulage et extrusion - Partie 2: Préparation des  
échantillons et détermination des propriétés (ISO 8986-  
2:2009)

Kunststoffe - Polybuten-1 (PB-1)-Formmassen - Teil 2:  
Herstellung von Probekörpern und Bestimmung von  
Eigenschaften (ISO 8986-2:2009)

This European Standard was approved by CEN on 21 October 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

## Foreword

This document (EN ISO 8986-2:2009) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2010, and conflicting national standards shall be withdrawn at the latest by May 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 8986-2:1995.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

### Endorsement notice

The text of ISO 8986-2:2009 has been approved by CEN as a EN ISO 8986-2:2009 without any modification.

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 8986-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This second edition cancels and replaces the first edition (ISO 8986-2:1995), which has been technically revised to reflect the changes made in the concurrent revision of ISO 8986-1. It also incorporates the Amendment ISO 8986-2:1995/Amd.1:2000.

ISO 8986 consists of the following parts, under the general title *Plastics — Polybutene-1 (PB-1) moulding and extrusion materials*:

- *Part 1: Designation system and basis for specifications*
- *Part 2: Preparation of test specimens and determination of properties*



# Plastics — Polybutene-1 (PB-1) moulding and extrusion materials —

## Part 2:

## Preparation of test specimens and determination of properties

### 1 Scope

This part of ISO 8986 specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of polybutene-1 (PB-1) moulding and extrusion materials. For the sake of simplicity, the designation polybutene and the abbreviation PB are used in both parts of ISO 8986. Requirements for handling test material and for conditioning both the test material before moulding and the specimens before testing are also specified.

Procedures and conditions for the preparation of test specimens and procedures for measuring properties of the materials from which these specimens are made are given. Properties and test methods which are suitable and necessary to characterize PB moulding and extrusion materials are listed.

The properties have been selected from the general test methods in ISO 10350-1. Other test methods in wide use for or of particular significance to these moulding and extrusion materials are also included in this part of ISO 8986, as is the designatory property specified in Part 1.

In order to obtain reproducible and comparable test results, it is necessary to use the methods of specimen preparation and conditioning, the specimen dimensions and the test procedures specified herein. Values determined will not necessarily be identical to those obtained using specimens of different dimensions or prepared using different procedures.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 62, *Plastics — Determination of water absorption*

ISO 75-2, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite*

ISO 178, *Plastics — Determination of flexural properties*

ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 179-2, *Plastics — Determination of Charpy impact properties — Part 2: Instrumented impact test*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 527-4, *Plastics — Determination of tensile properties — Part 4: Test conditions for isotropic and orthotropic fibre-reinforced plastic composites*

ISO 899-1, *Plastics — Determination of creep behaviour — Part 1: Tensile creep*

ISO 1133, *Plastics — Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics*

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method*

ISO 1183-3, *Plastics — Methods for determining the density of non-cellular plastics — Part 3: Gas pycnometer method*

ISO 1628-3, *Plastics — Determination of the viscosity of polymers in dilute solution using capillary viscometers — Part 3: Polyethylenes and polypropylenes*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 3167, *Plastics — Multipurpose test specimens*

ISO 4589-2, *Plastics — Determination of burning behaviour by oxygen index — Part 2: Ambient-temperature test*

ISO 8256, *Plastics — Determination of tensile-impact strength*

ISO 8986-1, *Plastics — Polybutene-1 (PB-1) moulding and extrusion materials — Part 1: Designation system and basis for specifications*

ISO 10350-1, *Plastics — Acquisition and presentation of comparable single-point data — Part 1: Moulding materials*

ISO 11357-2, *Plastics — Differential scanning calorimetry (DSC) — Part 2: Determination of glass transition temperature*

ISO 11357-3, *Plastics — Differential scanning calorimetry (DSC) — Part 3: Determination of temperature and enthalpy of melting and crystallization*

ISO 11357-6, *Plastics — Differential scanning calorimetry (DSC) — Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT)*

IEC 60093, *Methods of test for volume resistivity and surface resistivity of solid electrical insulating materials*

IEC 60112, *Method for the determination of the proof and the comparative tracking indices of solid insulating materials*

IEC 60243-1, *Electrical strength of insulating materials — Test methods — Part 1: Tests at power frequencies*

IEC 60250, *Recommended methods for the determination of the permittivity and dielectric dissipation factor of electrical insulating materials at power, audio and radio frequencies including metre wavelengths*

IEC 60296, *Fluids for electrotechnical applications — Unused mineral insulating oils for transformers and switchgear*



IEC 60695-11-10, *Fire hazard testing — Part 11-10: Test flames — 50 W horizontal and vertical flame test methods*

### 3 Preparation of test specimens

#### 3.1 General

The test specimens shall be prepared by compression moulding.

It is essential that the specimens are always prepared by the same procedure using the same processing conditions.

The material shall be kept in moisture-proof containers until it is required for use.

The moisture content of filled or reinforced materials shall be expressed as a percentage of the total mass of the compound.

#### 3.2 Treatment of the material before moulding

Before processing, no pretreatment of the material sample is normally necessary.

#### 3.3 Compression moulding

Compression-moulded sheets shall be prepared in accordance with ISO 293, using the conditions specified in Table 1.

**Table 1 — Conditions for compression moulding of test specimens**

Material	Moulding temperature °C	Average cooling rate °C/min	Demoulding temperature °C	Full pressure MPa	Full-pressure time min	Preheating pressure MPa	Preheating time min
All grades	200	30	30 ± 5	5 or 10 <sup>a</sup>	5 ± 1	Contact	5 to 15
<sup>a</sup> Use 5 MPa with a frame mould and 10 MPa with a positive mould.							

The test specimens required for the determination of the properties shall be machined from the compression-moulded sheets in accordance with ISO 2818 or punched out.

A type 1 (frame) mould may be used, but it is necessary to start cooling whilst simultaneously applying the full pressure. This avoids the melt being pressed out of the frame and avoids sink marks.

For thicker sheet ( $\approx 4$  mm), a type 2 (positive) mould has been found to work satisfactorily.

The preheating time depends on the type of mould and the type of energy input (steam or electricity). For frame moulds, 5 min is usually sufficient but for positive moulds, due to the bigger mass, a preheating time of up to 15 min may be necessary, especially if electric heating is used.

NOTE 1 Since only the average cooling rate is specified, the actual cooling rate during crystallization is not fixed. This can lead to significant deviations in properties related to crystallinity, such as density and mechanical properties.

NOTE 2 Since for frame moulds full pressure is only applied upon cooling, compression-moulded sheets may suffer from insufficient homogeneity and pellet boundaries may be preserved if the heating time or the pressure is insufficient.

## 4 Conditioning of test specimens

Before testing, test specimens shall be conditioned at atmospheric pressure in one of the standard atmospheres specified in ISO 291 for the length of time recommended by the material manufacturer. The conditioning atmosphere and conditioning time used shall be reported along with the test conditions in the test report.

Due to the temperature dependence of the conditioning process, conditioning of test specimens at 27 °C may require longer or lead to unsatisfactory test results. For the sake of the reproducibility of the results, conditioning at 23 °C is therefore preferred.

Because of the slowness of the crystalline-phase transition which takes place after PB compounds have solidified from the melt and which results in significant changes in characteristics such as shrinkage and tensile properties, it is necessary to delay physical testing after moulding until this phase transition is complete.

The use of accelerated ageing at elevated pressure is allowed if it can be demonstrated that the test results are reproducible and equivalent to those obtained on specimens aged at atmospheric pressure.

## 5 Determination of properties

In the determination of properties and the presentation of data, the standards, supplementary instructions and notes given in ISO 10350-1 shall be applied. All tests shall be carried out in one of the standard atmospheres specified in ISO 291 unless specifically stated otherwise in Tables 2 and 3.

NOTE Comparison of data obtained under different test conditions may lead to erroneous conclusions.

Table 2 is compiled from ISO 10350-1, and the properties listed are those which are appropriate to polybutene (PB) moulding and extrusion materials. These properties are those considered useful for comparisons of data generated for different thermoplastics.

Table 3 contains those properties, not found specifically in Table 2, which are in wide use or of particular significance in the practical characterization of polybutene (PB) moulding and extrusion materials.

Table 2 — General properties and test conditions (selected from ISO 10350-1)

Property	Unit	Standard	Specimen type (dimensions in mm)	Specimen preparation <sup>a</sup>	Test conditions and supplementary instructions
<b>Rheological properties</b>					
Melt volume-flow rate	cm <sup>3</sup> /10 min	ISO 1133	Moulding compound	—	See conditions given in ISO 8986-1
Melt mass-flow rate	g/10 min				Use melt density of 776,5 kg/m <sup>3</sup> to calculate the melt mass-flow rate
<b>Mechanical properties</b>					
Tensile modulus	MPa	ISO 527-2, ISO 527-4	Type 5A (ISO 527-2) or type 1B (ISO 527-4)	Q	Test speed 1 mm/min
Yield stress	MPa				Test speed 500 mm/min
Yield strain	%				Test speed 500 mm/min
Nominal strain at break	%				Test speed 50 mm/min
Stress at 50 % strain	MPa				Test speed 50 mm/min
Stress at break	MPa				Test speed 50 mm/min
Strain at break	%				Test speed 50 mm/min
Tensile creep modulus	MPa	ISO 899-1	See ISO 3167	Q	At 1 h } Strain ≤ 0,5 % At 1 000 h }
Flexural modulus	MPa	ISO 178	80 × 10 × 4	Q	Test speed 2 mm/min
Charpy impact strength	kJ/m <sup>2</sup>	ISO 179-1 or ISO 179-2	80 × 10 × 4	Q	Method 1eU (edgewise impact)
Charpy notched impact strength	kJ/m <sup>2</sup>		80 × 10 × 4 V-notch, r = 0,25	Q	Method 1eA (edgewise impact)
Tensile notched impact strength	kJ/m <sup>2</sup>	ISO 8256	80 × 10 × 4 double V-notch, r = 1	Q	Only to be quoted if fracture cannot be obtained with notched Charpy test
<b>Thermal properties</b>					
Melting temperature	°C	ISO 11357-3	Moulding compound	—	Use 10 °C/min
Glass transition temperature	°C	ISO 11357-2	Moulding compound	—	Use 20 °C/min
Temperature of deflection under load	°C	ISO 75-2	80 × 10 × 4 flatwise	Q	0,45 MPa and 1,8 MPa
Coefficient of linear thermal expansion	°C <sup>-1</sup>	TMA (see ISO 10350-1)	Prepared from ISO 3167	Q	Parallel } Quote the secant Normal } value over the temperature range 23 °C to 55 °C
Flammability	mm/min	IEC 60695-11-10	125 × 13 × 3	Q	Method A — linear burning rate of horizontal specimens
Oxygen index	%	ISO 4589-2	80 × 10 × 4	Q	Procedure A — top surface ignition

Table 2 (continued)

Property	Unit	Standard	Specimen type (dimensions in mm)	Specimen preparation <sup>a</sup>	Test conditions and supplementary instructions
<b>Electrical properties</b>					
Relative permittivity	—	IEC 60250	$\geq 80 \times \geq 80 \times 1$	Q	Frequency 100 Hz and 1 MHz (compensate for electrode edge effect)
Dissipation factor	—				
Volume resistivity	$\Omega \cdot m$	IEC 60093	$\geq 80 \times \geq 80 \times 1$	Q	Voltage 100 V
Surface resistivity	$\Omega$				
Electric strength	kV/mm	IEC 60243-1	$\geq 80 \times \geq 80 \times 1$ $\geq 80 \times \geq 80 \times 3$	Q	Use 25 mm/75 mm coaxial-cylinder electrode configuration. Immerse in IEC 60296 transformer oil. Use short time (rapid rise) test
Comparative tracking index	—	IEC 60112	$\geq 15 \times \geq 15 \times 4$	Q	Use solution A
<b>Other properties</b>					
Water absorption	%	ISO 62	$50 \times 50 \times 3$ or $\phi 50 \times 3$ disc	Q	24 h immersion in water at 23 °C
<sup>a</sup> Q = Compression moulding.					

Table 3 — Additional properties and test conditions of particular utility to PB moulding and extrusion materials

Property	Unit	Standard	Specimen type (dimensions in mm)	Specimen preparation	Test conditions and supplementary instructions
<b>Other properties</b>					
Viscosity number	ml/g	ISO 1628-3	Moulding compound	—	—
Oxidation induction time	min	ISO 11357-6	Moulding compound	—	Isothermal method, test temperature 220 °C
Density	kg/m <sup>3</sup>	ISO 1183-1, ISO 1183-2 or ISO 1183-3	See next column	Use extrudate from melt flow rate determination (see Table 2)	
NOTE Although density is no longer used as a designatory property for PB compounds, it has been kept in Table 3 because it is still used in practice.					



---

## BSI - British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001 Email: [orders@bsigroup.com](mailto:orders@bsigroup.com) You may also buy directly using a debit/credit card from the BSI Shop on the Website <http://www.bsigroup.com/shop>

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact Information Centre. Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048 Email: [info@bsigroup.com](mailto:info@bsigroup.com)

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001 Email: [membership@bsigroup.com](mailto:membership@bsigroup.com)

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsigroup.com/BSOL>

Further information about BSI is available on the BSI website at <http://www.bsigroup.com>.

### Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright and Licensing Manager. Tel: +44 (0)20 8996 7070 Email: [copyright@bsigroup.com](mailto:copyright@bsigroup.com)