

BS EN ISO 9117-6:2012



BSI Standards Publication

Paints and varnishes — Drying tests

Part 6: Print-free test (ISO 9117-6:2012)

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 9117-6:2012. It supersedes BS EN ISO 3678:1995 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/10, Test methods for paints.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012. Published by BSI Standards Limited 2012

ISBN 978 0 580 71912 7

ICS 87.040

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 August 2012.

Amendments issued since publication

Date	Text affected
------	---------------

English Version

Paints and varnishes - Drying tests - Part 6: Print-free test (ISO 9117-6:2012)

Peintures et vernis - Essais de séchage - Partie 6: Essai de séchage apparent complet (ISO 9117-6:2012)

Beschichtungsstoffe - Trocknungsprüfungen - Teil 6: Bestimmung der Abdruckfestigkeit (ISO 9117-6:2012)

This European Standard was approved by CEN on 30 June 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 9117-6:2012) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2013, and conflicting national standards shall be withdrawn at the latest by January 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 3678:1995.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, the United Kingdom and Turkey.

Endorsement notice

The text of ISO 9117-6:2012 has been approved by CEN as a EN ISO 9117-6:2012 without any modification.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9117-6 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

It cancels and replaces ISO 3678:1976, which has been technically revised.

ISO 9117 consists of the following parts, under the general title *Paints and varnishes — Drying tests*:

- *Part 1: Determination of through-dry state and through-dry time*
- *Part 2: Pressure test for stackability*
- *Part 3: Surface-drying test using ballotini*
- *Part 4: Test using a mechanical recorder*
- *Part 5: Modified Bandow-Wolff test*
- *Part 6: Print-free test*

Paints and varnishes — Drying tests —

Part 6: Print-free test

1 Scope

This part of ISO 9117 specifies a method for assessing, by means of a simple empirical test, the resistance of a coat of paint, varnish or related product to imprinting by a nylon gauze under a specified force applied for a specified time.

The method may be carried out

- either as a “pass/fail” test by determining whether the print-free state has been reached after a specified period of drying or, in the case of stoving coatings, after stoving and ageing under specified conditions,
- or by repeating the print-free test at suitable intervals until the print-free time is obtained.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1513, *Paints and varnishes — Examination and preparation of test samples*

ISO 1514, *Paints and varnishes — Standard panels for testing*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

print-free

state of a coating of paint or varnish when gauze of a specified grade under a specified force during a specified time does not leave on the surface an imprint, visible under normal corrected vision

3.2

print-free time

period of time elapsing between the moment at which a coating is applied to a prepared test panel and that at which the coating is assessed as just print-free, using the test procedure specified

4 Apparatus

4.1 **Squares** of woven monofilament polyamide gauze, minimum size 25 mm × 25 mm.

Unless otherwise specified, the gauze shall be of 0,120 mm thread diameter and of approximately 0,2 mm aperture. Depending upon the type of coating under test, other grades of similar construction may be used if necessary, subject to agreement between the interested parties.

4.2 Rubber discs, of diameter 22 mm, thickness 5 mm and hardness 50 IRHD \pm 3 IRHD¹⁾ (see ISO 48).

4.3 Cylindrical weights, of mass 200 g, 500 g and 1 000 g and diameter not less than 22 mm.

The diameter of the rubber discs and the mass of the weights may vary slightly from those specified in 4.2 and 4.3. The pressures on the coatings, however, shall be equal to those obtained using discs and weights of the dimensions specified in 4.2 and 4.3, i.e. 5,2 kPa (200 g), 13,2 kPa (500 g) and 26,3 kPa (1 000 g).

4.4 Stopwatch or stopclock.

5 Sampling

Take a representative sample of the product to be tested (or of each product in the case of a multi-coat system), in accordance with ISO 15528.

Examine and prepare each sample for testing, in accordance with ISO 1513.

6 Test panels

6.1 Substrate

The test panels shall be of glass, burnished steel, burnished tinplate or burnished aluminium, complying with the requirements of ISO 1514.

6.2 Preparation and coating of the panels

Prepare the panels in accordance with ISO 1514 unless otherwise required. The test panel shall be coated by the specified method with the appropriate primer and/or undercoat and allowed to dry for the specified period. In the case of multi-coat stoving products, the primer and/or undercoat shall be stoved under the agreed stoving conditions before applying the product under test by the specified method.

6.3 Thickness of coating

Determine the thickness, in micrometres, of the dry coating by the method specified, using one of the procedures specified in ISO 2808.

7 Procedure

7.1 Drying the test panel

Allow the coated panel to dry in a vertical position in the standard atmosphere specified in ISO 3270, (23 \pm 2) °C and relative humidity of (50 \pm 5) %, unless otherwise agreed. The panel shall be dried with free circulation of air but shielded from draughts and direct sunlight.

Stoving products shall be stoved and aged under the specified or agreed conditions.

7.2 Assessment of print-free state

7.2.1 After the completion of the specified drying time, place the test panel in a horizontal position.

1) International rubber hardness degrees.

7.2.2 Place a square of polyamide gauze (4.1) on the surface of the coating and place a rubber disc (4.2) centrally on the square.

Place the appropriate weight (4.3) carefully on the disc so that the axes of the disc and weight are coincident and start the stopwatch or stopclock (4.4).

7.2.3 Unless otherwise specified or agreed, remove the weight, rubber disc and gauze square after 10 min.

7.2.4 Examine the surface of the coating immediately in the test area, using normal corrected vision.

The surface is "print-free" if no imprint can be seen. Record the result as "print-free" or "not print-free".

7.3 Determination of print-free time

Take a number of coated test panels. At appropriate intervals, starting shortly before the coating is expected to be print-free and using an untouched area of the same panel for each test (or a different panel as necessary), carry out the test as specified in 7.2, until the test shows the coating to be print-free.

Record the time taken for the coating to become just print-free.

8 Test report

The test report shall include the following information:

- a) all details necessary to identify the product under test;
- b) a reference to this part of ISO 9117 (ISO 9117-6);
- c) details of the preparation of the test panels, including:
 - 1) the material, the thickness and the surface preparation of the substrate (see 6.1),
 - 2) the method of application of the test coating to the substrate, including the duration and conditions of drying between coats in the case of a multi-coat system (see 6.2),
 - 3) the dry-film thickness, in micrometres, of the coating and method of measurement from ISO 2808 (see 6.3);
- d) the duration and conditions of drying (or stoving) the coat and the conditions of ageing, if applicable, before testing (see 7.1);
- e) the intervals between tests where the print-free time is required;
- f) details of the grade of polyamide gauze used and the force applied in carrying out the test;
- g) the result of the test as required:
 - 1) either whether or not the coating was print-free after the specified time (pass/fail test),
 - 2) or the print-free time;
- h) any deviation, by agreement or otherwise, from the procedure specified, such as the duration of application of the gauze;
- i) any unusual features (anomalies) observed during the test;
- j) the date of the test.

Bibliography

- [1] ISO 48, *Rubber, vulcanized or thermoplastic — Determination of hardness (hardness between 10 IRHD and 100 IRHD)*
- [2] ISO 3270, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK



...making excellence a habit.™