

BS EN ISO 9455-10:2012



BSI Standards Publication

Soft soldering fluxes — Test methods

Part 10: Flux efficacy test, solder
spread method

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 9455-10:2012. It supersedes BS EN ISO 9455-10:2001 which is withdrawn.

The UK participation in its preparation was entrusted by Technical Committee NFE/27, Tin and tin alloys, to Subcommittee NFE/27/4, Solders and soldering fluxes.

BSI, as a member of CEN, is obliged to publish EN ISO 9455-10 as a British Standard. However, attention is drawn to the fact that during the development of this European Standard, the UK voted against its approval as a European Standard.

The UK Technical subcommittee NFE/27/4, Solders and soldering fluxes, submitted a negative vote due to the following:

- The test method uses brass test plates, on which the solder spread is measured. However, note 2 to paragraph 7.1 states that “an alternative is 10 oxidized copper test plates, each of dimensions 40 mm × 40 mm, cut from phosphorus deoxidized sheet, 0,5 mm thick, complying with ISO 197-1,[1] for each flux being tested.” It is thus envisaged that the solder spread can be measured on oxidised copper instead of brass.
- Paragraph 8.1 describes the preparation of the test plates prior to testing the extent of solder spread. This involves, inter alia, dipping the plates into a strong solution comprising sulphuric and nitric acids. As copper oxide reacts with both sulphuric and nitric acids, the effect of this would be to remove any oxidation from the surface, therefore, it would no longer be an oxidised copper plate. The note to paragraph 8.1 states “This preparation method is applicable to both brass and copper test plates”.

There is a lack of clarity as whether testing is permitted to both brass and oxidised test plates, as per clause 8.1, or whether it is confined to brass test plates, as per clause 7.1.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012

Published by BSI Standards Limited 2012

ISBN 978 0 580 72886 0

ICS 25.160.50

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2012.

Amendments issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 9455-10

September 2012

ICS 25.160.50

Supersedes EN ISO 9455-10:2000

English Version

**Soft soldering fluxes - Test methods - Part 10: Flux efficacy test,
solder spread method (ISO 9455-10:2012)**

Flux de brasage tendre - Méthodes d'essai - Partie 10:
Essai d'efficacité du flux, méthode d'étalement (ISO 9455-
10:2012)

Flussmittel zum Weichlöten - Prüfverfahren - Teil 10:
Bestimmung der Wirksamkeit des Flussmittels,
Ausbreitungsprüfung (ISO 9455-10:2012)

This European Standard was approved by CEN on 14 September 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
---------------	---

Foreword

This document (EN ISO 9455-10:2012) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2013, and conflicting national standards shall be withdrawn at the latest by March 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 9455-10:2000.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 9455-10:2012 has been approved by CEN as a EN ISO 9455-10:2012 without any modification.

Contents		Page
1	Scope	1
2	Normative references	1
3	Symbols	1
4	Principle	1
5	Reagents	2
6	Apparatus and materials	2
7	Test specimens	3
7.1	Brass test plates	3
7.2	Solder sample	3
8	Procedure	3
8.1	Preparation of test plates	3
8.2	Test method	3
8.3	Replicate tests	4
9	Expression of results	4
10	Precision	4
11	Test report	5
Annex A (informative) Method for the preparation of standard reference rosin (colophony) based liquid fluxes, having 25 % by mass non-volatile content		6
Annex B (informative) Chemical composition of brass test plates		8
Bibliography		9

Soft soldering fluxes — Test methods —

Part 10:

Flux efficacy test, solder spread method

1 Scope

This part of ISO 9455 specifies a method for the determination of the efficacy of a soft soldering flux. The method is known as the solder spread method of filler metal and is applicable to all flux classes defined in ISO 9454-1.

NOTE An alternative method for the determination of the flux efficacy, applicable to liquid fluxes only, known as the wetting balance method, is specified in ISO 9455-16.^[3]

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9453, *Soft solder alloys — Chemical compositions and forms*

ISO 9454-1:1990, *Soft soldering fluxes — Classification and requirements — Part 1: Classification, labelling and packaging*

3 Symbols

\bar{A}	arithmetic mean spread area, in square millimetres
H	height of spread solder, in millimetres
D	diameter, in millimetres, when the solder used is considered as a sphere, $D = 1,24 \times V^{1/3}$
R	reproducibility
r	repeatability
s_w	standard deviation within laboratory
s_b	standard deviation between laboratories
ρ	density, in grams per millilitre, of solder under test at the test temperature
V	volume, in millilitres, of the solder used

4 Principle

A specially prepared brass test sheet is treated with a known quantity of the flux under test and a standard quantity of specified solder alloy. Upon heating, the solder alloy melts and spreads across the surface of the brass test sheet, the extent of spread being a measure of the flux efficacy. The area covered by the solder is determined by means of a planimeter or other suitable technique.

This test method is applicable to all fluxes. If required, the efficacy of the flux sample under test can be compared with that of a standard flux (see Annex A).

NOTE It is possible to use copper as the test surface. However, it is preferable to use brass as the test surface in order to distinguish between various fluxes because it provides a better surface for differentiation than copper does.

5 Reagents

Use only reagents of recognized analytical grade and distilled or demineralized water or water of equivalent purity.

5.1 Acid preparation solution, prepared in a fume cupboard by cautiously mixing the following ingredients in the order given, cooling as necessary.

- 140 ml water;
- 225 ml nitric acid ($\rho = 1,42$ g/ml);
- 600 ml sulfuric acid ($\rho = 1,84$ g/ml);
- 5 g sodium chloride;
- 18 ml copper solution (5.2).

Thoroughly mix the solution.

This preparation solution shall be freshly prepared every day.

WARNING — The mixture is extremely corrosive and produces hazardous fumes.

5.2 Copper solution, prepared by dissolving 10 g pure copper turnings in 100 ml of 50 % by volume nitric acid solution ($\rho = 1,42$ g/ml).

5.3 Industrial methylated spirits.

5.4 Acetone.

6 Apparatus and materials

6.1 Solder bath, containing not less than 4 kg of molten solder. The liquid solder in the bath shall be at least 25 mm in depth, with a surface area easily capable of accommodating the test specimen. As a minimum, the bath temperature shall be capable of being maintained at a set temperature of the liquidus temperature of the alloy in the test plus 35 °C. The test temperature shall be documented.

6.2 Tongs, or other suitable mechanical device, for lowering the brass test plate (7.1), in a horizontal plane, onto the surface of the liquid solder in the bath (6.1) and raising it again, also in a horizontal plane.

6.3 Planimeter, suitable for measuring surface areas of the order of 100 mm².

6.4 Microsyringe, or micropipette, capable of delivering 25 µl (i.e. 0,025 ml).

6.5 Plastic tweezers or tongs, for use in the cleaning procedure for test plates.

6.6 Micrometer, as specified in ISO 3611.^[2]

6.7 Filter paper, for use in cleaning procedure for test plates.

7 Test specimens

7.1 Brass test plates

Each plate shall be of dimensions 40 mm × 40 mm. Prepare 10 plates, of alloy CuZn37 or CuZn40, cut from brass sheet 0,5 mm thick, for each flux being tested.

NOTE 1 Annex B gives the chemical composition of these two brasses.

NOTE 2 An alternative is 10 oxidized copper test plates, each of dimensions 40 mm × 40 mm, cut from phosphorus deoxidized sheet, 0,5 mm thick, complying with ISO 197-1,^[1] for each flux being tested.

NOTE 3 One corner of the test plate can be bent, to facilitate handling with the tongs (6.2).

7.2 Solder sample

Clean a length of solid solder wire as agreed between the contracting parties, with a diameter of 1 mm ± 0,05 mm, weighing between 0,49 g and 0,50 g with a filter paper soaked in industrial methylated spirits (5.3) or acetone (5.4). Wind the length of wire into a tight, flat spiral for use in the test. After cleaning, handle the solder wire only with clean cotton gloves.

The solder used for the test and the test temperature shall be selected from one of the following:

- S-Sn60Pb40 (in accordance with ISO 9453) at 235 °C ± 3 °C;
- S-Sn96Ag3Cu1 (in accordance with ISO 9453) at 255 °C ± 3 °C;
- any other solder or temperature combinations as agreed between the customer and the flux supplier — for test temperatures, see 6.1.

8 Procedure

8.1 Preparation of test plates

Immediately before use, pretreat the 10 test pieces in the following manner; handle with clean tongs or with a suitable mechanical device (6.2).

Degrease the test plates (7.1) thoroughly in acetone (5.4) and allow to dry in clean air.

Immerse each test plate separately for approximately 15 s in the acid preparation solution (5.1) using the plastic tweezers or tongs (6.5). Hold the solution at a temperature between 15 °C and 25 °C.

Wash the test plates in water for a maximum of 5 s.

Repeat the acid preparation operation not more than three times, until a uniform matt lustre on the surface of the test plates has been attained.

After the final rinsing in water, rinse the test plates in methylated spirits (5.3) and dry them with filter paper (6.7).

NOTE This preparation method is applicable to both brass and copper test plates.

8.2 Test method

Immediately after the cleaning operation specified in 8.1, take one of the test plates and apply the flux sample under test to the central region of the plate, in accordance with a) or b):

- a) for liquid flux samples: measure 0,025 ml ± 0,001 25 ml of the flux sample by means of the microsyringe or micropipette (6.4);
- b) for paste and solid flux samples: weigh 0,025 g ± 0,001 25 g of the flux sample.

Place a solder sample (7.2) in the middle of the test plate. Lower the test plate, with its plane horizontal, on to the surface of the solder in the solder bath of filler metal (6.1).

After 5 s of the start of spreading, remove the test plate from the solder bath, keeping it in a horizontal plane until it has cooled to room temperature.

Remove the flux residue with a suitable solvent.

Determine the area, in square millimetres, covered by the melted solder alloy by use of the planimeter (6.3), or measure the height of the solder by use of a micrometer (6.6) and calculate the ratio of spread, expressed as a percentage, by the formula:

$$\frac{D - H}{D} \times 100$$

where

H is the height of spread solder, in millimetres;

D is the diameter, in millimetres, when the solder used is considered as a sphere, $D = 1,24 \times V^{1/3}$;

V is the volume, in millilitres, of the solder used.

8.3 Replicate tests

Using the remaining nine test plates, re-prepare as specified in 8.1, repeat the test method specified in 8.2, calculating either the area or the ratio of spread as in the original sample.

9 Expression of results

The efficacy of the flux sample under test is expressed as the arithmetic mean and the standard deviation of the 10 areas of spread, in square millimetres or ratios of spread, expressed as a percentage, measured in the tests carried out as described in Clause 8.

The efficacy of the flux sample under test may also be expressed in comparison with results obtained by using the test described in Clause 8 on a standard flux, prepared as described in Annex A.

10 Precision

Interlaboratory tests have been carried out on two colophony fluxes without addition of halide and with 0,6 % by mass added halide.

Nine laboratories took part in the tests with the results given in Tables 1 to 3.

Table 1 — Precision for halide- and non-halide-type fluxes

Parameter		Flux type 1.1.2 0,6 % by mass halide	Flux type 1.1.3 halide-free
Arithmetic mean, mm ²	\bar{A}	283,1	155,7
Standard deviations			
— within laboratory	s_w^a	34,4	14,3
— between laboratories	s_b^a	62,8	20,4
Repeatability	r^a	96,4	40,0
Reproducibility	R^a	175,7	57,2

^a The evaluation is based on single values.

Table 2 — Precision for ratio of spread values on brass plates

Parameter		Flux type				
		1.1.1	1.1.3	1.2.2	2.2.2	3.2.1
Arithmetic mean, mm ²	\bar{A}	106,95	122,68	155,07	192,95	215,57
Standard deviations						
— within laboratory	s_w	7,44	8,33	11,70	10,77	10,36
— between laboratories	s_b	18,42	8,42	12,71	14,41	14,19
Repeatability	r	20,84	23,23	32,77	30,16	29,02
Reproducibility	R	51,58	23,57	35,60	40,36	39,72

Table 3 — Precision for area of spread and ratio of spread on copper plates

Parameter		Flux type									
		1.1.1		1.1.3		1.2.2		2.2.2		3.2.1	
		Area of spread	Ratio of spread	Area of spread	Ratio of spread	Area of spread	Ratio of spread	Area of spread	Ratio of spread	Area of spread	Ratio of spread
Arithmetic mean	\bar{A}	42,17	55,12	146,02	85,90	124,17	80,40	214,23	89,81	224,21	90,41
Standard deviations											
— within laboratory	s_w	5,45	4,10	4,22	0,45	6,36	1,39	18,12	1,88	11,22	0,45
— between laboratories	s_b	7,25	5,34	4,59	0,53	23,89	4,37	25,31	2,33	21,10	0,58
Repeatability	r	15,25	11,48	11,80	1,26	17,82	3,89	50,74	5,26	31,41	1,27
Reproducibility	R	20,31	14,96	12,86	1,49	66,89	12,23	70,87	6,52	59,08	1,63

11 Test report

The test report shall include at least the following information:

- identification of the test sample;
- the test method used, i.e. reference to this part of ISO 9455 (ISO 9455-10:2012);
- identification of test plate;
- grade of solder tested;
- temperature of test;
- the result obtained (i.e. area or ratio of spread obtained);
- any unusual features noted during the determination;
- details of any operation not included in this part of ISO 9455, or regarded as optional.

Annex A (informative)

Method for the preparation of standard reference rosin (colophony) based liquid fluxes, having 25 % by mass non-volatile content

A.1 General

This annex gives a method for the preparation of two standard rosin (colophony) based liquid fluxes having 25 % by mass non-volatile content, one non-activated and the other halogen activated (i.e being class 1.1.1.A and class 1.1.2.A, respectively, as defined in ISO 9454-1. The specifications for the flux constituents are based on IEC 60068-2-20:2008,^[4] Annex B.

The standard flux may be used as a reference against which the efficacy of the flux under test may be compared (see Clauses 4 and 9).

A.2 Principle

The non-activated flux is prepared by dissolving a special grade of rosin (colophony) in propan-2-ol. The halogen-activated flux is prepared in a similar way, with the addition of diethylamine hydrochloride.

A.3 Apparatus

Usual laboratory apparatus, including an oven capable of being maintained at $110\text{ °C} \pm 2\text{ °C}$, is required.

A.4 Reagents

Use only reagents of recognized analytical grade.

A.4.1 Rosin (colophony). Water white grade gum rosin, or equivalent, which shall comply with the following requirements:

- acid value (as KOH): 155 mg/g to 180 mg/g
- softening point: 70 °C minimum
- flow point: 76 °C minimum
- ash: 0,05 % by mass maximum
- solubility: to give a clear 1 + 1 solution in propan-2-ol

A.4.2 Diethylamine hydrochloride. Dried for 2 h at $110\text{ °C} \pm 2\text{ °C}$.

A.4.3 Propan-2-ol (isopropanol), which shall comply with the following requirements:

- propan-2-ol: 99,5 % by mass minimum
- acid content: 0,002 % by mass maximum
- non-volatile content: 0,2 % by mass maximum

A.5 Procedure

A.5.1 Non-activated rosin (colophony)

Weigh $25 \text{ g} \pm 0,1 \text{ g}$ rosin (A.4.1) and dissolve it with gentle mixing in $75 \text{ g} \pm 0,1 \text{ g}$ propan-2-ol (A.4.3).

A.5.2 Halogen-activated rosin (colophony)

Weigh $0,39 \text{ g} \pm 0,01 \text{ g}$ diethylamine hydrochloride (A.4.2) and dissolve it in $75 \text{ g} \pm 0,1 \text{ g}$ propan-2-ol (A.4.3). Then add $25 \text{ g} \pm 0,1 \text{ g}$ rosin (A.4.1) and dissolve it with gentle mixing. This flux solution contains a nominal 0,5 % by mass active chloride.

A.6 Storage

Store the standard flux solutions, prepared as described in A.5, in a container, properly closed at all times, away from heat or extreme cold.

Annex B (informative)

Chemical composition of brass test plates

Table B.1 — Chemical composition of brass test plates

Values as percentages by mass

Alloy	Cu	Zn	Fe	Pb
CuZn37	62,0 min.	balance	—	—
	64,0 max.		0,1 max.	0,1 max.
CuZn40	59,5 min.	balance	—	—
	61,5 max.		0,2 max.	0,3 max.

Bibliography

- [1] ISO 197-1, *Copper and copper alloys — Terms and definitions — Part 1: Materials*
- [2] ISO 3611, *Geometrical product specifications (GPS) — Dimensional measuring equipment: Micrometers for external measurements — Design and metrological characteristics*
- [3] ISO 9455-16, *Soft soldering fluxes — Test methods — Part 16: Flux efficacy test, wetting balance method*
- [4] IEC 60068-2-20:2008, *Environmental testing — Part 2-20: Tests — Test T: Test methods for solderability and resistance to soldering heat of devices with leads*
- [5] IEC 60068-2-54, *Environmental testing — Part 2-54: Tests — Test Ta: Solderability testing of electronic components by the wetting balance method*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™