

BS EN ISO 10306:2014



BSI Standards Publication

# Textiles — Cotton fibres — Evaluation of maturity by the air flow method

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of EN ISO 10306:2014. It supersedes BS EN ISO 10306:1995 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee TCI/24, Physical testing of textiles.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014.  
Published by BSI Standards Limited 2014

ISBN 978 0 580 69631 2  
ICS 59.060.10

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2014.

**Amendments/corrigenda issued since publication**

Date	Text affected
------	---------------

---

English Version

**Textiles - Cotton fibres - Evaluation of maturity by the air flow  
method (ISO 10306:2014)**Textiles - Fibres de coton - Évaluation de la maturité par la  
méthode à courant d'air (ISO 10306:2014)Textilien - Baumwollfasern - Bewertung der Reife durch das  
Luftstrom-Prüfverfahren (ISO 10306:2014)

This European Standard was approved by CEN on 20 April 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Foreword

This document (EN ISO 10306:2014) has been prepared by Technical Committee ISO/TC 38 "Textiles" in collaboration with Technical Committee CEN/TC 248 "Textiles and textile products" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2014, and conflicting national standards shall be withdrawn at the latest by December 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 10306:1995.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

### Endorsement notice

The text of ISO 10306:2014 has been approved by CEN as EN ISO 10306:2014 without any modification.

# Contents

Page

Foreword.....	iv
Introduction.....	v
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Principle.....</b>	<b>2</b>
<b>5 Apparatus and materials.....</b>	<b>2</b>
<b>6 Atmosphere for conditioning and testing.....</b>	<b>3</b>
<b>7 Sampling and number of specimens.....</b>	<b>3</b>
<b>8 Procedure.....</b>	<b>3</b>
<b>9 Calculations and expression of results.....</b>	<b>3</b>
<b>10 Test report.....</b>	<b>4</b>
<b>Annex A (normative) Operation of the air flow instrument “Fineness/Maturity Tester”.....</b>	<b>5</b>
<b>Annex B (normative) Method for instrument calibration.....</b>	<b>6</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 38, *Textiles*, Subcommittee SC 23, *Fibres and yarns*.

This second edition cancels and replaces the first edition (ISO 10306:1993), of which it constitutes a minor revision.

## Introduction

The term “cotton fibre maturity” is commonly used to signify the relative degree of fibre wall development. The measurement of the relative degree of wall thickening is too laborious for most practical purposes, therefore the determination of the maturity of cotton fibres is done by indirect methods. A microscopic method is described in ISO 4912:1981. This method has been used as a reference method for the industrial evaluation of the maturity of cotton fibres using air flow instruments, which is the object of this standard.





# Textiles — Cotton fibres — Evaluation of maturity by the air flow method

## 1 Scope

This International Standard specifies a method for the evaluation of the maturity of loose randomized cotton fibres by measuring the resistance to air flow of a plug of cotton fibres under two prescribed conditions. The method is applicable to cotton taken at random from bales. Laps and slivers or other sources of lint cotton may be tested, however results may differ if fibres are taken from bales.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139:2005, *Textiles — Standard atmospheres for conditioning and testing*

ISO 1130:1975, *Textile fibres — Some methods of sampling for testing*

ISO 2403:2014, *Textiles — Cotton fibres — Determination of micronaire value*

ISO 4912:1981, *Textiles — Cotton fibres — Evaluation of maturity — Microscopic method*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4912:1981 and ISO 2403:2014 apply. The following terms and definitions are repeated here for the convenience of the user.

### 3.1

#### **immature fibre**

fibre which, upon swelling, either assumes a spiral form or lies flat, thinly outlined and almost transparent

Note 1 to entry: It has a wall thickness of less than one-fourth of the maximum fibre width.

[SOURCE: ISO 4912:1981]

### 3.2

#### **mature fibres**

fibres, the cell walls of which have developed sufficiently so that upon swelling, they become unconvoluted and almost rod-like in shape

Note 1 to entry: Such fibres have a wall thickness equal to or greater than one-fourth of the maximum fibre width.

[SOURCE: ISO 4912:1981]

### 3.3

#### **maturity ratio, $M$**

ratio of the degree of wall thickening to a standard degree of thickening selected arbitrarily to equal 0,577

[SOURCE: ISO 4912:1981]

### 3.4

#### **percent maturity, $P_m$**

average percentage of mature fibres in a sample, based on the total number of fibres

[SOURCE: ISO 4912:1981]

### 3.5

#### **micronaire value**

measure of the air permeability of a mass of cotton under specified conditions, expressed in terms of an arbitrary scale, the so-called micronaire scale

Note 1 to entry: The micronaire scale is based on a range of cottons to which micronaire values have been assigned by international agreement.

[SOURCE: ISO 2403:2014]

## 4 Principle

Air is passed through a test specimen consisting of a plug of well-opened randomized cotton fibres. For the same mass of fibres the permeability is measured by two different compressions of the plug. For each compression, air is passed through the plug at a specified rate and the pressure drop across the plug is indicated on a pressure gauge and expressed as the height, in millimetres, of a water column. The pressure drop obtained at low compression of the plug is designated PL and the other, at high compression, is designated PH. These two pressures may be used to calculate a maturity ratio and fibre linear density or a percentage of mature fibres using appropriate formulae. The micronaire value is determined solely from the PL value.

## 5 Apparatus and materials

**5.1 Balance**, of sufficient capacity to weigh the test specimen required for the air flow instrument used, with a sensitivity of better than 0,005 g.

**5.2 Air flow instrument** (see [Annex A](#)).

The principal parts comprising the air flow instrument are:

**5.2.1 Compression cylinder**, with perforated end, of such dimensions that with the specified mass of specimen each cubic centimetre of the cylinder shall contain 0,191 1 g of cotton at low compression and 0,382 1 g of cotton at high compression.

**5.2.2 Means of measuring air permeability of the specimen**, comprising for example:

- a) a suitable air pump;
- b) two valves or other means for controlling the flow of air through the specimen or the pressure drop across the specimen in the compression cylinder;
- c) means for setting the required rate of air flow through the specimen and a gauge for measuring the air pressure drop across the specimen.

NOTE Details of certain commercially available instruments which comply with this specification are given in [Annexes A](#) and [B](#). The method of calibration of air flow instruments is described in [Annex B](#).

### 5.3 International calibration cotton standards

Reference cotton used for the calibration of air flow instruments is described in [B.2.2](#).

## 5.4 Specimen preparation apparatus

Any blending apparatus is considered suitable if it produces randomly oriented samples.

NOTE Apparatus that produces webs of predominantly parallel fibres is not suitable.

## 6 Atmosphere for conditioning and testing

**6.1** Condition test samples in the standard atmosphere for 4 h in moving air or alternatively for 12 h in still air. Preconditioning is not required.

**6.2** Weigh and test the specimen in the standard atmosphere for conditioning (see ISO 139:2005).

## 7 Sampling and number of specimens

The sampling scheme, the number of specimens to be tested and the number of measurements to be made on each specimen will normally be determined by the material specification or will be agreed between the interested parties. In the absence of any instructions, test at least two specimens, making two tests on each. Samples of raw cotton from bales may be taken according to the method described in ISO 1130:1975.

The mass of the test specimens shall be as specified by the manufacturer of the air flow instrument.

## 8 Procedure

**8.1** Before each series of measurements, make the necessary preliminary adjustments appropriate to the instrument in use (see [Annexes A](#) and [B](#)).

**8.2** Divide the weighed specimen with the fingers into four to six portions, tease each portion out randomly until about 50 mm to 70 mm in diameter and place each portion successively into the sample holder until the entire specimen is loaded. Carefully insert the first portion so as to fill in the bottom edges of the sample holder by pushing it well into the bottom of the sample holder and outwards to the edges. Take care to insert all the specimen and not to lose any of the fibres. Insert the compression plunger and lock it in its position. Avoid fibres sticking between the cylinder wall and the compression plunger.

**8.3** Cause air to flow through the specimen at the appropriate flow rate for the low compression of the plug and after 10 s note the reading, PL, on the pressure scale of the instrument to an accuracy of 1 mm of the water column. Next cause air to flow through the specimen at the appropriate flow rate for the high compression of the plug and after 10 s note the reading, PH, on the pressure scale of the instrument to the same accuracy of 1 mm of the water column.

**8.4** Remove the test specimen from the cylinder and reinsert it, reversing the individual portions, and repeat the procedure given in [8.2](#) and [8.3](#).

**8.5** Repeat the procedure given in [8.2](#) to [8.4](#) on a second test specimen taken from the same sample.

If the PL or PH readings of the two successive specimens from the same sample differ by more than 5 %, it is recommended to examine a new specimen from the same sample and to calculate the average readings for all specimens tested.

## 9 Calculations and expression of results

Average the two readings of each pressure drop, PL and PH, taken for each specimen tested from a sample. Using each pair of average readings, PL and PH, calculate the maturity ratio,  $M$ , or the percent

maturity,  $P_m$  of each specimen via the appropriate conversion formula (see [Annex A](#)). Average the readings of pressure drops PL and PH, and average the values calculated for the two specimens tested from a sample.

## 10 Test report

The test report shall include the following information:

- a) reference to this International Standard;
- b) the material source and if possible type and/or botanical species;
- c) the number of specimens tested, the number of readings per specimen, the number of samples used, and the sampling method;
- d) the average of the values measured for PL and PH, the calculated values such as maturity ratio,  $M$ , or percent maturity,  $P_m$ , and also the equation used;
- e) type, make and model of instrument used;
- f) date of the test.

## Annex A (normative)

### Operation of the air flow instrument “Fineness/Maturity Tester”

#### A.1 General

There are several models of “Fineness/Maturity Testers”. They vary only in details of construction and operation. Any details of the operation of a particular model which differ from the instructions given in this annex are described in the manufacturer’s instructions included with the instrument.

#### A.2 Fineness/Maturity Tester, Type .....

**A.2.1** Turn on the instrument and wait 15 min for it to warm up.

**A.2.2** Proceed to the different verifications recommended in the manufacturer’s manual.

**A.2.3** Calibrate the instrument following one of the methods described in [Annex B](#).

**A.2.4** Carry out the measurements as described in [Clause 8](#).

**A.2.5** Using the PL and PH readings, calculate either the maturity ratio or the percent maturity via conversion Formula (A.1) or (A.2), respectively.

##### A.2.5.1 Maturity ratio

$$M = 0,247 PL^{0,125} \left( \frac{PL}{PH} \right)^2 \quad (A.1)$$

##### A.2.5.2 Percent maturity

$$P_m = 95,0 \frac{PL}{PH} - 50,8 \quad (A.2)$$

NOTE PL and PH readings may also be used to calculate the microunits value using Formula (A.3) or linear density using Formula (A.4).

$$\text{Microunits value} = 0,60 + \frac{850}{PL + 40} \quad (A.3)$$

$$\text{Linear density (mtex)} = \frac{60\,000}{PL} \cdot \left( \frac{PH}{PL} \right)^{1,75} \quad (A.4)$$

## Annex B (normative)

### Method for instrument calibration

**B.1** The calibration of air flow instruments is performed by setting the air flow valves to the appropriate air flow rate corresponding to the degree of compression applied to the cotton fibre plug.

**B.2** For the calibration of the instrument proceed as follows:

**B.2.1** Set the air flow control successively for each compression of the plug so that the upper edge of the float comes to rest at the upper setting line on the manometer for the low compression and at the lower setting line on the manometer for the high compression, the test chamber being empty. The air flow is then set to 4 l/min or 1 l/min depending on the degree of compression. In both cases great care should be taken to align the top of the float with the setting line, avoiding parallax. These settings are critical and the readings should be checked at regular intervals during testing.

**B.2.2** Set the air flow control successively for each compression of the plug so that the manometer reads predetermined values of pressure drops PL and PH for the reference cotton, the test cylinder being filled with the specified mass of plug taken from the reference cotton used.

**NOTE** A series of international reference cottons for calibration are available from the Standards Section, Cotton Division, Agricultural Marketing Service, US Department of Agriculture, P.O. Box 17723, Memphis, TN 38112, USA.

Until the International Calibration Cotton Standards Committee takes over the work, the ITMF Working Group on Maturity will provide the standard values PL and PH to be used for reference cottons.









# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™