BS EN ISO 10581:2013



BSI Standards Publication

Resilient floor coverings — Homogeneous poly(vinyl chloride) floor covering — Specifications (ISO 10581:2011)



National foreword

This British Standard is the UK implementation of EN ISO 10581:2013. It is identical to ISO 10581:2011. It supersedes BS EN 649:2011 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/60, Resilient floor coverings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013

ISBN 978 0 580 82037 3

ICS 97.150

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2013.

Amendments issued since publication

Date Text affected

EUROPEAN STANDARD

EN ISO 10581

NORME EUROPÉENNE EUROPÄISCHE NORM

October 2013

ICS 97.150

Supersedes EN 649:2011

English Version

Resilient floor coverings - Homogeneous poly(vinyl chloride) floor covering - Specifications (ISO 10581:2011)

Revêtements de sol résilients - Revêtements de sol homogènes en poly(chlorure de vinyle) - Spécifications (ISO 10581:2011) Elastische Bodenbeläge - Homogene Polyvinylchlorid-Bodenbeläge - Spezifikation (ISO 10581:2011)

This European Standard was approved by CEN on 12 October 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

The text of ISO 10581:2011 has been prepared by Technical Committee ISO/TC 219 "Floor coverings" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 10581:2013 by Technical Committee CEN/TC 134 "Resilient, textile and laminate floor coverings" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2014, and conflicting national standards shall be withdrawn at the latest by April 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 649:2011.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 10581:2011 has been approved by CEN as EN ISO 10581:2013 without any modification.

Contents Page Forewordiv 1 Scope1 2 3 4 5 Classification3 6 Marking, labelling and packaging......5 Annex A (informative) Optional properties......6

BS EN ISO 10581:2013 ISO 10581:2011(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10581 was prepared by Technical Committee ISO/TC 219, Floor coverings.

Resilient floor coverings — Homogeneous poly(vinyl chloride) floor covering — Specification

1 Scope

This International Standard specifies the characteristics of homogeneous floor coverings, based on poly(vinyl chloride), supplied in either tile or roll form. Products may contain a transparent, non-PVC factory finish.

To encourage the consumer to make an informed choice, this International Standard includes a classification system (see ISO 10874) based on intensity of use, which shows where these floor coverings should give satisfactory service. It also specifies requirements for marking.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-BO2:1994, Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test

ISO 4918, Resilient, textile and laminate floor coverings — Castor chair test

ISO 10874, Resilient, textile and laminate floor coverings — Classification

ISO 24340, Resilient floor coverings — Determination of thickness of layers

ISO 24341, Resilient and textile floor coverings — Determination of length, width, and straightness of sheet

ISO 24342, Resilient and textile floor-coverings — Determination of side length, edge straightness and squareness of tiles

ISO 24346, Resilient floor coverings — Determination of overall thickness

ISO 23996, Resilient floor coverings — Determination of density

ISO 23997, Resilient floor coverings — Determination of mass per unit area

ISO 23999, Resilient floor coverings — Determination of dimensional stability and curling after exposure to heat

ISO 24343-1, Resilient and laminate floor coverings — Determination of indentation and residual indentation — Part 1: Residual indentation

ISO 24344, Resilient floor coverings — Determination of flexibility and deflection

ASTM F 1515, Standard Test Method for Measuring Light Stability of Resilient Flooring by Color Change

EN 684, Resilient floor coverings — Determination of seam strength

3 Terms and definitions

For the purposes of this document, the following terms apply.

3.1

poly(vinyl chloride) floor coverings

PVC

floor covering with surface layers which are produced using poly(vinyl chloride) as binder

3.2

homogeneous floor covering

floor covering with one or more layers of the same composition and colour, patterned throughout its thickness

3.3

factory finish

transparent coating applied during the manufacture

NOTE 1 The finish is usually not thicker than 0,03 mm.

NOTE 2 This coating should not be counted as part of the wear layer.

3.4

binder content

portion of the flooring composition, consisting of poly(vinyl chloride) resin, plasticizers and stabilizers

NOTE Binder content is expressed as a percentage mass fraction of the total composition.

4 Requirements

4.1 Identification requirements

Products described in this International Standard shall be identified by binder content by weight as shown in Table 1.

Table 1 — Identification requirements

Туре	Minimum Binder Content	Maximum Binder Content		
	%	%		
I	>55	_		
II	35	55		
III	25	<35		

4.2 General requirements

Floor coverings described in this International Standard shall conform to the appropriate general requirements specified in Table 2 when tested in accordance with the methods given therein.

Table 2 — General minimum requirements

Characteristic		Requirement	Test method	
Roll form:		Not less than the nominal values	ISO 24341	
length	m			
width	m			
Tiles:			ISO 24342	
side length (does not apply to planks)		Deviation ≤ 0,13 % of nominal length up to 0,5 mm maximum		
squareness and straightness for side length	mm	Deviation allowed at any point		
≤ 400 mm		≤0,25		
> 400 mm		≤0,35		
> 400 mm (intended for heat welding)		≤0,50		
Overall thickness:	mm		ISO 24346	
average		Nominal value +0,15 -0,10		
individual results		Shall not be more than ±0,15 from the average value		
Mass per unit area	g/m ²		ISO 23997	
average		Nominal value + 13 %/–10 %		
Residual indentation (average)	mm	≤ 0,1	ISO 24343-1	
Dimensional stability after exposure to heat:	%		ISO 23999	
sheets and tiles intended for welding		≤0,40		
tiles (intended for dry-joint laying)		≤0,25		
Flexibility		20 mm mandrel, no cracking. For products which show signs of cracking, perform a further test using a 40 mm mandrel. If results show no further cracking, record the use of a 40 mm mandrel.	ISO 24344, Method A	
Effect of castor chair		After 25 000 cycles, no delamination shall occur. No disturbance to the surface other than slight change in appearance.		
Colour fastness to artificial light		6 minimum	ISO 105-BO2, Method 3a	
		or		
		ΔE ≤ 8 after 300 hr.	ASTM F 1515	

^a Expose a full size test specimen. Store a further test specimen in the dark, which will constitute the reference standard for assessment of colour change.

5 Classification

The classification scheme for resilient floor coverings is described in ISO 10874. The requirements for homogeneous PVC floor covering in accordance with this scheme are specified in Table 3.

Table 3 — Classification of minimum requirements for level of use

Class	Symbol	Level of use	Overall thickness, nominal value mm		Seam strength			
			Type I	Type II	Type III	N/50 mm		
Domes	tic							
21		Moderate/Light	1.0	1.0	1.0	No requirement		
22		General/Medium	1.5	1.5	1.5			
22+	22+	General	1.5	1.5	1.5			
23		Heavy	1.5	1.5	1.5			
Comme	ercial	cial						
31		Moderate	1.5	1.5	1.5	When welded in accordance with the manufacturer's instructions: average value ≥240 Individual values ≥180		
32		General	1.5	1.5	2.0			
33		Heavy	2.0	2.0	2.0			
34		Very heavy	2.0	2.0	2.5			
Light In	ndustrial							
41		Moderate	1.5	1.5	2.0			
42		General	2.0	2.0	2.0			
43	43	Heavy	2.0	2.0	2.5			
Test Method		ISO 24346	ISO 24346	ISO 24346	EN 684			

6 Marking, labelling and packaging

Floor coverings covered by this International Standard and/or their packaging shall bear the following marking:

- a) number and date of this document, i.e. ISO 10581:2011;
- b) manufacturer or suppliers identification;
- c) product name;
- d) colour/pattern, batch number and, if applicable, roll number;
- e) classes/symbols appropriate for the product;
- f) for rolls: the length, width and thickness; and
- g) for tiles: the dimensions of a tile and the area in square metres contained in the package.

Annex A (informative)

Optional properties

Where the following properties are required for specific applications, the floor covering should be tested in accordance with the appropriate methods:

- Electrical resistance (ASTM F 150, EN 1081, ANSI/ESD S7.1, ANSI/ESD STM 97.1);
- Electrical propensity (EN 1815, ANSI/ESD STM97.2);
- Effects of stains (ASTM F 925, EN 423, ISO 26987);
- Reaction to fire; determination of the burning behaviour using a radiant heat source (EN ISO 9239-1:2002, ASTM E 648);
- Reaction to fire; Ignitability when subject to direct impingement of flame (EN ISO 11925-2:2002);
- Reaction to fire, specific optical density of smoke generated (ASTM E 662);
- Resistance to heat (ASTM F 1514).

Bibliography

- [1] ANSI/ESD S7.1, Resistive characterization of materials Floor materials
- [2] ANSI/ESD STM97.1, Floor materials and footwear Resistance measurement in combination with a person
- [3] ANSI/ESD STM97.2, Floor materials and footwear Voltage measurement in combination with a person
- [4] ASTM F 150, Standard Test Method for Electrical Resistance of Conductive and Static Dissipative Resilient Flooring
- [5] ASTM F 925, Standard Test Method for Resistance to Chemicals of Resilient Flooring
- [6] ASTM E 648, Standard Test Method for Critical Radiant Flux of Floor Covering Systems Using a Radiant Heat Energy Source
- [7] ASTM E 662, Standard Test Method for Specific Optical Density of Smoke Generated by Solid Materials
- [8] ASTM F 1514, Standard Test Method for Measuring Heat Stability of Resilient Flooring by Color Change
- [9] ASTM F 1913, Standard Specification for Vinyl Sheet Floor Covering Without Backing
- [10] EN 423, Resilient floor coverings Determination of the effect of stains
- [11] EN 649, Resilient floor coverings Homogeneous and heterogeneous poly(vinyl chloride) floor coverings Specification
- [12] EN 1081, Resilient floor coverings Determination of the electrical resistance
- [13] EN 1815, Resilient and textile floor coverings Assessment of static electrical propensity
- [14] EN ISO 9239-1:2002, Reaction to fire tests for floorings Part 1: Determination of the burning behaviour using a radiant heat source
- [15] EN ISO 11925-2:2002, Reaction to fire tests Ignitability of building products subjected to direct impingement of flame Part 2: Single-flame source test
- [16] ISO 26987, Resilient floor coverings Determination of staining and resistance to chemicals
- [17] JIS A 1454, Test Methods Resilient Floorcoverings
- [18] JIS A 5705, Floorcovering PVC





British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards -based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com
Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070 Email: copyright@bsigroup.com

