BS EN ISO 10582:2012

BSI Standards Publication

Resilient floor coverings — Heterogeneous poly(vinyl chloride) floor coverings — Specification

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 10582:2012. It is identical to ISO 10582:2010.

The UK participation in its preparation was entrusted to Technical Committee PRI/60, Resilient floor coverings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Published by BSI Standards Limited 2012

ISBN 978 0 580 75249 0

ICS 97.150

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 29 February 2012.

Amendments issued since publication

Amd. No.	Date	Text affected

EUROPEAN STANDARD

NORME EUROPÉENNE

EUROPÄISCHE NORM

EN ISO 10582

February 2012

ICS 97.150

English Version

Resilient floor coverings - Heterogeneous poly(vinyl chloride) floor coverings - Specification (ISO 10582:2010)

Revêtements de sol résilients - Revêtements de sol hétérogènes en poly(chlorure de vinyle) - Spécifications (ISO 10582:2010)

Elastische Bodenbeläge - Heterogene Polyvinylchlorid-Bodenbeläge - Spezifikation (ISO 10582:2010)

This European Standard was approved by CEN on 31 December 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword

The text of ISO 10582:2010 has been prepared by Technical Committee ISO/TC 219 “Floor coverings” of the International Organization for Standardization (ISO) and has been taken over as EN ISO 10582:2012 by Technical Committee CEN/TC 134 “Resilient, textile and laminate floor coverings” the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2012, and conflicting national standards shall be withdrawn at the latest by August 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 10582:2010 has been approved by CEN as a EN ISO 10582:2012 without any modification.

Contents

Page

INTERNATIONAL STANDARD **ISO 10582:2010(E)**

Resilient floor coverings — Heterogeneous poly(vinyl chloride) floor coverings — Specification

1 Scope

This International Standard specifies the characteristics of non-cushioned, heterogeneous floor coverings, based on poly(vinyl chloride) (PVC), supplied in either tile or roll form. Products may contain a transparent, non-PVC factory finish.

To encourage the consumer to make an informed choice, this International Standard includes a classification system (see ISO 10874) based on the intensity of use, which shows where these floor coverings give satisfactory service. It also specifies requirements for marking.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-B02:1994, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test*

ISO 105-B02:1994, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test*. Amendment 1:1998

ISO/TR 4918, *Textile floor coverings — Determination of wear — Castor chair test*

ISO 10874, *Resilient, textile and laminate floor coverings — Classification*

ISO 23996, *Resilient floor coverings — Determination of density*

ISO 23997, *Resilient floor coverings — Determination of mass per unit area*

ISO 23999, *Resilient floor coverings — Determination of dimensional stability and curling after exposure to heat*

ISO 24340, *Resilient floor coverings — Determination of thickness of layers*

ISO 24341, *Resilient and textile floor coverings — Determination of length, width and straightness of sheet*

ISO 24342, *Resilient and textile floor-coverings — Determination of side length, edge straightness and squareness of tiles*

ISO 24343-1, *Resilient and laminate floor coverings — Determination of indentation and residual indentation — Part 1: Residual indentation*

ISO 24344:2008, *Resilient floor coverings — Determination of flexibility and deflection*

ISO 24346, *Resilient floor coverings — Determination of overall thickness*

ASTM F1515, *Standard test method for measuring light stability of resilient flooring by color change*

EN 684, *Resilient floor coverings — Determination of seam strength*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1
heterogeneous floor covering
floor covering consisting of a wear layer and other layer(s) which differ in composition and/or design and can contain a reinforcement

3.2
poly(vinyl chloride) floor covering
floor covering with surface layer(s) which are produced using poly(vinyl chloride) as the binder

3.3
wear layer
layer of the floor covering directly exposed to wear

3.4
factory finish
transparent coating applied during the manufacture, usually not thicker than 0,03 mm

3.5
binder content
that portion of the flooring composition, consisting of poly(vinyl chloride) (PVC) resin, plasticizers and stabilizers

NOTE Binder content is expressed as a percentage mass fraction of the total composition.

4 Requirements

4.1 Identification requirements

Products described in this International Standard shall be identified by wear-layer binder content by mass as shown in Table 1.

Table 1 — Identification requirements

Type	Wear-layer binder content
I	Minimum 80 %
II	Minimum 30 %

4.2 General requirements

Floor coverings described in this International Standard shall conform to the appropriate general requirements specified in Table 2, when tested in accordance with the methods given therein.

Table 2 — General requirements

Characteristic	Requirement	Test method
Roll form: length: m width: mm	Not less than the nominal values	ISO 24341
Tiles: side length mm Does not apply to planks squareness and straightness for side length: mm $\leqslant$ 400 mm > 400 mm > 400 mm (intended for heat welding)	Deviation $\leqslant$ 0,15 % of nominal length up to 0,5 mm maximum Deviation allowed at any point $\leqslant$ 0,25 $\leqslant$ 0,35 $\leqslant$ 0,50	ISO 24342
Overall thickness: mm Average Individual results	 Nominal value $^{+0,13}_{-0,10}$ Average value ±0,15	ISO 24346
Total mass per unit area (average) g/m^2	Nominal value $^{+13}_{-10}$ %	ISO 23997
Dimensional stability after exposure to heat: % Sheets and tiles (intended for welding) Tiles (intended for dry-joint laying)	 $\leqslant$ 0,4 $\leqslant$ 0,25	ISO 23999
Curling after exposure to heat: mm Sheets and tiles (intended for heat welding) Tiles (intended for dry-joint laying)	 $\leqslant$ 8 $\leqslant$ 2	ISO 23999
Flexibility	Test using a 20 mm mandrel. For products which show signs of cracking, perform a further test using a 50 mm mandrel. If results show no further cracking, record the use of a 50 mm mandrel	ISO 24344:2008, Method A
Residual indentation (average) mm	$\leqslant$ 0,1	ISO 24343-1
Effect of castor chair	After 25 000 cycles, no delamination shall occur. No disturbance to the surface other than a slight change in appearance	ISO 4918
Colour fastness to artificial light	6 minimum or $\Delta E \leqslant$ 8 after 300 h, where E is the irradiance, expressed in watts per square metre	ISO 105-B02:1994, Method 3[a] ASTM F1515

[a] Expose a full size test specimen. Store a further test specimen in the dark, which will constitute the reference standard for assessment of colour change.

5 Classification

The classification scheme for resilient floor coverings is described in ISO 10874. The requirements for the use of heterogeneous poly(vinyl chloride) floor covering in accordance with this scheme are specified in Table 3.

Table 3 — Classification requirement for level of use (minimal)

Dimensions in millimetres

Class	Symbol	Level of use	Thickness of wear layer, nominal value		Nominal overall thickness	Seam strength N/50 mm
		Domestic	**Type I**	**Type II**	**All types**	
21		Moderate/light	0,15	0,40	1,0	No requirement
22		General/medium	0,20	0,50	1,5	
22+		General	0,20	0,50	1,5	
23		Heavy	0,30	0,65	1,5	
		Commercial				When welded in accordance with the manufacturer's instructions: Average value ⩾ 240 Individual values ⩾ 180
31		Moderate	0,30	0,65	2,0	
32		General	0,40	0,80	2,0	
33		Heavy	0,55	1,00	2,0	
34		Very heavy	0,70	1,50	2,0	
		Light industrial				
41		Moderate	0,40	0,80	2,0	
42		General	0,55	1,00	2,0	
43		Heavy	0,70	1,50	2,0	
Test method			ISO 24340		ISO 24346	EN 684

6 Marking, labelling and packaging

Floor coverings covered by this International Standard and/or their packaging shall bear the following marking:

a) number and date of this International Standard, i.e. ISO 10582:2010;

b) manufacturer's or supplier's identification;

c) product name;

d) colour/pattern, batch number and, if applicable, roll number;

e) classes/symbols appropriate for the product;

f) for rolls: the length, width and thickness;

g) for tiles: the dimensions of a tile and the area, in square metres, contained in the package.

Annex A
(informative)

Optional properties

Where the following properties are required for specific applications, the floor covering should be tested in accordance with the appropriate methods:

— electrical resistance (ASTM F150, EN 1081, ANSI/ESD S7.1, ANSI/ESD STM 97.1);

— electrical propensity (EN 1815, ANSI/ESD STM 97.2);

— effects of stains (ASTM F925, EN 423, ISO 26987:2008);

— reaction to fire; determination of the burning behaviour using a radiant heat source (ISO 9239-1:2010, ASTM E648);

— reaction to fire; ignitability when subject to direct impingement of flame (ISO 11925-2:2010);

— reaction to fire; specific optical density of smoke generated (ASTM E662);

— resistance to heat (ASTM F1514).

Bibliography

[1] ISO 9239-1:2010, *Reaction to fire tests for floorings — Part 1: Determination of the burning behaviour using a radiant heat source*

[2] ISO 11925-2:2010, *Reaction to fire tests — Ignitability of products subjected to direct impingement of flame — Part 2: Single-flame source test*

[3] ISO 26987:2008, *Resilient floor coverings — Determination of staining and resistance to chemicals*

[4] ANSI/ESD S7.1, *Resistive Characterization of Materials — Floor Materials*

[5] ANSI/ESD STM 97.1, *Floor Materials and Footwear — Resistance Measurement in Combination with a Person*

[6] ANSI/ESD STM 97.2, *Floor Materials and Footwear — Voltage Measurement in Combination with a Person*

[7] ASTM E648, *Standard Test Method for Critical Radiant Flux of Floor-Covering Systems Using a Radiant Heat Energy Source*

[8] ASTM E662, *Standard Test Method for Specific Optical Density of Smoke Generated by Solid Materials*

[9] ASTM F150, *Standard Test Method for Electrical Resistance of Conductive and Static Dissipative Resilient Flooring*

[10] ASTM F925, *Standard Test Method for Resistance to Chemicals of Resilient Flooring*

[11] ASTM F1303, *Standard Specification for Sheet Vinyl Floor Covering with Backing*

[12] ASTM F1514, *Standard Test Method for Measuring Heat Stability of Resilient Flooring by Color Change*

[13] ASTM F1700, *Standard Specification for Solid Vinyl Floor Tile*

[14] EN 423, *Resilient floor coverings — Determination of resistance to staining*

[15] EN 649, *Resilient floor coverings — Homogeneous and heterogeneous polyvinyl chloride floor coverings — Specification*

[16] EN 1081, *Resilient floor coverings — Determination of the electrical resistance*

[17] EN 1815, *Resilient and textile floor coverings — Assessment of static electrical propensity*

[18] JIS A 1454, *Japanese Industrial Standard, Test methods — Resilient floorcoverings*

[19] JIS A 5705, *Japanese Industrial Standard, Floorcovering — PVC*

This page deliberately left blank

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards -based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

Useful Contacts:

Customer Services
Tel: +44 845 086 9001
Email (orders): orders@bsigroup.com
Email (enquiries): cservices@bsigroup.com

Subscriptions
Tel: +44 845 086 9001
Email: subscriptions@bsigroup.com

Knowledge Centre
Tel: +44 20 8996 7004
Email: knowledgecentre@bsigroup.com

Copyright & Licensing
Tel: +44 20 8996 7070
Email: copyright@bsigroup.com

bsi.

...making excellence a habit.™