BS EN ISO 11114-2:2013



BSI Standards Publication

Gas cylinders — Compatibility of cylinder and valve materials with gas contents

Part 2: Non-metallic materials



National foreword

This British Standard is the UK implementation of EN ISO 11114-2:2013. It supersedes BS EN ISO 11114-2:2001, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PVE/3, Gas containers.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013.

ISBN 978 0 580 68976 5

ICS 23.020.30; 23.060.40

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2013.

Amendments issued since publication

Date Text affected

EUROPEAN STANDARD

EN ISO 11114-2

NORME EUROPÉENNE EUROPÄISCHE NORM

April 2013

ICS 23.020.30

Supersedes EN ISO 11114-2:2000

English Version

Gas cylinders - Compatibility of cylinder and valve materials with gas contents - Part 2: Non-metallic materials (ISO 11114-2:2013)

Bouteilles à gaz - Compatibilité des matériaux des bouteilles et des robinets avec les contenus gazeux - Partie 2: Matériaux non métalliques (ISO 11114-2:2013) Gasflaschen - Verträglichkeit von Flaschen- und Ventilwerkstoffen mit den in Berührung kommenden Gasen - Teil 2: Nichtmetallische Werkstoffe (ISO 11114-2:2013)

This European Standard was approved by CEN on 9 February 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 11114-2:2013) has been prepared by Technical Committee ISO/TC 58 "Gas cylinders" in collaboration with Technical Committee CEN/TC 23 "Transportable gas cylinders" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2013, and conflicting national standards shall be withdrawn at the latest by October 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 11114-2:2000.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 11114-2:2013 has been approved by CEN as EN ISO 11114-2:2013 without any modification.

Contents Page

Forewo	ordi	V
Introdu	oction	V
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4 4.1 4.2	Materials	2
5	General considerations	3
6 6.1 6.2 6.2.1	Specific considerations	4 4
6.2.2 6.2.3 6.2.4 6.2.5	Weight loss (W)	5 6 6
7 7.1 7.2 7.2.1 7.2.2	Compatibility data	7 7 8 8
7.2.3 7.2.4	Abbreviations for non-compatibility risks	9
Bibliog	raphy1	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 11114-2 was prepared by Technical Committee ISO/TC 58, *Gas cylinders*, in collaboration with Technical Committee CEN/TC 23, *Transportable Gas cylinders* in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition, Clauses 4 and 6, and Table 1 of which have been technically revised. Annex A has been deleted.

ISO 11114 consists of the following parts, under the general title *Gas cylinders* — *Compatibility of cylinder and valve materials with gas contents*:

- Part 1: Metallic materials;
- Part 2: Non-metallic materials;
- Part 3: Autogenous ignition test for non-metallic materials in oxygen atmosphere;
- Part 4: Test methods for selecting metallic materials resistant to hydrogen embrittlement.

Introduction

This part of ISO 11114 deals with the compatibility of non-metallic materials used for gas cylinders and gas cylinder valves with the gas contents of the cylinder. Compatibility of metallic materials is treated in ISO 11114-1.

Non-metallic materials are very often used for the construction of gas cylinder valves as seals, e.g. o-ring, gland packing, seats, or as lubrication products to avoid friction. They are also commonly used to ensure sealing of the valve/cylinder connection. For gas cylinders, they are sometimes used as an internal coating or as a liner for composite materials.

Non-metallic materials not in contact with the gas are not covered by this part of ISO 11114.

This part of ISO 11114 is based on current international experience and knowledge. Some data are derived from experience involving a mixture of the gas concerned with a dilutant, where no data for single component gases were available.

This part of ISO 11114 has been written to be in conformity with the UN Recommendations on the Transport of Dangerous Goods: Model Regulations. When published it will be submitted to the UN Sub Committee of Experts on the Transport of Dangerous Goods with a request that it be included in the Model Regulations. Where there is any conflict between this part of ISO 11114 and any applicable regulation, the regulation always takes precedence.

Gas cylinders — Compatibility of cylinder and valve materials with gas contents —

Part 2:

Non-metallic materials

1 Scope

This part of ISO 11114 gives guidance in the selection and evaluation of compatibility between non-metallic materials for gas cylinders and valves and the gas contents. It also covers bundles, tubes and pressure drums.

This part of ISO 11114 can be helpful for composite and laminated materials used for gas cylinders.

It does not cover the subject completely and is intended to give guidance only in evaluating the compatibility of gas/material combinations.

Only the influence of the gas in changing the material and mechanical properties is considered (for example chemical reaction or change in physical state). The basic properties of the materials, such as mechanical properties, required for design purposes are normally available from the materials supplier and are not considered in this part of ISO 11114.

The compatibility data given are related to single component gases but can be used to some extent for gas mixtures. Ceramics, glasses, and adhesives are not covered by this part of ISO 11114.

Other aspects such as quality of delivered gas are not considered.

This part of ISO 11114 is not intended to be used for cryogenic fluids (see ISO 21010).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11114-3, Transportable gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 3: Autogenous ignition test for non-metallic materials in oxygen atmosphere

ISO 10297, Gas cylinders — Refillable gas cylinder valves — Specification and type testing

ISO 15001, Anaesthetic and respiratory equipment — Compatibility with oxygen

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

BS EN ISO 11114-2:2013 **ISO 11114-2:2013(E)**

3.1

competent person

person who has the necessary technical knowledge, qualification, experience and authority to assess and approve materials for use with gases and to define any special conditions of use that are necessary

3.2

acceptable

material/gas combination that is satisfactory under normal conditions of use (as defined in Clause 5), provided that any indicated non-compatibility risks, as given in Table 1, are taken into account

3.3

not acceptable

material/single gas combination that is not safe under normal conditions of use (as defined in Clause 5)

NOTE For gas mixtures special conditions can apply.

3.4

dynamic sealing

where in normal operation the non-metallic material is used to provide a pressure seal between two surfaces that have relative motion to each other

3.5

static sealing

where in normal operation the non-metallic material is used to provide a pressure seal between two surfaces that have not relative motion to each other

4 Materials

4.1 General

Non-metallic materials shall be suitable for the intended service. They are suitable if their compatibility is stated as acceptable in Table 1, or the necessary properties have been proved by tests or long and safe experience to the satisfaction of a competent person.

If coated materials are used the suitability of the combination shall be assessed and approved if all technical aspects have been considered and validated by a competent person. These technical aspects include but are not limited to compatibility of the coating material with the intended gas, durability of the coating during all its intended use and gas permeability through it.

4.2 Types of material

The most commonly used non-metallic materials for gas cylinders and cylinder valves can be grouped as follows:

ioliows.	
— plast	ics;
— elast	omers;
— fluid	lubricants.
NOTE	Solid lubricants are sometimes used, e.g. MoS2.

a) Plastics:

Polytetrafluoroethylene (PTFE);

Materials considered in this part of ISO 11114 are as follows:

	—	Polychlorotrifluoroethylene (PCTFE);
		Polyvinylidenefluoride (PVDF);
		Polyamide (PA);
		Polypropylene (PP);
		Polyetheretherketone (PEEK);
	_	Polypropylene sulphide (PPS);
	_	Polyvinyl chloride (PVC)
	_	Polyimide (PI);
	_	Polyoxymethylene (POM).
b)	Ela	stomers:
		Butyl rubber (IIR);
		Nitrile rubber (NBR);
		Chloroprene rubber (CR);
		Fluorocarbon rubber (FKM);
		Methyl-vinyl-silicone rubber (VMQ);
		Ethylene propylene diene monomer (EPDM);
	_	Polyacrylate rubber (ACM);
		Polyurethane rubber (PUR);
	_	Methyl-fluoro-silicone rubber (FVMQ).
c)	Flui	id lubricants:
		Hydrocarbon (HC);
		Fluorocarbon (FC).

5 General considerations

It is important to note that these materials are generic types. Within each material type there are variations in the properties of the materials due to polymer differences and formulations used by manufacturers to modify physical and chemical properties of the material. The user of the material should therefore consult the manufacturer and if necessary carry out tests before using the material (for example for critical services such as oxygen and other oxidizing gases).

Lubricants are often used in valves to reduce friction and wear in the moving parts. For valves used for oxidizing gases or for gases supporting combustion, if lubrication is required, it shall be ensured that the lubricant is compatible for the intended application when the lubricated components are in contact with the oxidizing gas or the gas supporting combustion.

© ISO 2013 – All rights reserved

BS EN ISO 11114-2:2013 **ISO 11114-2:2013(E)**

Where the lubricant is listed as "not acceptable" in Table 1 for reasons other than violent reaction (F), it may be used safely and usually satisfactorily in applications which do not involve contact in normal operation with the gas. An example of such an application is the lubrication of the valve actuating mechanism not in contact with the gas.

Where the lubricant is listed as "not acceptable" for the reason of violent reaction (F), it should not be used in any part of the system that can be contacted by the gas, even under abnormal conditions such as in the event of a failure of the gas sealing system. If there is a risk of violent reaction, appropriate safety and suitability tests shall have been carried out for the lubricant application before it is used either on the lubricant itself, as specified in ISO 11114-3, or on the lubricated equipment in which it will be used, as specified in ISO 10297.

The properties of plastics and elastomers including compatibility are dependent on temperature. Low temperature can cause hardening and the possibility of embrittlement, whereas high temperature can cause softening and the possibility of material flow. Users of such materials shall check to ensure their suitability over the entire operating temperature range specified by the cylinder and valve manufacturing standards.

Some materials become brittle at low temperatures, especially at temperatures at the lower end of the normal operating range (e.g. fluorocarbon rubber). Temperatures in the refrigerant or cryogenic ranges affect many materials and caution shall be exercised at temperatures below -50 $^{\circ}$ C. This risk shall be considered in particular when transfilling by thermal siphoning at low temperature or similar procedures, or for cylinders regularly filled at low temperatures (e.g. CO_2).

6 Specific considerations

6.1 General

The compatibility of gases with non-metallic materials is affected by chemical reactions and physical influences, which can be classified as follows.

6.2 Non-compatibility risks

6.2.1 Violent reaction (oxidation/burning) (F)

6.2.1.1 Principle

Historically the majority of serious accidents from rapid oxidation or violent combustion have occurred with oxidizing gas supporting combustion at high pressure. Thorough investigation of all materials and factors should be conducted with great care and all data should be considered before designing or using equipment to handle oxidizing gases or gases supporting combustion.

Compatibility depends mainly on the operating conditions (pressure, temperature, gas velocity, particles, equipment design, and application). The risk shall particularly be considered with gases such as oxygen, fluorine, chlorine and nitrogen trifluoride. Most of the non-metallic materials can be ignited relatively easily when in contact with oxidizing gases (see ISO 10156) and even when in contact with gases not classified as oxidizing but still supporting combustion.

The selection of a material for use with oxygen and/or an oxygen enriched atmosphere is primarily a matter of understanding the circumstances that cause the material to react with oxygen. Most materials in contact with oxygen will not ignite without a source of ignition energy (e.g. friction, heat of compression, particle impacts, etc.). When an energy input rate, as converted to heat, is greater than the rate of heat dissipation, and the resulting heat increase is continued for sufficient time, ignition and combustion will occur.

Thus, two general factors shall be considered:

- a) the materials compatibility properties (ease of ignition and energy of combustion); and
- b) the different energy sources that will produce a sufficient increase in the temperature of the material.

These general factors should be viewed in the context of the entire system design so that the specific factors listed below will assume the proper relative significance.

The specific factors to take into consideration are

- the properties of the materials, which include the factors affecting ease of ignition and the conditions affecting potential resulting damage (heat of reaction),
- the operating conditions: e.g. pressure, temperature, oxygen and/or oxidizing gas concentrations in a gas mixture, influence of dilutant (e.g. helium), surface contamination,
- the potential sources of ignition (e.g. friction, heat of compression, heat from mass impact, heat from particle impact, static electricity, electrical arc, resonance, internal flexing),
- possible consequence (e.g. effects on the surroundings such as propagation of fire), and
- additional factors (e.g. performance requirements, prior experience, availability).

In conclusion the evaluation of compatibility of non-metallic materials is more critical than that of metallic materials, which generally perform well when in contact with oxygen.

6.2.1.2 Specifications for oxidizing gases

In accordance with 6.2.1.1, it is not possible to make a simple statement concerning the compatibility of non-metallic materials with oxidizing gases such as oxygen, chlorine, nitric oxide, nitrous oxide, nitrogen dioxide, nitrogen trifluoride, etc. (see ISO 10156).

For fluorine, which is the most oxidizing gas, all non-metallic materials would historically fall into the classification "not acceptable".

For fluorine mixtures the gases industry now has evidence of successful testing and safe history of use of PTFE and PCTFE under controlled conditions (e.g. low concentration and low pressure). Therefore following an assessment and authorisation by a competent person, these materials are acceptable in similar conditions. Oxygen and other oxidizing gases can react violently when tested with all non-metallic materials listed in 4.2 a), 4.2 b) and 4.2 c). Some materials such as PTFE and FKM are more resistant to ignition than other plastics and elastomers. HC lubricants are normally not acceptable. Under certain conditions other plastics and elastomers listed can be safely used in oxidizing service without presenting some of the disadvantages of PTFE, i.e. poor mechanical properties, and risk of release of toxic products for breathing gas applications, see ISO 15001, or FKM, i.e. swelling, poor mechanical properties at low temperature, risk of release of toxic products in breathing gas applications, etc..

Consequently, non-metallic materials may only be used if it has been proven by tests (or long and safe service experience), taking into account all the operating conditions and especially the design of the equipment, that their use is safe. ISO 11114-3 and ISO 21010 give testing methods for polymeric materials and fluid lubricants that will result in conservative value. Some non-metallic material can be safely used at higher pressure when they are tested in the final design configuration, e.g. in gas cylinder valves and regulator. Cylinder valves shall be tested according to ISO 10297 for oxygen service.

6.2.2 Weight loss (W)

6.2.2.1 Extraction

Solvent extraction of plasticizers from elastomers can cause shrinkage, especially in highly plasticized products.

© ISO 2013 – All rights reserved 5

BS EN ISO 11114-2:2013 **ISO 11114-2:2013(E)**

Some solvents, e.g. acetone or DMF¹⁾ used for dissolved gases such as acetylene, can damage non-metallic materials.

Liquefied gases can act as solvents.

6.2.2.2 Chemical attack

Some non-metallic materials can be chemically attacked by gases. This attack can sometimes lead to the complete destruction of the material, e.g. the chemical attack of silicone elastomer by ammonia.

6.2.3 Swelling of material (S)

Elastomers and plastics may be subject to swelling due to gas (or liquid) absorption. This can lead to an unacceptable increase of dimensions (especially for O-rings) or the cracking due to sudden out-gassing when the partial pressure is decreased, e.g. carbon dioxide with fluorocarbon.

Initial swelling can be masked by subsequent extraction of plasticizers and fillers while in service. Other important effects such as changes in mechanical strength and hardness should also be considered.

Differences in the compounding, formulation and curing of a given elastomer can cause significant differences in the swelling of the material in service.

Regardless of the above compatibility evaluation, the design configuration (e.g. static or dynamic sealing) shall be taken into account before deciding to use elastomers or plastics. In this part of ISO 11114, a swelling of more than approximately 15 % in normal service conditions is marked N (not acceptable for dynamic sealing); a swelling less than this is marked A (acceptable) provided other risks are also acceptable.

NOTE There is also a risk of cross bonding between sulphur vulcanised rubbers and copper alloys.

6.2.4 Change in mechanical properties (M)

Gases can lead to an unacceptable change of mechanical properties in some non-metallic materials. This can result, for example, in an increase in hardness or a decrease in elasticity. ISO 1817 gives testing methods to check the influence of the gas on the mechanical properties.

6.2.5 Other compatibility considerations

6.2.5.1 Impurities in the gas (I)

Some gases contain typical impurities which may not be compatible with the intended materials (e.g. acetone in acetylene, hydrogen sulphide in methane).

6.2.5.2 Contamination of the material (C)

Some materials become contaminated in toxic gas use by the toxic gas and become hazardous themselves (e.g. during maintenance of equipment).

6.2.5.3 Release of dangerous products (D)

Many materials when subjected to extreme conditions (such as elevated temperature) can release dangerous products (e.g. toxic products). This risk shall be considered in particular for breathing gases as specified in ISO 15001.

Dimethylformamide.

6.2.5.4 Ageing (G)

Ageing is a gradual change in the mechanical and physical properties of the material due to the environment in which it is used or stored. Many elastomer and plastic materials are particularly subject to ageing; some gases like oxygen and in general exposure to high temperatures may accelerate the ageing process, leading to degradation such as cracking, brittleness, etc.

6.2.5.5 Permeation (P)

Permeation is a slow process by which gas passes through materials.

The permeation of some gases (e.g. helium, hydrogen, carbon dioxide) through non-metallic material can be significant. For a given material, the permeation rate mainly depends on temperature, pressure, thickness, and surface area of the material in contact with the gas. The molecular radius of the gas and the specific formulation of plasticizers and other additives can cause a wide range of permeation rates for a particular type of plastic or elastomer.

This risk shall be considered for effects to the surroundings (e.g. toxicity, fire potential).

7 Compatibility data

7.1 Table of compatibility

Table 1 lists the gases in alphabetic order with the UN number in bracket. In this table, the compatibility data is given using the symbols and abbreviations defined in 7.2.1 and 7.2.2. When a gas/material combination is not acceptable, the main reason is given, using the appropriate abbreviation for the non-compatibility risk (see 6.2). The abbreviations are also sometimes used for acceptable combinations to show a limited risk.

If no UN number is listed in the table for a gas (or a liquid), this means that this gas has no official UN number but it may be transported using a generic NOS (Not Otherwise Specified) number (e.g. compressed gas, flammable, NOS, UN 1954).

Compatibility evaluations are based on the following documents:

- literature data;
- operational experiences; and
- laboratory tests.

The resistance to gases can be estimated by simple immersion tests in the respective gas with approximately the same or intensified exposure conditions (increase of temperature, pressure or flow rate). Time- and equipment-consuming test methods to evaluate the permeation, the absorption as well as the resistance to stress cracking are required in many cases.

Apart from the visual evaluation of detectable changes, changes in weight and dimension as well as the course of mechanical and other physical characteristics, depending on the immersion time are the parameters of immersion tests. They are consulted as classification characteristics.

In literature and company leaflets frequently used classifications are "resistant", "conditionally resistant" and "not resistant".

Test procedures are described in ISO 1817 and in ISO 9539.

© ISO 2013 – All rights reserved

7.2 Symbols and abbreviations

7.2.1 Symbols for compatibility

A = acceptable (see 3.2)

NOTE There can be a secondary risk associated (see 7.2.4).

N = not acceptable for use under normal service conditions (see 3.3)

a = No reliable recommendation can be made due to a lack of definitive information

u = The compatibility depends on the conditions of use (e.g. oxygen). The material may be used where it has been assessed and authorised by a competent person who specifies the conditions of use.

7.2.2 Abbreviations for materials

Abbreviation	Material
PTFE	Polytetrafluoroethylene
PCTFE	Polychlorotrifluoroethylene
PVDF	Polyvinylidenefluoride
PA	Polyamide
PI	Polyimide
PP	Polypropylene
POM	Polyoxymethylene
PEEK	Polyetheretherketone
PPS	Polypropylene sulphide
PVC	Polyvinyl chloride
IIR	Butyl rubber
NBR	Nitrile rubber
CR	Chloroprene rubber
FKM	Fluorocarbon rubber
VMQ	Methyl-vinyl-silicone rubber
EPDM	Ethylene propylene diene monomer
FVMQ	Methyl-fluoro-silicone rubber
ACM	Polyacrylate rubber
PUR	Polyurethane rubber
HC	Hydrocarbon
FC	Fluorocarbon

7.2.3 Abbreviations for non-compatibility risks

Symbols	Risk
а	No reliable recommendation can be made due to a lack of definitive information
Α	Acceptable
С	Contamination of material
u	The compatibility depends on the conditions of use
D	Dangerous product release
F	Flammable (Violent reaction)
G	Ageing
1	Impurities in the gas
М	Change of mechanical properties
N	Not acceptable for use under all normal service conditions
Р	Permeation
S	Swelling
W	Weight loss

7.2.4 Examples

EXAMPLE 1	
	A P

Symbol for compatibility = A

Abbreviation for non-compatibility risk = P

This example shows an acceptable material/gas combination, suitable for use in normal service conditions, provided the risk of permeation has been evaluated and found negligible.

EXAMPLE 2	
	N _{F,C}

Symbol for compatibility = N

Abbreviation for non-compatibility risk:

1st risk = F

2nd risk = C

This example shows a material/gas combination, not acceptable for general use with non-compatibility risks of violent reaction (1st risk) and contamination of material (2nd risk).

Table 1 — Compatibility of non-metallic materials with gases

				Plastics	ro.							·	Elastomers	ners							Fluid lubric	Fluid Iubricant	MoS2
(ON-NO)	Name	Formula	R#	PTFE	Ы	PCTFE PV	PVDF PA	В	POM	PEEK	S bbs	PVC	II Z	NBR C	CR FKM	M VMG	ď	EPDM FVM	MQ ACM	M PUR	A HC	5	
98 (2035)	1,1,1-TRIFLUOROETHANE	$C_2H_3F_3$	R143a	- V	- AS	S	В	SN	٧	A	Α			N SN	NS A		SN S		NS		NN	NN	Α
39 (1030)	1,1-DIFLUOROETHANE	$C_2H_4F_2$	R152a	/ V	A AS	S A	٧	SN	SN	SN	SN		∀ S∀	A A		SN	Y S		٧	_		MN	Α
40 (1959)	1,1-DIFLUOROETHYLENE	$C_2H_2F_2$	R1132a	- V	- AS	S	٧	SN	SN	SN	Α	I SN		A A	SN			NS		NS	ΝN	ΜN	A
97 (3082)	2-TRICHLORO-1,2,2- TRIFLUOROETHANE	$C_2Cl_3F_3$	R 113	<	- AS	∀	AW	∢	AS	⋖	⋖	N N	NS N	AS A	AS AS	SZ	SN N	SN	SN	SN	Š	Š	⋖
36 (1958)	1,2-DICHLORO-1,1,2,2- TETRAFLUOROETHANE	C ₂ Cl ₂ F ₄	R114	\ \	A AS	8	∢	SN	SZ	SN	A	SN	AS A	4	AS	SN	4	SN	⋖	⋖	Ň	×	∢
38 (2517)	1-CHLORO-1,1- DIFLUOROCHLORO- ETHANE	C ₂ H ₃ CIF ₂	R142b	4	A AS	Α	∢	S Z	S Z	S Z	SN	SN	AS A	AS A	AS NS	SS	∢	N S	∢	S S	Š	Ž	∢
24 (1021)	1-CHLORO-1,2,2,2- TETRAFLUOROETHANE	C ₂ HCIF ₄	R124	- V	Α .	A	A	SN	NS	SN	NS	SN	NS	NS	NS A	NS	SN	NS	NS	NS	NN	NN	A
113 (3161)	1-CHLORO-1,2- DIFLUOROETHANE	C ₂ H ₃ CIF ₂		- V	Α	A	∢	NS	SN	SN	SN	SN	NS N	N SN	NS A	SN	SN	NS	SN	SN			⋖
25 (1983)	1-CHLORO-2,2,2- TRIFLUOROETHANE	C ₂ H ₂ CIF ₃	R133a	/ v	A AS	S	A	SN	SN	SN	SN	SN	a	а	∢	SN	а	SN	SN	NS	NN	MN	∢
117 (2044)		C ₅ H ₁₂		Α .	- A	Α	Α	NS	٧	Α	٧	٧	VS ∀	A A	A	NS	SN S	A	NS				A
1 (1001)	ACETYLENE ²⁾	C_2H_2		Α	- A	Α	A W	/,I A	Α	Α				NW,I N	NW,I NW	V,I NW	V,I A	Α	NW,	/,I NW	,I NW	I NW,I	Α
105 (1002)				AF ,	AF AF		AF	AF	ΑF	AF	AF		AF A		AF AF					AF	AF	ΑF	٧
2 (1005)	AMMONIA	NH_3		A	NW A		,W A	Α	A	A				NW A	NN	WN V	۸	MN			MN	Α	Α
3 (1006)	ARGON	Ar		A	A	A	⋖	∢	⋖	⋖	4	Α	A			4	⋖	⋖	⋖	4	⋖		⋖
4 (2188)	ARSINE	AsH ₃			A ·		∢.		∢.	Α.						∢ :		Ì	∢ :		NC,	d NC,d	∢.
5 (1741)	BORON TRICHLORIDE	BCI ₃		Α,	- A		N :		Ž.	∢ ·	∢ .					NZ:			N :			∢ .	∢ ·
6 (1008) 9 (2419)	BORON TRIFLUORIDE BROMOTRIFLUORO- ETUNI ENE	BF ₃ C ₂ BrF ₃	R123B1	<	A AS	4 4 8 9	S S	A N	A S	A S	A N	A SN	NS N	X Z N N N	N SN	N N	N N N N	A N	N N	N N	A A	A WA	4 4
8 (1009)	BROMOTRIFLUORO- METHANE	CBrF ₃	R13B1	4	A AS	8	⋖	AS,V	∀	NS	SZ	NS	AS A	AS A	AS NS	R R	s AS	NS	⋖	⋖	AW	AW	<
10 (1010)	BUTADIENES	C₄H ₆		٧ ٧	A	A	∢	4	∢	4			Σ	NS,M N	NS,M A	NS,	Μ		NS	M NS,	Σ	∢	∢
12 (1011)	BUTANE	C ₄ H ₁₀		Α /	A		∢	Α	⋖	Α	٧	A	NS A	A A	A A	NS,	W.SM MS,	, M	Α	A	ΝN	⋖	A
13 (1012)	BUTYLENE	C_4H_8		A A	A	A	⋖	4	⋖			Σ	Σ				\boxtimes		NS	M NS,	Σ	⋖	⋖
16 (1013)	CARBON DIOXIDE	CO_2					⋖	⋖	NS,W		⋖			S,W	S,W	\geq		1)	∢	⋖	∢	⋖	⋖
17 (1016)		00		\ لا	A				⋖	⋖	⋖					Α		⋖	⋖		⋖		⋖
109 (2417)	CARBONYL FLUORIDE	COF ₂			A A			N S	≥ E	N S	≥ S	8	V V	ZZ	A N	≥ <	۷ ۲		N S	MN 2	N N	d NC,d	∢ <
19 (4504)	CANBOINTEGORINGE	200		C 9 003	62 12 Warning	Ther	ر ابر ابر	rick of viole	ont rea	- ÷		(<u>(</u>	(2	(2			2	(Z
20 (1017)	CHLORINE	\overline{Cl}_2		A	NF A			NF	본	NF	NS	- N	NF	N N	NF A	ΝN	N NF	분	Ν	Ŋ	٦	⋖	. ∢
110 (1589)	110 (1589) CHLORINE CYANIDE	CICN		Α .	- A				Α	Α	А	A			A								Α
111 (2548)		CIF5		l A	NW A			Α	NN	MN	NN			N WN	NW WN				MN /				Α
112 (1749)	112 (1749) CHLORINE TRIFLUORIDE	CIF ₃		A	NW A	NN	/ NW	Α	MN	NN	NW	NN	NW	NW NN	NW NW	NN N	NN N	/ NW	/ NW	/ NW			Α
																				İ]		

Some materials are not compatible because of the solvent used. 3 3

At high pressure risk of violent reaction due to oxygen.

Table 1 (continued)

				Plastics	κ								Ela	Elastomers	<i>(</i> ^							Fluid lubricant		MoS2
N-NO)	Name	Formula	# 2	PTFE	Ы	PCTFE	PVDF	PA	ЬР	POM PE	PEEK PPS	s PVC	¥ ∶	NBR	S CR	FKM	VMQ	EPDM	FVMQ	ACM	PUR	HC FC	0	
7 (1974) F	BROMOCHLORODI- FLUOROMETHANE	CBrCIF ₂	R12B1	٧	⋖	AS	< <	4	Z «	SN SN	SN S	SN	NS	NS	∢	∢	SN	SN	∢	NS	NS	NN NN	AW A	
21 (1018)	CHLORODIFLUORO- METHANE	CHCIF ₂	R22	АР	⋖	AS	4	4	АРА	AS	AS	SZ SZ	AS	SN	AS	SN	SN	∢	SZ	SN	SN	Z MN	WN A	
23 (1020) (CHLOROPENTAFLUORO- ETHANE	C ₂ CIF ₅	R115	A	∢	AS	∢	4	N SN	SN SN	SN S	SZ Z	⋖	∢	⋖	∢	SN	⋖	SN	∢	<	Z MN	A WN	
27 (1022) ⁽	CHLOROTRIFLUORO- METHANE	CCIF ₃	R13	A	<	AS	∢	4	N SN	SN SN	SN	SZ Z	⋖	∢	AS	∢	SN	⋖	SN	∢	NS	Z M	A WN	
37 (1026)	CYANOGEN	C_2N_2		٧	_	4					Ø	Ø	NS,	W NS,	W NR	4	۷	⋖	⋖			NC	NC	
	CYCLOPROPANE	C3H ₆				A	۷ V	A A	A		A	۷	NS		SN	Α	SN	NS	V	۷	A		A	
_	DEUTERIUM	4H on D		n		A					∢ .	⋖	∢	⋖	∢	∢	AΡ	Α.	V.	⋖ .				
32 (1911) [30 (1941) [DIBORANE DIBROMODIFLUORO-	B ₂ H ₆ CBr ₂ F ₂	R12B2	A AP	⋖ .	A AS	< <			A N N N N N N N N N N N N N N N N N N N	A N	A Z	A N	A N	∢ ∢	4 4	A NS	A N	A N	A NS	A NS	Z X	A A	
31 (no UN pet assigned)	DIBROMOTETRAFLUORO- ETHANE	C ₂ Br ₂ F ₄	R114B2	<		AS	< <	4	N SN	NS NS	S N	SN N	SN	S Z	AS	SZ	SN	SN	SN	NS	NS I	Z	WN A	
	DICHLORODIFLUORO- METHANE	CCI ₂ F ₂	R12	АР	A	AS	4	A	NS A	SN	SN	A	NS	AS	4	AS	NS,P	SN	NS	A	4	NW	NN A	
34 (1029) [[]	DICHLOROFLUORO- METHANE	CHCl ₂ F	R21	A	⋖	AS	4	4	AP N	SN SN	SZ 2	SZ Z	NS	SN	SN	SN	SN	SN	SZ	NS	NS	Z N	A W	
	DICHLOROSILANE	SiH ₂ Cl ₂		Α	-			NW I	,	IW NW			NN	NN	NN	Α	٧	NN	Α	NN		NC N	NC A	
(DIFLUOROMETHANE	CH_2F_2	R 32	٧	٧	NS	Y Y	A	(O	S	SN	SN	A	٧	∢	NS	SN	V	NS	NS	NS .	1	A	
	DIMETHYLAMINE	C ₂ H ₇ N		⋖	⋖		\otimes						∢ :		Š	≥ N	N.	4	N/N					
42 (1033)	DIMETHYLETHER	C ₂ H ₆ O		∢ .	-	Ą		NS	NS A	∢ .	A	NS	SN	NS	NS	SN	∢.	NS	V	NS	NS	Z MN	NW A	
118 (3161)	118 (3161) DIMETHYLSILANE	C ₂ H ₈ Si		A	A - A	- 1:	A Thorois		7	WW WW			Š		N N	N N	M	NN N	NN.		M		∢ <	
76 (1067)	(NITROGEN DIOXIDE) 3)	NO ₂ /N ₂ O ₄		900 0.2 A	NF VV		υ	NF N	N PIO	NF NF	<u>N</u>	¥	N N	¥	¥	ΝF	ΝF	NF	본	NF	본	S		
	DISILANE	Si_2H_6		Α	-	Α		a					Α	В	٧	Α	Α		A					
\neg	ETHANE	C ₂ H ₆			∢	A	۷,		Α :	A	∢ ;		SN .	∢ ,	SN.	∢,	NS,W	_	SN.		Α.	۷ .	A A	
46 (1037) E	ETHYL CHLORIDE	SH'C	K160	∢ <	-	AS		∀ <					Α N	∢ <	Ψ O	∢ <	NS.N		∢ <					
6	ETHYL METHYL ETHER	CHEO CHEO		< <		2 4		S			< <	SN	SS	SN	SZ	s N N	SN	S S	s S Z					
(;	ETHYLACETYLENE	C₄H ₆			A	А	A		A	4	۷	٧	⋖		⋖	٧			A	A			A	
=	ETHYLAMINE	C ₂ H ₇ N		ĺ	ĺ	V.					N.		Ž.		Ž.	N N	NZ.	∢ :	ΝN.			>	>	
47 (1962) E 48 (1040) E	ETHYLENE ETHYLENE OXIDE	C₂H₄ C₂H₄O		4 4	4 4	4 4	<u> </u>	A NS,W	A NS,W N	A NS,W NS	^	A A NS,W NS,V	,W NS,	W NS,W	W NS,W	A NS,W	NS,W		A NS,W	A NS,W	A NS,W	A N N N	A NR A	
49 (1045)	FLUORINE	Ľ.		see 6.2	×		There is	is a risk o	f violent	reaction	Ī	Ī		ļ							Ī	Ī	Ī	
		7		ш	Ь	ш	造,	는 ' 당 .	스 ⁴ 坅 .	N N N			불	¥.	岁	Ľ,	본 <	IJ.	₽,	NF <	ш		_	ш
53 (2192) (64 (1046) 1	GERMANE	GeH₄ He		A		Α <		4 <	A A	∢ <		∢ <	∢ <	∢ <	∢ <	∢ <	A A	∢ <	∢ <	Α <	A <	NC,d N	NC,d A	
- 1	TI LIOPOPPOPANE					۲ <			X <		< <	<	<	< <	< <	< <	۲ <		< <			1 <		
		C3F ₆ O		4 4	NSM	× ×	4 4		S.W	S.W	NS.W NS	NS/W NS/W		W.S.W	_		NS.W	NS.W	NS,W	NS.W	NS.W		< <	
	HEXAFLUOROETHANE	C_2F_6	R116			AS,W		A									NS,W		NS,W			N N	NW A	
56 (1858) H	HEXAFLUOROPROP YL EN E	C_3F_6		А	٧	AS	, A	۷ ۷	NS,W	SN W;SN	SN W;SN	MS,W NS,W	W NS,W	W NS,W	W NS,W	Α/	NS,W	NS,W	NS,W	WS,W	NS,W	N WN	NW A	
	HYDROGEN	H_2		Ω.	⋖	A		A		A			⋖	A		A	ΑЬ	4	ЧЬ	AP	A A	A A		
	HYDROGEN BROMIDE	HBr				Ą	Α,		Z :	NN NN	NN N	۷ ·	ŠZ.		NZ.	۷,	NN.	∢,	NN.	MN :		NC NC	O 0	
59 (1050) H	HYDROGEN CHLORIDE	HCI		A	⋖	¥		MN		MN			NZ NZ	NN N		⋖	MN	⋖	NN		MN	NC	1	

Table 1 (continued)

													L								ľ	:		ſ
				Plastics	S	,	•		ļ			,	Elas	Elastomers	,		j			,		riuid Iubricant		MoS2
(ON-NO)	Name	Formula	R #	PTFE	Ы	PCTFE	PVDF P	PA P	PP PC	POM PEEK	EK PPS	PVC	Ħ	NBR	CR	FKM	VMQ	EPDM	FVMQ	ACM	PUR I	нс FC	0	
60 (1051)	HYDROGEN CYANIDE	HCN		Α	_	∀ ∀	٧					٧	ΜN	MN	ΜN	٧		Α	MN	MN		NC NC	S	
	HYDROGEN FLUORIDE	Ή		A	-							٧	ΝN	MN	ΜN	¥		Α	MN					
62 (2197)	HYDROGEN IODIDE	Ξ		Α,				×				⋖	≥ N	N.	≥ N	∢,	× × N	A	MN	Š	NN NN	NC		
2)	HYDROGEN SELENIDE	H ₂ Se		۸ ç			Α ·	ı	A N		∢ <	, <	-	N E	-	∀								
63 (1053)	HYDROGEN SULPHIDE	H ₂ N		₽ <	∢ <		4 <				∢ <	∢ <	A N	Ž.	<u> </u>	<u> </u>	NN O	A	A <	<	<	NC V		
65 (1055)	SOBOLITYI ENE	Q4110		ζ <						< <	< <	ζ <	200	ζ <	2	ζ <		NO, M	ζ <	2 0	1 012			
	KRYPTON	Σ ₄ Ξ ₈		τ α	(d		< <	X A	X A	< <	∢ ∢	(∢	N 4	_	2 4	(<		Σ, Δ	τ Φ			\ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \	(<	
	METHANE	CH⁴		A				\ \ \		< <	Z	< <	SN	. ∢	< <	. ∢		NS	SN					
	METHYL BROMIDE	3r	R40B1	4					NS A	∢	NS	SN	SN	SN	SN	⋖	SN	NS	A	SN	NS	NN WN		
	METHYL FLUORIDE		R41	А		AS /				Α	Α	NS	NS	SN	NS	A		NS	Α					
	METHYL MERCAPTAN	CH4S		А	1		A	a ا	A	4	A	Α	ΝN	MN	MN	ΝN	A	Α	MN	-	_	NC NC	S	
126 (2455)	METHYL NITRITE	CH ₃ NO ₂		Α		A A		-	1	-	-	-	-	NN	-	A	-		-	-	-	-	Α	
	METHYLACETYLENE	C_3H_4		Α	Ā	A A	A	AW A		A	Α	Α	Α	,	1	а	a	а	-			NW,I A	Α	
	METHYLAMINE	CH ₅ N		Α					A				A	ΝN	ΝN	NN		А	MN	ΝN			A	
	METHYL CHLORIDE	CH ₃ CI	R40	A	لا	A	A			Α S	NS	NS	NS	NS	NS	⋖		NS	NS			NW WN	W A	
I)	METHYLCHLOROSILANE	CH ₅ SiCl		Α	1	A A		NS N	NS NS			NS	NS	NS	NS	SN	S	NS	SN		S		A	
71 (3161)	METHYLSILANE	CH_6Si		Α	_	A	- -	-	⋖	4	Α	4	٧	-	A	⋖		A	٧		A	NC NC	S	
73 (1065)	NEON	Ne		Α	, A		A	٧	Α	4	∢	٧	٧	Α	4	4	4	A	V	Α	A	A	A	
				see 6.5	see 6.2.1.2 Warning		There is	is a risk of	violent r	of violent reactions		-	-	-					_		-	=		
74 (1660)	NITRIC OXIDE	O N		Ad	¥.	Ad /	Ad	NF,W	NF NF	Ľ.	본	Ľ L	NF,W	V NF,W	, NE,W,	Ad	٩N	NF,W	Ą	N H	Ad	NF,C	NC,d A	
75 (1066)	NITROGEN	N_2		A	4		A	4	A	∢	⋖	⋖	۷	⋖	⋖	⋖	4	A	4	4	V V	A	A	
78 (2451)	NITROGEN TRIELLIORIDE	NE.		see 6.2	see 6.2.1.2 Warning		ere	a risk of	violent r	is a risk of violent reactions											•	•	•	
	MILIOGEIN IIVII EOONIDE	NI 3		Α	ц.		A		<u>ш</u>	ш	Ь	ட	ш	止	上	V	Ь	ш	ш	F	Ь	F	A	
119 (2421)	119 (2421) NITROGEN TRIOXIDE	, O, N		see 6.2	2 Wa		ere	risk	violent r	eact	Ī	!	!	!	!	!	Ī	!	!			Ī	∢ .	
		0 - 4		A	JNF.			N H	NF NF	<u>4</u> :	Y.	불	Y.	₹	Y.	¥	NF	J-N	¥	Y-	NF	NF F	∢ ⟨	
77 (1070)	NITROUS OXIDE	O,N	_	see 6.2	see 6.2.1.2 Warning		There is a	a risk of	violent r	act	Ī	!!	!!!	!	!	9	Ī	0	ŀ		Ī	Ī		
				Α,					NF NF			노 :	NF,S	_		SN .	Α .	AF,S	Α.	۷.	۷ .	NF A	A ·	
	OCTAFLUORO PROPANE		K218	۷,	ď		Α ·			∢ ‹	∢ •	SS	∢ ,	∢ .	∢ ,	۷ .		⋖・	AS					
(2422)	OCTAFLUOROBUI-Z-ENE	C ₄ F ₈	K 1318	4		AS	4 V		NS.	∢	∢	S N	∢	∢	⋖	AS	AS	∢	AS	S	SS	Z MN	NN A	
80 (1976)	CYCLOBUTANE	C_4F_8	RC318	⋖	∢	AS /	<u>۷</u>		NS A	⋖	⋖	SN	∢	⋖	⋖	AS	AS	⋖	AS	SN	SN	N N	A WN	
(2) (1072)	OXYGEN	ď		see 6.2	see 6.2.1.2 Warning		e	ı risk	violent r	of violent reactions	ŀ													
1			707	F,D			Ω			ш <		ш <	ш <	ш <	Д, Ф,	F,S,D	ц «	ш	LL <			ш	F,D A	
128 (3083)	PENTALLOCKOETHAINE PERCHLORYL ELLORIDE	C2D.F	K 123	۷ ۷	۲ .	τ 4	ξ Z	>	WN WN	X N	X N	₹ Ž	₹ Ž	₹ N	X X	∡ Ž	X N	X MN	X N	X NN	, MN	ξ .	{ ⊲	
	PERFLUORO (ETHYL	C,F,O		: ∢	SZ	. «						SN	SZ	SN	SZ	SN		SN	SN		SN		(∢	
(:)	VINYL ETHER)) 		. [1					!	!			!			2)	2			
130 (3153)	PERFLUORO (METHYL VINYL ETHER)	C_3F_6O		⋖	SN	٠ ٧		NS	NS NS	SN S	SN	SN	SZ	SN	SN	SN	NS	SN	NS	SN	SN	1	⋖	
83 (1076)	PHOSGENE	COCI2		Α		A	NW N	NW N	NW A	ΝN	MN /	ΝN	⋖	⋖	ΝN	۷	MN	۷	٧	MN		NC NC	CA	
84 (2199)	PHOSPHINE	PH_3		А	1		A	- 9	A	A		∢	Α	A	A	۷		A	A	MN	NN			
131 (2198)	PHOSPHORUS PENTAFI LIORIDE	PF ₅		⋖		∀	- 4	-	∢	∢	⋖	∢	,		,	⋖			⋖			-	⋖	
86 (2200)	PROPADIENE	C₃H₄		A	4		A	AW		⋖	4	⋖	⋖	SN	SN	⋖	ΝS	NS	∀	NS		W.I	A	
	PROPANE	C ₃ H ₈		A		. A		A	× ×	< <	< <	SN	NS	⋖	SN	< <	Μ,	MS'M	SN		NS	NM		
	PROPYLENE	C_3H_6		А			A A			٧	Α	NS	NS	NS	NS	A		NS	NS	SN				
1		,							Ì								1			1	1	1	l	1

Table 1 (continued)

																					٥	71117		
				Plastics	ç	,	•	ļ			•		Elastomers	ners	٠	•		•	•	į	_ =	ubricant	Mc	MoS2
(ON-NO)	Name	Formula	R#	PTFE	Ы	PCTFE P	PVDF PA	۱ PP	POM	A PEEK	Sdd)	PVC	II	NBR	CR	FKM V	VMQ	EPDM F	FVMQ /	ACM P	PUR HC	C FC		
88 (1280)	IDE	C ₃ H ₆ O		А	- ۷		NS,W NS,	W, NS,	W;W NS,W	W NS,W	/ NS,W	WS,W	NS'M	NS,W	NS,W	NS,W N	NS,W N	NS,W N	NS,W	NS,W N	NS,W NW	WN W	٨	
132 (2194)	SELENIUM HEXAFLUORIDE	SeF ₆		А	- ۷	٧	MN	∀ >	٧	٨	∢	٧	Ν×	MN	MN	A A	N MN	NN N	WN	NN	- MN	1	A	
	SILANE	SiH₄		Α	A A	٧		-	A	٧	٧			į,	İ.		A	A		A A		NC NC	A	
90 (1818)	SILICON TETRACHLORIDE	SiCl₄		⋖	- V	٧	MN	۷	ΝN	ΝN	ΝN	MN	ΝN	NN	/ MN	۷ ۷	NW A		NN I	NW N	NW NC	C NC	Α	
	SILICON TETRAFLUORIDE	SiF₄		Α	- A	۷ ۸	NN	۷ ۸	NN	NN	NN	NN	NN	NW	NW I	NW N	NW A			NW N	NW NC	C NC	A .	
106 (2676) STIBINE		SbH₃		Α	Y Y	۷ ۷	٧	Α	Α	Α	Α	٧	Α	/ MN	/ Y	∀ ∀	A A			A a	а	а	Α	
133 (2191)	DE	SO_2F_2		Α	- A		NN NN	NN N		NN	NN	NN	NN	NW	,		NW A				NW	-	Α	
92 (1079)	SULPHUR DIOXIDE	SO_2		Α	A A	۸	NN	۸ ۸	NN	Α		MN	Α	NW	NW	NW N	NW A		NW	NW A		NW,C NC	A	
93 (1080)	SULPHUR HEXAFLUORIDE SF ₆	${\sf SF}_6$		Α	Y Y	۷ ۷	٧	Α	Α	Α	Α	Α	A	/ V	/ Y	∀ ∀	A A	Y Y		NW A	Α	Α	Α	
94 (2418)	RIDE	SF ₄		A	Y Y	٧	A	∢	٧	٧	⋖	٧	A	٧ ٧	/ 4	∀ ∀	A A	V V		NW A	4	∢	A	
134 (2195)	TELLURIUM HEXAFLUORIDE	TeF ₆		A	Y Y	٧	MN	∢ >	⋖	⋖	∢	٧	N/N	MN	MN	A A	NN N	NN N	MN	NN N	- MN	1	4	
95 (1081)	TETRAFLUOROETHYLENE C2F4		R114	Α	- ۷	۷ ۷	٧	NS	Α	Α	Α	SN	A	Α .	/ V	A N	NS A		AS I	NS A		NN WN	۸	
18 (1982)	HANE	CF_4	R14	Α	V V	AS,W A	٧	Α	NS,V	W NS,W		Λ	W	W	Μ	A N	NS,W N	NS,W N	W	W	W	NW A	٧	
96 (1295)		SiHCl ₃		Α	- A	۸	NN	NN N	NN v	NN	NN	NN	NN	NW	NW	A	NW A		NW	NW	NW NC	C NC	A	
26 (1082)	TRIFLUOROCHLOROETHY LENE	C_2CIF_3	R1113	А	<u>-</u>	NS A	Α	NS	SN	NS	NS	NS	-		-	A N	N SN	NS SN	- SN		N SN	NW WN	٧	
52 (1984)	TRIFLUOROMETHANE	CHF_3	R23	Α	<u>-</u>	NS,W A	Α	Α	Α	Α	Α	NS,W	A	Α .	A .	A A	A A				NS N	NW A	Α	
99 (1083)	TRIMETHYLAMINE	C_3H_9N		Α	- V	NG N	NG,W NW	۸ ۸	Α	Α	MΝ	٧	A	AW I	NN W	NW N	NW A		NW I	NW NN	MN WN	W NRA	SA AS	
100 (2196)	TUNGSTEN HEXAFLUORIDE	${\sf WF}_{\sf e}$		A	A A	V V	1	4	٧	A	⋖	٧	NN	MN	MN	A A	NW A		MN	NN N	N MN	NC NC	A .	
101 (1085)	101 (1085) VINYL BROMIDE	C_2H_3Br	R140B1	Α	- ۷	AS A	-	NS		SN	SN	SN				A N	NS N			NS N	NS N	NN WN	۸	
102 (1086)		C_2H_3CI	R140	Α	- A	AS A	-	NS	SN	SN	NS	NS	NS	NS I	NS /	A N	NS N	NS N	NS I	NS N	NS N	NW NW	٨	
103 (1860)	103 (1860) VINYL FLUORIDE	C_2H_3F	R141	Α	- A	AS A	-	NS	NS	NS	NS	NS		NS I	NS /	A	NS N	NS N			NS N	NW NW	Λ	
135 (1087)	135 (1087) VINYL METHYL ETHER	C_3H_6O		Α	- A	۸	NS	SN S	SN	SN	NS	NS	NS	NS	NS N	NS N	NS N	NS N	NS I	NS N	NS -	-	A	
104 (2036) XENON		Xe		Α	∀	A	٧	Α	Α	V	Α	V	A	\ \	4 4	A A	A A	Α ,		A	V	٧	∢	

Bibliography

- [1] ISO 21010, Cryogenic vessels Gas/materials compatibility
- [2] ISO 11114-1, Gas cylinders Compatibility of cylinder and valve materials with gas contents Part 1: Metallic materials
- [3] ISO 10156, Gases and gas mixtures Determination of fire potential and oxidizing ability for the selection of cylinder valve outlets
- [4] ISO 1817, Rubber, vulcanized or thermoplastic Determination of the effect of liquids
- [5] ISO 9539, Gas welding equipment Materials for equipment used in gas welding, cutting and allied processes
- [6] UNECE, UN Recommendations on the Transport of Dangerous Goods: Model Regulations





British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards -based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com
Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070 Email: copyright@bsigroup.com

