

BS EN ISO 11642:2012



BSI Standards Publication

Leather — Tests for colour fastness — Colour fastness to water

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 11642:2012. It supersedes BS EN ISO 11642:1998 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee TC1/69, Footwear, leather and coated fabrics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012

Published by BSI Standards Limited 2012

ISBN 978 0 580 72960 7

ICS 59.140.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 December 2012.

Amendments issued since publication

Amd. No.	Date	Text affected
----------	------	---------------

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 11642

November 2012

ICS 59.140.30

Supersedes EN ISO 11642:1998

English Version

**Leather - Tests for colour fastness - Colour fastness to water
(ISO 11642:2012)**

Cuir - Essais de solidité des coloris - Solidité des coloris à l'eau (ISO 11642:2012)

Leder - Farbechtheitsprüfungen - Farbechtheit gegenüber Wasser (ISO 11642:2012)

This European Standard was approved by CEN on 14 November 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
---------------	---

Foreword

This document (EN ISO 11642:2012) has been prepared by Technical Committee CEN/TC 289 "Leather", the secretariat of which is held by UNI, in collaboration with the International Union of Leather Technologists and Chemists Societies.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2013, and conflicting national standards shall be withdrawn at the latest by May 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 11642:1998.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 11642:2012 has been approved by CEN as a EN ISO 11642:2012 without any modification.

Contents		Page
1	Scope	1
2	Normative references	1
3	Principle	2
4	Apparatus and materials.....	2
5	Test specimens.....	3
6	Procedure	3
7	Evaluation	4
8	Precision	4
9	Test report.....	4
Annex A (informative) Commercial sources for apparatus and materials.....		5

Leather — Tests for colour fastness — Colour fastness to water

1 Scope

This International Standard specifies a method for determining the colour fastness to water of leather of all kinds at all stages of processing.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A01, *Textiles — Tests for colour fastness — Part A01: General principles of testing*

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 105-A03, *Textiles — Tests for colour fastness — Part A03: Grey scale for assessing staining*

ISO 105-A04, *Textiles — Tests for colour fastness — Part A04: Method for the instrumental assessment of the degree of staining of adjacent fabrics*

ISO 105-A05, *Textiles — Tests for colour fastness — Part A05: Instrumental assessment of change in colour for determination of grey scale rating*

ISO 105-F01, *Textiles — Tests for colour fastness — Part F01: Specification for wool adjacent fabric*

ISO 105-F02, *Textiles — Tests for colour fastness — Part F02: Specification for cotton and viscose adjacent fabrics*

ISO 105-F03, *Textiles — Tests for colour fastness — Part F03: Specification for polyamide adjacent fabric*

ISO 105-F04, *Textiles — Tests for colour fastness — Part F04: Specification for polyester adjacent fabric*

ISO 105-F05, *Textiles — Tests for colour fastness — Part F05: Specification for acrylic adjacent fabric*

ISO 105-F06, *Textiles — Tests for colour fastness — Part F06: Specification for silk adjacent fabric*

ISO 105-F07, *Textiles — Tests for colour fastness — Part F07: Specification for secondary acetate adjacent fabric*

ISO 105-F10, *Textiles — Tests for colour fastness — Part F10: Specification for adjacent fabric: Multifibre*

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*

3 Principle

A leather specimen is soaked in demineralized water and a piece of adjacent fabric, also soaked in demineralized water, laid against each side to be tested. The composite specimen is left under pressure for a specified time in a suitable apparatus. The leather specimen and adjacent fabric are then dried, and the change in colour of the specimen and the staining of the adjacent fabric assessed with the grey scales.

Leathers with a finish may be tested intact or with the finish broken.

The general colour fastness testing principles shall be in accordance with those described in ISO 105-A01, taking into account that the substrate is leather.

4 Apparatus and materials

Ordinary laboratory apparatus and

4.1 Test apparatus, consisting of a stainless-steel frame, into which a rectangular weight-piece approximately 5 kg in mass and approximately 115 mm × 60 mm in cross-section fits accurately, so that a uniform pressure of $12,5 \pm 1,0$ kPa can be applied on the composite specimen, placed between rectangular plates of an inert material, e.g. glass or acrylic-resin, of the same length and width as the weight-piece and about 1,5 mm thick.

The test apparatus shall be constructed so that if the weight-piece is removed during the tests, the pressure of 12,5 kPa remains unchanged.

Other devices may be used provided that equivalent results are obtained.

NOTE An example of a suitable apparatus available commercially is given in Annex A.

4.2 Oven, maintained at $37 \text{ °C} \pm 2 \text{ °C}$.

4.3 Adjacent fabrics (see ISO 105-A01). Either

- a) a multifibre adjacent fabric, complying with ISO 105-F10, measuring approximately 100 mm × 40 mm, or
- b) single-fibre adjacent fabrics, complying with the relevant specification in ISO 105-F01 to F07.

NOTE Examples of suitable commercial sources are given in Annex A.

4.4 Demineralized water, grade 3 in accordance with ISO 3696:1987.

4.5 Fine-grained adhesive paper, grade P 180.

4.6 Grey scale for assessing staining, in accordance with ISO 105-A03.

4.7 Grey scale for assessing change in colour, in accordance with ISO 105-A02.

4.8 Spectrophotometer or colorimeter for assessing change in colour and staining, complying with ISO 105-A04 and ISO 105-A05.

4.9 A vessel suitable for evacuation, e.g. vacuum-desiccator.

4.10 Vacuum pump, capable of evacuating the desiccator vessel (4.9) to approximately 5 kPa (50 mbar) within 4 min.

5 Test specimens

5.1 If the piece of leather available for testing is a whole hide or skin, then first take a sample in accordance with ISO 2418.

5.2 If the leather has a finish and is to be tested with the finish broken, prepare the test specimen as follows:

Cut out a piece of leather approximately 120 mm × 50 mm and lay it out, finish-side down, on a sheet of abrasive paper (4.5), measuring approximately 150 mm × 200 mm, held flat on a work surface. Load the upper side of the piece of leather uniformly with a 1 kg weight. Move the piece of leather approximately 100 mm to and fro on the abrasive paper, carrying out 10 to-and-fro cycles.

NOTE With practice, the same roughening effect can be achieved holding the abrasive paper in the hand.

Brush the roughened area thoroughly to remove all dust. From the roughened area of the leather, cut out a test specimen measuring approximately 100 mm × 40 mm.

To test leather for upholstery application with a surface coating, larger leather pieces, e.g. approximately 110 mm × 50 mm can be used to avoid staining caused by contact of water with the leather fibres at the edge.

The fact that the finish has been broken shall be mentioned in the test report.

5.3 If the leather has no finish, or if it has a finish but is to be tested with the finish intact, simply cut out a test specimen measuring approximately 100 mm × 40 mm.

5.4 For each leather specimen cut out a piece (or pieces) of adjacent fabric (4.3), enough to cover the leather sample measuring approximately 100 mm × 40 mm. If both sides are to be tested then another piece(s) of adjacent fabric is required.

6 Procedure

6.1 Immerse the leather specimen and adjacent fabric(s) in demineralized water (4.4) in separate containing vessels, using for example bent glass rods to keep them immersed. (If testing more than one specimen simultaneously, several pieces of adjacent fabric may be immersed in the same containing vessel, but each leather specimen shall be immersed in a separate vessel. Place the containing vessels in the vacuum vessel (4.9), produce a vacuum of approximately 5 kPa within 4 min, and hold this vacuum for 2 min. Restore normal pressure. Repeat the procedure a further two times.

In the case of testing leather for upholstery with a surface coating, wet the surface with water but do not immerse the leather specimen in water.

Lay a piece (or pieces) of adjacent fabric out on a glass or acrylic-resin plate (4.1) and cover it with the leather specimen, with the side under test facing down. If both sides are to be tested, cover the leather specimen with a second piece (or pieces) of adjacent fabric. Cover the composite specimen with a second glass or acrylic-resin plate.

6.2 Preheat the loading weight-piece in the oven (4.2) at 37 °C ± 2 °C for at least 1 h. Place the composite specimen, between the two plates, in the test apparatus (4.1) and load it with the weight-piece. In order to allow excess demineralized water to run off, tilt the apparatus about 30° to each side for a few seconds. (When testing several composite specimens simultaneously, take care to ensure that each is placed centrally between two plates in such a way that the pressure is exerted evenly on it.) Place the loaded apparatus in the oven and leave at 37 °C ± 2 °C for 180 min ± 10 min.

6.3 At the end of the 180 min period, take off the load, remove the composite specimen from the apparatus, fix it together at one corner (by stitching or stapling), and dry it by hanging it in air at room temperature, with the specimen and its adjacent fabric(s) in contact only at the point they are fixed together.

7 Evaluation

7.1 When the composite specimen is dry, using D65 illumination according to ISO 105-A01:2010 (Clause 15), visually assess the staining of each kind of fibre in the adjacent fabric(s), using the appropriate grey scale (4.6) in accordance with ISO 105-A03. Also assess the change in colour (4.7) of the leather specimen in accordance with ISO 105-A02.

7.2 Alternatively, provided the staining and colour change is even, the grey scale staining and colour difference can be assessed instrumentally (4.8) in accordance with ISO 105-A05 and ISO 105-A04.

8 Precision

For the visual grey scale evaluations, an inter-person precision of $\pm 0,5$ grey scale units is normal.

9 Test report

The test report shall include the following information:

- a) a reference to this International Standard, ISO 11642;
- b) a description of the type of leather tested and which surface of the leather was tested;
- c) whether there was a finish and, if so, whether the finish was broken;
- d) the numerical grey scale ratings obtained for the staining of the adjacent fabric(s), giving a separate grey scale rating for each of the different types of fibre;
- e) the numerical grey scale rating obtained for the change in colour of the leather specimen;
- f) details of any deviations from the procedure specified.

Annex A (informative)

Commercial sources for apparatus and materials

Examples of suitable products available commercially are given below. This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of these products.

A.1 A suitable apparatus is:

- the Perspirometer (Hydrotest apparatus) from Karl Schröder KG, Karrillonstrasse 32, D-69469 Weinheim, Germany. Website: www.schroeder-prueftechnik.de
- the AATCC Perspiration Tester from SDL Atlas UK, Shawcross St., Stockport, SK13JW, UK. Website: www.sdlatlas.com
- the Perspirometer from James H. Heal & Co. Ltd, Richmond Works, Halifax, West Yorkshire HX3 6EP, UK. Website: www.james-heal.co.uk
- the Perspirometer from PFI Germany, Test and Research Institute, Marie-Curie-Strasse 19, D-66953 Pirmasens, Germany. Website: www.pfi-germany.de

Any other suitable apparatus may be used, provided it gives the same results.

A.2 Examples of suppliers for the adjacent fabrics conforming to ISO 105 Standards:

- EMPA Testmaterialien AG, Mövenstrasse 12, CH-9015 St. Gallen-Winkeln, Switzerland. Website: www.empa-testmaterials.ch
- SDC Enterprises Limited, Pitcliffe Way, Upper Castle Street, Bradford, BD5 7SG, UK. Website: www.sdcenterprises.co.uk
- Testfabrics Inc., PO Box 26, West Pittston, PA 18643 USA. Website: www.testfabrics.com

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™