BS EN ISO 11876:2010



BSI Standards Publication

Hardmetals — Determination of calcium, copper, iron, potassium, magnesium, manganese, sodium, nickel and zinc in cobalt metal powders — Flame atomic absorption spectrometric method (ISO 11876:2010)

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW



National foreword

This British Standard is the UK implementation of EN ISO 11876:2010.

The UK participation in its preparation was entrusted to Technical Committee ISE/65, Sintered metal components.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2010

ISBN 978 0 580 56452 9

ICS 77.160

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2010.

Amendments issued since publication

Date Text affected

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN ISO 11876

August 2010

ICS 77.160

English Version

Hardmetals - Determination of calcium, copper, iron, potassium, magnesium, manganese, sodium, nickel and zinc in cobalt metal powders - Flame atomic absorption spectrometric method (ISO 11876:2010)

Métaux-durs - Dosage du calcium, du cuivre, du fer, du potassium, du magnésium, du manganèse, du sodium, du nickel et du zinc dans les poudres métalliques de cobalt - Méthode par spectrométrie d'absorption atomique dans la flamme (ISO 11876:2010)

Hartmetalle - Bestimmung des Calcium-, Kupfer-, Eisen-, Kalium-, Magnesium-, Mangan-, Natrium-, Nickel- und Zinkgehaltes in Kobalt-Metallpulvern - Verfahren mit Flammen-Atomabsorptionsspektrometrie (ISO 11876:2010)

This European Standard was approved by CEN on 14 August 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 11876:2010) has been prepared by Technical Committee ISO/TC 119 "Powder metallurgy".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2011, and conflicting national standards shall be withdrawn at the latest by February 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 11876:2010 has been approved by CEN as a EN ISO 11876:2010 without any modification.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 11876 was prepared by Technical Committee ISO/TC 119, Powder metallurgy, Subcommittee SC 4, Sampling and testing methods for hardmetals.

Hardmetals — Determination of calcium, copper, iron, potassium, magnesium, manganese, sodium, nickel and zinc in cobalt metal powders — Flame atomic absorption spectrometric method

1 Scope

This International Standard specifies a flame atomic absorption spectrometric method to be used for the determination of the mass fractions of copper, potassium, magnesium, manganese, sodium and zinc in cobalt metal powders in the range of 0,001 % to 0,01 %, calcium in the range of 0,002 % to 0,01 %, and iron and nickel in the range of 0,002 % to 0,05 %.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3534-1:2006, Statistics — Vocabulary and symbols — Part 1: General statistical terms and terms used in probability

3 Reagents

Use only reagents of the highest purity and only double-distilled water or water of equivalent purity.

- **3.1 Nitric acid**, $\rho = 1,42$ g/ml, diluted 1 + 1.
- **3.2 Hydrochloric acid**, $\rho \approx 1.1$ g/ml (hydrochloric acid, $\rho = 1.19$ g/ml, diluted 1 + 1).
- 3.3 Cesium chloride solution, (20 g/1 000 ml).
- 3.4 Standard solutions, (1,000 g/1 000 ml) for calibration purposes for each element to be determined.

4 Procedure

4.1 Test portion

Weigh, to the nearest 0,001 g, approximately 1 g of the sample.

4.2 Dissolution of the test portion

Add 20 ml of nitric acid (3.1) and 10 ml of hydrochloric acid (3.2) and heat gently until the test portion is completely dissolved.

4.3 Dilution volume

- **4.3.1** Add 5 ml of the cesium chloride solution (3.3) and dilute to 100 ml.
- **4.3.2** Shake the analysed volume with 20 ml of freshwater and filter using appropriate filter media over a plug of cotton wool into a 50 ml or 100 ml volumetric flask. Depending on the concentration of the determined elements in the sample and/or the sensitivity of the photometer, the dilution volume may be either 50 ml or 100 ml in volumetric flask.

4.4 Preparation of calibration and blank solutions

- **4.4.1** Prepare at least three solutions according to 4.2 with a matrix as similar as possible to the test portion to be analysed but without making up to volume. Then add increasing volumes of property diluted standard solutions of the elements to be determined according to the concentration ranges to be covered. Make up to 100 ml and mix.
- **4.4.2** Prepare at least two blank solutions (see 4.4.1) without the addition of the relevant element to be determined.

4.5 Adjustment of the atomic absorption spectrometer

SAFETY PRECAUTIONS — Follow the manufacturer's recommendation on igniting and extinguishing the flame.

Optimize the response of the instrument at the wavelength given for the element to be determined (see Table 1). Preheat the burner for about 5 min and adjust the fuel and correct the burner to obtain maximum absorption while aspirating a calibration solution.

Make sure that the absorbance reading is not drifting. Aspirate water and set the initial reading to zero absorbance.

Element	Wavelength	Oxidant/fuel
	nm	
Са	422,7	N ₂ O/acetylene
Cu	324,8	air/acetylene
Fe	248,3	air/acetylene
K	766,5	air/acetylene
Mg	285,2	N ₂ O/acetylene
Mn	279,5	air/acetylene
Na	589,0	air/acetylene
Ni	232,0	air/acetylene
Zn	213,9	air/acetylene
NOTE Use slit recommended by the manufacturer.		

Table 1 — Parameters for atomic flame absorption

4.6 Atomic absorbance measurement

- **4.6.1** Aspirate first the blank solution and then the calibration and test solutions consecutively and record the reading. Aspirate water between each solution. Make at least two measurements for each solution. Solids which build up at the burner slit shall be removed; otherwise they cause a decrease in sensitivity.
- **4.6.2** Prepare a calibration curve by plotting the obtained absorbance values of the calibration solutions corrected for the blank against the concentration.
- **4.6.3** Convert the absorbance values of the test solution corrected for the blank to milligrams of the element per litre by means of the calibration curve.

5 Expression of results

5.1 Calculation

The mass fraction of the element, expressed as a percentage, is given by the following formula:

$$\frac{c \cdot V}{10\ 000 \cdot m}$$

where

- c is the concentration, in milligrams per litre (mg/l), of the element in the test solution;
- V is the dilution volume, in millilitres (ml);
- m is the mass of the test portion, in grams (g).

5.2 Permissible tolerances

The deviations between three independent determinations shall not exceed the values in Table 2.

Table 2 — Lower and upper limits of mass fraction of the element as a percentage

Element	Lower limit	Upper limit
Calcium	0,000 5 % ± 50 % (CV)	0,010 0 % \pm 20 % (CV)
Copper	0,000 5 % \pm 50 % (CV)	0,010 0 % \pm 20 % (CV)
Iron	0,000 5 % \pm 50 % (CV)	0,015 0 % \pm 20 % (CV)
Potassium	0,000 5 % \pm 50 % (CV)	0,010 0 % \pm 20 % (CV)
Magnesium	0,000 5 % \pm 50 % (CV)	0,010 0 % \pm 20 % (CV)
Sodium	0,000 5 % \pm 50 % (CV)	0,005 0 % \pm 20 % (CV)
Nickel	0,000 5 % \pm 50 % (CV)	0,020 0 % \pm 20 % (CV)
Zinc	0,000 5 % ± 100 % (CV)	0,010 0 % \pm 10 % (CV)
CV: coefficient of variation (see ISO 3534-1:2006, 2.38)		

5.3 Final result

Report the arithmetic mean of acceptable determinations, rounded to a mass fraction of 0,001 % and a mass fraction of 0,002 %.

6 Test report

The test report shall include the following information:

- a) a reference to this International Standard;
- b) all details necessary for identification of the test sample;
- c) the results obtained;
- d) all operations not specified in this International Standard, or regarded as optional;
- e) details of any occurrence which may have affected the result.

Bibliography

- [1] ISO 5725-1, Accuracy (trueness and precision) of measurement methods and results— Part 1: General principles and definitions
- [2] ISO 5725-2, Accuracy (trueness and precision) of measurement methods and results Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method
- [3] ISO 5725-3, Accuracy (trueness and precision) of measurement methods and results Part 3: Intermediate measures of the precision of a standard measurement method
- [4] SO 5725-4, Accuracy (trueness and precision) of measurement methods and results Part 4: Basic methods for the determination of the trueness of a standard measurement method
- [5] ISO 5725-5, Accuracy (trueness and precision) of measurement methods and results Part 5: Alternative methods for the determination of the precision of a standard measurement method
- [6] ISO 5725-6, Accuracy (trueness and precision) of measurement methods and results Part 6: Use in practice of accuracy values

British Standards Institution (BSI)

BSI is the independent national body responsible for preparing British Standards and other standards-related publications, information and services. It presents the UK view on standards in Europe and at the international level.

It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.

Tel: +44 (0)20 8996 9001 Fax: +44 (0)20 8996 7001

BSI offers Members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Tel: +44 (0)20 8996 7669 Fax: +44 (0)20 8996 7001 Email: plus@bsigroup.com

Buying standards

You may buy PDF and hard copy versions of standards directly using a credit card from the BSI Shop on the website **www.bsigroup.com/shop.** In addition all orders for BSI, international and foreign standards publications can be addressed to BSI Customer Services.

Tel: +44 (0)20 8996 9001 Fax: +44 (0)20 8996 7001 Email: orders@bsigroup.com

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Knowledge Centre.

Tel: +44 (0)20 8996 7004 Fax: +44 (0)20 8996 7005 Email: knowledgecentre@bsigroup.com

Various BSI electronic information services are also available which give details on all its products and services.

Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048 Email: info@bsigroup.com

BSI Subscribing Members are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration

Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001 Email: membership@bsigroup.com

Information regarding online access to British Standards via British Standards Online can be found at **www.bsigroup.com/BSOL**

Further information about BSI is available on the BSI website at **www.bsi-group.com/standards**

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. This does not preclude the free use, in the course of implementing the standard of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained. Details and advice can be obtained from the Copyright & Licensing Manager.

Tel: +44 (0)20 8996 7070 Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Tel +44 (0)20 8996 9001 Fax +44 (0)20 8996 7001 www.bsigroup.com/standards

