

# **Thermoplastics pipes for the conveyance of fluids — Dimensions and tolerances**

## **Part 1. Metric series**

ICS 23.040.20

**NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW**

---



## National foreword

This British Standard reproduces verbatim ISO 11922-1 : 1997 and implements it as the UK national standard.

This British Standard, together with BS 2782 : Part 11 : Method 1121B (identical to ISO 161-1) and BS ISO 4065, partially supersedes BS 5556 : 1978, which becomes obsolescent and retained only to support existing British Standards.

The UK participation in its preparation was entrusted to Technical Committee PRI/61, Plastics piping systems and components, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

### Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled 'International Standards Correspondence Index', or using the 'Find' facility of the BSI Standards Electronic Catalogue.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

### Summary of pages

This document comprises a front cover, an inside front cover, the ISO title page, pages ii and iii, a blank page, pages 1 to 13 and a back cover.

This British Standard, having been prepared under the direction of the Sector Board for Materials and Chemicals, was published under the authority of the Standards Board and comes into effect on 15 June 1997

© BSI 1997

### Amendments issued since publication

Amd. No.	Date	Text affected

ISBN 0 580 27767 4

INTERNATIONAL  
STANDARD

ISO  
11922-1

First edition  
1997-04-15

---

**Thermoplastics pipes for the conveyance  
of fluids — Dimensions and tolerances —**

**Part 1:**  
Metric series

*Tubes en matières thermoplastiques pour le transport des fluides —  
Dimensions et tolérances —*

*Partie 1: Série métrique*



Reference number  
ISO 11922-1:1997(E)



**BS ISO 11922-1 : 1997****Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 11922-1 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*.

Together with ISO 11922-2, it cancels and replaces ISO 3606:1976, ISO 3607:1977, ISO 3608:1976 and ISO 3609:1977.

ISO 11922 consists of the following parts, under the general title *Thermoplastics pipes for the conveyance of fluids — Dimensions and tolerances*:

- *Part 1: Metric series*
- *Part 2: Inch-based series*

Annex A of this part of ISO 11922 is for information only.

**Descriptors:** fluid pipelines, pipes (tubes), thermoplastic resins, plastic tubes, form specifications, dimensions, diameters, thickness, dimensional tolerances, form tolerances, metric system.

## Introduction

In the past, International Standards specifying the tolerances to be applied to thermoplastics pipes have covered individual materials separately. The philosophy of ISO 11922 is to combine these already published standards into a single two-part standard covering the tolerances for extruded pipes manufactured from all thermoplastics materials, thus avoiding the need for a standard to be developed for each individual material.

ISO 11922 therefore contains a number of tolerance grades covering the mean outside diameter, the out-of-roundness of the outside diameter, the wall thickness at any point and the mean wall thickness. The bodies responsible for writing the various product and system standards will choose, from the specified tolerance grades, that grade which is suitable for the application and material involved.



\* 5 \*

# Thermoplastics pipes for the conveyance of fluids — Dimensions and tolerances —

## Part 1: Metric series

### 1 Scope

This part of ISO 11922 specifies tolerance grades for the outside diameter, out-of-roundness and wall thickness of metric thermoplastics pipes for the conveyance of fluids and manufactured with nominal outside diameters and nominal pressures in accordance with ISO 161-1<sup>[1]</sup> and nominal wall thicknesses in accordance with ISO 4065<sup>[3]</sup> (see annex A).

It is applicable to smooth thermoplastics pipes of constant circular cross-section along the whole length of the pipe, whatever the method of manufacture, the pipe material or the intended application.

NOTE — It is intended that the tolerance grades specified in product standards be selected from this part of ISO 11922, taking into account the material and the intended application.

### 2 Normative reference

The following standard contains provisions which, through reference in this text, constitute provisions of this part of ISO 11922. At the time of publication, the edition indicated was valid. All standards are subject to revision, and parties to agreements based on this part of ISO 11922 are encouraged to investigate the possibility of applying the most recent editions of the standard indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 3126:1974, *Plastics pipes — Measurement of dimensions*.

### 3 Definitions

For the purposes of this part of ISO 11922, the following definitions apply.

**3.1 nominal outside diameter,  $d_n$ :** A numerical designation of size which is common to all components in a thermoplastics piping system other than flanges and components designated by thread size. It is a convenient round number for reference purposes.

NOTE — For metric pipes conforming to ISO 161-1, the nominal outside diameter, expressed in millimetres, is the minimum mean outside diameter  $d_{em,min}$  specified in the applicable pipe standard.

## BS ISO 11922-1 : 1997

### 3.2 Outside diameter, $d_e$

**3.2.1 mean outside diameter,  $d_{em}$ :** The measured length of the outer circumference of the pipe divided by  $\pi$ <sup>1)</sup>, rounded up to the nearest 0,1 mm.

**3.2.2 minimum mean outside diameter,  $d_{em,min}$ :** The minimum value of the mean outside diameter specified in the applicable pipe standard. It is equal to the nominal outside diameter  $d_n$ , expressed in millimetres.

**3.2.3 maximum mean outside diameter,  $d_{em,max}$ :** The maximum value of the mean outside diameter specified in the applicable pipe standard.

**3.2.4 outside diameter at any point,  $d_{ey}$ :** The measured outside diameter through the cross-section at any point of the pipe, rounded up to the nearest 0,1 mm.

**3.2.5 out-of-roundness:** The difference between the measured maximum outside diameter and the measured minimum outside diameter in the same cross-sectional plane of the pipe.

### 3.3 Terms relating to tolerances<sup>2)</sup>

**3.3.1 tolerance:** The permissible variation of the specified value of a quantity, expressed as the difference between permissible maximum and minimum values.

**3.3.2 permissible deviation:** The difference between a permissible limiting value and a reference value.

**3.3.3 tolerance grade:** In a standardized system of limits and fits, a group of tolerances considered as corresponding to the same level of accuracy for all basic sizes.

### 3.4 Wall thickness, $e$

**3.4.1 wall thickness at any point,  $e_y$ :** The measured wall thickness at any point around the circumference of the pipe, rounded up to the nearest 0,1 mm.

**3.4.2 minimum wall thickness,  $e_{y,min}$ :** The minimum wall thickness for the pipe specified in the applicable pipe standard.

**3.4.3 maximum wall thickness,  $e_{y,max}$ :** The maximum wall thickness for the pipe specified in the applicable pipe standard.

**3.4.4 mean wall thickness,  $e_m$ :** The arithmetic mean of at least four measurements regularly spaced around the same cross-sectional plane of the pipe, including the measured minimum and maximum values obtained, rounded up to the nearest 0,1 mm.

NOTE — The minimum number of measurements will be specified in the applicable pipe standard. The actual number of measurements will then depend on the fact that the measurement points have to be regularly spaced round the cross-sectional plane and, in addition, have to include both the minimum and the maximum measured values.

**3.4.5 nominal wall thickness,  $e_n$ :** The wall thickness, in millimetres, tabulated in ISO 4065, corresponding to the minimum wall thickness at any point  $e_{y,min}$ .

1) The value for  $\pi$  is taken to be 3,142.

2) These definitions are consistent with ISO 286-1<sup>2)</sup>.

## 4 Tolerances on outside diameters

### 4.1 Mean outside diameter

For pipes conforming to ISO 161-1, the values specified therein as nominal outside diameters are minimum mean outside diameters, expressed in millimetres, and the permissible deviations from these diameters shall be positive. Hence the tolerances shall be expressed in the form  $^{+x}_0$  mm, where  $x$  is the value of the tolerance from table 1 appropriate to the tolerance grade.

The values in table 1 are based on the  $d_n$  specified in the applicable product standard, all dimensions being expressed in millimetres.

**Grade A:** For all nominal outside diameters, the tolerance equals  $0,009d_n$ , rounded up to the nearest 0,1 mm, with a minimum value of 0,3 mm and a maximum value of 10,0 mm.

**Grade B:** For all nominal outside diameters, the tolerance equals  $0,006d_n$ , rounded up to the nearest 0,1 mm, with a minimum value of 0,3 mm and a maximum value of 4,0 mm.

**Grade C:** For all nominal outside diameters, the tolerance equals  $0,003d_n$ , rounded up to the nearest 0,1 mm, with a minimum value of 0,3 mm and a maximum value of 2,0 mm.

**Grade D:** For nominal outside diameters from 10 to 1 000, the tolerances have been based on practical experience where tighter tolerances than those specified for grade C are required.

**Grade E:** Practical experience and test data have demonstrated that, for certain types of joint for which grade B tolerances may generally be applicable, e.g. socket fusion joints in PE pipe systems, the calculated tolerances for nominal outside diameters of 110, 125 and 140 are too great and may lead to premature joint failure. Therefore, for such applications, grade E tolerances have been established.

### 4.2 Out-of-roundness of outside diameter

Four tolerance grades are given in table 2. The tolerance values for each grade are calculated from the nominal outside diameter  $d_n$  specified in the applicable product standard, all diameters being expressed in millimetres. The calculation factors used are based on practical experience. Grade K is recommended for coiled pipe, subject to an appropriate relaxation treatment being specified in the product standard.

**Grade K:** The tolerance equals  $0,06d_n$ , rounded up to the nearest 0,1 mm, with a minimum value of 1,0 mm, and is applicable to nominal outside diameters  $\leq 160$  only.

**Grade L:** The tolerance equals  $0,05d_n$ , rounded up to the nearest 0,1 mm, with a minimum value of 1,0 mm.

**Grade M:** The tolerance equals  $0,024d_n$ , rounded up to the nearest 0,1 mm, with a minimum value of 1,0 mm.

**Grade N:**

- a) For nominal outside diameters  $\leq 75$ , the tolerance equals  $(0,008d_n + 1)$  mm, rounded up to the nearest 0,1 mm, with a minimum value of 1,2 mm.
- b) For nominal outside diameters  $> 75$  but  $\leq 250$ , the tolerance equals  $0,02d_n$ , rounded up to the nearest 0,1 mm.
- c) For nominal outside diameters  $> 250$ , the tolerance equals  $0,035d_n$ , rounded up to the nearest 0,1 mm.

**NOTE** — The applicable pipe standard will specify the point in time at which the out-of-roundness is to be measured, e.g. at the time of extrusion, the time the product leaves the factory or the time of use.



BS ISO 11922-1 : 1997

Table 1 — Tolerances on mean outside diameters — Metric series

Tolerances in millimetres

Nominal outside diameter $d_n$	Tolerances (+x)				
	Grade A	Grade B	Grade C	Grade D	Grade E
10	0,3	0,3	0,3	0,2	—
12	0,3	0,3	0,3	0,2	—
16	0,3	0,3	0,3	0,2	—
20	0,3	0,3	0,3	0,2	—
25	0,3	0,3	0,3	0,2	—
32	0,3	0,3	0,3	0,2	—
40	0,4	0,3	0,3	0,2	—
50	0,5	0,3	0,3	0,2	—
63	0,6	0,4	0,3	0,2	—
75	0,7	0,5	0,3	0,2	—
90	0,9	0,6	0,3	0,3	—
110	1,0	0,7	0,4	0,3	0,6
125	1,2	0,8	0,4	0,3	0,6
140	1,3	0,9	0,5	0,4	0,8
160	1,5	1,0	0,5	0,4	—
180	1,7	1,1	0,6	0,5	—
200	1,8	1,2	0,6	0,5	—
225	2,1	1,4	0,7	0,5	—
250	2,3	1,5	0,8	0,6	—
280	2,6	1,7	0,9	0,6	—
315	2,9	1,9	1,0	0,6	—
355	3,2	2,2	1,1	0,7	—
400	3,6	2,4	1,2	0,7	—
450	4,1	2,7	1,4	0,8	—
500	4,5	3,0	1,5	0,9	—
560	5,0	3,4	1,7	1,0	—
630	5,7	3,8	1,9	1,1	—
710	6,4	4,0	2,0	1,2	—
800	7,2	4,0	2,0	1,3	—
900	8,1	4,0	2,0	1,5	—
1 000	9,0	4,0	2,0	1,6	—
1 200	10,0	—	—	—	—
1 400	10,0	—	—	—	—
1 600	10,0	—	—	—	—
1 800	10,0	—	—	—	—
2 000	10,0	—	—	—	—

Table 2 — Tolerances on out-of-roundness — Metric series

Tolerances in millimetres

Nominal outside diameter $d_n$	Tolerances			
	Grade K	Grade L	Grade M	Grade N
10	1,0	1,0	1,0	1,2
12	1,0	1,0	1,0	1,2
16	1,0	1,0	1,0	1,2
20	1,2	1,0	1,0	1,2
25	1,5	1,3	1,0	1,2
32	2,0	1,6	1,0	1,3
40	2,4	2,0	1,0	1,4
50	3,0	2,5	1,2	1,4
63	3,8	3,2	1,6	1,5
75	4,5	3,8	1,8	1,6
90	5,4	4,5	2,2	1,8
110	6,6	5,5	2,7	2,2
125	7,5	6,3	3,0	2,5
140	8,4	7,0	3,4	2,8
160	9,6	8,0	3,9	3,2
180	—	9,0	4,4	3,6
200	—	10,0	4,8	4,0
225	—	11,3	5,4	4,5
250	—	12,5	6,0	5,0
280	—	14,0	6,8	9,8
315	—	15,8	7,6	11,1
355	—	17,8	8,6	12,5
400	—	20,0	9,6	14,0
450	—	22,5	10,8	15,6
500	—	25,0	12,0	17,5
560	—	28,0	13,5	19,6
630	—	31,2	15,2	22,1
710	—	35,5	17,1	24,9
800	—	40,0	19,2	28,0
900	—	45,0	21,6	31,5
1 000	—	—	24,0	35,0
1 200	—	—	28,8	42,0
1 400	—	—	33,6	49,0
1 600	—	—	38,4	56,0
1 800	—	—	43,2	63,0
2 000	—	—	48,0	70,0

\*S\*

## BS ISO 11922-1 : 1997

### 5 Tolerances on wall thickness

#### 5.1 Wall thickness at any point $e_y$

Three tolerance grades are given in tables 3, 4 and 5 which cover minimum wall thicknesses  $e_{y,\min}$  up to 50 mm (tables 3 and 4) and 46 mm (table 5). The tolerance grade may be specified in product standards.

The tolerance values in tables 3, 4 and 5 are calculated from the relationships given below, where all values are expressed in millimetres, the relationships being based on practical experience of the extrusion of thermoplastics pipes of wall thickness up to 50 mm. The tolerance values specified in table 5 are normally used for pipes which are to be connected by mechanical fittings where it is necessary to have a tight tolerance on the wall thickness to allow compression of the pipe material without the need for extra sealing rings.

**Grade T** (see table 3):

- a) For  $e_{y,\min} \leq 4,6$ , the tolerance equals  $(0,1e_{y,\min} + 0,2)$  mm, rounded up to the nearest 0,1 mm.
- b) For  $e_{y,\min} > 4,6$ , the tolerance equals  $0,15e_{y,\min}$ , rounded up to the nearest 0,1 mm.

**Grade U** (see table 4): For  $e_{y,\min} > 3,5$ , the tolerance equals  $0,2e_{y,\min}$ , rounded up to the nearest 0,1 mm.

**Grade V** (see table 5): For  $e_{y,\min} \leq 46$ , the tolerance equals  $(0,1e_{y,\min} + 0,1)$  mm, rounded up to the nearest 0,1 mm.

The tolerances obtained for  $e_{y,\min}$  are used to determine  $e_{y,\max}$  from the following equation:

$$e_{y,\max} = (e_{y,\min} + t_y)$$

where  $t_y$  is the tolerance for the grade and minimum wall thickness concerned.

The limits for  $e_y$  shall be expressed as a positive permissible deviation relative to  $e_{y,\min}$ , viz:

$$e_y = e_{y,\min} \begin{matrix} +t_y \\ 0 \end{matrix}$$

**Table 3 — Tolerances on wall thickness at any point — Grade T**

Dimensions in millimetres

Minimum wall thickness		Grade T tolerance $t_y$	Minimum wall thickness		Grade T tolerance $t_y$
$e_{y,min}$			$e_{y,min}$		
>	≤		>	≤	
—	1,0	0,3	25,3	26,0	3,9
1,0	2,0	0,4	26,0	26,6	4,0
2,0	3,0	0,5	26,6	27,3	4,1
3,0	4,0	0,6	27,3	28,0	4,2
4,0	4,6	0,7	28,0	28,6	4,3
4,6	5,3	0,8	28,6	29,3	4,4
5,3	6,0	0,9	29,3	30,0	4,5
6,0	6,6	1,0	30,0	30,6	4,6
6,6	7,3	1,1	30,6	31,3	4,7
7,3	8,0	1,2	31,3	32,0	4,8
8,0	8,6	1,3	32,0	32,6	4,9
8,6	9,3	1,4	32,6	33,3	5,0
9,3	10,0	1,5	33,3	34,0	5,1
10,0	10,6	1,6	34,0	34,6	5,2
10,6	11,3	1,7	34,6	35,3	5,3
11,3	12,0	1,8	35,3	36,0	5,4
12,0	12,6	1,9	36,0	36,6	5,5
12,6	13,3	2,0	36,6	37,3	5,6
13,3	14,0	2,1	37,3	38,0	5,7
14,0	14,6	2,2	38,0	38,6	5,8
14,6	15,3	2,3	38,6	39,3	5,9
15,3	16,0	2,4	39,3	40,0	6,0
16,0	16,6	2,5	40,0	40,6	6,1
16,6	17,3	2,6	40,6	41,3	6,2
17,3	18,0	2,7	41,3	42,0	6,3
18,0	18,6	2,8	42,0	42,6	6,4
18,6	19,3	2,9	42,6	43,3	6,5
19,3	20,0	3,0	43,3	44,0	6,6
20,0	20,6	3,1	44,0	44,6	6,7
20,6	21,3	3,2	44,6	45,3	6,8
21,3	22,0	3,3	45,3	46,0	6,9
22,0	22,6	3,4	46,0	46,6	7,0
22,6	23,3	3,5	46,6	47,3	7,1
23,3	24,0	3,6	47,3	48,0	7,2
24,0	24,6	3,7	48,0	48,6	7,3
24,6	25,3	3,8	48,6	49,3	7,4
			49,3	50,0	7,5

\* 5 \*

**Table 4 — Tolerances on wall thickness at any point — Grade U**

Dimensions in millimetres

Minimum wall thickness		Grade U tolerance $t_y$	Minimum wall thickness		Grade U tolerance $t_y$	Minimum wall thickness		Grade U tolerance $t_y$
$e_{y,min}$	$e_{y,min}$		$e_{y,min}$	$e_{y,min}$		$e_{y,min}$	$e_{y,min}$	
>	≤		>	≤		>	≤	
3,5	4,0	0,7	19,5	20,0	3,9	35,5	36,0	7,1
4,0	4,5	0,8	20,0	20,5	4,0	36,0	36,5	7,2
4,5	5,0	0,9	20,5	21,0	4,1	36,5	37,0	7,3
5,0	5,5	1,0	21,0	21,5	4,2	37,0	37,5	7,4
5,5	6,0	1,1	21,5	22,0	4,3	37,5	38,0	7,5
6,0	6,5	1,2	22,0	22,5	4,4	38,0	38,5	7,6
6,5	7,0	1,3	22,5	23,0	4,5	38,5	39,0	7,7
7,0	7,5	1,4	23,0	23,5	4,6	39,0	39,5	7,8
7,5	8,0	1,5	23,5	24,0	4,7	39,5	40,0	7,9
8,0	8,5	1,6	24,0	24,5	4,8	40,0	40,5	8,0
8,5	9,0	1,7	24,5	25,0	4,9	40,5	41,0	8,1
9,0	9,5	1,8	25,0	25,5	5,0	41,0	41,5	8,2
9,5	10,0	1,9	25,5	26,0	5,1	41,5	42,0	8,3
10,0	10,5	2,0	26,0	26,5	5,2	42,0	42,5	8,4
10,5	11,0	2,1	26,5	27,0	5,3	42,5	43,0	8,5
11,0	11,5	2,2	27,0	27,5	5,4	43,0	43,5	8,6
11,5	12,0	2,3	27,5	28,0	5,5	43,5	44,0	8,7
12,0	12,5	2,4	28,0	28,5	5,6	44,0	44,5	8,8
12,5	13,0	2,5	28,5	29,0	5,7	44,5	45,0	8,9
13,0	13,5	2,6	29,0	29,5	5,8	45,0	45,5	9,0
13,5	14,0	2,7	29,5	30,0	5,9	45,5	46,0	9,1
14,0	14,5	2,8	30,0	30,5	6,0	46,0	46,5	9,2
14,5	15,0	2,9	30,5	31,0	6,1	46,5	47,0	9,3
15,0	15,5	3,0	31,0	31,5	6,2	47,0	47,5	9,4
15,5	16,0	3,1	31,5	32,0	6,3	47,5	48,0	9,5
16,0	16,5	3,2	32,0	32,5	6,4	48,0	48,5	9,6
16,5	17,0	3,3	32,5	33,0	6,5	48,5	49,0	9,7
17,0	17,5	3,4	33,0	33,5	6,6	49,0	49,5	9,8
17,5	18,0	3,5	33,5	34,0	6,7	49,5	50,0	9,9
18,0	18,5	3,6	34,0	34,5	6,8			
18,5	19,0	3,7	34,5	35,0	6,9			
19,0	19,5	3,8	35,0	35,5	7,0			

**Table 5 — Tolerances on wall thickness at any point — Grade V**

Dimensions in millimetres

Minimum wall thickness		Grade V tolerance $t_y$	Minimum wall thickness		Grade V tolerance $t_y$
$e_{y,min}$	$e_{y,min}$		$e_{y,min}$	$e_{y,min}$	
>	≤		>	≤	
—	1,0	0,2	23,0	24,0	2,5
1,0	2,0	0,3	24,0	25,0	2,6
2,0	3,0	0,4	25,0	26,0	2,7
3,0	4,0	0,5	26,0	27,0	2,8
4,0	5,0	0,6	27,0	28,0	2,9
5,0	6,0	0,7	28,0	29,0	3,0
6,0	7,0	0,8	29,0	30,0	3,1
7,0	8,0	0,9	30,0	31,0	3,2
8,0	9,0	1,0	31,0	32,0	3,3
9,0	10,0	1,1	32,0	33,0	3,4
10,0	11,0	1,2	33,0	34,0	3,5
11,0	12,0	1,3	34,0	35,0	3,6
12,0	13,0	1,4	35,0	36,0	3,7
13,0	14,0	1,5	36,0	37,0	3,8
14,0	15,0	1,6	37,0	38,0	3,9
15,0	16,0	1,7	38,0	39,0	4,0
16,0	17,0	1,8	39,0	40,0	4,1
17,0	18,0	1,9	40,0	41,0	4,2
18,0	19,0	2,0	41,0	42,0	4,3
19,0	20,0	2,1	42,0	43,0	4,4
20,0	21,0	2,2	43,0	44,0	4,5
21,0	22,0	2,3	44,0	45,0	4,6
22,0	23,0	2,4	45,0	46,0	4,7



**BS ISO 11922-1 : 1997****5.2 Mean wall thickness  $e_m$** 

Two tolerance grades are given in tables 6 and 7 which cover minimum wall thicknesses  $e_{y,\min}$  up to 50 mm. The tolerance grade may be specified in product standards.

The tolerance values in tables 6 and 7 are calculated from the following relationships, where all values are expressed in millimetres, the relationships being based on practical experience of the extrusion of thermoplastics pipes of wall thickness up to 50 mm.

**Grade W** (see table 6): For all minimum wall thicknesses up to 50 mm, the tolerance equals  $(0,1e_{y,\min} + 0,2)$  mm, rounded up to the nearest 0,1 mm.

**Grade X** (see table 7): For minimum wall thicknesses greater than 16 mm, the tolerance equals  $(0,15e_{y,\min} + 0,2)$  mm, rounded up to the nearest 0,1 mm.

For a cylindrical pipe, the minimum value of  $e_m$  equals the value of  $e_{y,\min}$ , and the tolerance obtained thus determines the positive permissible deviation of  $e_m$  from  $e_{y,\min}$ .

The limits for  $e_m$  shall therefore be expressed as:

$$e_m = e_{y,\min} \begin{matrix} +t_m \\ 0 \end{matrix}$$

where

$e_{y,\min}$  is as specified in the applicable pipe standard, in millimetres;

$t_m$  is the tolerance value from table 6 or 7, as applicable, in millimetres.

**6 Measurement of dimensions**

All measurements of outside diameter and wall thickness shall be made in accordance with the method specified in the applicable pipe standard, or in accordance with ISO 3126.

**Table 6 — Tolerances on mean wall thickness — Grade W**

Dimensions in millimetres

Minimum wall thickness		Grade W tolerance $t_m$	Minimum wall thickness		Grade W tolerance $t_m$
$e_{y,min}$			$e_{y,min}$		
>	≤		>	≤	
—	1,0	0,3	25,0	26,0	2,8
1,0	2,0	0,4	26,0	27,0	2,9
2,0	3,0	0,5	27,0	28,0	3,0
3,0	4,0	0,6	28,0	29,0	3,1
4,0	5,0	0,7	29,0	30,0	3,2
5,0	6,0	0,8	30,0	31,0	3,3
6,0	7,0	0,9	31,0	32,0	3,4
7,0	8,0	1,0	32,0	33,0	3,5
8,0	9,0	1,1	33,0	34,0	3,6
9,0	10,0	1,2	34,0	35,0	3,7
10,0	11,0	1,3	35,0	36,0	3,8
11,0	12,0	1,4	36,0	37,0	3,9
12,0	13,0	1,5	37,0	38,0	4,0
13,0	14,0	1,6	38,0	39,0	4,1
14,0	15,0	1,7	39,0	40,0	4,2
15,0	16,0	1,8	40,0	41,0	4,3
16,0	17,0	1,9	41,0	42,0	4,4
17,0	18,0	2,0	42,0	43,0	4,5
18,0	19,0	2,1	43,0	44,0	4,6
19,0	20,0	2,2	44,0	45,0	4,7
20,0	21,0	2,3	45,0	46,0	4,8
21,0	22,0	2,4	46,0	47,0	4,9
22,0	23,0	2,5	47,0	48,0	5,0
23,0	24,0	2,6	48,0	49,0	5,1
24,0	25,0	2,7	49,0	50,0	5,2

\*S\*



BS ISO 11922-1 : 1997

**Table 7 — Tolerances on mean wall thickness — Grade X**

Dimensions in millimetres

Minimum wall thickness		Grade X tolerance $t_m$	Minimum wall thickness		Grade X tolerance $t_m$
$e_{y,min} >$	$e_{y,min} \leq$		$e_{y,min} >$	$e_{y,min} \leq$	
16,0	16,7	2,7	32,7	33,3	5,2
16,7	17,3	2,8	33,3	34,0	5,3
17,3	18,0	2,9	34,0	34,7	5,4
18,0	18,7	3,0	34,7	35,3	5,5
18,7	19,3	3,1	35,3	36,0	5,6
19,3	20,0	3,2	36,0	36,7	5,7
20,0	20,7	3,3	36,7	37,3	5,8
20,7	21,3	3,4	37,3	38,0	5,9
21,3	22,0	3,5	38,0	38,7	6,0
22,0	22,7	3,6	38,7	39,3	6,1
22,7	23,3	3,7	39,3	40,0	6,2
23,3	24,0	3,8	40,0	40,7	6,3
24,0	24,7	3,9	40,7	41,3	6,4
24,7	25,3	4,0	41,3	42,0	6,5
25,3	26,0	4,1	42,0	42,7	6,6
26,0	26,7	4,2	42,7	43,3	6,7
26,7	27,3	4,3	43,3	44,0	6,8
27,3	28,0	4,4	44,0	44,7	6,9
28,0	28,7	4,5	44,7	45,3	7,0
28,7	29,3	4,6	45,3	46,0	7,1
29,3	30,0	4,7	46,0	46,7	7,2
30,0	30,7	4,8	46,7	47,3	7,3
30,7	31,3	4,9	47,3	48,0	7,4
31,3	32,0	5,0	48,0	48,7	7,5
32,0	32,7	5,1	48,7	49,3	7,6

**Annex A**  
(informative)

**Bibliography**

- [1] ISO 161-1:1996, *Thermoplastics pipes for the conveyance of fluids — Nominal outside diameters and nominal pressures — Part 1: Metric series.*
- [2] ISO 286-1:1988, *ISO system of limits and fits — Part 1: Bases of tolerances, deviations and fits.*
- [3] ISO 4065:1996, *Thermoplastics pipes — Universal wall thickness table.*



\* S \*

**BS ISO  
11922-1 : 1997**

---

**BSI — British Standards Institution**

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

**Contract requirements**

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

**Revisions**

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the responsible technical committee, the identity of which can be found on the inside front cover. Tel: 0181 996 9000; Fax: 0181 996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

**Buying standards**

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services, Sales Department at Chiswick: Tel: 0181 996 7000; Fax: 0181 996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

**Information on standards**

BSI provides a wide range of information on national, European and international standards through its Library, the Standardline Database, the BSI Information Technology Service (BITS) and its Technical Help to Exporters Service. Contact the Information Department at Chiswick: Tel: 0181 996 7111; Fax: 0181 996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Customer Services, Membership at Chiswick: Tel: 0181 996 7002; Fax: 0181 996 7001.

**Copyright**

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager, BSI, 389 Chiswick High Road, London W4 4AL.

BSI  
389 Chiswick High Road  
London  
W4 4AL