

BS EN ISO 11986:2010



BSI Standards Publication

# Ophthalmic optics — Contact lenses and contact lens care products — Determination of preservative uptake and release (ISO 11986:2010)

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of EN ISO 11986:2010. It supersedes BS EN ISO 11986:2001 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee CH/172/9, Contact lenses and contact lens care products.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2010

ISBN 978 0 580 65522 7

ICS 11.040.70

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 December 2010.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

English Version

**Ophthalmic optics - Contact lenses and contact lens care  
products - Determination of preservative uptake and release  
(ISO 11986:2010)**

Optique ophtalmique - Lentilles de contact et produits  
d'entretien pour lentilles de contact - Détermination de  
l'absorption/adsorption et du relargage des conservateurs  
(ISO 11986:2010)

Augenoptik - Kontaktlinsen und Kontaktlinsenpflegemittel -  
Bestimmung der Aufnahme und Wiederfreisetzung von  
Konservierungsmitteln (ISO 11986:2010)

This European Standard was approved by CEN on 31 October 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Foreword

This document (EN ISO 11986:2010) has been prepared by Technical Committee ISO/TC 172 "Optics and photonics" in collaboration with Technical Committee CEN/TC 170 "Ophthalmic optics" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2011, and conflicting national standards shall be withdrawn at the latest by May 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 11986:2000.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

### Endorsement notice

The text of ISO 11986:2010 has been approved by CEN as a EN ISO 11986:2010 without any modification.

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 11986 was prepared by Technical Committee ISO/TC 172, *Optics and photonics*, Subcommittee SC 7, *Ophthalmic optics and instruments*.

This second edition cancels and replaces the first edition (ISO 11986:1999), which has been technically revised.

## Introduction

Contact lens care products are a complex mixture of organic and inorganic substances. For reasons of microbiological safety, contact lens disinfecting solutions, as well as care products in multi-use containers, contain substances with antimicrobial activity. From many years of experience in contact lens wear, it is known that irritation and sensitization problems sometimes occur due to these preservatives being absorbed and released by the matrix of the contact lens. For these reasons, it is necessary to be able to estimate the extent of preservative uptake and release by contact lenses.

The preservative uptake and release test provides a general method for measuring the uptake of preservatives in solution by contact lenses and the release of preservatives from contact lenses in an aqueous medium. The analytical method to be used for quantification of specific preservatives is not indicated here. Chemical characteristics of the preservative, as well as concentration in the contact lens care product and degree of uptake by the contact lens, must be taken into consideration in selecting an appropriate analytical method. Contact lens uptake and release data may be useful in characterizing the potential for a new or modified contact lens material to produce a toxic or irritating reaction in the eye from the uptake and binding or release of preservatives from currently marketed contact lens care products.

# Ophthalmic optics — Contact lenses and contact lens care products — Determination of preservative uptake and release

## 1 Scope

This International Standard provides general procedures for the selection of methods, preparation of samples, and conduct of testing for the uptake and release of preservatives from contact lenses.

NOTE 1 Due to the manifest difficulties of reproducibility when coating contact lenses with mineral and organic deposits encountered during lens wear, these methods are only applicable to new and unused contact lenses.

NOTE 2 Preservative depletion by a contact lens in the limited volume of a lens case could compromise disinfection performance. This International Standard does not measure disinfection performance.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 18369-3:2006, *Ophthalmic optics — Contact lenses — Part 3: Measurement methods*

## 3 Principle

The contact lenses to be tested are immersed in the test product at  $25\text{ °C} \pm 2\text{ °C}$  and the preservative content analysed at regular intervals of time until a steady-state condition has been achieved.

After reaching the steady-state condition, each contact lens is immersed in 1 ml of saline solution for contact lens testing, the saline solution prepared in accordance with ISO 18369-3:2006, 4.7, at  $37\text{ °C} \pm 2\text{ °C}$ . At discrete intervals up to and including 16 h, and at intervals until no additional release is observed, if required, the solution is analysed for the amount of preservative that has been extracted at each time point.

## 4 Procedure

### 4.1 General

The following information shall be obtained before commencing the estimation:

- a) evidence that the selected test method is suitable for the detection and estimation of the particular preservative;

NOTE 1 Examples of methods suitable for analysing some preservatives are presented in US FDA guidelines (see Reference [2]).

- b) evidence that the test method has the required repeatability and reproducibility, and a detection limit suitable for the assay;

- c) the number of determinations required to satisfy b);

NOTE 2 Multiple determinations might be necessary when the analysis result is close to the limit of detection and/or when the analysis method has a low precision.

- d) the criteria needed to confirm that equilibrium has been achieved in the extraction process;
- e) the amount of test solution taken will need to ensure that the quantity of absorbed preservative does not reduce the concentration of the preservative in the test solution to less than 25 % of the initial preservative concentration in the test solution;
- f) a sufficient number of contact lenses of each material type shall be used to ensure that the quantity of absorbed and released preservative is higher than the detection limit of the method of analysis, and also ensure that enough lenses are available for preservative release measurement at each time point.

## 4.2 Uptake of preservatives from test product

**4.2.1** Select the appropriate contact lens care product and/or the appropriate contact lens material for testing.

**4.2.1.1** To determine the preservative uptake of a new or modified contact lens material, select the appropriate contact lens care product based on the intended use of the contact lens care product (e.g. recommended for use with hydrogel contact lenses, or rigid gas-permeable contact lenses).

**4.2.1.2** To determine the uptake of a new or modified preservative in the contact lens care product, select the appropriate contact lens materials for testing from currently marketed contact lenses based on the intended use of the contact lens care product (e.g. recommended for use with hydrogel contact lenses, or rigid gas-permeable contact lenses).

The selection of test lenses and lens care products should be justified. For hydrogel lenses, representatives from low water and medium/high water ionic and non-ionic lens groups and from silicone hydrogel lenses should be included. For rigid lenses, representative lenses from silicone, fluorine and silicon-fluorine lens groups should be included (see ISO 18369-1).

**4.2.2** Determine the initial preservative level in the test solution.

**4.2.3** Record the volume of soak solution and immerse the test lenses in the test solution in a suitable closed container (see the following paragraph) at  $25\text{ °C} \pm 2\text{ °C}$ , and shake occasionally (to ensure adequate mixing of the solution surrounding the contact lens during the study). Take aliquot portions of the test solution at different time intervals and analyse each for its preservative content. During day 1, take aliquot portions at the proposed regimen time, at 8 h and at 24 h. Continue the procedure at intervals of not less than 24 h until the aliquot portions show that no more preservative has been absorbed, or the maximum recommended storage time for the lenses in the contact lens care products has been reached. Additional time points during the first day may be included to determine the uptake profile.

It is preferable to use containers that have been demonstrated to absorb insignificant amounts of the preservative. However, if the container does absorb the preservative, this should be allowed for when carrying out the test procedure. In this case, for example, an appropriate control solution should also be monitored to determine the amount of preservative absorbed by the container.

NOTE 1 Alternatively, the amount of preservative taken up by the contact lens can be determined directly by methods that provide reproducible quantitative extraction from the contact lens, using a suitable solvent and measuring the amount of preservative found in the extraction solvent.

If the aliquot portions taken are large enough to significantly alter the ratio between the volume of the test solution and the mass of the test lenses, additional test lenses and containers should be used for each sampling interval.

NOTE 2 If the percentage of the preservative absorbed by the test lenses exceeds 75 % of the available preservative, it might be necessary to repeat the test with an increased ratio of the test solution volume to number/mass of test lenses.



### 4.3 Release of preservatives from test lenses

After reaching a steady-state condition (see 4.2.3), remove the test lenses from the test solution and remove any excess solution by gently touching each test lens with an absorbent tissue without using excessive force or contact time.

Immerse the test lenses in saline solution, prepared in accordance with ISO 18369-3:2006, 4.7, at a ratio of one lens per millilitre of saline solution, in a closed container. Leave the test lenses immersed at  $37\text{ °C} \pm 2\text{ °C}$  and shake occasionally.

Take aliquot portions of the solvent at different times and analyse each for its preservative content. Measure aliquot portions of the solvent at 1 h, 2 h, 4 h and 16 h and until no additional release (steady state) is observed.

**NOTE** If the aliquot portions taken are large enough to significantly alter the ratio between the test solution and the mass of the test lenses, use additional test lenses and containers for each sampling interval.

If 1 ml of saline solution (see ISO 18369-3:2006, 4.7) is not sufficient to immerse the test lens, then an additional minimal known quantity of saline solution may be added to ensure that the lens is fully immersed, and the volume is recorded. The total volume of saline solution must be used to calculate the concentration of preservative in the extracting saline solution.

## 5 Expression of results

**5.1** The quantity of preservative absorbed by the contact lenses at each measured time point shall be determined by either

- a) calculating the difference between the preservative content in the test solution before the contact lenses were immersed, and the concentration in the test solution after each time point or after reaching the equilibrium of the preservative uptake; or
- b) a direct measurement method of the quantitative amount of preservative taken up by the contact lens.

**5.2** If no preservative uptake is detected by direct measurement, the results shall be expressed as a preservative uptake that is less than the limit of detection of the test method. If no preservative uptake is detected by the difference method, the results shall be expressed as less than the limit of detection of the test method.

**5.3** The preservative uptake is calculated using each measured time point and plotted as the uptake of preservative versus time.

**5.4** The rate of preservative uptake,  $K_n$ , shall be expressed for each time point from the following equation:

$$K_n = \frac{U_n - U_{n-1}}{t_n - t_{n-1}}$$

where

$U_n$  is the quantity of preservative taken up at a time point;

$U_{n-1}$  is the quantity of preservative taken up at the previous time point;

$t_n$  is the time the lens has been immersed in the solution for measurement  $n$ ;

$t_{n-1}$  is the time the lens had been immersed in the solution in the previous measurement  $n-1$ .

Preservative release from the contact lenses shall be calculated from the concentration of the preservative found in the extracting solvent at each measured point and after reaching a steady state.

**5.5** The quantity of preservative released is calculated using each measured time point and plotted as the release of preservative versus time.

**5.6** The rate of preservative released,  $K'_n$ , at each time point shall be calculated using the following equation:

$$K'_n = \frac{R_n - R_{n-1}}{t_n - t_{n-1}}$$

where

$R_n$  is the quantity of preservative released at a time point;

$R_{n-1}$  is the quantity of preservative released at the previous time point;

$t_n$  is the time the lens has been immersed in the solution for measurement  $n$ ;

$t_{n-1}$  is the time the lens had been immersed in the solution in the previous measurement  $n-1$ .

**5.7** In the test report, preservative values shall be expressed as either

- a) micrograms of preservative per milligram of dry lens mass (for hydrogel contact lenses), or
- b) micrograms of preservative per lens, where the lens is a  $-3,00$  D lens with maximum supplied diameter for all lenses, or
- c) micrograms of preservative per square centimetre of lens surface of non-hydrogel contact lenses.

**5.8** The rates of uptake and release shall be expressed as either

- a) micrograms of preservative per unit time per lens, where the lens is a  $-3,00$  D lens with maximum supplied diameter, or
- b) micrograms of preservative per milligram of lens dry weight per unit time.

## 6 Test report

The test report shall include at least the following information:

- a) a reference to this International Standard, i.e. ISO 11986:2010;
- b) the identity of the contact lens used, including the lot numbers and the types of contact lens material (e.g. hydrogel material group or identification of a silicone hydrogel manufacturer);
- c) the identity of the preservative used, its concentration and the volume of test solution used per number of lenses in the lens care solution test;
- d) the identity of the selected solvent used for the extraction;
- e) the duration of soak time, the detection limit and the calibration curve for the analytical method;
- f) the date of the test;
- g) the results of the test, as specified in Clause 5.

## Bibliography

- [1] ISO 18369-1, *Ophthalmic optics — Contact lenses — Part 1: Vocabulary, classification system and recommendations for labelling specifications*
- [2] *The Guidance For Industry, Premarket Notification (510 (K))*, Guidance Document for Contact Lens Care Products, U.S. Department of Health and Human Service, Food and Drug Administration, Center for Devices and Radiological Health, Chem. — Appendix A. Preservative Uptake/Release Testing Procedures, May 1, 1997, pp. 82-85





# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™