

BS EN ISO 12625-4:2016



BSI Standards Publication

## Tissue paper and tissue products

Part 4: Determination of tensile strength, stretch at maximum force and tensile energy absorption (ISO 12625-4:2016)

**National foreword**

This British Standard is the UK implementation of EN ISO 12625-4:2016. It supersedes BS EN ISO 12625-4:2005 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PAI/11, Methods of test for paper, board and pulps.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2017.  
Published by BSI Standards Limited 2017

ISBN 978 0 580 90263 5

ICS 85.080.20

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2017.

**Amendments/corrigenda issued since publication**

Date	Text affected
------	---------------

---

English Version

**Tissue paper and tissue products - Part 4: Determination  
of tensile strength, stretch at maximum force and tensile  
energy absorption (ISO 12625-4:2016)**

Papier tissue et produits tissue - Partie 4:  
Détermination de la résistance à la rupture par  
traction, de l'allongement à la force maximale et de  
l'absorption d'énergie à la rupture par traction (ISO  
12625-4:2016)

Tissue-Papier und Tissue-Produkte - Teil 4:  
Bestimmung der breitenbezogenen Bruchkraft, der  
Dehnung bei maximaler Kraft und des  
Arbeitsaufnahmevermögens (ISO 12625-4:2016)

This European Standard was approved by CEN on 21 November 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

## **European foreword**

This document (EN ISO 12625-4:2016) has been prepared by Technical Committee ISO/TC 6 "Paper, board and pulps" in collaboration with Technical Committee CEN/TC 172 "Pulp, paper and board" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2017, and conflicting national standards shall be withdrawn at the latest by June 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 12625-4:2005.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

### **Endorsement notice**

The text of ISO 12625-4:2016 has been approved by CEN as EN ISO 12625-4:2016 without any modification.

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>2</b>
<b>5 Apparatus</b> .....	<b>2</b>
<b>6 Conditioning</b> .....	<b>3</b>
<b>7 Preparation of test pieces</b> .....	<b>3</b>
7.1 General.....	3
7.2 Dimensions.....	3
7.3 Number of test pieces.....	4
<b>8 Procedure</b> .....	<b>4</b>
<b>9 Calculation</b> .....	<b>4</b>
9.1 General.....	4
9.2 Tensile strength.....	4
9.3 Tensile index.....	5
9.4 Stretch at maximum force.....	5
9.5 Tensile energy absorption.....	5
9.6 Tensile energy absorption index.....	6
<b>10 Test report</b> .....	<b>6</b>
<b>Annex A (informative) Precision</b> .....	<b>7</b>
<b>Bibliography</b> .....	<b>9</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by the European Committee Standardization (CEN) Technical Committee CEN/TC 172, *Pulp, paper and board*, in collaboration with ISO Technical Committee TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 12625-4:2005), which has been technically revised with the following changes:

- a) “stretch at break” was replaced by “stretch at maximum force”;
- b) in [Clause 7](#), a more detailed description of the preparation of the test pieces was included;
- c) the number of test pieces required has been clarified with more detailed information;
- d) in [Clause 8](#), the procedure for the measurement was clarified;
- e) in [Clause 10](#), additional information is to be included in the test report;
- f) this document has been editorially updated.

A list of all parts in the ISO 12625 series can be found on the ISO website.

# Tissue paper and tissue products —

## Part 4:

# Determination of tensile strength, stretch at maximum force and tensile energy absorption

## 1 Scope

This document specifies a test method for the determination of the tensile strength, stretch at maximum force and tensile energy absorption of tissue paper and tissue products. It uses a tensile-testing apparatus operating with a constant rate of elongation.

It also specifies the method of calculating the tensile index and the tensile energy absorption index.

In cases where impurities and contraries have to be determined, ISO 15755<sup>[6]</sup> applies for these detections in tissue paper and tissue products.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 1924-2, *Paper and board — Determination of tensile properties — Part 2: Constant rate of elongation method (20 mm/min)*

ISO 7500-1, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 12625-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

### 3.1

#### **tensile strength**

maximum tensile force per unit width that a test piece will withstand before breaking in a tensile test

### 3.2

#### **tensile index**

*tensile strength* (3.1) divided by grammage

### 3.3

#### **stretch at maximum force**

ratio of the elongation of a test piece, over its initial length, at the moment when the maximum tensile force is reached during a tensile test

Note 1 to entry: Stretch at maximum force is expressed as a percentage of the initial length.

### 3.4

#### **tensile energy absorption**

##### **TEA**

amount of energy absorbed per unit surface area of a test piece while being stretched, until the onset of break (the moment of maximum tensile force) in a tensile test

[SOURCE: ISO 12625-1:2011, 4.59]

### 3.5

#### **tensile energy absorption index**

*tensile energy absorption* (3.5) divided by grammage

[SOURCE: ISO 1924-2:2008, 3.7]

## 4 Principle

A test piece of tissue paper or tissue product, of given dimensions, is stretched to break at a constant rate of elongation using a tensile-testing apparatus that measures and records the tensile force as a function of the elongation of the test piece.

From the recorded data, the tensile strength, the corresponding stretch at maximum force and the tensile energy absorption can be calculated.

The test can be carried out by a vertical or a horizontal tensile strength tester. Precision data are available in [Annex A](#).

## 5 Apparatus

### 5.1 Tensile-testing apparatus

#### 5.1.1 General

The tensile-testing apparatus shall be in accordance with ISO 1924-2. It is capable of stretching a test piece of tissue paper or tissue product of given dimensions, at a constant rate of elongation of  $(50 \pm 2)$  mm/min, and recording the tensile force as a function of elongation on a strip chart recorder or any equivalent device.

The elongation shall be recorded to an accuracy of  $\pm 0,1$  mm. The measurement of the elongation shall start at a tension of  $(5 \pm 1)$  N/m.

The force-measuring system shall measure loads with an accuracy of  $\pm 1$  % of the reading or  $\pm 0,1$  N, whichever is greater, and shall be calibrated and verified to conform to the requirements of ISO 7500-1.

#### 5.1.2 Means for measuring the area of the force-elongation curve

The tensile-testing apparatus shall provide a means for measuring the area between the force-elongation curve and the elongation axis to an accuracy of  $\pm 2$  % of the true value as determined by numerical integration of the raw data.

NOTE Most modern tensile testers are equipped with an electronic or electro-mechanical integrator that can be used for this purpose. The area can also be determined from a graphical output of the data on chart paper using a planimeter.



### 5.1.3 Clamps

The tensile-testing apparatus shall have two clamps of at least 50 mm in width. Each clamp shall be designed to grip the test piece firmly along a straight line across the full width of the test piece, without causing any damage, and shall have means for adjusting the clamping force.

The clamps should preferably grip the test piece between a cylindrical and a flat surface, with the plane of the test piece tangential to the cylindrical surface. Other types of clamps may be used if it can be ensured that the test piece does not slip or suffer any damage during the test.

During the test, the clamping lines shall be parallel to each other within an angle of 1°. The clamping lines shall be perpendicular to the direction of the applied tensile force and to the longest dimension of the test piece to the same level of accuracy.

The distance between the clamping lines (i.e. the test span length) shall be adjusted to  $(100 \pm 1)$  mm, except that a test span length of  $(50 \pm 1)$  mm shall be used for finished paper products of which one or both of the dimensions is insufficient to provide a test piece of the length required in [7.2](#).

NOTE Toilet tissue sheets having one or both dimensions of about 98 mm are an example of such a material.

## 5.2 Cutting device

The cutting device shall be capable of repeatedly cutting test pieces  $(50,0 \pm 0,5)$  mm wide, with undamaged, straight, smooth and parallel edges.

## 6 Conditioning

Condition the samples according to ISO 187 and keep them in the standard atmosphere throughout the test.

Conditioning shall be done prior to the preparation of test pieces.

## 7 Preparation of test pieces

### 7.1 General

**7.1.1** If the tests are being made to evaluate a lot, the sample shall be selected in accordance with ISO 186. If the tests are being made on another type of sample, make sure that the specimens taken are representative of the sample. Each test piece shall be free from perforations and faults not normally inherent in the tissue.

**7.1.2** For converted tissue products, testing shall be done on the product as received, regardless of the number of plies which are supplied as a product unit. Generally, a single finished product sheet is suitable for use as a test piece.

**7.1.3** Tissue that has not been converted into a finished product shall be tested as a single ply unless otherwise agreed between the parties concerned.

### 7.2 Dimensions

Each test piece shall be  $(50,0 \pm 0,5)$  mm in width and at least 150 mm in length. With the exception of tissue paper or tissue products with an embossed pattern over all or part of the surface, the test pieces shall be free of creases, kinks, wrinkles, folds or other thickness variations.

For finished products with dimensions or perforations which make cutting of a test piece of at least 150 mm impossible, cut the longest piece possible. In such cases, a test span length of  $(50 \pm 1)$  mm

for the tensile tester clamps (5.1.3) shall be used. This deviation from the normal procedure shall be recorded in the test report.

### 7.3 Number of test pieces

Cut at least 10 test pieces in the machine direction and 10 test pieces in the cross direction for the selected specimens, making a total of at least 20 test pieces from each sample of tissue paper or tissue product.

## 8 Procedure

8.1 Ensure that the tensile-testing apparatus is calibrated and check the zero position of the recording device. Check that the clamps are aligned to meet the requirements in 5.1.3.

8.2 The elongation rate between the clamps shall be kept constant at  $(50 \pm 2)$  mm/min (5.1).

8.3 Place the test piece in the clamps so that any observable slack is eliminated but the test piece is not placed under any significant strain (5.1). The test piece shall not be clamped with a tension greater than 5 N/m.

8.4 Do not touch the test area of the test piece between the clamps with the fingers. Align the test piece as parallel as possible to the pulling direction, tightly clamp the test piece and initiate the test.

8.5 Test the test pieces from each sample. Record all readings, except for test pieces that break within 5 mm from the clamping line, until 10 valid results are available for each direction. If more than 20 % of the test pieces cut from a particular specimen break within 5 mm of the clamping line, reject all the readings obtained for that specimen. Inspect the apparatus for conformity with the specifications and take the appropriate remedial measures.

## 9 Calculation

### 9.1 General

Calculate and report the results separately for the machine direction and for the cross direction from Formula (1) to Formula (6).

### 9.2 Tensile strength

Calculate the mean maximum tensile force ( $\bar{F}$ ) in newtons from all the single values ( $F$ ) available representing acceptable test results. Calculate the mean tensile strength ( $\bar{S}$ ) from Formula (1):

$$\bar{S} = \frac{\bar{F}}{w_x} \times 10^3 \quad (1)$$

where

$\bar{S}$  is the tensile strength, expressed in newtons per metre (N/m);

$\bar{F}$  is the maximum tensile force in newtons (N);

$w_x$  is the initial width, in millimetres, of the test piece (50 mm).

Report the tensile strength in newtons per metre to three significant figures.

### 9.3 Tensile index

Calculate the tensile index,  $I$ , from [Formula \(2\)](#):

$$I = \frac{\bar{S}}{g} \quad (2)$$

where

$I$  is the tensile index, expressed in newton metres per gram (Nm/g);

$\bar{S}$  is the tensile strength in newtons per metre (N/m);

$g$  is the grammage, in grams per square metre (g/m<sup>2</sup>), determined according to ISO 12625-6.

Report the tensile index in newton metres per gram to three significant figures.

### 9.4 Stretch at maximum force

Calculate the mean elongation at break corresponding to the stretch of the test piece at the moment when the maximum force is reached. Calculate the stretch at maximum force,  $A$ , from [Formula \(3\)](#):

$$A = \frac{\varepsilon}{l} \times 100 \quad (3)$$

where

$A$  is the mean stretch at maximum force in percentage (%);

$\varepsilon$  is the mean elongation at maximum force in millimetres (mm);

$l$  is the length of the test piece between the clamps, before elongation (see [5.1.3](#)), in millimetres (mm).

Report the result to the first decimal place.

### 9.5 Tensile energy absorption

Determine the area under the force-elongation curve up to the point of maximum tensile force and calculate the tensile energy absorption,  $Z$ , from [Formula \(4\)](#):

$$Z = \frac{E}{w \times l} \times 1\,000 \quad (4)$$

and the mean tensile energy absorption,  $\bar{Z}$ , from [Formula \(5\)](#):

$$\bar{Z} = \frac{\sum Z}{n} \quad (5)$$

where

$Z$  is the tensile energy absorption by a single test piece during the test until maximum force, in joules per square metre (J/m<sup>2</sup>);

$\bar{Z}$  is the mean tensile energy absorption in joules per square metre (J/m<sup>2</sup>);

$E$  is the work, in millijoules, equivalent to the area under the force/elongation curve (mJ);

$w$  is the initial width, in millimetres, of the test piece (50 mm);

$l$  is the initial test length, in millimetres (standard 100 mm);

$n$  is the number of single values of the tensile energy absorption.

Report the mean tensile energy absorption in joules per square metre ( $\text{J}/\text{m}^2$ ) to the first decimal place.

## 9.6 Tensile energy absorption index

Calculate the tensile energy absorption index,  $I_Z$ , using [Formula \(6\)](#):

$$I_Z = \frac{\bar{Z}}{g} \quad (6)$$

where

$I_Z$  is the tensile energy absorption index, in joules per gram ( $\text{J}/\text{g}$ );

$\bar{Z}$  is the mean tensile energy absorption, in joules per square metre ( $\text{J}/\text{m}^2$ );

$g$  is the grammage, in grams per square metre ( $\text{g}/\text{m}^2$ ), determined in accordance with ISO 12625-6.

Report the tensile energy absorption index, in joules per gram, to the first decimal place.

## 10 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 12625-4;
- b) the date and place of testing;
- c) the description and identification of the sample (for example, product category and dimensions under test);
- d) the number of single values used to calculate the tensile strength, elongation at maximum force and tensile energy absorption;
- e) the mean tensile strength in machine and cross direction in newtons per metre to three significant figures;
- f) the standard deviation or coefficient of variation to two significant figures;
- g) the mean stretch at maximum force, in percentage, in the machine and cross direction, rounded to the first decimal place, standard deviation or coefficient of variation;
- h) the tensile energy absorption in machine and cross direction, in joules per square metre, rounded to the first decimal;
- i) any deviation from this document and any other circumstances that may have affected the test results;
- j) the conditioning atmosphere used.

## Annex A (informative)

### Precision

#### A.1 General

The data have been obtained from CEPI-CTS, the Comparative Testing Service of the Confederation of European Paper Industries. The results are from a test round performed in 2012 by qualified laboratories. Two samples were tested according to this document. The data for tensile strength are presented in [A.2](#). The data for stretch at maximum force are presented in [A.3](#).

The repeatability and reproducibility results from the test are reported in [Table A.1](#) to [Table A.4](#).

Precision data for tensile energy absorption is not available at the moment.

The calculations were made according to ISO/TR 24498[7] and TAPPI T 1200 sp-07[8].

The repeatability standard deviation reported in [Table A.1](#) and [Table A.3](#) is the “pooled” repeatability standard deviation, which means that the standard deviation is calculated as the root-mean-square of the standard deviations of the participating laboratories. This differs from the conventional definition of repeatability in ISO 5725-1[3].

The repeatability and reproducibility limits reported are estimates of the maximum difference which should be expected in 19 of 20 instances, when comparing two test results for material similar to those described under similar test conditions. These estimates may not be valid for different materials or different test conditions. Repeatability and reproducibility limits are calculated by multiplying the repeatability and reproducibility standard deviations by 2,77.

NOTE 1 The repeatability standard deviation and the within-laboratory standard deviation are identical. However, the reproducibility standard deviation is not the same as between-laboratories standard deviation. The reproducibility standard deviation includes both the between-laboratories standard deviation and the standard deviation within a laboratory, viz.:

$$s_{repeatability}^2 = s_{within\ lab}^2$$

but

$$s_{reproducibility}^2 = s_{within\ lab}^2 + s_{between\ lab}^2$$

NOTE 2  $2,77 = 1,96 \sqrt{2}$ , provided that the test results have a normal distribution and that the standard deviation,  $s$ , is based on a large number of tests.

## A.2 Tensile strength

Table A.1 — Repeatability results of an interlaboratory test by qualified laboratories (tensile strength)

Sample	Number of laboratories	Mean tensile strength	Repeatability standard deviation	Coefficient of variation	Repeatability limit
			$s_r$	$C_{V,r}$	$r$
		N/m	N/m	%	N/m
A	11	121	9,0	7,4	25
B	10	643	27	4,2	74

Table A.2 — Reproducibility results of an interlaboratory test by qualified laboratories (tensile strength)

Sample	Number of laboratories	Mean tensile strength	Reproducibility standard deviation	Coefficient of variation	Reproducibility limit
			$s_R$	$C_{V,R}$	$R$
		N/m	N/m	%	N/m
A	11	121	11	9,1	30
B	10	643	30	4,7	84

## A.3 Stretch at maximum force

Table A.3 — Repeatability results of an interlaboratory test by qualified laboratories (stretch at maximum force)

Sample	Number of laboratories	Mean stretch at maximum force	Repeatability standard deviation	Coefficient of variation	Repeatability limit
			$s_r$	$C_{V,r}$	$r$
		%	%	%	%
A	10	16,8	1,7	9,9	4,6
B	10	15,5	0,76	4,9	2,1

Table A.4 — Reproducibility results of an interlaboratory test by qualified laboratories (stretch at maximum force)

Sample	Number of laboratories	Mean stretch at maximum force	Reproducibility standard deviation	Coefficient of variation	Reproducibility limit
			$s_R$	$C_{V,R}$	$R$
		%	%	%	%
A	10	16,8	1,9	11	5,1
B	10	15,5	1,3	8,1	3,5

## Bibliography

- [1] ISO 287, *Paper and board — Determination of moisture content of a lot — Oven-drying method*
- [2] ISO 638, *Paper, board and pulps — Determination of dry matter content — Oven-drying method*
- [3] ISO 5725-1, *Accuracy (trueness and precision) of measurement methods and results — Part 1: General principles and definitions*
- [4] ISO 12625-1, *Tissue paper and tissue products — Part 1: General guidance on terms*
- [5] ISO 12625-6, *Tissue paper and tissue products — Part 6: Determination of grammage*
- [6] ISO 15755, *Paper and board — Estimation of contraries*
- [7] ISO/TR 24498, *Paper, board and pulps — Estimation of uncertainty for test methods*
- [8] TAPPI T 1200 sp-07, *Interlaboratory Evaluation of Test Methods to Determine TAPPI Repeatability and Reproducibility*







# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

## Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

## Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com).

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Useful Contacts

### Customer Services

**Tel:** +44 345 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 345 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)

### BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK