### **BS EN ISO 12670:2015**



## **BSI Standards Publication**

Thermal spraying —
Components with thermally sprayed coatings —
Technical supply conditions



BS EN ISO 12670:2015 BRITISH STANDARD

#### **National foreword**

This British Standard is the UK implementation of EN ISO 12670:2015. It is identical to ISO 12670:2011. It supersedes both BS EN 15311:2007 and BS ISO 12670:2011 which are withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/40, Thermal spraying and thermally sprayed coatings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015. Published by BSI Standards Limited 2015

ISBN 978 0 580 89464 0

ICS 25.220.20

# Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 December 2011.

#### Amendments/corrigenda issued since publication

| Date            | Text affected                                   |  |  |  |
|-----------------|-------------------------------------------------|--|--|--|
| 31 October 2015 | This corrigendum renumbers BS ISO 12670:2011 as |  |  |  |
|                 | BS EN ISO 12670:2015                            |  |  |  |

## **EUROPEAN STANDARD**

NORME EUROPÉENNE

# **EN ISO 12670**

## **EUROPÄISCHE NORM**

October 2015

ICS 25.220.20

Supersedes EN 15311:2007

#### **English Version**

## Thermal spraying - Components with thermally sprayed coatings - Technical supply conditions (ISO 12670:2011)

Projection thermique - Éléments traités par projection thermique - Conditions techniques de livraison (ISO 12670:2011)

Thermisches Spritzen - Bauteile mit thermisch gespritzten Schichten - Technische Lieferbedingungen (ISO 12670:2011)

This European Standard was approved by CEN on 27 September 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

## **European foreword**

The text of ISO 12670:2011 has been prepared by Technical Committee ISO/TC 107 "Metallic and other inorganic coatings" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 12670:2015 by Technical Committee CEN/TC 240 "Thermal spraying and thermally sprayed coatings" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2016, and conflicting national standards shall be withdrawn at the latest by April 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 15311:2007.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

#### **Endorsement notice**

The text of ISO 12670:2011 has been approved by CEN as EN ISO 12670:2015 without any modification.

#### **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 12670 was prepared by Technical Committee ISO/TC 107, Metallic and other inorganic coatings.

# Thermal spraying — Components with thermally sprayed coatings — Technical supply conditions

#### 1 Scope

This International Standard specifies technical supply conditions for parts with thermally sprayed coatings for the manufacturing or repair of components.

This International Standard applies to applications where quality requirements according to ISO 14922-2 (comprehensive requirements) or ISO 14922-3 (standard requirements) are required.

#### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2063, Thermal spraying — Metallic and other inorganic coatings — Zinc, aluminium and their alloys

ISO 4288, Geometrical Product Specifications (GPS) — Surface texture: Profile method — Rules and procedures for the assessment of surface texture

ISO 6507-1, Metallic materials — Vickers hardness test — Part 1: Test method

ISO 12690, Metallic and other inorganic coatings — Thermal spray coordination — Tasks and responsibilities

ISO 14232, Thermal spraying — Powders — Composition and technical supply conditions

ISO 14916, Thermal spraying — Determination of tensile adhesive strength

ISO 14918, Thermal spraying — Approval testing of thermal sprayers

ISO 14919, Thermal spraying — Wires, rods and cords for flame and arc spraying — Classification — Technical supply conditions

ISO 14923, Thermal spraying — Characterization and testing of thermally sprayed coatings

EN 473, Non destructive testing — Qualification and certification of NDT personnel — General principles

EN 657, Thermal spraying — Terminology, classification

EN 1395-1, Thermal spraying — Acceptance inspection of thermal spraying equipment — Part 1: General requirements

#### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 657 apply.

#### 4 Requirements

#### 4.1 General requirements

#### 4.1.1 Specifying the general requirements

This International Standard, which specifies the general requirements for supply, shall be indicated in the list of parts or in other manufacturing or delivery instructions.

#### 4.1.2 Qualification of the manufacturer

The manufacturer of the thermally sprayed coating shall possess a quality management system, shall fulfil all requirements stipulated in the coating specification for the part, shall employ qualified personnel and is responsible for keeping the spraying equipment in a functional and safe condition.

Considering the following standards can help to fulfil the quality requirements for the coating:

- a) spraying coordinator (supervisor): qualified according to ISO 12690;
- b) thermal sprayer: qualified according to ISO 14918 or qualified by appropriate skill and knowledge;
- c) non-destructive testing personnel: qualification according to EN 473;
- d) spraying equipment: checked according to the relevant part of EN 1395 or qualified by the unobjectionable and unchanged function of the spraying equipment documented by test reports or coating results.

#### 4.1.3 Preparing the instructions for thermal spraying (spray procedure specification)

The manufacturer is responsible for preparing the spray procedure specification in written form.

The spray procedure specification shall refer to the coating specification and the manufacturing instructions, such as the list of parts, instructions of substrate and spraying material, drawings and tests.

If required, the spray procedure specification can be qualified by a component-related spray procedure qualification according to EN 15648.

#### 4.2 Technical requirements

#### 4.2.1 Spraying materials

Only spraying materials which are required in the coating specification and indicated in the spray procedure specification shall be applied. The spraying material shall comply with the technical supply conditions indicated in ISO 14232 for spraying powders and ISO 14919 for spraying wires, rods and cords.

The conformity of the delivered with the required spraying material shall be safeguarded, for example by comparing the composition indicated on the test certificate with the required one.

All spraying materials shall be stored in suitable packages.

The processing instructions of the manufacturer/supplier of the spraying material shall be considered.

#### 4.2.2 Spray procedure specification

The spray procedure specification shall contain all parameters, including, for the relative motion between the gun and the part or the identification number of the motion programme, those which are necessary for the spraying process of the relevant part. The necessary parameters are to be determined by spraying tests or taken from an appropriate similar application.

The spray procedure specification may be qualified by a procedure qualification, for example according to EN 15648, if required.

The preparation of the substrate's surface shall be specified in the spray procedure specification. Further instructions can be taken from EN 13507.

Post-treatments, like machining, sealing of the coating or heat treatment of the part, shall be specified in the spray procedure specification or in the operation sequence plan (see ISO 14924). A test may be required to ensure that the sprayed coating and/or the part will not be damaged by the post-treatment process.

ISO 14920 contains instructions if fusing of self-fluxing alloys is required.

Any modification of parameters, spraying and/or auxiliary materials, design of the part, spraying procedure or spraying equipment requires a check of the coating's quality. A revision of the spray procedure specification or preparation of a new one is required.

#### 4.2.3 Requirements for acceptance criteria for thermally sprayed coatings

Requirements for acceptance criteria shall be specified in the coating specification, e.g. maximum and/or minimum values of hardness, tensile adhesive strength, coating thickness, coating structure, porosity, roughness, grit residues in the interface, non-melted particles, time limit between surface preparation and spraying, etc. If applicable, reference samples for bend and cupping tests, or test procedures for wear, corrosion or thermal cycling tests can be agreed upon between the contracting parties.

In the case of applications for corrosion protection by zinc or aluminium, ISO 2063 shall apply for testing and acceptance criteria.

Acceptance criteria and admissible imperfections which are not specified in the coating specification or in the manufacturing or testing instructions shall be agreed between the contracting parties.

#### 5 Quality tests

#### 5.1 General

Usually, tests and their scope are specified in the coating specification. If they are not indicated there, test instructions are to be prepared by the coating manufacturer. This can be done in agreement with the customer, if required.

Tables 1 and 2 will help to select and specify the appropriate tests and their scope.

#### 5.2 Tests, scope of tests and requirements for accompanying test specimens

In the case of mass production or series production of thermally coated parts and when tests indicated in Table 1 are applied, the actual number of parts within a batch shall be considered. Accompanying test specimens for certain tests are mentioned in Table 2.

Where a single part is to be coated, the percentage of the surface for random testing shall be calculated according to the size of the coated area. The influence of the process stability (process carried out manually, completely mechanized, or controlled in closed-loop form) shall be considered when random tests are specified.

Table 1 — Tests on the part

| Coating condition                                    | Visual<br>inspection | Measuring<br>the coating<br>thickness <sup>a</sup> | Measuring<br>the geometry | Penetration<br>test <sup>b</sup> | Measuring<br>the<br>roughness <sup>c</sup> | Hardness<br>test <sup>d</sup> |
|------------------------------------------------------|----------------------|----------------------------------------------------|---------------------------|----------------------------------|--------------------------------------------|-------------------------------|
| Coating as sprayed                                   | 100                  | rt                                                 | rt                        | _                                | rt                                         | rt                            |
| Coating sprayed and machined                         | 100                  | rt                                                 | rt                        | _                                | rt                                         | rt                            |
| Coating<br>sprayed and<br>thermally post-<br>treated | 100                  | rt                                                 | rt                        | rt                               | rt                                         | rt                            |

100: the coating of any single part, or of each single part within a batch, shall be tested.

- b Measurement is practicable only if the coating is not porous.
- c Roughness in the as-sprayed condition can be compared with reference samples according to ISO 8503-1, visually or by scanning. Measuring the roughness after machining shall be carried out according to ISO 4288.
- d A hardness test carried out on the part itself can be accepted only if the coating or the part will not be damaged.

Table 2 — Requirements for accompanying test pieces for certain tests

| Coatings condition                         | Determination of<br>tensile adhesive<br>strength <sup>a</sup> | Materialographic examination <sup>b</sup> | Hardness test <sup>c</sup> | Bend test <sup>d</sup> | Cupping test <sup>e</sup> |
|--------------------------------------------|---------------------------------------------------------------|-------------------------------------------|----------------------------|------------------------|---------------------------|
| Coating as sprayed                         | Y/B                                                           | Y/B                                       | Y/B                        | X                      | X                         |
| Coating sprayed and thermally post-treated | _                                                             | Y/E                                       | Y/E                        | Х                      | Х                         |

Y/B: required per batch.

Y/E: required in the case of a procedure evaluation or qualification.

- X: Usually, the test is applied as a shop test only. Tests can be required, if reference samples are agreed between the contracting parties.
- —: The test is senseless or not practicable.
- <sup>a</sup> The determination shall be carried out according to ISO 14916. Results, the adhesive used and the bonding procedure shall be documented in the test report.
- b The preparation method for the test specimen shall be agreed upon between contracting parties. The examination can also be used to measure the coating thickness.
- The hardness test shall be carried out according to ISO 6507-1 if the test on the part is not acceptable.
- d The number and design of the test specimen, test procedure and admissible crack structures in the coating shall be agreed upon between the contracting parties.
- <sup>e</sup> Can be applied according to ISO 20482. The test procedure and admissible crack structures in the coating shall be agreed upon between the contracting parties.

#### 5.3 Test on the part

The surface characteristics described in ISO 14923 shall be assessed by visual inspection carried out by a skilled and qualified person. Wherever possible, required tests shall be carried out on the part.

A 100 %-visual inspection shall be carried out after finishing the coating, even if this is not specified in the manufacturing instructions. In case of doubt about the quality of the sprayed coating, the test's sensitivity shall be raised by using a magnification of  $6 \times$  to  $10 \times$ .

rt: random test.

a If geometric, technological or physical conditions enable this measurement.

#### 5.4 Test on accompanying test specimens

Accompanying test specimens shall undergo the same operation steps of the spraying procedure as the part itself. The test specimen's material shall correspond to the material of the part in its mechanical and physical properties.

Tests shall be carried out according to ISO 14923, if possible. Where test procedures are not specified in the coating specification or in the test instructions, the test method shall be agreed between the contracting parties.

#### 5.5 Rejection of a defective thermally sprayed coating

Where a sprayed coating or the accompanying test specimen did not pass the required tests, the defective thermally sprayed coating shall be removed. After cleaning and preparation, the part and the test specimen can be coated again according to the qualified spray procedure specification. However, if the defects show that the specification will not fulfil the requirements of the coating specification, the spray procedure specification shall be revised and qualified again.

Testing shall be carried out according to the original instructions and scope.

#### 5.6 Documentation

The manufacturer/supplier is responsible for fulfilling all requirements of the coating specification and, if applicable, any agreements between the contracting parties. The test results shall be documented.

### **Bibliography**

- [1] ISO 6508-1, Metallic materials Rockwell hardness test Part 1: Test method (scales A, B, C, D, E, F, G, H, K, N, T)
- [2] ISO 8503-1, Preparation of steel substrates before application of paints and related products Surface roughness characteristics of blast-cleaned steel substrates Part 1: Specifications and definitions for ISO surface profile comparators for the assessment of abrasive blast-cleaned surfaces
- [3] ISO 12679, Thermal spraying Recommendations for thermal spraying
- [4] ISO 14920, Thermal spraying Spraying and fusing of self-fluxing alloys
- [5] ISO 14922-1, Thermal spraying Quality requirements of thermally sprayed structures Part 1: Guidance for selection and use
- [6] ISO 14922-2, Thermal spraying Quality requirements of thermally sprayed structures Part 2: Comprehensive quality requirements
- [7] ISO 14922-3, Thermal spraying Quality requirements of thermally sprayed structures Part 3: Standard quality requirements
- [8] ISO 14922-4, Thermal spraying Quality requirements of thermally sprayed structures Part 4: Elementary quality requirements
- [9] ISO 14924, Thermal spraying Post-treatment and finishing of thermally sprayed coatings
- [10] ISO 20482, Metallic materials Sheet and strip Erichsen cupping test
- [11] EN 1274, Thermal spraying Powders Composition, technical supply conditions
- [12] EN 13507, Thermal spraying Pre-treatment of surfaces of metallic parts and components for thermal spraying
- [13] EN 15648, Thermal spraying Component related procedure qualification



ICS 25.220.20

Price based on 6 pages



# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

#### About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards -based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

#### Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

#### **Buying standards**

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

#### **Subscriptions**

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

#### **BSI Group Headquarters**

389 Chiswick High Road London W4 4AL UK

#### **Revisions**

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

#### Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

#### **Useful Contacts:**

#### **Customer Services**

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com
Email (enquiries): cservices@bsigroup.com

#### Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

#### Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

#### **Copyright & Licensing**

Tel: +44 20 8996 7070 Email: copyright@bsigroup.com

