

# Paints and varnishes — Corrosion protection of steel structures by protective paint systems —

## Part 7: Execution and supervision of paintwork

The European Standard EN ISO 12944-7:1998 has the status of a  
British Standard

ICS 87.020; 91.080.10

# National foreword

This British Standard is the English language version of EN ISO 12944-7:1998. It is identical with ISO 12944-7:1998. Together with the other seven parts of BS EN ISO 12944, it partially supersedes BS 5493:1977 which is declared obsolescent.

The UK participation in its preparation was entrusted to Technical Committee STI/27, Paint systems for metallic substrates, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

## Cross-references

Attention is drawn to the fact that CEN and CENELEC Standards normally include an annex which lists normative references to international publications with their corresponding European publications. The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled "International Standards Correspondence Index", or by using the "Find" facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

## Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, the EN ISO title page, page 2, the ISO title page, pages ii to iv, pages 1 to 7 and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

This British Standard, having been prepared under the direction of the Sector Committee for Materials and Chemicals, was published under the authority of the Standards Committee and comes into effect on 15 November 1998

© BSI 05-1999

ISBN 0 580 30350 0

## Amendments issued since publication

Amd. No.	Date	Comments

---

# Contents

	Page
National foreword	Inside front cover
Foreword	2
Foreword	iii
Text of ISO 12944-7	1

---



---

ICS 87.020; 91.080.10

Descriptors: See ISO document

English version

# Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 7: Execution and supervision of paint work

(ISO 12944-7:1998)

Peintures et vernis — Anticorrosion des structures en acier par systèmes de peinture — Partie 7: Exécution et surveillance des travaux de peinture (ISO 12944-7:1998)

Beschichtungsstoffe — Korrosionsschutz von Stahlbauten durch Beschichtungsstoffe — Teil 7: Ausführung und Überwachung der Beschichtungsarbeiten (ISO 12944-7:1998)

This European Standard was approved by CEN on 13 November 1997.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

## CEN

European Committee for Standardization  
Comité Européen de Normalisation  
Europäisches Komitee für Normung

**Central Secretariat: rue de Stassart 36, B-1050 Brussels**

## Foreword

The text of the International Standard ISO 12944-7:1998 has been prepared by Technical Committee ISO/TC 35 “Paints and varnishes” in collaboration with Technical Committee CEN/TC 139 “Paints and varnishes”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1998, and conflicting national standards shall be withdrawn at the latest by November 1998.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

## Endorsement notice

The text of the International Standard ISO 12944-7:1998 was approved by CEN as a European Standard without any modification.

NOTE Normative references to International Standards are listed in Annex ZA (normative).

INTERNATIONAL  
STANDARD

ISO  
12944-7

First edition  
1998-05-15

---

---

**Paints and varnishes — Corrosion  
protection of steel structures by protective  
paint systems —**

**Part 7:**  
Execution and supervision of paint work

*Peintures et vernis — Anticorrosion des structures en acier par systèmes  
de peinture —*

*Partie 7: Exécution et surveillance des travaux de peinture*



## Contents

	Page
Foreword	iii
Introduction	1
1 Scope	1
2 Normative references	1
3 Preconditions for the execution of the paint work	2
3.1 Qualification	2
3.2 Condition of the substrate	2
3.3 Health and safety and environmental protection	2
4 Coating materials	2
4.1 Supply	2
4.2 Storage	2
5 Execution of the paint work	3
5.1 General	3
5.2 Application conditions	3
5.3 Application methods	4
5.4 Evaluation before work commences	4
6 Supervision of the paint work	4
6.1 General	4
6.2 Measurement and test instruments	4
6.3 Checking the paint coating	5
7 Reference areas	5
7.1 General	5
7.2 Previously coated surfaces	5
7.3 Reference area records	5
7.4 Assessment of coating	6
Annex A (informative) Number of reference areas	7
Annex ZA (normative) Normative references to international publications with their relevant European publications	7

**Descriptors:** Paints, varnishes, steel construction, corrosion, corrosion prevention, protective coatings, paint coats, painting.



## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International Organizations, governmental and non governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 12944-7 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 14, *Protective paint systems for steel structures*.

ISO 12944 consists of the following parts under the general title *Paints and varnishes — Corrosion protection of steel structures by protective paint systems*:

- *Part 1: General introduction;*
- *Part 2: Classification of environments;*
- *Part 3: Design considerations;*
- *Part 4: Types of surface and surface preparation;*
- *Part 5: Protective paint systems;*
- *Part 6: Laboratory performance test methods;*
- *Part 7: Execution and supervision of paint work;*
- *Part 8: Development of specifications for new work and maintenance.*

Annex A of this part of ISO 12944 is for information only.



## Introduction

Unprotected steel in the atmosphere, in water and in soil is subjected to corrosion that may lead to damage. Therefore, to avoid corrosion damage, steel structures are normally protected to withstand the corrosion stresses during the service life required of the structure.

There are different ways of protecting steel structures from corrosion. ISO 12944 deals with protection by paint systems and covers, in the various parts, all features that are important in achieving adequate corrosion protection. Additional or other measures are possible but require particular agreement between the interested parties.

In order to ensure effective corrosion protection of steel structures, it is necessary for owners of such structures, planners, consultants, companies carrying out corrosion protection work, inspectors of protective coatings and manufacturers of coating materials to have at their disposal state-of-the-art information in concise form on corrosion protection by paint systems. Such information has to be as complete as possible, unambiguous and easily understandable to avoid difficulties and misunderstandings between the parties concerned with the practical implementation of protection work.

This International Standard – ISO 12944 – is intended to give this information in the form of a series of instructions. It is written for those who have some technical knowledge. It is also assumed that the user of ISO 12944 is familiar with other relevant International Standards, in particular those dealing with surface preparation, as well as relevant national regulations.

Although ISO 12944 does not deal with financial and contractual questions, attention is drawn to the fact that, because of the considerable implications of inadequate corrosion protection, non-compliance with requirements and recommendations given in this standard may result in serious financial consequences.

ISO 12944-1 defines the overall scope of all parts of ISO 12944. It gives some basic terms and definitions and a general introduction to the other parts of ISO 12944. Furthermore, it includes a general statement on health, safety and environmental protection, and guidelines for using ISO 12944 for a given project.

This part of ISO 12944 describes how paint work on steel structures is to be executed and supervised after the surface has been prepared in accordance with ISO 12944-4. Examples of protective paint systems suitable for this purpose are given in ISO 12944-5.

## 1 Scope

**1.1** This part of ISO 12944 deals with the execution and supervision of paint work on steel structures in the workshop or on site.

**1.2** This part of ISO 12944 does not apply to:

- the preparation of surfaces to be painted (see ISO 12944-4) and the supervision of such work,
- the application of metallic coatings,
- pre-treatment methods such as phosphating and chromating and paint application methods such as dipping, powder coating or coil coating.

## 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 12944. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 12944 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 1512:1991, *Paints and varnishes — Sampling of products in liquid or paste form.*

ISO 1513:1992, *Paints and varnishes — Examination and preparation of samples for testing.*

ISO 2409:1992, *Paints and varnishes — Cross-cut test.*

ISO 2808:1997, *Paints and varnishes — Determination of film thickness.*

ISO 4624:1978, *Paints and varnishes — Pull-off test for adhesion.*

ISO 8502-4:1993, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 4: Guidance on the estimation of the probability of condensation prior to paint application.*

ISO 9001:1994, *Quality systems — Model for quality assurance in design, development, production, installation and servicing.*

ISO 9002:1994, *Quality systems — Model for quality assurance in production, installation and servicing.*

ISO 12944-1:1998, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 1: General introduction.*

ISO 12944-4:1998, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 4: Types of surface and surface preparation.*

ISO 12944-5:1998, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 5: Protective paint systems.*

ISO 12944-8:1998, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 8: Development of specifications for new work and maintenance.*

### **3 Preconditions for the execution of the paint work**

#### **3.1 Qualification**

**3.1.1** Companies contracted to apply protective paint systems to steel structures, and their personnel, shall be capable of carrying out the work properly and safely. Work requiring particular care with regard to its execution shall only be carried out by personnel having qualifications which have been certified by an approved body, provided no other agreements have been made between the parties concerned.

**3.1.2** Where the contractor has a quality management system in operation, a quality plan shall be prepared by the contractor which includes his general standards of workmanship. A method statement shall be provided for each stage of the work.

The contractor shall show that he will be able to achieve the specified quality level at each stage. Evidence for this is, for example, given by the use of a quality assurance system in accordance with ISO 9001 or ISO 9002.

Unless otherwise agreed, the contractor shall provide the client with extracts of all execution and supervision standards given in his quality manual that are relevant to the specification.

#### **3.2 Condition of the substrate**

A protective paint system requires proper surface preparation, which depends on the initial and final condition of the surface. The respective requirements shall be specified in the painting specification and be capable of achievement.

Methods of surface preparation are described in ISO 12944-4. The prepared surfaces shall be assessed with regard to visual cleanliness, surface profile and chemical cleanliness, using the methods given in ISO 12944-4.

The requirements for the supervision of these aspects of the work, the frequency of assessment, and the location of the assessment work shall be agreed between the parties concerned.

If the condition of the surface differs from that described in the specification, the client shall be informed.

The temperature of the surface shall be without doubt above the dew point of the surrounding air, unless otherwise specified in the paint manufacturer's technical data sheet.

#### **3.3 Health and safety and environmental protection**

The applicable regulations concerning health and safety and environmental protection shall be complied with. See ISO 12944-1 and ISO 12944-8.

### **4 Coating materials**

#### **4.1 Supply**

The coating materials shall be supplied in such a condition that they are ready for use by the application method specified at the time of ordering. Paint manufacturers' technical data sheets shall comprise all details which are necessary for their use.

If any testing is required, it shall be specified, indicating the methods to be used. Sampling and further processing of samples shall be in accordance with ISO 1512 and ISO 1513.

Any detail not included in the paint manufacturer's technical data sheet that could affect the application conditions or the final quality of the work shall be given by the manufacturer.

#### **4.2 Storage**

The manufacturer shall indicate on the container the date by which the coating materials should be used (shelf life). Unless other temperatures are indicated in the manufacturer's instructions or specified elsewhere, coating materials shall be stored at temperatures above + 3 °C and under + 30 °C. Water-borne coating materials, in particular, may become unusable after freezing.

Coating materials and any other materials used (solvents, thinners etc.) shall be stored in a secured area.

Paint containers shall be kept sealed until the contents are prepared for use. Partly used containers may be re-sealed and used later, if not otherwise indicated in the paint manufacturer's technical data sheet. Partly used containers shall be clearly marked.

## 5 Execution of the paint work

### 5.1 General

The surfaces to be treated shall be safely accessible and well illuminated.

When using the coating materials, the manufacturer's technical data sheet shall be observed unless specifically stated otherwise in the painting specification.

Prior to and during the application, the coating materials shall be verified to ensure:

- conformity of the container label with the specified product description;
- no skin formation;
- no irreversible settling;
- usability under the given site conditions.

Any sediment present shall be easily redispersible.

Any viscosity adjustment — which may be necessary due to low application temperatures or different application methods — shall be made in accordance with the paint manufacturer's instructions. The client shall be informed, if required in the specification, of any such adjustment.

The application methods will depend on the type of coating material, the surface, the type and size of the structure and the local conditions. Regulations and requirements with regard to environmental protection may affect the choice of the application method. Unless otherwise specified, the application method shall be agreed.

The priming coat shall cover the entire surface profile of the steel surface. Each coat shall be applied as uniformly as possible and without leaving any areas uncovered.

Methods for the measurement of film thickness are described in ISO 2808. The procedure for checking nominal dry film thicknesses (instruments, calibration, and any allowance to be made for the contribution of the surface roughness to the result) shall be agreed between the interested parties.

Unless agreed otherwise, individual dry film thicknesses of less than 80 % of the nominal dry film thickness are not acceptable. Unless agreed otherwise, individual values between 80 % and 100 % of the nominal dry film thickness are acceptable provided that the overall average (mean) is equal to or greater than the nominal dry film thickness.

Care shall be taken to achieve the nominal dry film thickness and to avoid areas of excessive thickness. It is recommended that the maximum dry film thickness is not greater than 3 times the nominal film thickness. In the case of excessive maximum dry film thickness, expert agreement shall be found between the parties. For products or systems which have a critical maximum dry film thickness and in special cases, information given in the manufacturer's technical data sheet shall be observed.

All surfaces that are difficult to access and, for example, edges, corners, welds and riveted and bolted connections, shall be painted with particular care.

If additional edge protection is required, a stripe coat extending across a reasonable width (approximately 25 mm) on both sides of the edge shall be applied.

To assist in achieving the required dry film thickness, the wet film thickness shall be periodically checked during application.

The time interval between the application of coats, and between application of the final coat and use, given in the manufacturer's technical data sheet for the coating material, or as otherwise required by the specification, shall be adhered to.

Defects in any paint coat which may lead to a reduction in the protection provided by the coat, or which have a significant effect on the appearance, shall be repaired prior to application of the next coat. To avoid damage, the coating shall be sufficiently hard before transporting and handling.

Areas which are not to be painted or are to be painted with a low film thickness only, for example surfaces which will subsequently be welded and faying surfaces (those for which a close-tolerance fit is necessary) shall be identified to the contractor before painting commences.

### 5.2 Application conditions

In order to ensure the protection required from the coating, the ambient conditions on site shall be checked to ensure that they meet the requirements given in the paint manufacturer's technical data sheet for the particular coating material. This shall also apply to drying and reaction times.

During the planning stage before starting the work, measures shall be defined by which adverse effects on the environment can be avoided or reduced to a minimum.

During the execution of the corrosion protection work, care shall be taken that the work is not affected by any outside influences that could lead to a reduction in the quality of the coating. Paint work shall take place in an area separated or protected from the work of other trades (blast-cleaning, welding etc.). If adverse weather conditions occur during application, the work shall be stopped and the freshly coated area protected as far as practical. The lowest and highest permissible temperature of the surface to be coated and of the surrounding air shall be as stated in the manufacturer's technical data sheet.

Coating materials shall not be applied at temperatures below 3 °C above the dew point, determined in accordance with ISO 8502-4. Wet surfaces shall only be painted with those coating materials which are permitted in the technical data sheet or approved by the paint manufacturer.

When painting components which are to be welded on site, such components shall be masked in all areas which will be subject to preheating and welding. In the case of multicoat systems, every coat shall be stepped back.

### **5.3 Application methods**

#### **5.3.1 Brush application**

Brushes shall be suitable for their intended use. This applies particularly to corners, rivet heads, bolt heads, and angles and areas which are difficult to access. Details shall be given in the specification.

#### **5.3.2 Roller application**

The coating materials used shall be suitable for this method of application and shall have good levelling properties. The type and size of the roller shall be appropriate to the particular job. Roller application is normally not recommended for the application of anticorrosive primers.

#### **5.3.3 Spray application**

The following spraying methods are among those commonly used:

- conventional, low-pressure air spray;
- airless spray;
- air-assisted airless spray;
- electrostatic spray.

The paint viscosity, spraying pressure, type of nozzle, temperature of paint material, distance to the surface to be coated and spraying angle shall be selected so that uniform and continuous coatings are produced.

When using these methods, suitable precautions shall be taken to avoid spray mist spreading over the surroundings.

If the required film thickness cannot be achieved on edges, in corners or in areas of the structure which are difficult to access (spray shadows), these areas shall be precoated, by brushing, using a stripe coat, or spraying.

For coating materials having a tendency to settle, the paint container shall be fitted with a mechanical stirrer.

#### **5.3.4 Other application methods**

If other methods are used, for example flow-coating, application of hot-melt coating materials or application of anticorrosive tapes, they shall be carried out in accordance with the manufacturer's instructions.

### **5.4 Evaluation before work commences**

The application method specified shall be evaluated using the specified materials to ensure that they give the required protection. If the application method and/or the specified materials are found to be unsuitable, the specification shall be amended accordingly by the parties involved and any consequences, e.g. cost, time, shall be taken into consideration.

## **6 Supervision of the paint work**

### **6.1 General**

The execution of the work shall be supervised at all stages. Supervision shall be undertaken by suitable qualified and experienced people. The contractor shall be responsible for carrying out this supervision himself, but additional supervision by the client — even for corrosion protection work in the workshop — is advisable.

When coating materials with which the contractor is unfamiliar are to be applied, the manufacturer of the coating material shall be consulted.

The level of supervision will depend on the type and importance of the project, the degree of difficulty of the work and local conditions, and on the type of coating and its intended service life. This supervision will require appropriate technical knowledge and experience.

### **6.2 Measurement and test instruments**

The instrument manufacturer's instructions for the use of their equipment shall be complied with. The instruments used shall be checked, calibrated and maintained at regular intervals and the results shall be recorded.

### 6.3 Checking the paint coating

Coatings shall be checked for compliance with the specification, for example:

- by visual assessment, e.g. for uniformity, colour, hiding power and defects such as holidays, wrinkling, cratering, air bubbles, flaking, cracks and curtains;
- by means of instruments for compliance with the following characteristics of the dry film, if required:
  - dry film thickness: generally by non-destructive methods (see ISO 2808) [see also a) below];
  - adhesion: by destructive methods (see ISO 2409 or ISO 4624);
  - porosity: by flow or high-voltage detectors.

For dry film thickness measurements, the parties concerned shall agree on the following:

- a) The method to be used, the measurement instrument to be used, details of the calibration of the measurement instrument, and how to take into account the contribution of the surface profile to the result.
- b) The sampling plan — how and how many measurements are to be made for each type of surface.
- c) How the results are to be reported and how they are to be compared with acceptance criteria.

Dry film thicknesses (including the nominal and maximum thicknesses) shall be checked at each critical stage, and when the complete system has been applied. A critical stage is, for example, when there is a change in the responsibility for the paint work or when a long time elapses between application of priming coats and subsequent coats.

The coating on contact surfaces of preloaded bolted connections, for example high-strength fitted bolts in friction-grip connections and high-strength bolts in shear-type bearing connections shall be checked for conformity with the agreements made in the contract.

If destructive testing is necessary, notch-cutter measurements are acceptable. Such instruments can be used to check the thickness of individual coats and that of the complete system, and the sequence of the coats can also be checked. When testing for pores, the instrument and test voltage used shall be agreed between the parties concerned. Any coating damage shall be repaired in accordance with the specification. See ISO 12944-8.

## 7 Reference areas

### 7.1 General

Reference areas are suitable areas on the structure used to establish a minimum acceptable standard for the work, to check that data provided by a manufacturer or contractor is correct and to enable the performance of the coating to be assessed at any time after completion. Reference areas are normally not used for guarantee purposes but may be used for this purpose if agreed between the contracting parties.

If reference areas are required, they shall be prepared in locations in which the corrosive stresses are typical for the structure concerned. All surface preparation and paint application work on reference areas shall be carried out in the presence of representatives of all parties concerned, who shall give their agreement in writing when the reference areas are in accordance with the specification. All reference areas shall be accurately documented and may also be permanently marked on the structure itself (see ISO 12944-8).

The size and number of reference areas shall be in reasonable proportion, both practically and economically, to the area of the complete structure. See also ISO 12944-8.

### 7.2 Previously coated surfaces

In the particular case of previously coated surfaces, two types of reference area (A and B) may be prepared. Such previous coatings may be either old coatings or coatings applied recently by other contractors.

#### Type A reference area

Surface preparation and application of coatings *is* in accordance with the specification.

#### Type B reference area

All existing organic coatings are removed to the bare substrate, and the complete coating system is then applied, all in accordance with the specification.

### 7.3 Reference area records

The contractor shall keep records on the preparation of reference areas for each step of the work (for recommended form, see ISO 12944-8, Annex B). The records shall include all relevant data and shall be approved by all parties concerned.

#### 7.4 Assessment of coating

The coating shall be assessed by methods agreed between the parties concerned, preferably using international or national standards.

Defects in the coating could occur at the following locations:

- on the structure but not in the reference area(s);
- both on the structure and in the reference area(s);
- in the reference area(s) only.

If reference areas are used for guarantee purposes, possible causes of the defects shall be determined by suitably qualified and experienced personnel approved by the parties concerned.

If reference areas have been damaged, the defects shall be carefully repaired but these repaired parts are no longer valid as reference areas.



## Annex A (informative)

### Number of reference areas

Size of structure (painted area) m <sup>2</sup>	Recommended maximum number of reference areas	Recommended maximum percentage of reference area relative to total area of structure	Recommended maximum total area of reference areas m <sup>2</sup>
up to 2 000	3	0,6	12
above 2 000 to 5 000	5	0,5	25
above 5 000 to 10 000	7	0,5	50
above 10 000 to 25 000	7	0,3	75
above 25 000 to 50 000	9	0,2	100
above 50 000	9	0,2	200

## Annex ZA (normative)

### Normative references to international publications with their relevant European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN</u>	<u>Year</u>
ISO 1512	1991	Paints and varnishes — Sampling of products in liquid or paste form	EN 21512	1994
ISO 1513	1995	Paints and varnishes — Examination and preparation of samples for testing	EN ISO 1513	1994
ISO 2409	1992	Paints and varnishes — Cross-cut test	EN ISO 2409	1994
ISO 4624	1978	Paints and varnishes — Pull-off test	EN 24624	1992
ISO 9001	1994	Quality systems — Model for quality assurance in design/development, production, installation and servicing	EN ISO 9001	1994
ISO 9002	1994	Quality systems — Model for quality assurance in production, installation and servicing	EN ISO 9002	1994
ISO 12944-1	1998	Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 1: General introduction	EN ISO 12944-1	1998
ISO 12944-4	1998	Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 4: Types of surface and surface preparation	EN ISO 12944-4	1998
ISO 12944-5	1998	Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 5: Protective paint systems	EN ISO 12944-5	1998
ISO 12944-8	1998	Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 8: Development of specifications for new work and maintenance	EN ISO 12944-8	1998

---

---

## **BSI — British Standards Institution**

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### **Revisions**

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### **Buying standards**

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### **Information on standards**

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

### **Copyright**

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.