

Welding consumables — Gases and gas mixtures for fusion welding and allied processes

ICS 25.160.20; 71.100.20

National foreword

This British Standard is the UK implementation of EN ISO 14175:2008. It supersedes BS EN 439:1994 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee WEE/39, Welding consumables.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2008

© BSI 2008

ISBN 978 0 580 55179 6

Amendments/corrigenda issued since publication

Date	Comments

English Version

Welding consumables - Gases and gas mixtures for fusion
welding and allied processes (ISO 14175:2008)

Produits consommables pour le soudage - Gaz et
mélanges gazeux pour le soudage par fusion et les
techniques connexes (ISO 14175:2008)

Schweißzusätze - Gase und Mischgase für das
Lichtbogenschweißen und verwandte Prozesse (ISO
14175:2008)

This European Standard was approved by CEN on 7 February 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This document (EN ISO 14175:2008) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2008, and conflicting national standards shall be withdrawn at the latest by September 2008.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 439:1994.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 14175:2008 has been approved by CEN as a EN ISO 14175:2008 without any modification.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 14175 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

This second edition cancels and replaces the first edition (ISO 14175:1997) which has been technically revised.

Requests for official interpretations of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 3 via your national standards body, a complete listing of which can be found at www.iso.org.

Welding consumables — Gases and gas mixtures for fusion welding and allied processes

1 Scope

This International Standard specifies requirements for the classification of gases and gas mixtures used in fusion welding and allied processes including, but not limited to:

- tungsten arc welding (Process 141);
- gas-shielded metal arc welding (Process 13);
- plasma arc welding (Process 15);
- plasma arc cutting (Process 83);
- laser welding (Process 52);
- laser cutting (Process 84);
- arc braze welding (Process 972).

NOTE Process numbers are in accordance with ISO 4063.

The purpose of this International Standard is to classify and designate shielding, backing, process and assist gases in accordance with their chemical properties and metallurgical behaviour as the basis for correct selection by the user and to simplify the possible qualification procedures.

Gas purities and mixing tolerances are specified as delivered by the supplier (manufacturer) and not at the point of use.

Gases or gas mixtures may be supplied in either liquid or gaseous form, but when used for welding and allied processes, the gases are always used in the gaseous form.

Fuel gases, such as acetylene, natural gas, propane, etc., and resonator gases, as used in gas lasers, are not covered by this International Standard.

Transportation and handling of gases and containers shall be in accordance with local, national and regional standards and regulations as required.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 31-0:1992, *Quantities and units — Part 0: General principles*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

base gas

major or only component of a pure or mixed gas

3.2

classification

number of this International Standard, followed by the symbol for the gas or gas mixture (main group and sub-group)

3.3

component

gaseous substance that is essential to the performance of the gas mixture

EXAMPLE In a mixture containing 11 % of CO₂ in argon, CO₂ is considered a component while argon is the base gas.

3.4

container

vessel used for the shipment and/or storage of pure or mixed gases in a gaseous or liquid state

3.5

designation

classification plus the symbols for all chemical components plus the nominal composition in volume percent

NOTE Symbols for chemical components are given in 5.2.

EXAMPLE A mixture of argon containing 11 % CO₂ is designated as ISO 14175-M20-ArC-11.

3.6

impurity

gaseous substance with chemical composition different from the base gas, component or gas mixture

3.7

mixture

gas consisting of two or more components

3.8

nominal value

percentage value of a component, quoted by the manufacturer or supplier, which corresponds to the general composition given by the designation

3.9

symbol

main-group and sub-group of a gas mixture

NOTE Symbols are given in Table 2 (see also 5.1).

EXAMPLE The symbol for a mixture of argon containing 11 % CO₂ is M20.

4 Properties of gases

4.1 General

Relevant physical and chemical properties of the gases considered in this International Standard are given in Table 1.

Table 1 — Properties of gas components

Type of gas	Chemical symbol	Density ^a (air = 1,293) kg/m ³	Relative density ^a to air	Boiling point at 0,101 MPa °C	Reactivity during welding
Argon	Ar	1,784	1,380	– 185,9	Inert
Helium	He	0,178	0,138	– 268,9	Inert
Carbon dioxide	CO ₂	1,977	1,529	– 78,5 ^b	Oxidizing
Oxygen	O ₂	1,429	1,105	– 183,0	Oxidizing
Nitrogen	N ₂	1,251	0,968	– 195,8	Low reactive ^c
Hydrogen	H ₂	0,090	0,070	– 252,8	Reducing

^a Specified at 0 °C and 0,101 MPa (1,013 bar).
^b Sublimation temperature (solid to gas transition temperature).
^c The behaviour of nitrogen varies with different materials and applications. Possible influences must be considered by the user.

4.2 Rounding-off procedure

For purposes of determining compliance with the requirements of this International Standard, the actual test values obtained shall be subjected to the rounding-off rules of ISO 31-0:1992, Annex B, Rule A. If the measured values are obtained by equipment calibrated in units other than those of this International Standard, the measured values shall be converted to the units of this International Standard before rounding off. If an average value is to be compared to the requirements of this International Standard, rounding off shall be done only after calculating the average. In the case where the testing standard cited in the normative references of this International Standard contains instructions for rounding off that conflict with the instructions of this International Standard, the rounding-off requirements of the testing standard shall apply. The rounded-off results shall fulfill the requirements of the appropriate table for the classification under test.

5 Classification and designation

5.1 Classification

5.1.1 General

Gases and gas mixtures shall be classified by the number of this International Standard, followed by the symbol for the gas in accordance with Table 2.

NOTE The classification is based on the reactivity of the gas or gas mixture.

5.1.2 Main group

The letter codes and numbers used for the main groups are:

- I: inert gases and inert gas mixtures;
- M1, M2 and M3: oxidising mixtures containing oxygen and/or carbon dioxide;
- C: highly oxidising gas and highly oxidising mixtures;
- R: reducing gas mixtures;
- N: low reactive gas or reducing gas mixtures, containing nitrogen;
- O: oxygen;
- Z: gas mixtures containing components not listed or mixtures outside the composition ranges listed in Table 2.

5.1.3 Sub-group

The main groups, except Z, are divided into sub-groups based on the presence and level of different components having an influence on the reactivity (see Table 2). The values indicated in Table 2 are nominal values.

5.1.4 Classification examples

EXAMPLE 1 For a gas mixture containing 6 % carbon dioxide, 4 % oxygen in argon:

Classification: ISO 14175 – M25

EXAMPLE 2 For a gas mixture containing 30 % helium in argon:

Classification: ISO 14175 – I3

EXAMPLE 3 For a gas mixture containing 5 % hydrogen in argon:

Classification: ISO 14175 – R1

EXAMPLE 4 For a gas mixture containing 0,05 % of oxygen in argon:

Classification: ISO 14175 – Z

5.2 Designation

5.2.1 General

Gases and gas mixtures are designated by the classification (see 5.1) and the symbols of their chemical components as below, followed by the corresponding nominal composition in volume percent:

- Ar: argon
- C: carbon dioxide
- H: hydrogen
- N: nitrogen

— O: oxygen

— He: helium

The base gas symbol shall be followed by the symbols for the other components in decreasing order of percent, followed by the nominal composition values, in volume percent, which are separated by a dash.

5.2.2 Designation examples

EXAMPLE 1 For a gas mixture containing 6 % carbon dioxide, 4 % oxygen in argon:

Classification: ISO 14175 – M25

Designation: ISO 14175 – M25 – ArCO – 6/4

EXAMPLE 2 For a gas mixture containing 30 % helium in argon:

Classification: ISO 14175 – I3

Designation: ISO 14175 – I3 – ArHe – 30

EXAMPLE 3 For a gas mixture containing 5 % hydrogen in argon:

Classification: ISO 14175 – R1

Designation: ISO 14175 – R1 – ArH – 5

EXAMPLE 4 For a gas mixture containing 7,5 % argon, 2,5 % carbon dioxide in helium:

Classification: ISO 14175 – M12

Designation: ISO 14175 – M12 – HeArC – 7,5/2,5

For gas mixtures containing components listed, but outside the ranges in Table 2, the letter Z prefixes the symbol for the base gas and symbols for components as above, followed by the nominal composition values, in volume percent, which are separated by a dash.

EXAMPLE 5 For a gas mixture containing 0,05 % of oxygen in argon:

Classification: ISO 14175 – Z

Designation: ISO 14175 – Z – ArO – 0,05

For gas mixtures containing components not listed in Table 2, the letter Z prefixes the symbol for the base gas and symbols for components as above, but with a plus sign preceding the unlisted component, followed by the nominal composition values, in volume percent, which are separated by a dash.

EXAMPLE 6 For a gas mixture containing 0,05 % of xenon, chemical symbol Xe, in argon:

Classification: ISO 14175 – Z

Designation: ISO 14175 – Z – Ar+Xe – 0,05

Table 2 — Classification of process gases for fusion welding and allied processes

Symbol		Components in nominal percentage of volume					
Main group	Sub-group	Oxidizing		Inert		Reducing	Low reactivity
		CO ₂	O ₂	Ar	He	H ₂	N ₂
I	1			100			
	2				100		
	3			balance	0,5 ≤ He ≤ 95		
M1	1	0,5 ≤ CO ₂ ≤ 5		balance ^a		0,5 ≤ H ₂ ≤ 5	
	2	0,5 ≤ CO ₂ ≤ 5		balance ^a			
	3		0,5 ≤ O ₂ ≤ 3	balance ^a			
	4	0,5 ≤ CO ₂ ≤ 5	0,5 ≤ O ₂ ≤ 3	balance ^a			
M2	0	5 < CO ₂ ≤ 15		balance ^a			
	1	15 < CO ₂ ≤ 25		balance ^a			
	2		3 < O ₂ ≤ 10	balance ^a			
	3	0,5 ≤ CO ₂ ≤ 5	3 < O ₂ ≤ 10	balance ^a			
	4	5 < CO ₂ ≤ 15	0,5 ≤ O ₂ ≤ 3	balance ^a			
	5	5 < CO ₂ ≤ 15	3 < O ₂ ≤ 10	balance ^a			
	6	15 < CO ₂ ≤ 25	0,5 ≤ O ₂ ≤ 3	balance ^a			
M3	7	15 < CO ₂ ≤ 25	3 < O ₂ ≤ 10	balance ^a			
	1	25 < CO ₂ ≤ 50		balance ^a			
	2		10 < O ₂ ≤ 15	balance ^a			
	3	25 < CO ₂ ≤ 50	2 < O ₂ ≤ 10	balance ^a			
	4	5 < CO ₂ ≤ 25	10 < O ₂ ≤ 15	balance ^a			
C	5	25 < CO ₂ ≤ 50	10 < O ₂ ≤ 15	balance ^a			
	1	100					
R	2	balance	0,5 ≤ O ₂ ≤ 30				
	1			balance ^a		0,5 ≤ H ₂ ≤ 15	
N	2			balance ^a		15 < H ₂ ≤ 50	
	1						100
	2			balance ^a			0,5 ≤ N ₂ ≤ 5
	3			balance ^a			5 < N ₂ ≤ 50
	4			balance ^a		0,5 ≤ H ₂ ≤ 10	0,5 ≤ N ₂ ≤ 5
O	5					0,5 ≤ H ₂ ≤ 50	balance
	1		100				
Z	Gas mixtures containing components not listed, or mixtures outside the composition ranges listed. ^b						

^a For the purpose of this classification, argon may be substituted partially or completely by helium.

^b Two gas mixtures with the same Z-classification may not be interchangeable.

6 Tolerances of mixtures

Mixture tolerances apply to the volumetric percentage of the components in accordance with Table 3.

Table 3 — Mixture tolerances

Component gas nominal concentration %	Allowable tolerance
> 5	± 10 % of the nominal
1 to 5	± 0,5 % absolute
< 1	Not specified in this International Standard

EXAMPLE 1 An addition of 25 % carbon dioxide nominal value shall not vary by more than ± 2,5 % (from 22,5 % to 27,5 %).

EXAMPLE 2 An addition of 2,5 % oxygen shall not vary by more than ± 0,5 % (from 2,0 % to 3,0 %).

7 Purities and dew point

The purity and dew point of gas components and gas mixtures shall meet the requirements of Table 4.

Moisture can be expressed as concentration in ppm (parts per million) or as dew points at 0,101 MPa in °C.

Purities and moisture contents for special gas mixtures are not specified in this International Standard.

8 Testing

Testing of gases and gas mixtures for composition and impurity may be carried out by the manufacturer or supplier using established standards for testing and control (see also Bibliography). The results of the testing shall fulfil the requirements given in Tables 2 and 3.

Any special or additional testing requirements should be agreed between the purchaser and the manufacturer or supplier.

Table 4 — Minimum requirements on purities and moisture contents of gases and gas mixtures

Main groups/gas		Purity % by volume minimum	Dew point at 0,101 MPa °C	Moisture ppm max. volume
I	inert	99,99	– 50	40
M1 ^a	gas mix	99,9	– 50	40
M2 ^a	gas mix	99,9	– 44	80
M3 ^a	gas mix	99,9	– 40	120
C ^a	carbon dioxide	99,8	– 40	120
R	reducing	99,95	– 50	40
N	nitrogen	99,9	– 50	40
O	oxygen	99,5	– 50	40
NOTE For certain applications a higher purity and/or lower dew point may be recommended to avoid possible oxidation and contamination				
^a Nitrogen: 1 000 ppm maximum.				

9 Retesting

If any test fails to meet the requirement, that test shall be repeated twice. The results of both retests shall meet the requirement. Samples for the retest may be taken from the original container or from a new container. Retests need only be for those specific elements that failed to meet their test requirement. If the results of one or both retests fail to meet the requirement, the gas under test shall be considered as not meeting the requirements of this specification for that classification and designation.

In the event that, during preparation or after completion of any test, it is clearly determined that prescribed or proper procedures were not followed in preparing the sample(s) or in conducting the tests, the test shall be considered invalid, without regard to whether the test was actually completed, or whether the test results met, or failed to meet, the requirement. That test shall be repeated following proper prescribed procedures. In this case, the requirement for doubling the number of test samples does not apply.

10 Marking

The outside of each container (see 3.4) shall be clearly marked with at least the following information:

- a) name of manufacturer or supplier;
- b) trade name;
- c) designation in accordance with this International Standard (see 5.2);
- d) health and safety warnings in accordance with local, national and regional standards and regulations as required.

Bibliography

- [1] ASTM E260, *Standard Practice for Packed Column Gas Chromatography*
- [2] JIS Z 3253, *Shielding gases for arc welding and plasma arc cutting*
- [3] ISO 4063, *Welding and allied processes — Nomenclature of processes and reference numbers*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.