

# Binders for paints and varnishes — Determination of the viscosity of industrial cellulose nitrate solutions and classifications of such solutions

ICS 87.060.20

## National foreword

This British Standard is the UK implementation of EN ISO 14446:2010. It is identical to ISO 14446:1999. It supersedes BS 6782-11:1999, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/3, Paint media and related products.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard, having been prepared under the direction of the Sector Committee for Materials and Chemicals, was published under the authority of the Standards Committee and comes into effect on 15 September 1999

© BSI 2011

ISBN 978 0 580 71428 3

### Amendments/corrigenda issued since publication

Date	Comments
28 February 2011	This corrigendum renumbers BS 6782-11:1999 as BS EN ISO 14446:2010.

EUROPEAN STANDARD

EN ISO 14446

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2010

ICS 87.060.20; 83.080.20

English Version

## Binders for paints and varnishes - Determination of the viscosity of industrial cellulose nitrate solutions and classification of such solutions (ISO 14446:1999)

Liants pour peintures et vernis - Détermination de la viscosité des solutions de nitrate de cellulose industrielles et classification de ces solutions (ISO 14446:1999)

Bindemittel für Beschichtungsstoffe - Bestimmung der Viskosität technischer Cellulosenitrat-Lösungen und Einteilung solcher Lösungen (ISO 14446:1999)

This European Standard was approved by CEN on 16 October 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

## **Foreword**

The text of ISO 14446:1999 has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 14446:2010 by Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2011, and conflicting national standards shall be withdrawn at the latest by May 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

### **Endorsement notice**

The text of ISO 14446:1999 has been approved by CEN as a EN ISO 14446:2010 without any modification.

# Binders for paints and varnishes — Determination of the viscosity of industrial cellulose nitrate solutions and classification of such solutions

## 1 Scope

This International Standard specifies a method of determining the viscosity of industrial cellulose nitrate, usually referred to as nitrocellulose, the nitrogen content of which can vary between 10,7 % by mass and 12,6 % by mass, depending on the type.

It also gives a classification system for industrial cellulose nitrate solutions (see annex A) which is based on viscosity measurements made using the method. The use of a standard procedure results in "standard" types and avoids classification differences which could be caused by the fact that there are many ways of determining viscosity and a wide variety of solvents available.

## 2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 760:1978, *Determination of water — Karl Fischer method (General method)*.

ISO 2811-1:1997, *Paints and varnishes — Determination of density — Part 1: Pyknometer method*.

ISO 2811-2:1997, *Paints and varnishes — Determination of density — Part 2: Immersed body (plummet) method*.

ISO 2811-3:1997, *Paints and varnishes — Determination of density — Part 3: Oscillation method*.

ISO 12058-1:1997, *Plastics — Determination of viscosity using a falling-ball viscometer — Part 1: Inclined-tube method*.

ISO 15528:—<sup>1)</sup>, *Paints and varnishes — Sampling*.

## 3 Principle

The cellulose nitrate is dissolved in an acetone/water mixture at a concentration which will depend on the type of cellulose nitrate concerned. The density of the solution is determined using a pyknometer and the viscosity using a Höppler falling-ball viscometer. The dynamic viscosity of the solution is calculated from the results obtained.

---

<sup>1)</sup> To be published. (Revision of ISO 842:1984 and ISO 1512:1991)

## 4 Apparatus and reagents

Ordinary laboratory apparatus and glassware, together with the following:

- 4.1 **Falling-ball viscometer**, as specified in ISO 12058-1, using ball No. 4.
- 4.2 **Thermostat**, capable of maintaining the water jacket round the falling-ball viscometer at  $(20 \pm 0,1)$  °C.
- 4.3 **Stopwatch**, accurate to  $\pm 0,1$  s.
- 4.4 **Drying oven**, capable of being maintained at  $(65 \pm 2)$  °C, with a back-up safety system to ensure that this temperature is not exceeded.
- 4.5 **Analytical balance**, capable of weighing to 1 mg.
- 4.6 **Bottle-shaking or rolling device**.
- 4.7 **Pyknometer**, capacity 25 ml, as specified in ISO 2811-1, or **plummet**, as specified in ISO 2811-2, or **oscillator**, as specified in ISO 2811-3.
- 4.8 **Weighing bottle**, capacity 250 ml, with a wide mouth and stopper.
- 4.9 **Watch glass** or **Petri dish**.
- 4.10 **Acetone/water mixture**, containing  $(5 \pm 0,2)$  % by mass of water. The water content of the mixture shall be checked using the method described in ISO 760.

## 5 Sampling and preparation of samples for testing

**WARNING** — For safety reasons, cellulose nitrate should always be moistened with water or a suitable organic liquid, normally ethanol, isopropanol or butanol.

- 5.1 Take a representative sample of the cellulose nitrate to be tested, as described in ISO 15528.
- 5.2 Spread the moist sample in a thin layer on a watch glass or Petri dish and heat it in an air oven at  $(65 \pm 2)$  °C to constant mass. This is reached when the results of two weighings made at an interval of 30 min do not differ by more than 1 mg.

For safety reasons, the door of the oven shall be left slightly open.

- 5.3 Allow the dried cellulose nitrate to cool in a desiccator and keep it in the desiccator until needed for weighing out the test portion.

NOTE Cellulose nitrate is hygroscopic.

Do not store dried cellulose nitrate. Any dried cellulose nitrate not used shall be moistened again.

## 6 Preparation of apparatus for testing

- 6.1 Clean the viscometer, the pyknometer or plummet or oscillator and the weighing bottle with acetone before use and dry in a stream of clean, dry air.

Repeat this cleaning procedure before every determination.

- 6.2 Determine the viscometer constant  $K$  (see ISO 12058-1) at a temperature of  $(20 \pm 0,1)$  °C with a certified reference liquid. Repeat this determination from time to time.

## 7 Procedure

**7.1** Weigh into the weighing bottle, to the nearest 1 mg, an amount of the dried cellulose nitrate sufficient for the determination of the dynamic viscosity and the density. If the type of cellulose nitrate in the sample is known, add the quantity of acetone necessary to give the concentration required for that particular type of cellulose nitrate (see Table A.1) and stopper the bottle. If the type of cellulose nitrate is not known, make an educated guess as to the amount of acetone necessary.

**7.2** Shake or roll the bottle for 6 h at a temperature of  $(20 \pm 5)$  °C to dissolve the cellulose nitrate. If the cellulose nitrate is not completely dissolved after this time, discard the solution.

**7.3** Determine immediately, to the nearest 0,1 s, the time of fall using the falling-ball viscometer method described in ISO 12058-1 four times at a temperature of  $(20 \pm 0,1)$  °C using ball No. 4.

The times of fall shall not differ by more than 0,5 s.

**7.4** Determine from another portion of the test solution the density with a pycnometer, using the method described in ISO 2811-1, or a plummet, using the method described in ISO 2811-2, or an oscillator, using the method described in ISO 2811-3.

**7.5** If the type of cellulose nitrate in the sample is not known, carry out two further determinations using test solutions of concentrations which will give viscosities successively closer to  $(400 \pm 25)$  mPa·s.

## 8 Expression of results

**8.1** The dynamic viscosity  $\eta$ , in mPa·s, is given by the following equation:

$$\eta = K(\rho_1 - \rho_2) \times t$$

where

$K$  is the viscometer constant, in mPa·s·cm<sup>3</sup>/(g s) (see ISO 12058-1:1997, Table 1);

$\rho_1$  is the density, in g/cm<sup>3</sup>, of the ball;

$\rho_2$  is the density, in g/cm<sup>3</sup>, of the cellulose nitrate solution;

$t$  is the time of fall, in s, of the ball.

**8.2** To determine the type of cellulose nitrate in a sample in which the type is not known, plot a curve of concentration versus viscosity for the three determinations carried out (see 7.5) and read off the concentration of the solution having a viscosity of  $(400 \pm 25)$  mPa·s. Knowledge of the N<sub>2</sub> content will enable the designation to be read from Table A.1.

## 9 Precision

The following precision data have been taken from ISO 12058-1.

### 9.1 Repeatability ( $r$ )

The value below which the absolute difference between two single test results, each the mean of duplicates, obtained on identical material by one operator in one laboratory within a short interval of time using the standardized test method, may be expected to lie with a 95 % probability is 0,5 %.

## **9.2 Reproducibility (*R*)**

The value below which the absolute difference between two test results, each the mean of duplicates, obtained on identical material by operators in different laboratories using the standardized test method, may be expected to lie with a 95 % probability is 2 %.

## **10 Test report**

The test report shall contain at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this International Standard (ISO 14446);
- c) the concentration of cellulose nitrate in the test solution, in % by mass;
- d) the result of the test, as indicated in clause 8;
- e) details of any incident which may have affected the result;
- f) any deviation from the test method specified;
- g) the date of the test.



## Annex A (normative)

### Classification system for industrial cellulose nitrate

The classification system for industrial cellulose nitrate comprises two elements (see Table A.1):

- a number indicating the concentration of the solution that is required to give a viscosity of  $(400 \pm 25)$  mPa·s, followed by
- a letter identifying the solvent in which it is soluble (corresponding to the  $N_2$  content), i.e.
  - E in the case of an ester-soluble grade ( $N_2$  content about 11,8 % to 12,3 %),
  - M in the case of a medium-soluble grade ( $N_2$  content about 11,3 % to 11,8 %),
  - A in the case of an alcohol-soluble grade ( $N_2$  content about 10,7 % to 11,3 %).

Since solutions of cellulose nitrate are non-Newtonian in behaviour, the results of viscosity measurements on solutions of different types of cellulose nitrate are only comparable if they have been made within the same restricted viscosity range, as well as at the same shear rate.

The viscosity range  $(400 \pm 25)$  mPa·s has been chosen since solutions having a viscosity within this range are convenient to prepare, they require only relatively small quantities of cellulose nitrate and their concentrations correspond to those used in many practical applications.

The Höppler falling-ball viscometer is used as a convenient way of determining the viscosity.

All measurements are made in solutions prepared using as solvent a mixture of 95 % by mass of acetone plus 5 % by mass of water.

**EXAMPLE** An ester-soluble cellulose nitrate which, when dissolved in the above-mentioned solvent mixture at a concentration of 24 % by mass, gives a viscosity of  $(400 \pm 25)$  mPa·s is designated type 24E.

A dynamic viscosity other than  $(400 \pm 25)$  mPa·s may be agreed between the interested parties, but shall be reported in the test report.

Table A.1 — Classification of cellulose nitrate solutions by the concentration of the test solution that gives a viscosity of  $(400 \pm 25)$  mPa·s

Concentration of test solution % by mass <sup>a</sup>	Classification by type <sup>b</sup>		
	Soluble in esters	Medium-soluble <sup>c</sup>	Soluble in alcohols
3			
4	Type 4E		
5			
6			
7	Type 7E		
8	Type 8E		
9	Type 9E		
10			
11			
12	Type 12E	Type 12M	
13			
14		Type 14M	
15	Type 15E		Type 15A
16		Type 16M	
17		Type 17M	
18		Type 18M	
19		Type 19M	
20			
21	Type 21E	Type 21M	
22	Type 22E		
23			Type 23A
24	Type 24E	Type 24M	
25			
26		Type 26M	
27	Type 27E	Type 27M	Type 27A
28	Type 28E		
29		Type 29M	
30			Type 30A
31			
32	Type 32E	Type 32M	
33			
34	Type 34E	Type 34M	
35			
36		Type 36M	
37			
38	Type 38E		

<sup>a</sup> Of dry cellulose nitrate.

<sup>b</sup> The designations listed are examples of typical types and do not exclude additional types.

<sup>c</sup> Medium-soluble cellulose nitrate is normally used in printing inks and for coating of cellophane.



---

## BSI - British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001 Email: [orders@bsigroup.com](mailto:orders@bsigroup.com) You may also buy directly using a debit/credit card from the BSI Shop on the Website <http://www.bsigroup.com/shop>

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact Information Centre. Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048 Email: [info@bsigroup.com](mailto:info@bsigroup.com)

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001 Email: [membership@bsigroup.com](mailto:membership@bsigroup.com)

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsigroup.com/BSOL>

Further information about BSI is available on the BSI website at <http://www.bsigroup.com>

### Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright and Licensing Manager. Tel: +44 (0)20 8996 7070 Email: [copyright@bsigroup.com](mailto:copyright@bsigroup.com)