

BS EN ISO 14920:2015



BSI Standards Publication

Thermal spraying — Spraying and fusing of self-fluxing alloys

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 14920:2015. It supersedes BS EN ISO 14920:1999 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/40, Thermal spraying and thermally sprayed coatings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015. Published by BSI Standards Limited 2015

ISBN 978 0 580 79715 6

ICS 25.220.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2015.

Amendments issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN ISO 14920

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2015

ICS 25.220.20

Supersedes EN ISO 14920:1999

English Version

Thermal spraying - Spraying and fusing of self-fluxing alloys (ISO 14920:2015)

Projection thermique - Projection et fusion d'alliages
autofondants (ISO 14920:2015)

Thermisches Spritzen - Spritzen und Einschmelzen von
selbstfließenden Legierungen (ISO 14920:2015)

This European Standard was approved by CEN on 18 October 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 14920:2015) has been prepared by Technical Committee CEN/TC 240 "Thermal spraying and thermally sprayed coatings" the secretariat of which is held by DIN, in collaboration with Technical Committee ISO/TC 107 "Metallic and other inorganic coatings".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2015, and conflicting national standards shall be withdrawn at the latest by July 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 14920:1999.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 14920:2015 has been approved by CEN as EN ISO 14920:2015 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Influence on the substrate and design	1
3.1 Substrate metal.....	1
3.2 Design.....	1
4 Spray material of the self-fluxing alloy	2
4.1 Selection.....	2
4.2 Composition.....	2
5 Preparation of the component	2
5.1 General.....	2
5.2 Methods of surface preparation.....	3
5.3 Cleanliness.....	3
6 Spray and fusion process	3
6.1 Spraying with simultaneous fusion.....	3
6.1.1 Procedure.....	3
6.1.2 Particle size and particle size range of the powder particles.....	3
6.1.3 Coating thickness.....	3
6.2 Spraying with subsequent fusion.....	4
6.2.1 Procedure.....	4
6.2.2 Particle size and particle size range of the powder particles.....	4
6.2.3 Coating thickness.....	4
6.3 Spraying technique — Procedure.....	4
6.3.1 General.....	4
6.3.2 Preheating.....	4
6.3.3 Spraying.....	4
6.3.4 Fusing the deposit.....	5
6.3.5 Cooling.....	5
7 Final machining	5
8 Hardness testing	5
8.1 General.....	5
8.2 Standard hardness test.....	6
Annex A (informative) Reference values for the expected hardness of the fused coating	7
Bibliography	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. www.iso.org/directives

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. www.iso.org/patents

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword - Supplementary information](#)

ISO 14920 was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 240, *Thermal spraying and thermally sprayed coatings*, in collaboration with Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 14920:1999), which has been technically revised.

Introduction

Requests for official interpretations of any aspect of this standard should be directed to the secretariat of ISO/TC 107/WG 1 via your national standards body, a complete listing which can be found at www.iso.org.

Thermal spraying — Spraying and fusing of self-fluxing alloys

1 Scope

This International standard defines the procedure for thermal spraying of self-fluxing alloys that are simultaneously or subsequently fused to create a homogeneous, diffusion bonded coating.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11124-1, *Preparation of steel substrates before application of paints and related products — Specifications for metallic blast-cleaning abrasives — Part 1: General introduction and classification*

ISO 11126-1, *Preparation of steel substrates before application of paints and related products — Specifications for non-metallic blast-cleaning abrasives — Part 1: General introduction and classification*

ISO 12679, *Thermal spraying — Recommendations for thermal spraying*

ISO 14924, *Thermal spraying — Post-treatment and finishing of thermally sprayed coatings*

EN 1274, *Thermal spraying — Powders — Composition, technical supply conditions*

EN 13507, *Thermal spraying — Pre-treatment of surfaces of metallic parts and components for thermal spraying*

3 Influence on the substrate and design

3.1 Substrate metal

Due to the heat transfer into the substrate metal when fusing the coating, in order to bond the coating with the substrate metal by diffusion, the possible effects of such heating on the substrate metal shall be considered:

- a) scaling;
- b) the need to stress relieve;
- c) an irreversible transformation of the mechanical and/or metallurgical properties.

Martensitic steels are susceptible to stress cracking and alloys containing significant amounts of C, Al, Ti, Mg, S, sulfides, P, and nitrogen can create porosity in the coating and may render the substrate metal liable to stress cracking.

3.2 Design

The preparation of the component for spraying and fusing of a coating usually includes a reduction of the design dimensions, if pre-machining is applied. Consideration shall be given to the effect of such a reduction on the loading of the component, as the coating does not contribute to the strength of the component. Consideration shall be given, to the fact that the sprayed and fused coating will have differing physical properties to the substrate material.

The fatigue strength, the deformation resistance, and other properties of the component can be affected by the application of the coating.

Due to the heat input during fusing unacceptable deformation of the component may occur. Measures to prevent distortion or deformation can be used, such as, to erect or hang the parts along their centre-of-gravity axis or by the use of supporting jigs.

4 Spray material of the self-fluxing alloy

4.1 Selection

The properties of the coating are determined by the selection of the spray material and the spray and fuse procedure, e.g.:

- a) hardness;
- b) resistance to wear and/or corrosion;
- c) machinability;
- d) suitability for the foreseen application.

4.2 Composition

The chemical composition of the spray material and the structure of the coating determine its metallurgical and technological properties as well as its machinability.

For substrate alloys, which can create a martensitic structure, see [6.3.5](#).

[Table A.1](#), contains reference values for the expected hardness of the fused coating.

5 Preparation of the component

5.1 General

5.1.1 All components to be coated shall be free from surface contamination such as oil, grease, rust and other dirt. Particular attention shall be paid to porous components, because oil and grease can exude out of the pores during the preheating or coating process.

5.1.2 Any prior surface treatments, for example nitriding, galvanic or other protective coatings shall be removed before the preparation of the surface to be coated.

5.1.3 If the area to be coated and the bordering areas of the component are to be machined then this preparation shall be suitable for the coating process. Recommendations for suitable designs are given in ISO 12679.

Where the coating is required to terminate at a point other than the end or edge of the component, the depression shall be machined to provide an angle of 30° to 40° at each end, blending smoothly with the adjoining surface. Alternatively, if the coating can be continued around a chamfered and/or rounded edge, the risk of spalling of the coating will be reduced.

Where the coating shall finish to a square edge, the component shall be left longer than the proposed finished overall size and the excess shall be machined off after finishing the coating process.

5.2 Methods of surface preparation

5.2.1 Surface preparation shall be carried out according to EN 13507.

The surface to be coated should be grit blasted using suitable angular grit according to ISO 11124-1 or ISO 11126-1.

NOTE The choice of the grit blasting material can influence the bond strength of the coating.

5.2.2 The grit blasting operation shall be confined to the area to be coated. The adjacent areas shall be masked, so that the surfaces will not be damaged and will not be coated later on. The masking material shall resist the grit blasting and shall not contaminate the prepared surface to be sprayed.

5.2.3 Masking material, intended to prevent the adherence of spray particles, shall be able to withstand the preheating and spray particle temperatures.

5.2.4 Drilled holes and other orifices, which are required not to be grit blasted and coated, shall be plugged. Plugs of steel or rubber are recommended for this purpose, they shall be shaped and positioned in such a manner as not to mask any part of the surface to be prepared. After grit blasting the plugs shall be replaced with pieces of carbon suitably shaped to prevent ingress of the coating material. They shall protrude with their top surface to be caught for subsequent machining.

5.3 Cleanliness

After preparation the surface to be coated shall not be contaminated with oil, grease, water or fingerprints. In the case of contamination the surface shall be completely re-prepared.

6 Spray and fusion process

6.1 Spraying with simultaneous fusion

6.1.1 Procedure

This operation of spraying with simultaneous fusion is carried out manually using an oxy/acetylene torch, which is fitted with a hopper for the spray powder.

A suitable self-fluxing powder is fed from the hopper into the gas stream and heated by the flame, accelerated and sprayed to the component, where it is simultaneously fused to the substrate metal. Using this continuous process a coating is created, whose properties depend on the self-fluxing powder used.

6.1.2 Particle size and particle size range of the powder particles

The suitable grain size and the particle size range depend on the design of the powder feed system. In order to avoid powder feed restrictions and blockages the powder size range recommended by the torch supplier shall be used.

6.1.3 Coating thickness

A limitation on deposit thickness is dependent on the chosen alloy, the required coating quality, and the acceptable residual stresses, which will increase with deposit thickness.

NOTE Spraying and fusing of thicker coatings demands higher skill from the executing operator.

6.2 Spraying with subsequent fusion

6.2.1 Procedure

For spraying and subsequent fusion the procedures spraying and fusion are separated. Both procedures can be manual or mechanized. Usually, spraying is carried out using powder flame spraying (PFS).

A suitable self-fluxing powder is transported by the carrier gas from the powder feeder into the fuel gas oxygen jet, heated and accelerated by the flame and sprayed onto the component until the desired coating thickness is achieved.

Fusion of the deposit is a separate operation, which shall be carried out as soon as possible after spraying using one of the following methods:

- a) manually, using an oxy/acetylene torch with suitable capacity;
- b) by inductive heating;
- c) by fusion in a furnace under vacuum or in an inert gas atmosphere;
- d) with a laser beam;
- e) or by other heating processes.

6.2.2 Particle size and particle size range of the powder particles

The suitable grain size and the particle size range depend on the design of the powder feed system. In order to avoid powder feed restrictions and blockages the grain size and the powder size range recommended by the spraying equipment supplier shall be used.

6.2.3 Coating thickness

A limitation on deposit thickness is dependent on the chosen alloy, the required coating quality, and the acceptable residual stresses. Usually, the coating thickness is limited to 1,6 mm with 1 mm being preferred. The deposit should be approximately 25 % thicker in the as sprayed state to allow for shrinkage during fusion.

6.3 Spraying technique — Procedure

6.3.1 General

The thermal spraying of the coating shall be started immediately after the surface preparation and before any visible deterioration of the surface has set in (moisture, coat, oxidation, etc.).

6.3.2 Preheating

The surface to be sprayed shall be pre-heated immediately before spraying. The pre-heating temperature depends upon the composition of the substrate. When preheating contamination or local overheating of the surface shall be avoided.

6.3.3 Spraying

Spraying shall be continuous until the coating reaches the required thickness including the shrinkage allowance of 20 % to 25%. After spraying there shall be no visible evidence of defects, like cracks, lifting of the deposit, blisters, spalling on edges or at the end of the coating. If defects are detected the sprayed coating shall be removed completely and the preparation and the thermal spraying shall be repeated.

6.3.4 Fusing the deposit

The deposit shall be heated to a temperature within the melting range of the selected self-fluxing alloy and fused. The heating shall be such that the interface between the self-fluxing alloy and the substrate reaches the fusing temperature to ensure a complete melting of the coating and rapid diffusion.

Fusing can be performed using an oxy-acetylene torch or mechanized by induction heating, laser beam or in a vacuum or shielding gas furnace.

The heating rate and the duration within the temperature range depend upon the composition of the coating alloy and of the size and complexity of the component. Prolonged heating within the fusion range shall be avoided to prevent excessive diffusion between the coating and the substrate and to avoid deformation of the component and/or of the coating.

When the correct fusion temperature is reached it is indicated by the appearance of the coating, which exhibits a marked increase in reflectivity, generally known as a „wet shine“, and is visible when employing manual or partly mechanized fusion. The fusion area of the sprayed surface shall exhibit this “wet shine”. If heated by torch or induction coil the heat source should be moved progressively over the surface of the part to continue this “wet shine”. Usually when melting in a furnace this „wet shine“ is not visible. In case of doubt the suitable fusion temperature shall be determined by tests. The appearance of a local hot spot during fusion indicates a local coating or bonding defect. In this case the coating shall be rejected.

6.3.5 Cooling

After fusing, to avoid undue stresses, creating cracks and/or distortion, cooling shall be retarded. This can be achieved by packing the component in an insulating material or by a controlled cooling in a furnace.

If substrates are coated, which are subjected to a martensitic change when cooling down from the fusion temperature specialized cooling procedures will be necessary. A subsequent heat treatment may be necessary to restore the technological and mechanical properties of the substrate metal.

7 Final machining

Machinability depends upon the properties of the self-fluxing alloy. Information regarding machining of fused coatings is given in ISO 14924.

If the recommendations in ISO 14924 are not sufficient to solve the machining task advice from a manufacturer of machining tools should be sought.

Because adjacent areas or the whole component will also be brought to high temperature to fuse the coating, the coating and fusion process and further heat treatments, if necessary, should be completed before carrying out the final machining of other areas.

8 Hardness testing

8.1 General

The spray material is often selected with respect to the achievable hardness and less according to the chemical composition.

EN 1274 contains several spray powders for such applications. [Table A.1](#) shows informative examples of expected hardness values. If necessary, a different alloy not listed in EN 1274 may be agreed upon between the customer and the supplier, which meets the required hardness and the valid supply specifications. In case of doubt test coatings shall be produced to meet the defined hardness range using the selected powder.

8.2 Standard hardness test

Test piece properties:

- 50 mm × 50 mm × 6,0 mm to 6,5 mm made out of unalloyed carbon steel.

Test piece preparation:

- Edges of test piece should have a 2 mm chamfer.

The powder sample shall be representative of chosen batch.

Spray technique:

- Use spray torch with foreseen parameter setting for the application and spray a deposit of uniform thickness of 1,0 mm to 2,0 mm.

Fusing technique:

- Fusing shall be carried out using the expected procedure for the application (see [6.3.4](#)).

Cooling:

- The test piece shall be cooled by packing in insulation material, by controlled cooling in a furnace or in still air to below 500 °C.

Preparation for hardness test:

- Level underside of the test piece first by grinding or finishing (test piece can be deformed);
- Machine test face to a smooth and even finish to get a test area of about (20 × 20) mm (grinding or milling with hard metal tool), so that a minimum coating thickness of 1 mm remains.

A minimum of 7 readings, 8 mm apart, shall be taken. Discard the highest and lowest readings, and take an average of the remaining 5. The mean value and/or the range can be taken as a requirement into the supply specification.

Annex A (informative)

Reference values for the expected hardness of the fused coating

Table A.1 — Reference values for the expected hardness of the fused coating

Spray material according to EN 1274		Hardness of the coating HRC
Abbreviation	Chemical composition	
2.6	NiCrBSi 83 10	30 to 40
2.7	NiCrBSi 85 8	
2.8	NiCrBSi 80 11	40 to 50
2.10	NiCrBSi 74 14	50 to 55
2.9	NiCrBSi 74 15	55 to 60
2.14	NiCrCuMoBSi 67 17 3 3	60 to 65
2.19	CoCrNiWBSi 53 20 13 7	45 to 50
2.20	CoCrNiWBSi 47 19 15 13	48 to 52

Bibliography

- [1] ISO 6508-1, *Metallic materials — Rockwell hardness test — Part 1: Test method*¹⁾
- [2] ISO 10474, *Steel and steel products — Inspection documents*

1) To be published (Revision of ISO 6508-1:2005).

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™