

# Plastics — Poly(vinyl alcohol) (PVAL) materials —

## Part 2: Determination of properties

The European Standard EN ISO 15023-2:2006 has the status of a British Standard

ICS 83.080.20

## National foreword

This British Standard is the official English language version of EN ISO 15023-2:2006. It is identical with ISO 15023-2:2003.

The UK participation in its preparation was entrusted to Technical Committee PRI/82, Thermoplastic materials, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

### Cross-references

The British Standards which implement international publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 7 May 2003

### Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, the ISO title page, pages iv to vi, pages 1 to 17 and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

### Amendments issued since publication

Amd. No.	Date	Comments
16031	June 2006	Renumbers BS ISO 15023-2:2003 as BS EN ISO 15023-2:2006.

ICS 83.080.20

English Version

Plastics - Poly(vinyl alcohol) (PVAL) materials - Part 2:  
Determination of properties (ISO 15023-2:2003)

Plastiques - Matériaux en poly(alcool de vinyle) (PVAL) -  
Partie 2: Détermination des propriétés (ISO 15023-2:2003)

Kunststoffe - Polyvinylalkohol (PVAL)-Formmassen - Teil 2:  
Bestimmung von Eigenschaften (ISO 15023-2:2003)

This European Standard was approved by CEN on 16 March 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

## Foreword

The text of ISO 15023-2:2003 has been prepared by Technical Committee ISO/TC 61 "Plastics" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 15023-2:2006 by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2006, and conflicting national standards shall be withdrawn at the latest by October 2006.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

### Endorsement notice

The text of ISO 15023-2:2003 has been approved by CEN as EN ISO 15023-2:2006 without any modifications.

INTERNATIONAL  
STANDARD

ISO  
15023-2

First edition  
2003-04-15

---

---

**Plastics — Poly(vinyl alcohol) (PVAL)  
materials —**

**Part 2:  
Determination of properties**

*Plastiques — Matériaux en poly(alcool de vinyle) (PVAL) —  
Partie 2: Détermination des propriétés*





<b>Contents</b>	Page
<b>Foreword</b> .....	vi
<b>1 Scope</b> .....	1
<b>2 Normative references</b> .....	1
<b>3 Determination of properties</b> .....	2
<b>Annex A (normative) Determination of volatile-matter content</b> .....	3
<b>Annex B (normative) Determination of sodium acetate content</b> .....	5
<b>Annex C (normative) Calculation of ash</b> .....	8
<b>Annex D (normative) Determination of degree of hydrolysis</b> .....	9
<b>Annex E (normative) Determination of viscosity of 4 % aqueous solution by the Brookfield Test method or the inclined-tube falling-ball method</b> .....	12

## **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 15023-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

ISO 15023 consists of the following parts, under the general title *Plastics — Poly(vinyl alcohol) (PVAL) materials*:

- *Part 1: Designation system and basis for specifications*
- *Part 2: Determination of properties*



# Plastics — Poly(vinyl alcohol) (PVAL) materials —

## Part 2: Determination of properties

### 1 Scope

This part of ISO 15023 specifies the methods to be used in determining the properties of poly(vinyl alcohol), which is normally prepared by hydrolysis of poly(vinyl acetate) and whose composition comprises vinyl alcohol monomeric units and vinyl acetate monomeric units. This part of ISO 15023 is applicable to poly(vinyl alcohol) with a vinyl alcohol unit content (degree of hydrolysis) from 70 mol % to 100 mol %.

In addition to the designatory properties specified in ISO 15023-1 (degree of hydrolysis and viscosity of an aqueous solution), this part of ISO 15023 includes a number of other properties which are commonly used to specify PVAL materials (see Table 1).

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 976:1996, *Rubber and plastics — Polymer dispersions and rubber latices — Determination of pH*

ISO 6587:1992, *Paper, board and pulps — Determination of conductivity of aqueous extracts*

ISO 8130-1:1992, *Coating powders — Part 1: Determination of particle size distribution by sieving*

ISO 12058-1:1997, *Plastics — Determination of viscosity using a falling-ball viscometer — Part 1: Inclined-tube method*

ISO 15023-1:2001, *Plastics — Poly(vinyl alcohol) (PVAL) materials — Part 1: Designation system and basis for specifications*

### 3 Determination of properties

In the determination of properties and the presentation of results, the standards, methods and special conditions listed in Table 1 shall apply. The properties listed in Table 1 are those appropriate to poly(vinyl alcohol).

**Table 1 — Properties and test conditions**

Property	Method	Unit	Test conditions and supplementary instructions
Volatile-matter content	Annex A	% by mass	105 °C, 3 h
Sodium acetate content	Annex B	% by mass	Titration or conductivity method
Ash	Annex C	% by mass	
Degree of hydrolysis	Annex D	mol %	Titration method
Viscosity of 4 % aqueous solution	Annex E	mPa·s	Rotational or inclined-tube falling-ball viscometer, 20 °C
Particle size distribution	ISO 8130-1	%	
pH of aqueous solution	ISO 976	—	Concentration (4,0 ± 0,2) %

## Annex A (normative)

### Determination of volatile-matter content

#### A.1 Scope

This annex specifies the method to be used for the determination of the volatile-matter content of PVAL.

#### A.2 Principle

The volatile-matter content is calculated from the loss in mass of a specimen heated at 105 °C for 3 h.

#### A.3 Method

##### A.3.1 Apparatus

**A.3.1.1 Constant-temperature oven**, able to maintain a temperature of  $(105 \pm 2)$  °C.

**A.3.1.2 Weighing dish**, shallow, about 60 mm in diameter and 30 mm in height, of glass, aluminium or preferably stainless steel, with a lid.

**A.3.1.3 Balance**, capable of weighing to 0,001 g.

**A.3.1.4 Desiccator**, containing silica gel as a drying agent.

##### A.3.2 Procedure

Carry out the determination in duplicate.

Weigh the dish (A.3.1.2) with its lid to the nearest 0,001 g ( $m_0$ ), after heating it in the oven (A.3.1.1) maintained at  $(105 \pm 2)$  °C for 1 h and cooling it to room temperature in the desiccator (A.3.1.4). Spread about 5 g of resin evenly over the bottom of the dish, replace the lid and weigh to the nearest 0,001 g ( $m_1$ ). Place the assembly in the oven at  $(105 \pm 2)$  °C, remove the lid (leaving it in the oven) and close the oven door. After  $3 \text{ h} \pm 5 \text{ min}$ , remove the assembly from the oven, allow to cool in the desiccator and weigh to the nearest 0,001 g ( $m_2$ ).

#### A.4 Expression of results

Calculate the volatile-matter content  $w_{\text{VM}}$ , as a percentage by mass, from the following equation:

$$w_{\text{VM}} = \frac{m_1 - m_2}{m_1 - m_0} \times 100$$

where

$m_0$  is the mass, in g, of the dish;

$m_1$  is the initial mass, in g, of the dish plus test portion;

$m_2$  is the mass, in g, of the dish plus test portion after heating.

Calculate the mean of the results of the two determinations and express the final result to two places of decimals.

### **A.5 Test report**

The test report shall include the following particulars:

- a) a reference to this part of ISO 15023;
- b) all details necessary for complete identification of the material tested;
- c) the volatile-matter content, calculated as the arithmetic mean of the two determinations;
- d) the individual results of the two determinations;
- e) the date of the test.

## Annex B (normative)

### Determination of sodium acetate content

#### B.1 Scope

This annex specifies the method to be used for the determination of the sodium acetate content of PVAL. The content can be determined either by a titration method or by a conductivity method. Additives can interfere with the determination, and these methods may not be suitable for PVAL containing them.

#### B.2 Principle

##### B.2.1 Titration method

The sample is dissolved in water and the solution titrated with hydrochloric acid using methyl orange as indicator. The sodium acetate content is calculated as a percentage by mass.

##### B.2.2 Conductivity method

The conductivity of an aqueous solution of the sample is measured in a conductometer. The sodium acetate content of the solution is determined by calibrating the conductometer with solutions containing known amounts of sodium acetate.

#### B.3 Titration method

##### B.3.1 Reagents

**B.3.1.1 Hydrochloric acid**, 0,1 mol/l.

**B.3.1.2 Methyl orange indicator**, 1 g/l solution in ethanol, or **mixed methylene blue/methyl yellow indicator**, prepared by mixing equal parts of a 0,1 % solution of methylene blue in reagent-grade ethanol with a 0,1 % solution of methyl yellow in reagent-grade ethanol.

##### B.3.2 Apparatus

**B.3.2.1 Conical flask**, 300 ml, with ground-glass stopper.

**B.3.2.2 Cylinder**, 200 ml, graduated in 2 ml.

**B.3.2.3 Burette**, 50 ml, graduated in 0,1 ml.

##### B.3.3 Procedure

Carry out the determination in duplicate.

Weigh about 5 g of sample to the nearest 0,001 g into the conical flask (B.3.2.1), add about 150 ml of water and dissolve by heating.

A sample with a low degree of hydrolysis may sometimes cause the solution to become turbid. If this occurs, cool the solution slowly while stirring gently. Alternatively, a 3:1 water/methanol mixture may be used.

After dissolution, cool and titrate with 0,1 mol/l hydrochloric acid to an end point where the solution turns from orange-yellow to red if methyl orange is used as indicator or from green to light purple if methylene blue/methyl yellow is used.

Carry out a blank test separately.

### **B.3.4 Expression of results**

Calculate the sodium acetate content  $w_{\text{NaAc}}$ , as a percentage by mass, from the following equation:

$$w_{\text{NaAc}} = \frac{(V_1 - V_0) \times c \times 0,082\ 03}{m} \times 100$$

where

$V_1$  is the volume, in ml, of hydrochloric acid required for the test solution;

$V_0$  is the volume, in ml, of hydrochloric acid required for the blank;

$c$  is the actual concentration, in mol/l, of the hydrochloric acid;

0,082 03 is the molecular mass of sodium acetate divided by 1 000;

$m$  is the mass, in g, of the test portion.

Calculate the mean of the results of the two determinations and express the final result to two places of decimals.

## **B.4 Conductivity method**

### **B.4.1 Reagent**

**B.4.1.1 Sodium acetate**, reagent grade.

### **B.4.2 Apparatus**

**B.4.2.1 Conical flask**, 100 ml, with ground-glass stopper.

**B.4.2.2 Cylinder**, 100 ml, graduated in 1 ml.

**B.4.2.3 Conductivity meter**, as specified in ISO 6587.

**B.4.2.4 Thermometer**, graduated in 0,1 °C.

**B.4.2.5 Volumetric flask**, 100 ml, with ground-glass stopper.

### **B.4.3 Procedure**

Carry out the determination in duplicate.

Weigh 0,5 g of sample to the nearest 0,001 g into a conical flask, add about 50 ml of water and dissolve by heating.

A sample with a low degree of hydrolysis may sometimes cause the solution to become turbid. If this occurs, cool the solution slowly while stirring gently.

Transfer the solution to a 100 ml volumetric flask and make up to the mark with water.

Transfer about 50 ml of the aqueous solution in the volumetric flask to the measuring cell of the conductivity meter. Measure the conductivity at  $30\text{ }^{\circ}\text{C} \pm 0,1\text{ }^{\circ}\text{C}$ .

#### B.4.4 Calibration curve

Prepare the calibration curve as follows:

- Prepare four or five aqueous sodium acetate solutions covering a suitable range of concentrations and measure their conductivities.
- Prepare the calibration curve by plotting the conductivity values against the corresponding sodium acetate concentrations (g/100 ml).

#### B.4.5 Expression of results

Calculate the sodium acetate content  $w_{\text{NaAc}}$ , as a percentage by mass, from the following equation:

$$w_{\text{NaAc}} = \frac{\rho_{\text{NaAc}}}{m} \times 100$$

where

$\rho_{\text{NaAc}}$  is the concentration of sodium acetate in the test solution, in g/100 ml, obtained from the calibration curve;

$m$  is the mass, in g, of the test portion.

Calculate the mean of the results of the two determinations and express the final result to two places of decimals.

### B.5 Test report

The test report shall include the following particulars:

- a) a reference to this part of ISO 15023;
- b) all details necessary for complete identification of the material tested;
- c) the sodium acetate content, calculated as the arithmetic mean of the two determinations;
- d) the individual results of the two determinations;
- e) the date of the test.

## Annex D (normative)

### Determination of degree of hydrolysis

#### D.1 Scope

This annex specifies the method to be used for the determination of the degree of hydrolysis of PVAL. The method is intended for PVAL without plasticizers and free of additives, fillers, dyes and any other materials which could interfere with the determination. When they are present, they must be separated by a method agreed between the contracting parties. This method is applicable to PVAL with a nominal degree of hydrolysis from 70 mol % up to 100 mol %.

#### D.2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

##### D.2.1

##### **degree of hydrolysis**

the molar percentage, in mol %, of the vinyl alcohol unit in the poly(vinyl alcohol), as given by the equation:

$$\text{Degree of hydrolysis} = \frac{\text{Vinyl alcohol unit content}}{\text{Vinyl alcohol unit content} + \text{Vinyl acetate unit content}} \times 100$$

#### D.3 Principle

The degree of hydrolysis is obtained by determining the residual acetic acid group content, in mol %, by titration with sodium hydroxide and subtracting the result from 100 mol %.

#### D.4 Reagents

- D.4.1 **Sodium hydroxide solution**, 0,1 mol/l.
- D.4.2 **Sodium hydroxide solution**, 0,5 mol/l.
- D.4.3 **Sulfuric acid or hydrochloric acid**, 0,1 mol/l.
- D.4.4 **Sulfuric acid or hydrochloric acid**, 0,5 mol/l.
- D.4.5 **Phenolphthalein solution**, 10 g/l, in 90 % (by volume) ethyl alcohol.



## Annex D (normative)

### Determination of degree of hydrolysis

#### D.1 Scope

This annex specifies the method to be used for the determination of the degree of hydrolysis of PVAL. The method is intended for PVAL without plasticizers and free of additives, fillers, dyes and any other materials which could interfere with the determination. When they are present, they must be separated by a method agreed between the contracting parties. This method is applicable to PVAL with a nominal degree of hydrolysis from 70 mol % up to 100 mol %.

#### D.2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

##### D.2.1

##### **degree of hydrolysis**

the molar percentage, in mol %, of the vinyl alcohol unit in the poly(vinyl alcohol), as given by the equation:

$$\text{Degree of hydrolysis} = \frac{\text{Vinyl alcohol unit content}}{\text{Vinyl alcohol unit content} + \text{Vinyl acetate unit content}} \times 100$$

#### D.3 Principle

The degree of hydrolysis is obtained by determining the residual acetic acid group content, in mol %, by titration with sodium hydroxide and subtracting the result from 100 mol %.

#### D.4 Reagents

**D.4.1 Sodium hydroxide solution**, 0,1 mol/l.

**D.4.2 Sodium hydroxide solution**, 0,5 mol/l.

**D.4.3 Sulfuric acid or hydrochloric acid**, 0,1 mol/l.

**D.4.4 Sulfuric acid or hydrochloric acid**, 0,5 mol/l.

**D.4.5 Phenolphthalein solution**, 10 g/l, in 90 % (by volume) ethyl alcohol.

## D.5 Apparatus

- D.5.1 Conical flask**, 300 ml, with ground-glass stopper.
- D.5.2 Burettes**, 25 ml, graduated in 0,1 ml.
- D.5.3 Measuring cylinder**, 100 ml, graduated in 1 ml.
- D.5.4 Dissolving apparatus**, capable of heating with stirring.
- D.5.5 Balance**, accurate to 0,001 g.

## D.6 Procedure

- D.6.1** Carry out the determination in duplicate.
- D.6.2** Weigh, to the nearest 0,001 g, a test portion of about the mass specified in Table D.1 into the conical flask (D.5.1).
- D.6.3** Add 100 ml of water and 3 drops of phenolphthalein solution (D.4.5) and heat to a temperature of at least 90 °C for 30 min in the dissolving apparatus (D.5.4) to dissolve the test portion completely, leaving the conical flask open to allow volatile organic matter in the test portion to escape.
- A sample with a low degree of hydrolysis may sometimes cause the solution to become turbid. If this occurs, cool the solution slowly while stirring gently. Alternatively, a 3:1 water/methanol mixture may be used.
- D.6.4** After cooling to room temperature, add 25 ml of 0,1 mol/l or 0,5 mol/l sodium hydroxide solution (D.4.1 or D.4.2) as specified in Table D.1 from a burette (D.5.2). Stopper the flask, stir, and allow to stand at room temperature for 2 h or more (or boil under reflux).
- D.6.5** Add to the flask from a burette (D.5.2) 25 ml of sulfuric or hydrochloric acid (D.4.3 or D.4.4) of the same concentration as the sodium hydroxide solution used in D.6.4, stopper the flask and stir well.
- D.6.6** Titrate excess sulfuric or hydrochloric acid with sodium hydroxide solution, of the same concentration as used in D.6.4, to a faint pink end point.
- D.6.7** Separately, carry out a blank test following the procedure described in D.6.3 to D.6.6, i.e. without the test portion.

**Table D.1 — Test portion size and concentration of reagent solutions used**

Estimated degree of hydrolysis mol %	Test portion g	Concentration of reagent solutions used mol/l
At least 97	3	0,1
At least 90 but less than 97	3	0,5
At least 80 but less than 90	2	0,5
At least 70 but less than 80	1	0,5

## D.7 Expression of results

Calculate the degree of hydrolysis  $H$ , in mol %, from the following equations:

$$X_1 = \frac{(V_1 - V_0) \times c \times 0,060\,05}{m \times \left(1 - \frac{w_{VM} + w_{NaAc}}{100}\right)} \times 100$$

$$X_2 = \frac{44,05 \times X_1}{60,05 - 0,42 \times X_1}$$

$$H = 100 - X_2$$

where

$X_1$  is the amount of acetic acid, in percent by mass, corresponding to the residual acetate content;

$X_2$  is the residual acetate content, in mol %;

$V_1$  is the volume, in ml, of 0,1 mol/l or 0,5 mol/l sodium hydroxide solution consumed by the test solution;

$V_0$  is the volume, in ml, of 0,1 mol/l or 0,5 mol/l sodium hydroxide solution consumed by the blank;

$c$  is the concentration of the reagent solutions used (0,1 mol/l or 0,5 mol/l);

0,060 05 is the molecular mass of acetic acid divided by 1 000;

$m$  is the mass, in g, of the test portion;

$w_{VM}$  is the volatile-matter content, in percent by mass, of the PVAL (see Annex A);

$w_{NaAc}$  is the sodium acetate content, in percent by mass, of the PVAL (see Annex B);

44,05 is the molecular mass of a vinyl alcohol unit;

60,05 is the molecular mass of acetic acid;

0,42 is a factor obtained from the following equation relating  $X_1$  and  $X_2$ :

$$X_1 = \frac{X_2 \times 60,05}{X_2 \times 86,09 + (100 - X_2) \times 44,05} \times 100$$

where 86,09 is the molecular mass of vinyl acetate.

Calculate the mean of the results of the two determinations and express the final result to two places of decimals.

## D.8 Test report

The test report shall include the following particulars:

- a reference to this part of ISO 15023;
- all details necessary for complete identification of the material tested;
- the degree of hydrolysis, calculated as the arithmetic mean of the two determinations;
- the individual results of the two determinations;
- the date of the test.

## Annex E (normative)

### Determination of viscosity of 4 % aqueous solution by the Brookfield Test method or the inclined-tube falling-ball method

#### E.1 Scope

This annex specifies methods of determining the viscosity of a 4 % aqueous solution of PVAL by the Brookfield Test method or the inclined-tube falling-ball method.

#### E.2 Principle

Three aqueous solutions of PVAL spanning a range of concentrations each side of 4 % are prepared and their viscosities measured with a Brookfield-type viscometer or an inclined-tube falling-ball viscometer. The viscosity at a concentration of 4 % is obtained from a concentration-viscosity graph.

#### E.3 Brookfield Test method

##### E.3.1 Apparatus

**E.3.1.1 Brookfield-type viscometer**, Model LVF or Model LVT (see Note), chosen according to the viscosity range in which the measurements are to be made (see Table E.2). The Brookfield UL adapter accessory can be used with both models. Do not use spindles which show signs of corrosion or eccentricity.

NOTE The Model LVF has four rotational frequencies, and the Model LVT has eight (see Table E.1). Each has a set of four spindles. The Brookfield Test method may be carried out using equipment supplied by a number of manufacturers.

**Table E.1 — Rotational frequencies available for the two models of viscometer**

Model	Rotational frequencies min <sup>-1</sup>							
	LVF	60	30	12	6			
LVT	60	30	12	6	3	1,5	0,6	0,3

**Table E.2 — Maximum value of viscosity as a function of viscometer type, rotational frequency and spindle**

Model	Rotational frequency min <sup>-1</sup>	Spindle				
		UL adapter	No. 1	No. 2	No. 3	No. 4
		Maximum viscosity mPa·s				
LVF and LVT	60	10	100	500	2 000	10 000
	30	20	200	1 000	4 000	20 000
	12	50	500	2 500	10 000	50 000
	6	100	1 000	5 000	20 000	100 000
LVT only	3	200	2 000	10 000	40 000	200 000
	1,5	400	4 000	20 000	80 000	400 000
	0.6	1 000	10 000	50 000	200 000	1 000 000
	0.3	2 000	20 000	100 000	400 000	2 000 000

Adjustment and calibration of these viscometers are usually carried out by the manufacturer.

It is recommended that the adjustment and calibration be checked from time to time by means of pure-Newtonian liquids of known viscosity, either in the user's laboratory or by an accredited calibration laboratory.

**E.3.1.2 Conical flasks**, 500 ml.

**E.3.1.3 Beaker**, of diameter at least 65 mm and capacity at least 300 ml.

**E.3.1.4 Thermostatic water bath**, able to maintain a temperature of  $(20,0 \pm 0,1)$  °C.

**E.3.1.5 Weighing dish**, shallow, 60 mm in diameter and 30 mm in height, of glass, aluminium or (preferably) stainless steel, with a lid.

**E.3.1.6 Drying oven**, able to maintain a temperature of  $(105 \pm 20)$  °C.

**E.3.1.7 Desiccator**, with silica gel as drying agent.

**E.3.1.8 Water bath**, usable with boiling water, in which the weighing dish (E.3.1.5) can be placed.

## **E.3.2 Procedure**

### **E.3.2.1 Number of determinations**

Carry out the determination in duplicate.

### **E.3.2.2 Dissolution of sample**

**E.3.2.2.1** Weigh, to the nearest 0,001 g, three test portions, each of at least 15 g, into three separate conical flasks (E.3.1.2).

**E.3.2.2.2** Add water in amounts calculated using the following equation to prepare aqueous solutions with concentrations of 3,8 %, 4,0 % and 4,2 % by mass:

$$m_w = \frac{m_0 \times (100 - w_{VM})}{c_s} - m_0$$

where

$m_w$  is the mass, in g, of water to be added;

$m_0$  is the mass, in g, of the test portion;

$w_{VM}$  is the volatile-matter content, as a percentage by mass;

$c_s$  is the desired concentration of the solution.

**E.3.2.2.3** Heat the flasks to dissolve the test portions completely, and allow them to cool to about 20 °C, de-aerating the solutions completely.

A sample with a low degree of hydrolysis may sometimes cause the solution to become turbid. If this occurs, cool the solution slowly while stirring gently.

### **E.3.2.3 Measurement of viscosity**

**E.3.2.3.1** Mount the viscometer (E.3.1.1), with its guard stirrup fitted if applicable, on its stand.

**E.3.2.3.2** Fill the beaker (E.3.1.3) with one of the test solutions, taking care not to introduce air bubbles, then place it in the thermostatic water bath (E.3.1.4) for a sufficient time to reach  $(20,0 \pm 0,1)$  °C.

**E.3.2.3.3** With the beaker still in the bath, hold the chosen spindle (see Note) at an angle of approximately 45° to the surface of the solution and lower it into the solution. Orientate the spindle vertically, and connect it to the shaft of the viscometer. Check that the spindle is vertical and that it is immersed to the underside of the mark on its shaft.

**NOTE** It is necessary to choose a spindle and rotational frequency such that no measurements correspond to less than 20 % or more than 95 % of full-scale deflection. However, for the best accuracy it is advisable to keep to the range 45 % to 95 % of full scale.

**E.3.2.3.4** Start the motor and run at the chosen rotational frequency (see note to E.3.2.3.3), monitoring the torque meter. When a stable value has been reached on the meter, lock the needle and the motor to take the reading.

**E.3.2.3.4** Repeat with the remaining test solutions.

### **E.3.2.4 Measurement of exact concentrations of test solutions**

**E.3.2.4.1** Place a previously washed weighing dish (E.3.1.5) in the drying oven (E.3.1.6) at  $(105 \pm 2)$  °C and dry for at least 1 h. Allow the dish to cool to room temperature in the desiccator (E.3.1.7) and weigh to the nearest 0,001 g.

**E.3.2.4.2** Place about 5 g of one of the test solutions prepared in E.3.2.2 in the weighing dish and weigh to the nearest 0,001 g.

**E.3.2.4.3** Evaporate the solution to dryness on the boiling-water bath (E.3.1.8) and dry at  $(105 \pm 2)$  °C in the oven for at least 4 h.

**E.3.2.4.4** After drying, allow the dish to cool to room temperature in the desiccator and weigh to the nearest 0,001 g.

E.3.3.4.5 Repeat with the remaining test solutions.

**E.3.2.5 Calculation**

E.3.2.5.1 Calculate the exact concentration  $c_s$  of each test solution, as a percentage by mass, using the following equation:

$$c_s = \frac{m_2 - m_3}{m_1 - m_3} \times 100$$

where

$m_1$  is the total mass, in grams, of the test solution and weighing dish before drying;

$m_2$  is the total mass, in grams, of the test solution and weighing dish after drying;

$m_3$  is the mass, in grams, of the weighing dish.

E.3.2.5.2 Calculate the viscosity  $\eta$ , in mPa·s, of each test solution using the following equation:

$$\eta = \kappa \times \theta$$

where

$\kappa$  is a coefficient depending on the rotational-frequency/spindle combination used (see Table E.3);

$\theta$  is the value read from the scale (0 to 100).

**Table E.3 — Coefficient  $\kappa$  for each rotational-frequency/spindle combination**

Spindle <sup>a</sup>	Rotational frequency min <sup>-1</sup>							
	60	30	12	6	3	1,5	0,6	0,3
Coefficient $\kappa$								
UL adapter	0,1	0,2	0,5	1	2	4	10	20
No. 1	1	2	5	10	20	40	100	200
No. 2	5	10	25	50	100	200	500	1 000
No. 3	20	40	100	200	400	800	2 000	4 000
No. 4	100	200	500	1 000	2 400	4 000	10 000	20 000

<sup>a</sup> It may be necessary to calibrate each spindle with liquids of known viscosity and to use slightly different values of  $\kappa$ .

**E.4 Inclined-tube falling-ball method**

**E.4.1 Apparatus**

E.4.1.1 **Conical flasks**, 300 ml.

E.4.1.2 **Thermostatic water bath**, able to maintain a temperature of  $(20,0 \pm 0,1)$  °C.

**E.4.1.3 Inclined-tube falling-ball viscometer with steel balls**, with a falling time of at least 10 s, as specified in ISO 12058-1.

**E.4.1.4 Oven**, able to maintain a temperature of  $(105 \pm 2) ^\circ\text{C}$ .

**E.4.1.5 Desiccator**, containing silica gel as the drying agent.

**E.4.1.6 Stopwatch**, able to measure to 0,1 s accurately.

## E.4.2 Procedure

### E.4.2.1 Number of determinations

Carry out the determination in duplicate.

### E.4.2.2 Dissolution of sample

Make up three test solutions following the same procedure as in E.3.2.2.

### E.4.2.3 Measurement of viscosity

**E.4.2.3.1** Place each of the test solutions prepared in the falling-ball viscometer and adjust the temperature of the solution to  $(20,0 \pm 0,1) ^\circ\text{C}$ .

**E.4.2.3.2** Measure to the nearest 0,1 s with the stopwatch the time required for the steel ball to travel the distance between the upper and lower graduations.

### E.4.2.4 Determination of exact concentrations of test solutions

Determine the exact concentration of each test solution by the procedure given in E.3.2.4 and the calculation given in E.3.2.5.1.

### E.4.2.5 Calculation

Calculate the viscosity  $\eta$ , in mPa-s, of each test solution using the following equation:

$$\eta = K \times (\rho_1 - \rho_2) \times t$$

where

$\rho_1$  is the density, in  $\text{g/cm}^3$ , of the ball at  $20 ^\circ\text{C}$ ;

$\rho_2$  is the density, in  $\text{g/cm}^3$ , of a 4 % aqueous solution of PVAL at  $20 ^\circ\text{C}$  (normally taken as  $1,008 \text{ g/cm}^3$ );

$t$  is the time, in seconds, taken for the ball to travel between the two graduations;

$K$  is the viscometer calibration constant for the ball used, obtained as follows:

$$K = \eta_0 / (\rho_1 - \rho_3) \times t$$

where

$\eta_0$  is the absolute viscosity, in mPa-s, of a standard solution (see Note) used to calibrate the viscometer at  $20 ^\circ\text{C}$ ;

$\rho_1$  is the density, in  $\text{g/cm}^3$ , of the ball at  $20 ^\circ\text{C}$ ;



$\rho_3$  is the density, in g/cm<sup>3</sup>, of a standard solution (see Note) used to calibrate the viscometer at 20 °C;

$t$  is the time, in seconds, taken for the ball to travel between the two graduations.

NOTE The standard solution is a pure-Newtonian liquid of known viscosity, with which the time taken for the ball to travel between the two graduations is at least 10 s.

## E.5 Expression of results

Plot a graph with the ordinate representing the viscosity and the abscissa the concentration determined for each test solution, and read off it the viscosity, in mPa·s, at 4 % concentration.

Calculate the mean of the results of the two determinations and express the final result to one place of decimals.

## E.6 Test report

The test report shall include the following particulars:

- a) a reference to this part of ISO 15023;
- b) all details necessary for complete identification of the material tested;
- c) the viscosity, calculated as the arithmetic mean of the two determinations;
- d) the individual results of the two determinations;
- e) the date of the test.

---

---

## BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: [orders@bsi-global.com](mailto:orders@bsi-global.com). Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: [info@bsi-global.com](mailto:info@bsi-global.com).

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: [membership@bsi-global.com](mailto:membership@bsi-global.com).

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

### Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: [copyright@bsi-global.com](mailto:copyright@bsi-global.com).