

BS EN ISO 17228:2015



BSI Standards Publication

Leather — Tests for colour fastness — Change in colour with accelerated ageing

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 17228:2015. It supersedes BS ISO 17228:2005 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear, leather and coated fabrics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.
Published by BSI Standards Limited 2015

ISBN 978 0 580 78782 9
ICS 59.140.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2015.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN ISO 17228

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2015

ICS 59.140.30

Supersedes EN ISO 17228:2006

English Version

Leather - Tests for colour fastness - Change in colour with accelerated ageing (ISO 17228:2015)

Cuir - Essais de solidité des coloris - Changement de couleur avec vieillissement accéléré (ISO 17228:2015)

Leder - Farbechtheitsprüfungen - Farbänderung durch beschleunigtes Altern (ISO 17228:2015)

This European Standard was approved by CEN on 3 January 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 17228:2015) has been prepared by Technical Committee ISO/TC IULTCS “International Union of Leather Technologists and Chemists Societies” in collaboration with Technical Committee CEN/TC 289 “Leather” the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2015, and conflicting national standards shall be withdrawn at the latest by September 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 17228:2006.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 17228:2015 has been approved by CEN as EN ISO 17228:2015 without any modification.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	2
5 Test specimens	2
6 Ageing by heat alone	2
6.1 Principle.....	2
6.2 Procedure.....	3
7 Ageing by heat and elevated humidity	4
7.1 Principle.....	4
7.2 Procedure.....	4
8 Cyclic variation in heat and elevated humidity	5
8.1 Principle.....	5
8.2 Procedure.....	5
9 Test report	7
Annex A (informative) Comments on specific aspects of the colour-measurement procedure	8
Bibliography	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

ISO 17228 was prepared by the Fastness Tests Commission of the International Union of Leather Technologists and Chemists Societies (IUF Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

It is based on IUF 412 published in *J. Soc. Leather Tech. Chem.*, **86** pp. 325-331, 2002, and declared an official method of the IULTCS in May 2003.

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

This second edition cancels and replaces the first edition (ISO 17228:2005), which has been technically revised. This new version is a general update of the procedures and in [Tables 1](#), [2](#), and [3](#) includes additional ageing options.

[Annex A](#) is informative.

Leather — Tests for colour fastness — Change in colour with accelerated ageing

1 Scope

This International Standard specifies various ageing procedures to obtain an indication of the changes that could occur when leather is exposed to a certain environment for a prolonged time. Over time, the surface colour of leather and the leather itself change due to ageing and to the action of the surroundings on the leather. The test conditions to be used depend on the type of leather and its intended use.

This procedure can also be used to age specimens for the test of dimensional change according to ISO 17130.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A01, *Textiles — Tests for colour fastness — Part A01: General principles of testing*

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 105-A03, *Textiles — Tests for colour fastness — Part A03: Grey scale for assessing staining*

ISO 105-A04, *Textiles — Tests for colour fastness — Part A04: Method for the instrumental assessment of the degree of staining of adjacent fabrics*

ISO 105-A05, *Textiles — Tests for colour fastness — Part A05: Instrumental assessment of change in colour for determination of grey scale rating*

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 2419, *Leather — Physical and mechanical tests — Sample preparation and conditioning*

ISO 17130, *Leather — Physical and mechanical tests — Determination of dimensional change*

3 Principle

A test specimen of leather is exposed to at least one of the three following conditions:

- heat (see [Clause 6](#));
- heat and humidity (see [Clause 7](#));
- cycles of different temperature and humidity (see [Clause 8](#)).

One or more of these procedures may take place simultaneously. The change in colour of the specimen is assessed with the standard grey scale and, if applicable, any changes in the finish or appearance are noted.

These procedures can also be used to prepare the leather specimen for other physical or fastness tests after accelerated ageing. The assessment of dimension change is described in ISO 17130.

NOTE Accelerated ageing tests are for guidance only and they are not necessarily representative of long term use at ambient temperatures.

The general colour fastness testing principles shall be in accordance with those described in ISO 105-A01, taking into account that the substrate is leather.

4 Apparatus

Use normal laboratory apparatus and the following:

- 4.1 Oven**, fitted with a central rack, capable of maintaining a temperature within ± 2 °C of the defined temperature. The oven should have a vent, preferably with a circulating fan, and an inside made of inert materials.
- 4.2 Climate chamber**, fitted with a central rack, capable of maintaining a temperature within ± 2 °C of the defined temperature and a relative humidity within ± 5 % of the defined relative humidity.
- 4.3 Suitable system for holding the specimen** and preventing contact with the oven or climate chamber sides.
- 4.4 Grey scale for assessing change in colour**, complying with ISO 105-A02, or an **instrumental system for assessing change in colour**, complying with ISO 105-A05.
- 4.5 Grey scale for assessing staining**, complying with ISO 105-A03, or an **instrumental system for assessing staining**, complying with ISO 105-A04.
- 4.6 Stop clock**, readable to 1 s.

5 Test specimens

- 5.1** Prior to cutting out specimens, condition the piece of leather in accordance with ISO 2419.
- 5.2** Cut out two representative test specimens measuring not less than 100 mm × 100 mm.

If the piece of leather available for testing is a whole hide or skin, then the specimens shall be taken in accordance with standard procedures given in ISO 2418.

NOTE If other properties, such as dimensional change, are to be measured, then additional test specimens are used due to different kind of storage during the ageing step.

6 Ageing by heat alone

6.1 Principle

The purpose of this procedure is to simulate ageing by the application of heat. Two different types of change can be involved:

- a) the change in colour of the substances in the leather;
- b) the evaporation of volatile substances or the migration of substances, leading to a change in the colour and/or other properties of the leather or finish.

As both the exposure time and the temperature can be varied, this procedure can be used for a variety of purposes, including preparing specimens for other tests.

6.2 Procedure

6.2.1 Pre-heat the oven (4.1) to the desired temperature (see 6.2.3).

6.2.2 Place one test specimen (the reference specimen) in a place where it is protected from light and kept under standard conditions, according to ISO 2419.

6.2.3 Hang the other test specimen with a clip from, or place it on, the holder (4.3) in the middle of the oven such that the air has free access to both sides.

Unless specified otherwise, age the specimen under one of the sets of conditions indicated in Table 1.

Table 1 — Ageing by heat

Method	Conditions for ageing by heat	Recommended use
6A	24 h ± 1 h at 60 °C ± 2 °C	General-purpose ageing conditions
6B	24 h ± 1 h at 100 °C ± 2 °C	Specifically for yellowing of individual products in undyed leather
6C	72 h ± 2 h at 60 °C ± 2 °C	Extended general-purpose ageing
6D	72 h ± 2 h at 100 °C ± 2 °C	Ageing of automotive leather
6E	168 h ± 2 h at 90 °C ± 2 °C	Extended ageing of automotive leather
6F	168 h ± 2 h at 60 °C ± 2 °C	Extended ageing at moderate temperature
6G	168 h ± 2 h at 100 °C ± 2 °C	Extended ageing at elevated temperature
6H	4 h ± 0,2 h at 100 °C ± 2 °C	Short ageing of automotive leather
6J	144 h ± 2 h at 100 °C ± 2 °C	Ageing of automotive leather
6K	168 h ± 2 h at 120 °C ± 2 °C	Extended ageing of automotive leather at high temperature

The sets of conditions given in Table 1 have been selected to provide a range of conditions for different applications. If other conditions are used, then they shall be clearly noted in the test report.

6.2.4 After the period of time has elapsed, remove the test specimen from the oven. Allow the specimen to cool. Then, recondition both the test and the reference specimen under standard conditions according to ISO 2419 for 24 h.

6.2.5 Either visually assess the colour difference between the aged specimen and the reference specimen using the appropriate grey scale in accordance with ISO 105-A02, (4.4) or alternatively, assess the grey scale colour difference instrumentally in accordance with ISO 105-A05, (4.4). If required, e.g. for light coloured leathers, ISO 105-A03, (4.5), or instrumentally with ISO 105-A04, (4.5), can be used to assess the grey scale colour difference.

NOTE In the case of undyed leather, the change in colour is often referred to as yellowing. See Annex A for further details.

6.2.6 If required, compare the aged specimen with the reference specimen and note any visually apparent changes in appearance, hue, or shrinkage and comment on any change in flexibility as assessed manually.

7 Ageing by heat and elevated humidity

7.1 Principle

This procedure is similar to the application of heat, but the moisture present acts as a mild hydrolysing agent, thus simulating ageing at ambient conditions with some degree of humidity. At high humidities, some substances can migrate to the surface.

As different levels of humidity can be used, and the time and temperature can be varied, this procedure can be used for a variety of purposes, including preparing specimens for other tests.

7.2 Procedure

7.2.1 Bring the climate chamber (4.2) to the desired temperature and humidity (see 7.2.3).

7.2.2 Place one test specimen (the reference specimen) in a place where it is protected from light and kept under standard conditions according to ISO 2419.

7.2.3 Hang the other test specimen with a clip from, or place it on, the holder (4.3) in the middle of the climate chamber such that the air has free access to both sides.

Unless specified otherwise, age the specimen under one of the sets of conditions indicated in Table 2.

Table 2 — Ageing by heat and elevated humidity

Method	Conditions for ageing by heat and elevated relative humidity (r.h.)	Recommended use
7A	24 h ± 1 h at 50 °C ± 2 °C and 90 % r.h. ± 5 % r.h.	General-purpose ageing conditions
7B	96 h ± 2 h at 50 °C ± 2 °C and 90 % r.h. ± 5 % r.h.	Extended general-purpose ageing
7C	12 h ± 1 h at 70 °C ± 2 °C and 90 % r.h. ± 5 % r.h.	Migration test for finished leather
7D	48 h ± 1 h at 55 °C ± 2 °C and 80 % r.h. ± 5 % r.h.	Climate test for automotive leather
7E	168 h ± 2 h at 40 °C ± 2 °C and 95 % r.h. ± 5 % r.h.	Extended climate test for automotive leather
7F	16 h ± 1 h at 40 °C ± 2 °C and 95 % r.h. ± 5 % r.h.	General-purpose ageing conditions
7G	72 h ± 1 h at 60 °C ± 2 °C and 85 % r.h. ± 5 % r.h.	Simulate transport in closed container
7H	168 h ± 2 h at 70 °C ± 2 °C and 75 % r.h. ± 5 % r.h.	Climate test for automotive leather
7J	168 h ± 2 h at 70 °C ± 2 °C and 95 % r.h. ± 5 % r.h.	Climate test for automotive leather

The sets of conditions given in Table 2 have been selected to provide a range of conditions for different applications. If other conditions are used, then they shall be clearly noted in the test report.

7.2.4 After the period of time has elapsed, remove the test specimen from the climate chamber. Allow the specimen to cool. Then recondition both the test and the reference specimen under standard conditions according to ISO 2419 for 24 h.

7.2.5 Either visually or instrumentally, assess the colour difference between the aged specimen and the reference specimen as described in 6.2.5.

7.2.6 If required, compare the aged specimen with the reference specimen and note any visually apparent changes in appearance, hue, or shrinkage and comment on any change in flexibility as assessed manually.

8 Cyclic variation in heat and elevated humidity

8.1 Principle

This procedure is similar to those in [Clauses 6](#) and [7](#), but the temperature and humidity are varied cyclically to simulate the changes which could be experienced during a typical day. This procedure is especially used for automotive leather.

As different levels of humidity can be used, and the time and temperature can be varied, the procedure can be used for a variety of other purposes, including preparing specimens for other tests.

8.2 Procedure

8.2.1 Bring the climate chamber ([4.2](#)) to the desired temperature and humidity starting conditions, see [Table 3](#).

8.2.2 Place one test specimen (the reference specimen) in a place where it is protected from light and kept under standard conditions according to ISO 2419.

8.2.3 Hang the other test specimen with a clip from, or place it on, the holder ([4.3](#)) in the middle of the climate chamber such that the air has free access to both sides.

Unless specified otherwise, age the specimen for the given number of cycles under one of the sets of conditions indicated in [Table 3](#).

Table 3 — Ageing under cyclic temperature/humidity conditions

Method	Conditions for cycling at various temperatures and relative humidities (r.h.)	Recommended use
8A	One cycle consists of: —24 h ± 1 h at 38 °C ± 2 °C and 95 % r.h. ± 5 % r.h.; —24 h ± 1 h at 100 °C ± 2 °C. Run three cycles under these conditions.	General-purpose climate test for automotive leather
8B	One cycle consists of: —4,0 h ± 0,2 h at 70 °C ± 2 °C and 20 % r.h. ± 5 % r.h.; —16 h ± 1 h at 38 °C ± 2 °C and 95 % r.h. ± 5 % r.h.; —4,0 h ± 0,2 h at -30 °C ± 2 °C. Run 10 cycles under these conditions.	Extended climate test for automotive leather (including temperatures below freezing)
8C	One cycle consists of: —4,0 h ± 0,2 h at 40 °C ± 2 °C and 90 % r.h. ± 5 % r.h.; —2,0 h ± 0,2 h heating to 120 °C (above 90 °C, switch humidity control off); —4,0 h ± 0,2 h at 120 °C ± 2 °C; —2,0 h ± 0,2 h cooling to 40 °C ± 2 °C and 90 % r.h. ± 5 % r.h. (switch humidity control back on only after reaching 40 °C). Run 20 cycles under these conditions.	Simulation of warm, humid climate for automotive leather

NOTE The programming of climate chamber depends on the technical construction. To avoid high humidity at high temperatures, it is necessary for many climate chambers to switch on the humidity control after high temperature periods (>100 °C) only after reaching the defined temperature of the wet period.

Table 3 (continued)

Method	Conditions for cycling at various temperatures and relative humidities (r.h.)	Recommended use
8D	<p>One cycle consists of:</p> <ul style="list-style-type: none"> —4,0 h ± 0,2 h at 10°C ± 2 °C and 92 % r.h. ± 3 % r.h.; —2,0 h ± 0,2 h at 90°C ± 2 °C and max. 20 %. <p>rates of heating: approx. 1,5 °C/min (temperature should not exceed 50 °C at 40 % r.h. during heating and cooling)</p> <p>Run 10 cycles (or if required, 30 cycles) under these conditions.</p>	Simulation of warm, humid climate for automotive leather
8E	<p><u>Pre-conditioning:</u></p> <p>900 min ± 10 min at 23 °C and 50 % r.h.;</p> <p><u>One cycle consists of:</u></p> <ul style="list-style-type: none"> —29 min heating to 70 °C and 50 % r.h.; —31 min heating to 120 °C and < 10 % r.h.; —120 min at 120 °C; —20 min cooling to 70 °C and 50 % r.h.; —40 min cooling to 15 °C and 95 % r.h.; —120 min at 15 °C and 95 % r.h. <p>Run nine cycles under these conditions.</p> <p><u>Post-run:</u></p> <ul style="list-style-type: none"> —29 min heating to 70 °C and 50 % r.h.; —31 min heating to 120 °C and < 10 % r.h.; —180 min at 120 °C. <p><u>Unless given, the maximum deviations are:</u></p> <ul style="list-style-type: none"> —for time: ±2 min; —for temperature: ±2 °C; —for relative humidity: ±5 % r.h. 	Simulation of warm, humid climate for automotive leather
<p>NOTE The programming of climate chamber depends on the technical construction. To avoid high humidity at high temperatures, it is necessary for many climate chambers to switch on the humidity control after high temperature periods (>100 °C) only after reaching the defined temperature of the wet period.</p>		

The sets of conditions given in [Table 3](#) have been selected to provide a range of conditions for different applications. If other conditions are used, then they shall be clearly noted in the test report.

8.2.4 After the period of time has elapsed, remove the test specimen from the climate chamber. Allow the specimen to cool. Then, recondition both the test and the reference specimen under standard conditions in accordance with ISO 2419 for 24 h.

8.2.5 Either visually or instrumentally, assess the colour difference between the aged specimen and the reference specimen as described in [6.2.5](#).

8.2.6 If required, compare the aged specimen with the reference specimen and note any visually apparent changes in appearance, hue, or shrinkage and comment on any change in flexibility as assessed manually.

9 Test report

The test report shall include the following information:

- a) a reference to this International Standard, i.e. ISO 17228;
- b) a description of the type of leather tested;
- c) the ageing method selected and the ageing conditions used, i.e. type of ageing, time, temperature, humidity, and number of cycles (if relevant);
- d) the numerical rating obtained for the change in colour of the aged specimen, stating which grey scale was used;
- e) if required, any change in appearance, hue, or flexibility and any shrinkage of the aged specimen;
- f) details of any deviations from the procedure specified;
- g) the dates between which the ageing was carried out.

Annex A (informative)

Comments on specific aspects of the colour-measurement procedure

A.1 Instrumental colour measurement

The actual colour change of the aged specimen compared with the reference specimen can be measured instrumentally. It is recommended that the colour change be measured at four different positions on the specimen and that the result be given as the average of these measurements.

Details on measuring surface colour and colour differences are given in ISO 105-J01 and ISO 105-J03.

A.2 Evaluation of yellowing

One typical use of ageing procedures is the evaluation of the propensity of chemical agents used in the tanning, retanning, and fat liquoring processes to change the colour of the leather substrate, normally referred to as yellowing. This is carried out using treated, undyed leather specimens. The degree of yellowing of undyed leather is commonly assessed by measuring it instrumentally using a reflectance spectrophotometer.

A number of yellowing formulae are given in the literature. Two examples of procedures commonly used in the leather industry to assess the degree of yellowing are as follows:

EXAMPLE 1 Using the CIELab system.

The change in yellowness is determined from the Δb^* colour difference value using D65 illumination (including spectral reflection) and the 10° standard observer. ISO 105-J01 and ISO 105-J03 give details of the measurement of surface colour and colour differences.

EXAMPLE 2 Using DIN 6167.

The so-called yellowing factor G is calculated using D65 illumination (including spectral reflection) and the 10° standard observer:

$$G = \frac{1,301 \times X - 1,149 \times Z}{Y} \times 100$$

where

X , Y , and Z are the standard tristimulus values.

In both cases, the degree of yellowing of the reference specimen is subtracted from that of the aged specimen.

Bibliography

- [1] ISO 105-J01, *Textiles — Tests for colour fastness — Part J01: General principles for measurement of surface colour*
- [2] ISO 105-J03, *Textiles — Tests for colour fastness — Part J03: Calculation of colour differences*
- [3] DIN 6167, *Description of yellowness of nearwhite or nearcolourless materials*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™