

BS EN ISO 17229:2016



BSI Standards Publication

Leather — Physical and mechanical tests — Determination of water vapour absorption

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 17229:2016. It supersedes BS EN ISO 17229:2002 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear, leather and coated fabrics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 90473 8

ICS 59.140.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2016.

Amendments issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN ISO 17229

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2016

ICS 59.140.30

Supersedes EN ISO 17229:2002

English Version

Leather - Physical and mechanical tests - Determination of water vapour absorption (ISO 17229:2016)

Cuir - Essais physiques et mécaniques - Détermination
de l'absorption de vapeur d'eau (ISO 17229:2016)

Leder - Physikalische und mechanische Prüfungen -
Bestimmung der Wasserdampfaufnahme (ISO
17229:2016)

This European Standard was approved by CEN on 23 January 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 17229:2016) has been prepared by Technical Committee IULTCS “International Union of Leather Technologists and Chemists Societies” in collaboration with Technical Committee CEN/TC 289 “Leather” the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2016, and conflicting national standards shall be withdrawn at the latest by September 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 17229:2002.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 17229:2016 has been approved by CEN as EN ISO 17229:2016 without any modification.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	1
5 Sampling and sample preparation	2
6 Procedure	2
7 Expression of results	2
8 Test report	2
Annex A (informative) Water vapour number	4
Bibliography	5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

ISO 17229 was prepared by the Physical Test Commission of the International Union of Leather Technologists and Chemists Societies (IUP Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

It is based on IUP 42 which was published in *J. Soc. Leather Tech. Chem.* **84**, p. 395, (2000) and confirmed as an official method of the IULTCS in March 2001.

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

This second edition cancels and replaces the first edition (ISO 17229:2002), of which it constitutes a minor revision to align item c) of Clause 8 with ISO 2419:2012.

Leather — Physical and mechanical tests — Determination of water vapour absorption

1 Scope

This International Standard specifies a method for determining the water vapour absorption of leather. The method is applicable for all leathers but is particularly relevant for leathers intended for footwear uppers and linings.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 2419, *Leather — Physical and mechanical tests — Sample preparation and conditioning*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

3 Principle

The test piece and an impermeable material are clamped over the opening of a metal container containing 50 ml of water for a specified time. The water vapour absorption of the test piece is determined by the increase in mass.

4 Apparatus

4.1 Cylindrical metal or glass container, with internal diameter of $35 \text{ mm} \pm 0,5 \text{ mm}$, internal depth $104 \text{ mm} \pm 1 \text{ mm}$ and an external diameter at the top opening of at least 55 mm, fitted with a metal ring or lid which can be securely clamped to the cylindrical metal container.

4.2 Balance, weighing to 0,001 g.

4.3 Stop clock, reading to 1 min.

4.4 Vernier callipers, reading to 0,1 mm.

4.5 Disc of impermeable material, for example rubber or metal, with the same diameter as the test piece.

4.6 Press knife, the inner wall of which is a right angled circular cylinder of diameter $43 \text{ mm} \pm 1 \text{ mm}$ as specified in ISO 2419.

4.7 Distilled or deionized water, conforming to the requirements of grade 3 of ISO 3696.

5 Sampling and sample preparation

5.1 Sample in accordance with ISO 2418. From the sample, cut three circular test pieces by applying the press knife to the grain surface, if distinguishable.

If there is a requirement for more than two hides or skins to be tested in one batch, then only one test piece need be taken from each hide or skin, provided that the overall total is not less than three test pieces.

5.2 Condition the test piece in accordance with ISO 2419.

NOTE Results will vary depending on the conditioning method used.

5.3 Weigh the test piece to the nearest 0,001 g and record its mass as m_1 .

6 Procedure

6.1 Using vernier callipers, measure the internal diameter of the cylindrical container (to the nearest 0,1 mm) in two mutually perpendicular directions and calculate the mean diameter.

6.2 Pour 50 ml \pm 5 ml of distilled or deionized water at 20 °C \pm 2 °C or 23 °C \pm 2 °C into the cylindrical metal container (4.1).

6.3 Place the test piece centrally over the container with the side which would be exposed to the higher humidity in use facing downwards. Place a disc of impermeable material over the test piece and clamp the upper ring or lid in place taking care not to splash water onto the test piece.

6.4 Keep the container at a temperature of 20 °C \pm 2 °C or 23 °C \pm 2 °C for 8 h \pm 0,1 h.

6.5 Remove the test piece, weigh immediately to the nearest 0,001 g and record its mass as m_2 .

6.6 If the test piece is splashed with water discard it and repeat the test with a fresh test piece.

7 Expression of results

Calculate the water vapour absorption, A_{wv} , in milligrams per square centimetre, using Formula (1):

$$A_{wv} = \frac{4(m_2 - m_1) \times 10^5}{\pi d^2} \quad (1)$$

where

m_1 is the initial mass of the test piece, in grams;

m_2 is the final mass of the test piece, in grams;

d is the internal diameter of the cylindrical container, in millimetres.

The calculation of the water vapour number is given in informative [Annex A](#).

8 Test report

The test report shall include the following:

a) a reference to this International Standard, i.e. ISO 17229;

- b) the mean water vapour absorption, A_{wv} , in milligrams per square centimetre, expressed to one decimal place;
- c) the standard atmosphere used for conditioning and testing as given in ISO 2419;
- d) any deviations from the method specified in this International Standard;
- e) full details for identification of the sample and any deviation from ISO 2418 with respect to sampling.

Annex A (informative)

Water vapour number

It is common practice to combine the results of water vapour permeability, P_{wv} , as determined in ISO 14268, and water vapour absorption, A_{wv} , as determined in this International Standard, to determine the water vapour number, W_{pn} .

Calculate the water vapour number, W_{pn} , in milligrams per square centimetre 8 h, using Formula (A.1):

$$W_{pn} = t \times P_{wv} + A_{wv} \quad (\text{A.1})$$

where

t is 8 h;

P_{wv} is the water vapour permeability;

A_{wv} is the water vapour absorption.

Bibliography

- [1] ISO 14268, *Leather — Physical and mechanical tests — Determination of water vapour permeability*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK