

BS EN ISO 17230:2011



BSI Standards Publication

**Leather — Physical and
mechanical tests —
Determination of water
penetration pressure (ISO
17230:2006)**

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 17230:2011. It is identical to ISO 17230:2006. It supersedes BS EN 14289:2003 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear, leather and coated fabrics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2011

ISBN 978 0 580 72291 2

ICS 59.140.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2011.

Amendments issued since publication

Date	Text affected
------	---------------

English Version

Leather - Physical and mechanical tests - Determination of water penetration pressure (ISO 17230:2006)

Cuir - Essais physiques et mécaniques - Détermination de la pression de pénétration de l'eau (ISO 17230:2006)

Leder - Physikalische und mechanische Prüfungen - Bestimmung des Wasserdurchlässigkeitsdruckes (ISO 17230:2006)

This European Standard was approved by CEN on 18 August 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

The text of ISO 17230:2006 has been prepared by International Union of Leather Technologists and Chemists Societies and has been taken over as EN ISO 17230:2011 by Technical Committee CEN/TC 289 "Leather" the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2012, and conflicting national standards shall be withdrawn at the latest by March 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14289:2003.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 17230:2006 has been approved by CEN as a EN ISO 17230:2011 without any modification.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17230 was prepared by the Physical Test Commission of the International Union of Leather Technologists and Chemists Societies (IUP Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI. It was published as EN 14289. It is based on IUP 45 published in *J. Soc. Leather Tech. Chem.*, **86** (7), p. 345, 2002, and declared an official method of the IULTCS in May 2003.

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

Leather — Physical and mechanical tests — Determination of water penetration pressure

1 Scope

This International Standard describes a method for determining the water penetration pressure of leather.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 2419, *Leather — Physical and mechanical tests — Sample preparation and conditioning*

ISO 3696, *Water for analytical laboratory use — Specifications and test methods*

3 Principle

A sample of leather is clamped over a container of water with the surface of the leather in contact with the water. The water pressure is raised at a specified rate and the pressure required to force droplets of water through the leather is measured.

4 Apparatus

4.1 Cup, in the form of a short non-corrosive metal circular cylinder, internal diameter $40,0 \text{ mm} \pm 0,2 \text{ mm}$ with the open end uppermost.

4.2 Annular clamp, internal diameter $40,0 \text{ mm} \pm 0,2 \text{ mm}$, capable of clamping the leather test piece across the cup (4.1) without slippage when a pressure of 65 kPa is applied.

4.3 Stiff wire gauze, with eight holes per 25 mm, circular in shape and held in place around the circumference by the annular clamp (4.2), or welded into position.

4.4 Means of increasing pressure, such that the water in the cup is subjected to a uniform increase in pressure of $3 \text{ kPa/min} \pm 0,3 \text{ kPa/min}$ to a maximum pressure of 65 kPa.

4.5 Distilled or deionized water, conforming to the requirements of grade 3 of ISO 3696.

4.6 Press knife, the inner surface of which is a right angled circular cylinder, capable of cutting a circular test piece which can be clamped between the cup (4.1) and annular clamp (4.2) and conforming to ISO 2419.

NOTE To preserve the area of a test skin or hide, the whole skin or hide may be placed on the test apparatus and the press knife becomes optional.

5 Sampling and sample preparation

5.1 Sample in accordance with ISO 2418. Cut three test pieces by applying the press knife (4.6) to the grain surface.

NOTE If there is a requirement for more than two hides or skins to be tested in one batch, then only one sample need be taken from each hide or skin, provided that the overall total is not less than three test pieces.

5.2 Carry out all further steps at $20\text{ °C} \pm 2\text{ °C}$ or $23\text{ °C} \pm 2\text{ °C}$. There is no need to condition test pieces nor is there any need for humidity control.

6 Procedure

6.1 Fill the cup (4.1) with distilled or deionized water (4.5) at the controlled temperature (5.2).

6.2 Place the leather over the cup with the surface which would be wetted in wear in contact with the water. Place a stiff gauze over the leather and clamp in position.

NOTE The stiff gauze prevents the leather from becoming distended during the test.

6.3 Apply pressure to the water, increasing the pressure at a uniform rate of $3,0\text{ kPa/min} \pm 0,3\text{ kPa/min}$ until completion of the test.

6.4 Observe the surface of the leather for the appearance of globules of water which have been forced through the leather and note the pressure when three such globules are visible. This is the water penetration pressure.

NOTE 1 The appearance of the third droplet is taken as the end point rather than the first so that the result will not be duly influenced by the presence of a few capillaries of slightly greater dimensions than the remainder.

NOTE 2 If the leather is not sufficiently waterproof to be assessed by this test, then failure will be as damp patches rather than discrete droplets. These results are less reliable. If the leather fails at a pressure of less than 2,5 kPa, then these low pressures are of little value in discriminating between samples.

6.5 If the third droplet has not appeared when a pressure of 65 kPa is reached, terminate the test.

7 Expression of results

7.1 Express the water penetration pressure to the nearest 0,1 kPa. If the leather has not failed at a pressure of 65 kPa, report the water penetration pressure as "greater than 65 kPa".

7.2 If the leather fails because the water penetrates as damp patches, include this as a comment on the test report.

NOTE Penetration pressures are sometimes expressed as "mmHg" or "cmHg". If the results are to be expressed in these units, then $1\text{ kPa} = 7,5\text{ mmHg} = 0,75\text{ cmHg}$.

8 Test report

The test report shall include the following for each test piece:

- a) a reference to this International Standard, i.e. ISO 17230:2006;
- b) the water penetration pressure, in kPa;
- c) the mode of failure if this is by formation of damp patches;
- d) the temperature at which the test was carried out (i.e. $20\text{ °C} \pm 2\text{ °C}$ or $23\text{ °C} \pm 2\text{ °C}$);
- e) any deviations from the method specified in this International Standard;
- f) full details for identification of the sample and any deviation from ISO 2418 with respect to sampling.

Annex A (informative)

Source of apparatus

One example of a suitable product available commercially is given below.

“R & B Hydrostatic Triple Head Tester”¹⁾ manufactured by:

R & B Instruments, Unit 3a, Farnley Low Mills, Bangor Terrace, Leeds LS12 5PS, UK.

1) “R & B Hydrostatic Triple Head Tester” is an example of a suitable product available commercially. This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of this product.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™