

BS EN ISO 17672:2016



BSI Standards Publication

Brazing — Filler metals (ISO 17672:2016)

bsi.

National foreword

This British Standard is the UK implementation of EN ISO 17672:2016. It supersedes BS EN ISO 17672:2010 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee WEE/19, Brazing and braze welding.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 83296 3

ICS 25.160.50

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2016.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 17672

September 2016

ICS 25.160.50

Supersedes EN ISO 17672:2010

English Version

Brazing - Filler metals (ISO 17672:2016)

Brasage fort - Métaux d'apport (ISO 17672:2016)

Hartlöten - Lote (ISO 17672:2016)

This European Standard was approved by CEN on 29 July 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 17672:2016) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding and allied processes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2017, and conflicting national standards shall be withdrawn at the latest by March 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 17672:2010.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 17672:2016 has been approved by CEN as EN ISO 17672:2016 without any modification.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Composition	1
4 Special vacuum requirement	2
5 Chemical analysis	2
6 Designation	3
7 Technical delivery conditions	3
7.1 Types of product	3
7.2 Dimensions	3
7.2.1 General	3
7.2.2 Foils	3
7.2.3 Rods	4
7.2.4 Wires	5
7.3 Condition	5
7.4 Marking	5
7.5 Packaging	5
7.6 Product certificates	5
8 Metal hazards	5
Annex A (normative) Codification	16
Bibliography	21

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 44, *Welding and allied processes*.

This second edition cancels and replaces the first edition (ISO 17672:2010), which has been technically revised.

Requests for official interpretations of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44 via your national standards body. A complete listing of these bodies can be found at www.iso.org.

Brazing — Filler metals

1 Scope

This International Standard specifies the compositional ranges of a series of filler metals used for brazing. The filler metals are divided into seven classes, related to their composition, but not necessarily to the major element present.

NOTE 1 For the major element(s) present, see [Annex A](#).

In the case of composite products, such as flux-coated rods, pastes or plastics tapes, this International Standard covers only the filler metal that forms parts of such products. The melting temperatures given in the tables are only approximate, as they necessarily vary within the compositional range of the filler metal. Therefore, they are given only for information. Technical delivery conditions are given for brazing filler metals and products containing brazing filler metals with other constituents such as flux and/or binders.

NOTE 2 For some applications, e.g. precious metal jewellery, aerospace and dental, filler metals other than those included in this International Standard are often used and these are covered by other International Standards to which reference can be made.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3677, *Filler metal for soft soldering and braze welding — Designation*

ISO 80000-1:2009, *Quantities and units — Part 1: General*

3 Composition

The filler metal shall have a composition in accordance with [Tables 5 to 13](#) for the particular type, except as modified for special vacuum requirements (see [Clause 4](#) and [Table 1](#)).

If the values for an element range from 0 (—) to a defined value, the element may be, but does not have to be, in that brazing filler metal.

For the purposes of determining compliance with composition limits, any value obtained from the analysis shall be rounded to the same number of decimal places as used in this International Standard in expressing the specified limit. The following rules shall be used for rounding.

- a) When the figure immediately after the last figure to be retained is less than five, then the last figure to be retained shall be kept unchanged.
- b) When the figure immediately after the last figure to be retained is either
 - 1) greater than five, or
 - 2) equal to five and followed by at least one figure other than zero,the last figure to be retained shall be increased by one.
- c) When the figure immediately after the last figure to be retained is equal to five, and followed by zeros only, then the last figure to be retained shall be left unchanged if even, and increased by one

if odd. For the purposes of determining compliance with the requirements of this International Standard, the actual test values obtained shall be subjected to the rounding-off instructions given in ISO 80000-1:2009, Annex B.

NOTE The chemical analysis is of the bulk material, but the material can be composed of discrete powders with different individual compositions or multiple layers of roll-clad foils where each layer can have a different individual composition.

4 Special vacuum requirement

In a few instances, which are most likely to apply to Ag 272, Pd 287, Pd 387, Pd 388, Pd 481, Pd 483, Pd 484, Pd 587, Pd 647 and Au 295, Au 375, Au 625, Au 752, Au 801 and Au 827, lower impurity limits can be required for brazing in vacuum or service in vacuum and these limits shall be as given in [Table 1](#).

Filler metals complying with [Table 1](#) shall have the letter V added as a suffix to the codification plus the digit 1 or 2 to indicate the grade.

NOTE Grade 1 is intended for the most demanding duties, Grade 2 for less demanding.

Table 1 — Impurity limits for special vacuum requirements

Impurity	Limit % by mass max.	
	Grade 1	Grade 2
Ca ^a	0,005	0,005
Cd	0,001	0,002
P	0,002	0,002 ^b
Pb	0,002	0,002
Zn	0,001	0,002
Mn ^c	0,001	0,002
In ^c	0,002	0,003
All other elements where vapour pressure at 500 °C is > 1,3 × 10 ⁻⁵ Pa ^d	0,001	0,002

^a For filler metal Ag 272 (see [Table 6](#)), lower levels may be available by agreement between the purchaser and the supplier.

^b For filler metal Ag 272, 0,02 % maximum.

^c Except where otherwise specified in [Tables 5 to 13](#).

^d Examples of such elements are Ca, Cs, K, Li, Mg, Na, Rb, S, Sb, Se, Sr, Te and Tl. For such elements (including Cd, Pb and Zn), the total is limited to 0,010 %.

5 Chemical analysis

Chemical analyses shall be carried out by any suitable method, but it should be noted that in the case of many brazing alloys, the use of reference standards may be essential, as agreed between the purchaser and the supplier. Analysis is only required to be carried out routinely for those elements for which specific limits are shown. If, however, the presence of other elements is suspected or in the course of routine analysis is indicated to be in excess of the limits laid down for unnamed elements, or would bring the total of impurities above the specified limit, further analyses shall be carried out for such elements.

6 Designation

The filler metal shall be designated by the description “filler metal,” reference to this International Standard (i.e. ISO 17672) and a code. Details of the two options for the code system used are given in [Annex A](#).

As an example, the designations of an aluminium filler metal containing 11 % to 13 % Si, in accordance with this International Standard, can be made in one of the following ways:

EXAMPLE 1 Filler metal ISO 17672-Al 112

where

- “Filler metal” is the description;
“ISO 17672” is the reference to this International Standard;
“Al 112” is the short code given in [Tables 5 to 13](#).

EXAMPLE 2 Filler metal ISO 17672-B-Al88Si-575/585

where

- “Filler metal” is the description;
“ISO 17672” is the reference to this International Standard;
“B” denotes brazing;
“Al88Si-575/585” is the code in accordance with ISO 3677.

7 Technical delivery conditions

7.1 Types of product

The form of the material shall be agreed between the purchaser and the manufacturer/supplier at the time of placing the order.

NOTE Brazing filler metals are available as rod, wire, foil (or preforms made from them) or powder, although not all filler metals are necessarily available in every type of product. They are also available as a constituent of brazing pastes or, particularly in the case of aluminium brazing filler metals, clad onto one or both sides of an alloy sheet. Rods can be completely or partially coated with flux.

7.2 Dimensions

7.2.1 General

Dimensions and tolerances for foils (see [7.2.2](#)), rods (see [7.2.3](#)) and, to a lesser extent, wires (see [7.2.4](#)) are defined. For other forms and dimensions not listed in the respective tables, the purchaser and the manufacturer/supplier shall agree on the dimensions and tolerances at the time of placing the order.

7.2.2 Foils

The tolerances for thickness, width and camber are given in [Tables 2, 3](#) and [4](#).

Table 2 — Thickness tolerance for foils

Thickness nominal size mm		Limits of thickness related to width over 1 mm (nominal size)
over	to	
—	0,05	±10 %
0,05	0,1	±0,005 mm
0,1	0,2	±0,010 mm
0,2	0,3	±0,015 mm
0,3	0,4	±0,018 mm
0,4	0,5	±0,020 mm
0,5	0,8	±0,025 mm
0,8	1,2	±0,030 mm
1,2	2,0	±0,035 mm

Table 3 — Width tolerance for foils

Thickness nominal size mm		Limits of width related to width (nominal size) mm		
over	to	to 50 mm	over 50 mm to 100 mm	over 100 mm
—	0,1	+0,2 0	+0,3 0	+0,4 0
0,1	1,0	+0,2 0	+0,3 0	+0,4 0
1,0	2,0	+0,3 0	+0,4 0	+0,5 0

Table 4 — Camber tolerance for foils

Thickness nominal size mm		Max. camber for width nominal size mm/m				
over	to	from 3 mm to 10 mm	over 10 mm to 15 mm	over 15 mm to 30 mm	over 30 mm to 50 mm	over 50 mm
—	0,5	10	7	4	3	3
0,5	2,0	15	10	6	4	4

7.2.3 Rods

For rods, the preferred diameters are 1 mm, 1,5 mm, 2 mm, 2,5 mm, 3 mm and 5 mm and the preferred lengths are 500 mm and 1 000 mm. The tolerance on diameter shall be ±3 % for drawn rods and ±0,3 mm for other fabrication processes. The tolerance on length shall be ±5 mm.

7.2.4 Wires

For wires, there are no preferred diameters and the tolerance on diameter shall be $\pm 3\%$.

7.3 Condition

The surface of brazing filler metals shall be free from contamination which could adversely affect brazing. With flux-coated rods, the coating shall firmly adhere to the rod and shall not break off during proper handling and usage. Welds, when present, shall have been made so as not to interfere with uniform, uninterrupted feeding of filler metal on automatic and semiautomatic brazing.

7.4 Marking

Since in many cases the marking of brazing filler metals themselves is impracticable, reliance shall be placed on the marking of packets. The outside of each smallest unit package shall be clearly marked with the following information:

- a) the designation in accordance with [Clause 6](#);
- b) the name of the manufacturer/supplier;
- c) the trade name (if any);
- d) the quantity of material and, if applicable, the dimensions;
- e) the supplier's batch number;
- f) health and safety warnings (as required by national regulations).

7.5 Packaging

Brazing filler metals or products containing them shall be packed to provide sufficient safeguard against damage and deterioration during transportation and storage.

7.6 Product certificates

If certificates (like those specified in ISO 14344) of conformity and/or analysis are required, the purchaser and the manufacturer/supplier shall agree on the details at the time of placing the order.

8 Metal hazards

Although not directly relevant to the requirements of this International Standard, any national requirements for limiting exposure to metal hazards, e.g. fume, should be observed. This is particularly important when using brazing filler metals containing cadmium as an alloying element.

Table 5 — Class Al: aluminium and magnesium brazing filler metals

Code	Composition % by mass							Melting temperature (approximate)			
	Si	Fe	Cu	Mn	Mg	Zn	Others	Non-defined elements	Al	Solidus	Liquidus
	min./max.	min./max.	min./max.	min./max.	min./max.	min./max.	min./max.	Each	Total max.	min./max.	°C
Al-Si alloys											
Al 105	4,5/6,0	-/0,6	-/0,30	-/0,15	-/0,20	-/0,10	Ti: -/0,15	0,05	0,15	Remainder	575
Al 107	6,8/8,2	-/0,8	-/0,25	-/0,10	-/-	-/0,20	-/-	0,05	0,15	Remainder	575
Al 110	9,0/11,0	-/0,8	-/0,30	-/0,05	-/0,05	-/0,10	Ti: -/0,20	0,05	0,15	Remainder	575
Al 112	11,0/13,0	-/0,8	-/0,30	-/0,15	-/0,10	-/0,20	-/-	0,05	0,15	Remainder	575
Al-Si-Cu alloys											
Al 210	9,3/10,7	-/0,8	3,3/4,7	-/0,15	-/0,15	-/0,20	Cr: -/0,15	0,05	0,15	Remainder	520
Al-Si-Mg alloys											
Al 310	9,0/10,5	-/0,8	-/0,25	-/0,10	1,0/2,0	-/0,20	-/-	0,05	0,15	Remainder	555
Al 311	9,0/10,5	-/0,8	-/0,25	-/0,10	1,0/2,0	-/0,20	Bi: 0,02/0,20	0,05	0,15	Remainder	555
Al 315	9,5/11,0	-/0,8	-/0,25	-/0,10	0,20/1,0	-/0,20	-/-	0,05	0,15	Remainder	559
Al 317	11,0/13,0	-/0,8	-/0,25	-/0,10	0,10/0,50	-/0,20	-/-	0,05	0,15	Remainder	562
Al 319	10,5/13,0	-/0,8	-/0,25	-/0,10	1,0/2,0	-/0,20	-/-	0,05	0,15	Remainder	559
Al-Si-Zn alloys											
Al 410	9,0/11,0	-/0,8	-/0,3	-/0,05	-/0,05	0,50/3,0	-/-	0,05	0,15	Remainder	576
Al 415	6,8/8,2	-/0,8	-/0,25	-/0,10	-/-	0,50/3,0	-/-	0,05	0,15	Remainder	576
Mg alloys											
Mg 001	-/0,05	-/0,005	-/0,05	0,15/1,5	Remainder	1,7/2,3	Be: Ni: -/0,0002/0,0008 -/0,005	0,05	0,30	8,3/9,7	443
Maximum impurity limits applicable to all types are (% by mass) Cd 0,010 and Pb 0,025.											

Table 6 — Class Ag: silver brazing filler metals

Code	Composition % by mass								Melting temperature (approximate)	
	Ag min./ max.	Cu min./ max.	Zn min./ max.	Cd min./ max.	Sn min./ max.	Ni min./ max.	Mn min./ max.	Others min./max.	Solidus °C	Liqui- dus °C
Ag-Cu-Zn-Sn alloys										
Ag 125	24,0/26,0	39,0/41,0	31,0/35,0	—/—	1,5/2,5	—/—	—/—	—/—	680	760
Ag 130	29,0/31,0	35,0/37,0	30,0/34,0	—/—	1,5/2,5	—/—	—/—	—/—	665	755
Ag 134	33,0/35,0	35,0/37,0	25,5/29,5	—/—	2,0/3,0	—/—	—/—	—/—	630	730
Ag 138	37,0/39,0	31,0/33,0	26,0/30,0	—/—	1,5/2,5	—/—	—/—	—/—	650	720
Ag 140	39,0/41,0	29,0/31,0	26,0/30,0	—/—	1,5/2,5	—/—	—/—	—/—	650	710
Ag 145	44,0/46,0	26,0/28,0	23,5/27,5	—/—	2,0/3,0	—/—	—/—	—/—	640	680
Ag 155	54,0/56,0	20,0/22,0	20,0/24,0	—/—	1,5/2,5	—/—	—/—	—/—	630	660
Ag 156	55,0/57,0	21,0/23,0	15,0/19,0	—/—	4,5/5,5	—/—	—/—	—/—	620	655
Ag 160	59,0/61,0	29,0/31,0	—/—	—/—	9,5/10,5	—/—	—/—	—/—	600	730
Ag-Cu-Zn alloys										
Ag 205	4,0/6,0	54,0/56,0	38,0/42,0	—/—	—/—	—/—	—/—	Si: 0,05/0,25	820	870
Ag 212	11,0/13,0	47,0/49,0	38,0/42,0	—/—	—/—	—/—	—/—	Si: 0,05/0,25	800	830
Ag 220	19,0/21,0	43,0/45,0	34,0/38,0	—/—	—/—	—/—	—/—	Si: 0,05/0,25	690	810
Ag 225	24,0/26,0	39,0/41,0	33,0/37,0	—/—	—/—	—/—	—/—	—/—	700	790
Ag 230	29,0/31,0	37,0/39,0	30,0/34,0	—/—	—/—	—/—	—/—	—/—	680	765
Ag 230 ^a	29,0/31,0	35,0/37,0	29,5/34,0	—/—	—/—	2,0/2,5	—/—	Si: 0,05/0,15	675	790
Ag 235	34,0/36,0	31,0/33,0	31,0/35,0	—/—	—/—	—/—	—/—	—/—	685	755
Ag 244	43,0/45,0	29,0/31,0	24,0/28,0	—/—	—/—	—/—	—/—	—/—	675	735
Ag 245	44,0/46,0	29,0/31,0	23,0/27,0	—/—	—/—	—/—	—/—	—/—	665	745
Ag 250	49,0/51,0	33,0/35,0	14,0/18,0	—/—	—/—	—/—	—/—	—/—	690	775
Ag 265	64,0/66,0	19,0/21,0	13,0/17,0	—/—	—/—	—/—	—/—	—/—	670	720
Ag 270	69,0/71,0	19,0/21,0	8,0/12,0	—/—	—/—	—/—	—/—	—/—	690	740
Ag 272 ^a	71,0/73,0	27,0/29,0	—/—	—/—	—/—	—/—	—/—	—/—	780	780
Ag-Cu-Zn-Cd alloys										
Ag 326	24,0/26,0	29,0/31,0	25,5/29,5	16,5/18,5	—/—	—/—	—/—	—/—	605	720
Ag 330	29,0/31,0	27,0/29,0	19,0/23,0	19,0/23,0	—/—	—/—	—/—	—/—	600	690
Ag 335	34,0/36,0	25,0/27,0	19,0/23,0	17,0/19,0	—/—	—/—	—/—	—/—	610	700
Ag 340	39,0/41,0	18,0/20,0	19,0/23,0	18,0/22,0	—/—	—/—	—/—	—/—	595	630
Ag 345	44,0/46,0	14,0/16,0	14,0/18,0	23,0/25,0	—/—	—/—	—/—	—/—	605	620
Ag 350	49,0/51,0	14,5/16,5	14,5/18,5	17,0/19,0	—/—	—/—	—/—	—/—	620	640
Ag 351	49,0/51,0	14,5/16,5	13,5/17,5	15,0/17,0	—/—	2,5/3,5	—/—	—/—	635	655
Ag-Cu-Zn-Ni-Mn alloys										
Ag 425	24,0/26,0	37,0/39,0	31,0/35,0	—/—	—/—	1,5/2,5	1,5/2,5	—/—	705	800
Maximum impurity limits applicable to all types are (% by mass) Al 0,001, Bi 0,030, Cd 0,010, P 0,008, Pb 0,025; Si 0,05; total of all impurities = 0,15; total of all impurities for Ag 427, Ag 449 and Ag 485 = 0,30.										
If Si is intentionally added to all alloys of Table 6 , the range shall be between 0,05 and 0,25 (% by mass).										
The filler metals then have to be designated additionally by description Si at the end. For example: Filler metal ISO 17672-Ag 155Si or Filler metal ISO 17672-B-Ag55ZnCuSn(Si)-630/660.										
^a For special vacuum applications, see Table 1 .										

Table 6 (continued)

Code	Composition % by mass								Melting temperature (approximate)	
	Ag min./ max.	Cu min./ max.	Zn min./ max.	Cd min./ max.	Sn min./ max.	Ni min./ max.	Mn min./ max.	Others min./max.	Solidus °C	Liqui- dus °C
Ag 427	26,0/28,0	37,0/39,0	18,0/22,0	—/—	—/—	5,0/6,0	8,5/10,5	—/—	680	830
Ag 440	39,0/41,0	29,0/31,0	26,0/30,0	—/—	—/—	1,5/2,5	—/—	—/—	670	780
Ag 449	48,0/50,0	15,0/17,0	21,0/25,0	—/—	—/—	4,0/5,0	7,0/8,0	—/—	680	705
Ag 450	49,0/51,0	19,0/21,0	26,0/30,0	—/—	—/—	1,5/2,5	—/—	—/—	660	705
Ag 454	53,0/55,0	37,5/42,5	4,0/6,0	—/—	—/—	0,5/1,5	—/—	—/—	720	855
Ag 456	55,0/57,0	41,0/43,0	—/—	—/—	—/—	1,5/2,5	—/—	—/—	770	895
Ag 456 ^a	55,0/57,0	26,25/28,25	—/—	—/—	—/—	2,0/2,5		In: 13,5/15,5	600	710
Ag 463	62,0/64,0	27,5/29,5	—/—	—/—	5,0/7,0	2,0/3,0	—/—	—/—	690	800
Ag 485	84,0/86,0	—/—	—/—	—/—	—/—	—/—	14,0/16,0	—/—	960	970
Maximum impurity limits applicable to all types are (% by mass) Al 0,001, Bi 0,030, Cd 0,010, P 0,008, Pb 0,025; Si 0,05; total of all impurities = 0,15; total of all impurities for Ag 427, Ag 449 and Ag 485 = 0,30.										
If Si is intentionally added to all alloys of Table 6 , the range shall be between 0,05 and 0,25 (% by mass).										
The filler metals then have to be designated additionally by description Si at the end. For example: Filler metal ISO 17672-Ag 155Si or Filler metal ISO 17672-B-Ag55ZnCuSn(Si)-630/660.										
^a For special vacuum applications, see Table 1 .										

Table 7 — Class CuP: copper-phosphorus brazing filler metals

Code	Composition % by mass				Melting temperature (ap- proximate)	
	Cu	P min./max.	Ag min./max.	Other min./max.	Solidus °C	Liquidus ^a °C
Cu P alloys						
CuP 178	Remainder	4,8/5,3	—/—	—/—	710	925
CuP 179	Remainder	5,9/6,5	—/—	—/—	710	890
CuP 180	Remainder	6,6/7,4	—/—	—/—	710	820
CuP 181	Remainder	7,0/7,5	—/—	—/—	710	793
CuP 182	Remainder	7,5/8,1	—/—	—/—	710	770
Ag-Cu-P alloys						
CuP 279	Remainder	5,9/6,7	1,5/2,5	—/—	645	825
CuP 280	Remainder	6,8/7,2	1,8/2,2	—/—	645	788
CuP 281	Remainder	5,8/6,2	4,8/5,2	—/—	645	815
CuP 281 ^a	Remainder	5,7/6,3	4,5/5,5	—/—	645	815
CuP 282	Remainder	6,5/7,0	4,8/5,2	—/—	645	771
CuP 283	Remainder	7,0/7,5	5,8/6,2	—/—	645	720
Maximum impurity limits applicable to all types are (% by mass) Al 0,01, Bi 0,030, Cd 0,010, Pb 0,025, Zn 0,05, Zn + Cd 0,05; total of all impurities = 0,25.						
If Si is intentionally added to all alloys of Table 7 , the range shall be between 0,05 and 0,25 (% by mass).						
The filler metals then have to be designated additionally by description Si at the end. For example: Filler metal ISO 17672-CuP 279Si or Filler metal ISO 17672-B-Cu92PAg(Si)-645/825.						
These filler metals should never be used on ferrous metals, nickel alloys or copper alloys containing nickel.						
^a Unlike the majority of filler metals in this International Standard, which only flow satisfactorily at, around or above the liquidus, most copper phosphorus filler metals are sufficiently fluid for brazing at a temperature significantly below the liquidus.						

Table 7 (continued)

Code	Composition % by mass				Melting temperature (ap- proximate)	
	Cu	P min./max.	Ag min./max.	Other min./max.	Solidus °C	Liquidus ^a °C
CuP 283 ^a	Remainder	7,0/7,5	5,8/6,2	Ni 0,05/0,15	645	720
CuP 284	Remainder	4,8/5,2	14,5/15,5	—/—	645	800
CuP 285	Remainder	6,0/6,7	17,2/18,0	—/—	645	666
CuP 286	Remainder	6,6/7,5	17,0/19,0	—/—	645	645
Cu-Sn-Si-Sb alloys						
CuP 385	Remainder	6,0/7,0	—/—	Sn 6,0/7,0	635	675
				Si 0,01/0,4		
CuP 386	Remainder	6,4/7,2	—/—	Sn 6,5/7,5	650	700
CuP 389	Remainder	5,6/6,4	—/—	Sb 1,8/2,2	690	825
Maximum impurity limits applicable to all types are (% by mass) Al 0,01, Bi 0,030, Cd 0,010, Pb 0,025, Zn 0,05, Zn + Cd 0,05; total of all impurities = 0,25.						
If Si is intentionally added to all alloys of Table 7 , the range shall be between 0,05 and 0,25 (% by mass).						
The filler metals then have to be designated additionally by description Si at the end. For example: Filler metal ISO 17672-CuP 279Si or Filler metal ISO 17672-B-Cu92PAG(Si)-645/825.						
These filler metals should never be used on ferrous metals, nickel alloys or copper alloys containing nickel.						
^a Unlike the majority of filler metals in this International Standard, which only flow satisfactorily at, around or above the liquidus, most copper phosphorus filler metals are sufficiently fluid for brazing at a temperature significantly below the liquidus.						

Table 8 — Class Cu: copper brazing filler metals — High Cu alloys

Code	Composition % by mass						Total impurity limits (see table footnote) max.	Melting temperature (approximate) Liquidus °C
	Cu (including Ag) min.	Sn min./max.	Ag min./max.	Ni min./max.	P min./max.	Others min./max.		
Copper-cuprous oxide								
Cu 087	86,50	—/—	—/—	—/—	—/—	—/—	0,50	1 083
Cu 099	99,00	—/—	—/—	—/—	—/—	—/—	0,30 (excluding O)	1 083
Copper (99,9 min.)								
Cu 102	99,95	—/—	—/—	—/—	—/—	—/—	0,03 (excluding Ag)	1 083
Cu 110	99,90	—/—	—/—	—/—	—/—	—/—	0,04 (excluding O and Ag)	1 083
Cu 141	Remainder	—/—	—/—	—/—	—/0,075	—/—	0,060 (excluding Ag, As and Ni)	1 083
Cu-Ag alloy								
Cu 188	Remainder	—/—	0,8/1,2	—/—	—/—	Bi; —/0,1	—/—	0,3 (including Bi 0,1 max.)
Cu-Ni alloys								
Cu 186	Remainder	—/—	—/—	2,5/3,5	—/—	B: 0,02/0,05	—/—	0,15 (excluding Ag)
Cu-Sn alloys								
Cu 922	Remainder	5,5/7,0	—/—	—/—	0,01/0,40	—/—	—/—	Al 0,005
Cu 925	Remainder	11,0/13,0	—/—	—/—	0,01/0,40	—/—	—/—	Zn 0,05, others 0,1; total 0,4
Maximum impurity limits applicable to all types are (% by mass) Al 0,02 (except Cu 922), Cd 0,010 and Pb 0,025.								

Table 9 — Class Cu: copper brazing filler metals — Cu-Zn alloys

Code	Composition % by mass							Melting temperature (approximate)	
	Cu min./max.	Zn	Sn min./max.	Si min./max.	Mn min./max.	Ni min./max.	Fe min./max.	Solidus °C	Liquidus °C
Cu 470	57,0/61,0	Remainder	0,2/0,5	—/—	—/—	—/—	—/—	875	895
Cu 470 a	58,5/61,5	Remainder	—/—	0,2/0,4	—/—	—/—	—/—	875	895
Cu 471	56,0/60,0	Remainder	0,2/0,5	0,15/0,2	0,05/0,25	—/—	—/—	870	900
Cu 670	58,5/61,5	Remainder	—/0,2	0,15/0,4	0,05/0,25	—/—	—/—	870	900
Cu 671	56,0/62,0	Remainder	0,5/1,5	0,1/0,5	0,2/1,0	0,2/1,5	—/—	870	890
Cu 680	56,0/60,0	Remainder	0,8/1,1	0,04/0,20	0,01/0,50	0,20/0,80	0,2/1,2	866	882
Cu 681	56,0/60,0	Remainder	0,8/1,1	0,04/0,15	0,01/0,50	—/—	0,2/1,2	866	888
Cu 773	46,0/50,0	Remainder	—/—	0,15/0,2	—/—	9,0/11,0	—/—	890	920

Maximum impurity limits applicable to all types are (% by mass) Al 0,01, As 0,01, Bi 0,01, Cd 0,010, Fe 0,25, Pb 0,025, Sb 0,01; total impurities (excluding Fe) 0,2.

Table 10 — Class Cu: copper brazing filler metals — Cu special alloys

Code	Cu	Al	Composition % by mass						Melting temperature (approximate)		
			Fe	Mn	Ni	P	Si	Sn	Zn	Total impurities max.	Solidus °C
	min./max.	min./max.	min./max.	min./max.	min./max.	min./max.	min./max.	min./max.	min./max.	min./max.	Liquidus °C
Cu-Si-Mn alloys											
Cu 511	Remainder	-/0,01	-/0,03	0,1/0,4	-/0,1	-/0,020	0,1/0,4	0,5/1,0	-	0,1	1 020
Cu 521	Remainder	-/0,01	-/0,1	0,5/1,5	-/-	-/0,02	1,5/2,0	0,1/0,3	-/0,2	0,5	1 030
Cu 541	Remainder	-/0,05	-/0,2	0,7/1,3	-/-	-/0,05	2,7/3,2	-	-/0,4	0,5	1 035
Cu-Al alloys											
Cu 551	Remainder	4,5/5,5	-/0,5	0,1/1,0	1,0/2,5	-/-	-/0,1	-	-/0,2	0,5	1 040
Cu 561	Remainder	7,0/9,0	-/0,5	-/0,5	-/0,5	-/-	-/0,2	-/0,1	-/0,2	0,2	1 030
Cu 565	Remainder	8,5/11,5	0,5/1,5	-/-	-/-	-/-	-/0,1	-	-/0,02	0,5	1 030
Cu-Mn-Ni alloys											
Cu 571	Remainder	7,0/8,5	2,0/4,0	11,0/14,0	1,5/3,0	-/-	-/0,1	-	-/0,15	0,5	945
Cu 595	Remainder	-/0,01	-/-	11,0/14,0	1,5/5,0	-/-	0,10/0,25	-/-	-/-	0,5	965
Maximum impurity limits applicable to all types are (% by mass) Cd 0,010 and Pb 0,025.											

Table 11 – Classes Ni: nickel (and cobalt brazing) filler metals

Code	Composition % by mass										Melting temperature (approximate)			
	Ni min./ max.	Co min./max.	Cr min./max.	Si min./max.	B min./max.	Fe min./max.	C min./max.	P min./max.	W min./max.	Cu min./max.	Mn min./max.	Mo min./max.	Nb min./max.	Liquidus °C
Ni-Cr-B alloys														
Ni 600 Rem.	-/0,10	13,0/15,0	4,0/5,0	2,75/3,50	4,0/5,0	0,60/0,90	-/0,02	-/-	-/-	-/-	-/-	-/-	980	1 060
Ni 610 Rem.	-/0,10	13,0/15,0	4,0/5,0	2,75/3,50	4,0/5,0	-/0,06	-/0,02	-/-	-/-	-/-	-/-	-/-	980	1 070
Ni 612 Rem.	-/0,10	13,5/16,5	-/-	3,25/4,0	-/1,5	-/0,06	-/0,02	-/-	-/-	-/-	-/-	-/-	1 055	1 055
Ni 620 Rem.	-/0,10	6,0/8,0	4,0/5,0	2,75/3,50	2,5/3,5	-/0,06	-/0,02	-/-	-/-	-/-	-/-	-/-	970	1 000
Ni-Si-B alloys														
Ni 630 Rem.	-/0,10	-/-	4,0/5,0	2,75/3,50	-/0,5	-/0,06	-/0,02	-/-	-/-	-/-	-/-	-/-	980	1 040
Ni 631 Rem.	-/0,10	-/-	3,0/4,0	1,50/2,20	-/1,5	-/0,06	-/0,02	-/-	-/-	-/-	-/-	-/-	980	1 070
Ni-Cr-Si alloys														
Ni 650 Rem.	-/0,10	18,5/19,5	9,75/10,50	-/0,03	-/-	-/0,06	-/0,02	-/-	-/-	-/-	-/-	-/-	1 080	1 135
Ni 655 Rem.	-/0,10	21,0/23,0	6,0/7,0	-/0,01	-/-	-/0,16	3,5/4,5	-/-	-/-	-/-	-/-	-/-	960	1 079
Ni 660 Rem.	-/0,10	18,5/19,5	7,0/7,5	1,0/1,5	-/0,5	-/0,10	-/0,02	-/-	-/-	-/-	-/-	-/-	1 065	1 150
Ni 661 Rem.	-/1,0	14,5/15,5	7,0/7,5	1,1/1,6	-/1,0	-/0,06	-/0,02	-/-	-/-	-/-	-/-	-/-	1 030	1 125
Ni-W-Cr alloys														
Ni 670 Rem.	-/0,10	10,0/13,0	3,0/4,0	2,0/3,0	2,5/4,5	0,40/0,55	-/0,02	15,0/17,0	-/-	-/-	-/-	-/-	970	1 105
Ni 671 Rem.	-/0,10	9,0/11,75	3,35/4,25	2,2/3,1	2,5/4,0	0,30/0,50	-/0,02	11,5/12,75	-/-	-/-	-/-	-/-	970	1 095
Ni-P alloys														
Ni 700 Rem.	-/0,10	-/-	-/-	-/-	-/-	-/0,06	10,0/12,0	-/-	-/-	-/-	-/-	-/-	875	875
Ni 710 Rem.	-/0,10	13,0/15,0	-/0,10	-/0,02	-/0,2	-/0,06	9,7/10,5	-/-	-/-	-/0,04	-/-	-/-	890	890
Ni 720 Rem.	-/0,10	24,0/26,0	-/0,10	-/0,02	-/0,2	-/0,06	9,0/11,0	-/-	-/-	-/-	-/-	-/-	880	950
Ni-Mn-Si-Cu alloys														
Ni 800 Rem.	-/0,10	-/-	6,0/8,0	-/-	-/0,06	-/0,02	-/-	4,0/5,0	21,5/24,5	-/-	-/-	-/-	980	1 010
Ni-Cr-B-Si-Cu-Mo-Nb alloys														
Maximum impurity limits applicable to all types are (% by mass) Al 0,05, Cd 0,010, Pb 0,025, S 0,02, Se 0,005, Ti 0,05, Zr 0,05; if elements other than those given here are found to be present, the amount of these elements shall be determined; the total of such other elements shall not exceed 0,50 %.														

Table 11 (continued)

Code	Composition % by mass												Melting temperature (approximate)		
	Ni min./ max.	Co min./max.	Cr min./max.	Si min./max.	B min./max.	Fe min./max.	C min./max.	P min./max.	W min./max.	Cu min./max.	Mn min./max.	Mo min./max.	Nb min./max.	Liquidus °C	Solidus °C
Ni 810	—/0,10	7,0/9,0	3,8/4,8	2,75/3,50	—/0,4	—/0,06	—/0,02	—/—	2,0/3,0	—/—	1,5/2,5	1,5/2,5	970	1 080	
Co-Ni-Si-W alloys															
Co 900	16,0/18,0	Rem.	18,0/20,0	7,5/8,5	0,70/0,90	—/1,0	0,35/0,45	—/0,02	3,5/4,5	—/—	—/—	—/—	—/—	1 120	1 150

Maximum impurity limits applicable to all types are (% by mass) Al 0,05, Cd 0,010, Pb 0,025, S 0,02, Se 0,005, Ti 0,05, Zr 0,05; if elements other than those given here are found to be present, the amount of these elements shall be determined; the total of such other elements shall not exceed 0,50 %.

Table 12 — Class Pd: palladium bearing brazing filler metals

Code	Composition % by mass						Melting temperature (approximate)	
	Ag min./max.	Cu min./max.	Pd min./max.	Mn min./max.	Ni min./max.	Co min./max.	Solidus °C	Liquidus °C
Pd 287 ^a	67,0/69,0	26,0/27,0	4,5/5,5	—/—	—/—	—/—	805	810
Pd 288 ^a	94,5/95,5	—/—	4,5/5,5	—/—	—/—	—/—	970	1 010
Pd 387 ^a	57,0/59,0	31,0/33,0	9,5/10,5	—/—	—/—	—/—	825	850
Pd 388 ^a	67,0/68,0	22,0/23,0	9,5/10,5	—/—	—/—	—/—	830	860
Pd 481 ^a	64,5/65,5	19,5/20,5	14,5/15,5	—/—	—/—	—/—	850	900
Pd 483 ^a	—/—	81,5/82,5	17,5/18,5	—/—	—/—	—/—	1 080	1 090
Pd 484 ^a	51,5/52,5	27,5/28,5	19,5/20,5	—/—	—/—	—/—	875	900
Pd 485 ^a	74,5/75,5	—/—	19,5/20,5	4,5/5,5	—/—	—/—	1 000	1 120
Pd 496 ^a	—/—	—/—	20,5/21,5	30,5/31,5	47,0/49,0	—/—	1 120	1 120
Pd 587 ^a	53,0/55,0	20,5/21,5	24,5/25,5	—/—	—/—	—/—	900	950
Pd 597 ^a	63,0/65,0	—/—	32,0/—33,5	2,5/3,5	—/—	—/—	1 180	1 200
Pd 647 ^a	—/—	—/—	59,5/60,5	—/—	39,5/40,5	—/—	1 235	1 235
Pd 657 ^a	—/—	—/—	64,0/66,0	—/—	—/0,06	34,0/36,0	1 235	1 252

For Pd 287, Pd 288, Pd 387, Pd 388, Pd 481, Pd 483, Pd 484, Pd 587 and Pd 657, maximum impurity limits applicable are (% by mass) Al 0,0010, P 0,008, Ti 0,002, Zr 0,002; total of all impurities = 0,15.

For Pd 485 and Pd 597, maximum impurity limits are (% by mass) Al 0,010, Ti 0,01, Zr 0,01; total of all impurities = 0,30.

^a For special vacuum applications, see [Table 1](#).

Table 13 — Class Au: gold bearing brazing filler metals

Code	Composition % by mass						Melting temperature (approximate)	
	Au min./max.	Cu min./max.	Ni min./max.	Pd min./max.	Ag min./max.	Others min./max.	Solidus °C	Liquidus °C
Au 295 ^a	29,5/30,5	69,5/70,5	—/—	—/—	—/—	—/—	995	1 020
Au 300	29,5/30,5	—/—	35,5/36,5	33,5/34,5	—/—	—/—	1 135	1 165
Au 351	34,5/35,5	61,0/63,0	2,5/3,5	—/—	—/—	—/—	975	1 030
Au 354	34,5/35,5	64,5/65,5	—/—	—/—	—/—	—/—	990	1 010
Au 375 ^a	37,0/38,0	62,0/63,0	—/—	—/—	—/—	—/—	980	1 000
Au 503	49,5/50,5	49,5/50,5	—/—	—/—	—/—	—/—	955	970
Au 507	49,5/50,5	—/—	24,5/25,5	24,0/26,0	—/—	Co —/0,06	1 100	1 120
Au 625 ^a	62,0/63,0	37,0/38,0	—/—	—/—	—/—	—/—	930	940
Au 700	69,5/70,5	—/—	21,5/22,5	7,5/8,5	—/—	—/—	1 005	1 045
Au 752 ^a	74,5/75,5	—/—	24,5/25,5	—/—	—/—	—/—	950	990
Au 755	74,5/75,5	11,5/13,5	—/—	—/—	12,0/13,0	—/—	880	895
Au 800	79,5/80,5	19,5/20,5	—/—	—/—	—/—	—/—	890	890
Au 801 ^a	79,5/80,5	18,5/19,5	—/—	—/—	—/—	Fe 0,5/1,5	905	910
Au 827 ^a	81,5/82,5	—/—	17,5/18,5	—/—	—/—	—/—	950	950
Au 927	91,0/93,0	—/—	—/—	7,0/9,0	—/—	—/—	1 200	1 240

Maximum impurity limits applicable to all types are (% by mass) Al 0,0010, Cd 0,010, P 0,008, Pb 0,025, Ti 0,002, Zr 0,002; total of all impurities = 0,15.

^a For special vacuum applications, see [Table 1](#).

Annex A (normative)

Codification

Two systems for the codification of filler metals are used in this International Standard. For the purposes of identifying a filler metal complying with this International Standard, e.g. in other International Standards, in orders, in brazing procedures or on drawings, any of these systems can be used.

The first system divides the filler metals into seven classes. The class to which a filler metal is assigned is based, in most cases, on the major element present, but in some instances, it has been decided by the similarity of the filler metal to others in the same class.

The seven classes are as follows:

- a) Al: filler metals containing aluminium as the major element;
- b) Ag: filler metals containing silver as a significant addition, even if not the major element;
- c) CuP: filler metals containing copper as the major element with an addition of phosphorus;
- d) Cu: filler metals containing copper as the major element, not elsewhere classified;
- e) Ni: filler metals containing nickel as the major element; one is based on cobalt;
- f) Pd: filler metals containing palladium, in any amount;
- g) Au: filler metals containing gold, in any amount.

The code for each filler metal consists of the two letters for the class, followed by three digits.

The second system is that given in ISO 3677. However, this system can assign the same code to filler metals which differ only slightly in chemical composition but significantly in behaviour.

The relationship between these two systems and the former systems is given in [Table A.1](#).

Table A.1 — Codification systems

ISO	ISO 3677	AWS	EN 1044	JIS
Aluminium brazing filler metals				
Al 105	B-Al95Si-575/630		AL 101	
Al 107	B-Al92Si-575/615	BA1Si-2	AL 102	BA4343
Al 110	B-Al90Si-575/590	BA1Si-5	AL 103	BA4045
Al 112	B-Al88Si-575/585	BA1Si-4	AL 104	BA4047
Al 210	B-Al86SiCu-520/585	BA1Si-3	AL 201	BA4145
Al 310	B-Al89SiMg-555/590	BA1Si-7	AL 301	BA4004
Al 311	B-Al89SiMg(Bi)-555/590	BA1Si-11	AL 302	BA4104
Al 315	B-Al90Si-559/591			BA4005
Al 317	B-Al88SiMg-562/582	BA1Si-9		
Al 319	B-Al89SiMg-559/579			BA4N04
Al 410	B-Al87SiZn-576/588			BA4N45
Al 415	B-Al90SiZn-576/609			BA4N43
Mg 001	B-Mg88AlZnMn-443/599	BMg-1		

Table A.1 (continued)

ISO	ISO 3677	AWS	EN 1044	JIS
Silver brazing filler metals				
Ag 125	B-Cu40ZnAgSn-680/760	BAg-37	AG 108	
Ag 130	B-Cu36ZnAgSn-665/755		AG 107	
Ag 134	B-Cu36AgZnSn-630/730		AG 106	BAg-7B
Ag 138	B-Ag38CuZnSn-650/720	BAg-34		BAg-34
Ag 140	B-Ag40CuZnSn-650/710	BAg-28	AG 105	BAg-28
Ag 145	B-Ag45CuZnSn-640/680	BAg-36	AG 104	BAg-7A
Ag 155	B-Ag55ZnCuSn-630/660		AG 103	
Ag 156	B-Ag56CuZnSn-620/655	BAg-7	AG 102	BAg-7
Ag 160	B-Ag60CuSn-600/730	BAg-18	AG 402	BAg-18
Ag 205	B-Cu55ZnAg(Si)-820/870		AG 208	
Ag 212	B-Cu48ZnAg(Si)-800/830		AG 207	
Ag 220	B-Cu43ZnAg(Si)-690/810		AG 206	
Ag 225	B-Cu40ZnAg-700/790		AG 205	BAg-20A
Ag 230	B-Cu38ZnAg-680/765	BAg-20	AG 204	BAg-20
Ag 230 ^a	B-CuZnAgNi-676/788			
Ag 235	B-Ag35ZnCu-685/755	BAg-35		BAg-35
Ag 244	B-Ag44CuZn-675/735		AG 203	
Ag 245	BAg-45CuZn-665/745	BAg-5		BAg-5
Ag 250	B-Ag50CuZn-690/775	BAg-6		BAg-6
Ag 265	B-Ag65CuZn-670/720	BAg-9		BAg-9
Ag 270	B-Ag70CuZn-690/740	BAg-10		BAg-10
Ag 272	B-Ag72Cu-780	BAg-8	AG 401	BAg-8
Ag 326	B-Cu30ZnAgCd-605/720	BAg-33	AG 307	
Ag 330	B-Ag30CuCdZn-600/690		AG 306	
Ag 335	B-Ag35CuZnCd-610/700	BAg-2	AG 305	BAg-2
Ag 340	B-Ag40ZnCdCu-595/630		AG 304	
Ag 345	B-Ag45CdZnCu-605/620	BAg-1	AG 302	BAg-1
Ag 350	B-Ag50CdZnCu-620/640	BAg-1a	AG 301	BAg-1A
Ag 351	B-Ag50CdZnCuNi-635/655	BAg-3	AG 351	
Ag 425	B-Cu38ZnAgNiMn-705/800	BAg-26		BAg-26
Ag 427	B-Cu38AgZnMnNi-680/830		AG 503	
Ag 440	B-Ag40CuZnNi-670/780	BAg-4		BAg-4
Ag 449	B-Ag49ZnCuMnNi-680/705	BAg-22	AG 502	BAg-22
Ag 450	B-Ag50ZnCuNi-660/705	BAg-24		BAg-24
Ag 454	B-Ag54CuZnNi-720/855	BAg-13		BAg-13
Ag 456	B-Ag56CuNi-770/895	BAg-13a		BAg-13A
Ag 456 ^a	B-Ag56CuInNi-600/710		AG 403	
Ag 463	B-Ag63CuSnNi-690/800	BAg-21		BAg-21
Ag 485	B-Ag85Mn-960/970	BAg-23	AG 501	BAg-23
Copper-phosphorus brazing filler metals				
CuP 178	B-Cu95P-710/925			BCuP-1
CuP 179	B-Cu94P-710/890		CP 203	
CuP 180	B-Cu93P-710/820		CP 202	BCuP-2

Table A.1 (continued)

ISO	ISO 3677	AWS	EN 1044	JIS
CuP 181	B-Cu93P-710/793	BCuP-2		
CuP 182	B-Cu92P-710/770		CP 201	
CuP 279	B-Cu92PAG-645/825		CP 105	
CuP 280	B-Cu91PAG-643/788	BCuP-6		BCuP-6
CuP 281	B-Cu89PAG-645/815	BCuP-3		
CuP 281 ^a	B-Cu89PAG-645/815		CP 104	
CuP 282	B-Cu88PAG-643/771	BCuP-7		BCuP-7
CuP 283	B-Cu87PAG-643/720	BCuP-4		BCuP-4
CuP 283 ^a	B-Cu87PAG(Ni)-643/720		CP 103	
CuP 284	B-Cu80AgP-645/800	BCuP-5	CP 102	BCuP-5
CuP 285	B-Cu76AgP-643/666	BCuP-8		
CuP 286	B-Cu75AgP-645		CP 101	BCuP-8
CuP 385	B-Cu87PSn(Si)-635/675	BCuP-9		BCuP-9
CuP 386	B-Cu86SnP-650/700		CP 302	
CuP 389	B-Cu92PSb-690/825		CP 301	
Copper brazing filler metals				
Cu 087	B-Cu87-1083	BCu-2		BCu-2
Cu 099	B-Cu99-1083	BCu-1a	CU 103	BCu-1A
Cu 102	B-Cu100-1083	BCu-3	CU 102	
Cu 110	B-Cu100-1083	BCu-1b	CU 101	BCu-1
Cu 141	B-Cu100(P)-1083	BCu-1	CU 104	
Cu 186	B-Cu97Ni(B)-1083/1100		CU 105	
Cu 188	B-Cu99Ag-1070/1080		CU 106	
Cu 922	B-Cu94Sn(P)-910/1040		CU 201	
Cu 925	B-Cu88Sn(P)-825/990		CU 202	
Cu 470	B-Cu60Zn(Sn)-875/895	RBCuZn-A	CU 302	BCu-6
Cu 470 ^a	B-Cu60Zn(Si)-875/895		CU 301	BCu-5
Cu 471	B-Cu58Zn(Sn)(Si)(Mn)-870/900		CU 304	
Cu 670	B-Cu60Zn(Si)(Mn)-870/900		CU 303	
Cu 671	B-Cu59ZnSn(Ni)(Mn)(Si)-870/890		CU 306	
Cu 680	B-Cu58ZnSn(Fe)(Ni)(Mn)-866/882	RBCuZn-B		
Cu 681	B-Cu58ZnSn(Fe)(Mn)(Si)-866/888	RBCuZn-C		
Cu 773	B-Cu48ZnNi(Si)-890/920	RBCuZn-D	CU 305	BCu-8
Cu 511	B-Cu99(Sn)(Mn)(Si)-1020/1050			
Cu 521	B-Cu97SiMn(Sn)-1030/1050			
Cu 541	B-Cu96SiMn-980/1035			
Cu 551	B-Cu92AlNi(Mn)-1040/1075			
Cu 561	B-Cu92Al-1030/1040			
Cu 565	B-Cu89AlFe-1030/1040			
Cu 571	B-Cu74MnAlFeNi-945/985			
Cu 595	B-Cu84MnNi-965/1000			

Table A.1 (continued)

ISO	ISO 3677	AWS	EN 1044	JIS
Nickel and cobalt brazing filler materials				
Ni 600	B-Ni73CrFeSiB(C)-980/1060	BNi-1	NI 101	BNi-1
Ni 610	B-Ni74CrFeSiB-980/1070	BNi-1a	NI 1A1	BNi-1A
Ni 612	B-Ni81CrB-1055	BNi-9	NI 109	BNi-9
Ni 620	B-Ni82CrSiBFe-970/1000	BNi-2	NI 102	BNi-2
Ni 630	B-Ni92SiB-980/1040	BNi-3	NI 103	BNi-3
Ni 631	B-Ni95SiB-980/1070	BNi-4	NI 104	BNi-4
Ni 650	B-Ni71CrSi-1080/1135	BNi-5	NI 105	BNi-5
Ni 655	B-Ni68CrSiP-960/1079			
Ni 660	B-Ni73CrSiB-1065/1150	BNi-5a		BNi-5A
Ni 661	B-Ni77CrSiBFe-1030/1125	BNi-5b		BNi-5B
Ni 670	B-Ni63WCrFeSiB-970/1105	BNi-10	NI 110	BNi-10
Ni 671	B-Ni67WCrSiFeB-970/1095	BNi-11	NI 111	BNi-11
Ni 700	B-Ni89P-875	BNi-6	NI 106	BNi-6
Ni 710	B-Ni76CrP-890	BNi-7	NI 107	BNi-7
Ni 720	B-Ni65CrP-880/950	BNi-12	NI 112	BNi-12
Ni 800	B-Ni66MnSiCu-980/1010	BNi-8	NI 108	BNi-8
Ni 810	B-Ni78CrSiBCuMo-970/1080	BNi-13		BNi-13
Co 900	B-Co51CrNiSiW(B)-1120/1150	BCo-1	CO 101	BCo-1
Palladium bearing brazing filler metals				
Pd 287	B-Ag68CuPd-805/810	BVAg-30	PD 106	BPd-1
Pd 288	B-Ag95Pd-970/1010		PD 204	BPd-7
Pd 387	B-Ag58CuPd-825/850	BVAg-31	PD 105	BPd-2
Pd 388	B-Ag68CuPd-830/860		PD 104	BPd-3
Pd 481	B-Ag65CuPd-850/900		PD 103	BPd-4
Pd 483	B-Cu82Pd-1080/1090		PD 203	BPd-8
Pd 484	B-Ag52CuPd-875/900		PD 102	BPd-5
Pd 485	B-Ag75PdMn-1000/1120		PD 202	BPd-9
Pd 496	B-Ni48MnPd-1120			BPd-11
Pd 587	B-Ag54PdCu-900/950	BVAg-32	PD 101	BPd-6
Pd 597	B-Ag64PdMn-1180/1200			BPd-10
Pd 647	B-Pd60Ni-1235		PD 201	BPd-14
Pd 657	BPd65Co-1235/1252	BPVPd-1	PD 301	
Gold bearing brazing filler metals				
Au 295	B-Cu70Au-995/1020		AU 104	BAu-1A
Au 300	B-Ni36PdAu-1135/1165	BAu-5		BAu-5
Au 351	B-Cu62AuNi-975-1030	BAu-3		BAu-3
Au 354	B-Cu65Au-990/1010	BVAu-9		
Au 375	B-Cu62Au-980/1000	BAu-1	AU 103	BAu-1
Au 503	B-Au50Cu-955/970	BVAu-10		BAu-11
Au 507	B-Au50NiPd-1100/1120	BVAu-7		
Au 625	B-Au62Cu-930/940		AU 102	
Au 700	B-Au70NiPd-1005/1045	BAu-6		BAu-6
Au 752	B-Au75Ni-950/990		AU 106	

Table A.1 (*continued*)

ISO	ISO 3677	AWS	EN 1044	JIS
Au 755	B-Au75AgCu-880/895			BAu-12
Au 800	B-Au80Cu-890	BAu-2		BAu-2
Au 801	B-Au80Cu(Fe)-905/910		AU 101	
Au 827	B-Au82Ni-950	BAu-4	AU 105	
Au 927	B-Au92Pd-1200/1240	BVAu-8		

Bibliography

- [1] ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*
- [2] EN 1044, *Brazing — Filler metals*

This page deliberately left blank

This page deliberately left blank

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Rewrites

Our British Standards and other publications are updated by amendment or revision. We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK