

BS EN ISO 17683:2015



BSI Standards Publication

Ships and marine technology — Ceramic weld backing for marine use

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 17683:2015. It is identical to ISO 17683:2014. It supersedes BS ISO 17683:2014 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee WEE/-/1, Briefing committee for welding.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 88231 9

ICS 47.020.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 28 February 2014.

Amendments/corrigenda issued since publication

Date	Text affected
31 January 2016	This corrigendum renumbers BS ISO 17683:2014 as BS EN ISO 17683:2015

EUROPEAN STANDARD

EN ISO 17683

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2015

ICS 47.020.10

English Version

Ships and marine technology - Ceramic weld backing for marine use (ISO 17683:2014)

Navires et technologie maritime - Soutien de soudures
en céramique pour usage maritime (ISO 17683:2014)

Schiffe und Meerestechnik - Keramische
Schweißbadsicherungen für maritime Anwendungen
(ISO 17683:2014)

This European Standard was approved by CEN on 11 June 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

The text of ISO 17683:2014 has been prepared by Technical Committee ISO/TC 8 “Ships and marine technology” of the International Organization for Standardization (ISO) and has been taken over as EN ISO 17683:2015 by Technical Committee CEN/TC 121 “Welding and allied processes” the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2016, and conflicting national standards shall be withdrawn at the latest by June 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 17683:2014 has been approved by CEN as EN ISO 17683:2015 without any modification.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Classification	1
5 Dimensions and appearance	2
5.1 General	2
5.2 Dimensions	2
5.3 Appearance	2
6 Performance and test	2
6.1 Moisture absorption rate	2
6.2 Refractoriness	3
6.3 Chemical composition	3
6.4 Adhesive aluminium foil tape	3
6.5 Metal cases	3
7 Type approval test	4
7.1 General	4
7.2 Test items	4
7.3 Acceptance criteria	4
8 Acceptance test	4
8.1 Test items	4
8.2 Acceptance criteria	4
9 Marking, packaging, and storage	5
9.1 Marking	5
9.2 Packaging	5
9.3 Storage	5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 8, *Ships and marine technology*, Subcommittee SC 8, *Ship design*.

Ships and marine technology — Ceramic weld backing for marine use

1 Scope

This International Standard specifies the classification, dimension and appearance, performance, and test methods for ceramic weld backing. It also specifies marking, packaging, and storage.

This International Standard is applicable to designing, manufacturing, testing, and accepting ceramic weld backing that are to be used in the double side form with single side weld, such as arc welding, gas welding, vertical gas welding, and submerged arc welding, and the shaping structural steel welding end for carbon steel, stainless steel, aluminium alloy, copper alloy, and so on.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 528, *Refractory products — Determination of pyrometric cone equivalent (refractoriness)*

ISO 29862, *Self adhesive tapes — Determination of peel adhesion properties*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

ceramic weld backing block

ceramic block with certain geometric shape manufactured by inorganic material

3.2

moisture absorption rate

W_a

ratio of the weight of water vapour absorbed on the surface of ceramic weld backing block to the weight of the dried sample, with certain temperature, humidity, and time

3.3

adhesive aluminium foil tape

strip of aluminium foil coated with pressure-sensitive adhesive and covered with release paper

3.4

metal case

case which is made of low carbon steel, and used for combining ceramic weld backing blocks

4 Classification

According to the fixed method, ceramic weld backing is classified as follows:

- a) type I — ceramic weld backing with adhesive aluminium foil tape;
- b) type II — ceramic weld backing with metal cases.

5 Dimensions and appearance

5.1 General

For inspection of its dimensions and appearance, six strips of ceramic weld backing shall be randomly selected. Each one of the samples shall meet the requirements in 5.2 and 5.3.

5.2 Dimensions

5.2.1 The tolerance of thickness for ceramic weld backing block shall be $\pm 0,5$ mm of its thickness.

5.2.2 The length tolerance for a strip of ceramic weld backing shall be -10 mm to $+20$ mm of its length.

5.2.3 The centreline tolerance for ceramic weld backing block with moulding groove shall be $\pm 1,0$ mm.

5.2.4 The angle tolerances of a triangular or trapezoidal ceramic weld backing block shall be $\pm 2^\circ$.

5.3 Appearance

5.3.1 Defects, such as damage and rounded corners, are not allowed for the joints between ceramic weld backing blocks other than rounded corners made by the mould itself.

5.3.2 Within the area of the groove of the ceramic weld backing blocks and 2 mm on either side of them, mould sticking grain shall not be larger than 0,5 mm and the defect of the pit and damages shall not be more than 0,5 mm on the surface of the ceramic weld backing blocks.

6 Performance and test

6.1 Moisture absorption rate

6.1.1 The moisture absorption rate shall be measured as follows.

- a) Randomly select three samples among the ceramic weld backing blocks. The dust on their surface shall be blown clear. Lay the samples on a tray, then put into an oven of constant temperature and humidity together.
- b) Switch on the power of the oven and adjust the humidity to (95 ± 3) % and the temperature to (25 ± 2) °C.
- c) Keep the samples and tray in the oven for 4 h, then take the samples out of the oven, weigh all samples, and record the weights as m_2 separately with an accuracy of 0,001 g.
- d) Lay the samples on the tray, then place into the oven of constant temperature. Switch on the power of the oven, adjust the temperature to 200 °C, and keep for 2 h.
- e) Take the samples out of the oven and keep it in the dryer until it cools down to the room temperature. Weigh all samples by an analytical balance, and record the weights as m_1 separately with an accuracy of 0,001 g.
- f) The moisture absorption rate for each sample shall be calculated in accordance with Formula (1).

$$W_a = \frac{m_2 - m_1}{m_1} \times 100 \% \quad (1)$$

where

W_a is the value of the moisture absorption rate (%);

m_1 is the weight of dried sample (g);

m_2 is the weight of sample which has absorbed water vapour sufficiently (g).

g) Calculate the average value of the three samples.

6.1.2 The average value of the moisture absorption rate shall be less than 0,35 %.

6.2 Refractoriness

6.2.1 The refractoriness should be determined according to the welding method and melting point for the metal to be welded.

6.2.2 Randomly select one ceramic weld backing block. The test of the refractoriness shall be conducted according to ISO 528.

6.3 Chemical composition

6.3.1 The content of sulfur and phosphorus in the ceramic weld backing shall be analysed by an appropriate method and shall be less than 0,1 %.

6.3.2 The content of boron in the ceramic weld backing shall be analysed by an appropriate method and shall be less than 0,01 %.

6.3.3 Any analytical technique can be used, but in case of dispute, reference shall be made to established, published methods.

6.4 Adhesive aluminium foil tape

6.4.1 Randomly select one strip of type I ceramic weld backing for the adhesive aluminium foil tape test.

6.4.2 The peeling strength of adhesive aluminium foil tape shall be determined in accordance with ISO 29862 and shall be more than 12 N/25 mm.

6.5 Metal cases

6.5.1 Randomly select one strip of type II ceramic weld backing for the metal cases test.

6.5.2 Erect the strip of ceramic weld backing, and there is no loose between the ceramic weld backing and metal cases.

7 Type approval test

7.1 General

The type approval test shall be carried out under one of the following situations:

- a) initial production;
- b) upon reproduction or re-manufacturing, after being suspended from production for half a year or more, or production for 4 y continuously;
- c) whenever the manufacturing technique which could affect the performance or quality of the products, or its ingredient and raw material, is changed significantly.

7.2 Test items

The following tests for type approval shall be carried out, in addition to the items required in [5.2](#) and [5.3](#):

- a) moisture absorption rate (see [6.1](#));
- b) refractoriness (see [6.2](#));
- c) chemical composition (see [6.3](#));
- d) adhesive aluminium foil tape (for type I) (see [6.4](#));
- e) metal cases (for type II) (see [6.5](#)).

7.3 Acceptance criteria

If the samples meet all test requirements, the batch of ceramic weld backing will be deemed to have passed the type test. However, if the samples fail to meet any of the test requirements, additional double of samples shall be tested. If the additional samples pass all test requirements, the batch of ceramic weld backing will be deemed to have passed the type test. Otherwise, the batch of ceramic weld backing will be deemed to have failed the type test.

8 Acceptance test

8.1 Test items

Prior to delivery of the batch of ceramic weld backing blocks, the manufacturer shall test every batch of ceramic weld backing block for the following items:

- a) dimensions and tolerances (see [5.2](#));
- b) appearance (see [5.3](#));
- c) moisture absorption rate (see [6.1](#));
- d) chemical composition (see [6.3](#)).

8.2 Acceptance criteria

With the same lot of raw materials, ingredients, and manufacturing technique, the ceramic weld backing can be inspected as one batch which should not be more than 500 000 m. If less than 500 000 m, the products should be treated as a batch.

If the batch of ceramic weld backing meets the requirements specified in 8.1, the batch of the products will be deemed to have passed the acceptance test. However, if some samples fail to meet any of the test requirements, additional double of samples can be allowed only one time for re-test. If the additional samples pass the test requirements in 8.1, the batch of the products will be deemed to have passed the acceptance test. Otherwise, the batch of the products will be deemed to have failed the acceptance test.

9 Marking, packaging, and storage

9.1 Marking

9.1.1 The type of an accepted ceramic weld backing is to be marked after the number of this International Standard (i.e. ISO 17683). For example, a ceramic weld backing of type I is to be marked as follows:

Ceramic weld backing ISO 17683-I

9.1.2 Markings on the package shall have the following information:

- a) the number of this International Standard (i.e. ISO 17683:2014);
- b) the name of the manufacturer or supplier;
- c) the trade name, lot number, and number of pieces;
- d) health and safety warnings as required;
- e) the country of origin.

9.2 Packaging

Ceramic weld backing shall be suitably packaged to ensure against damage during shipment and storage under normal conditions.

9.3 Storage

The ceramic weld backing should be maintained in a dry, ventilated room.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™