

BS EN ISO 17698:2016



BSI Standards Publication

**Footwear — Test methods
for uppers — Delamination
resistance (ISO 17698:2016)**

National foreword

This British Standard is the UK implementation of EN ISO 17698:2016. It supersedes BS EN 13514:2002 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear, leather and coated fabrics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016. Published by BSI Standards Limited 2016

ISBN 978 0 580 80866 1

ICS 61.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2016.

Amendments issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN ISO 17698

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2016

ICS 61.060

Supersedes EN 13514:2001

English Version

Footwear - Test methods for uppers - Delamination resistance (ISO 17698:2016)

Chaussures - Méthodes d'essai des tiges - Résistance au
dé laminage (ISO 17698:2016)

Schuhe - Prüfverfahren für Obermaterialien -
Beständigkeit gegen Schichtentrennung (ISO
17698:2016)

This European Standard was approved by CEN on 15 April 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 17698:2016) has been prepared by Technical Committee ISO/TC 216 “Footwear” in collaboration with Technical Committee CEN/TC 309 “Footwear” the secretariat of which is held by AENOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2016, and conflicting national standards shall be withdrawn at the latest by November 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13514:2001.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 17698:2016 has been approved by CEN as EN ISO 17698:2016 without any modification.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Apparatus and material	1
5 Sampling	2
6 Test method	3
6.1 Principle	3
6.2 Procedure	4
7 Expression of results	6
8 Test report	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

ISO 17698 was prepared by the European Committee Standardization (CEN) Technical Committee CEN/TC 309, *Footwear*, in collaboration with ISO Technical Committee TC 216, *Footwear*, in accordance with the agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 17698:2003), which has been technically revised.

This International Standard is based on the IULTCS/IUF 470 Method.

Footwear — Test methods for uppers — Delamination resistance

1 Scope

This International Standard specifies a test method for determining the delamination resistance of uppers made from coated material, in order to assess the suitability for the end use.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 7500-1¹⁾, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system*

ISO 17709²⁾, *Footwear — Sampling location, preparation and duration of conditioning of samples and test pieces*

ISO 18454³⁾, *Footwear — Standard atmospheres for conditioning and testing of footwear and components for footwear*

ISO 20870⁴⁾, *Footwear — Ageing conditioning*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

delamination resistance

strength of adhesion between a coating and its base material

4 Apparatus and material

The following apparatus and material shall be used.

4.1 Tensile testing machine, with a jaw separation rate of (100 ± 10) mm/min, a force range appropriate to the specimen under test (normally a range of 0 N to 200 N is suitable for test specimens of polyurethane coated fabric) and the capability of measuring the force to an accuracy greater than 2 % as specified by ISO 7500-1, class 2.

4.2 Autographic recorder, or similar means of continuously recording the force.

1) To be published.

2) ISO 17709 is equivalent to EN 13400.

3) ISO 18454 is equivalent to EN 12222.

4) ISO 20870 is equivalent to EN 12749.

4.3 Rapid acting platen press, capable of applying a pressure of (550 ± 50) kPa on an area of $50 \text{ mm} \times 70 \text{ mm}$.

4.4 Rubber pad, of thickness at least 10 mm and hardness (40 ± 10) IRHD.

4.5 Radiant heater, capable of heating a dry adhesive film on resin rubber to $80 \text{ }^\circ\text{C}$ to $90 \text{ }^\circ\text{C}$ within 15 s, normally mounting the adhesive film from 100 mm to 150 mm from a heater element of power approximately 3 kW and area of approximately $0,06 \text{ m}^2$ is satisfactory. Commercial equipment used for reactivating soles and uppers in footwear production is suitable.

4.6 Means of checking that the temperature of the adhesive film is within the range $80 \text{ }^\circ\text{C}$ to $90 \text{ }^\circ\text{C}$. Heat sensitive crayons are suitable, preferably with a melting temperature of $83 \text{ }^\circ\text{C}$. Also suitable are infra-red temperature measuring guns.

4.7 Resin rubber, thickness $(3,5 \pm 0,2)$ mm and hardness (95 ± 2) IRHD with a surface peel tear strength greater than that of the test specimen.

NOTE Hardness (95 ± 2) IRHD is equal to Shore A.

4.8 Solvent-borne polyurethane adhesive, which will bond well to resin rubber and the coated surface of the test specimen.

4.9 Adhesion primer, such as a halogenating solution used in footwear manufacture, for rubber can be helpful in producing satisfactory bonds.

4.10 Cutting device, such as a press knife or scissors capable of cutting rectangular test specimens of dimensions $(50 \pm 1) \text{ mm} \times (70 \pm 1) \text{ mm}$. In addition, if carrying out the test on hydrolysed test specimens, a second cutting device is required to cut square test specimens $(70 \pm 1) \text{ mm} \times (70 \pm 1) \text{ mm}$.

4.11 Cutting device, such as a sharp knife or rotary disc cutter for cutting test specimens from bonded test assemblies. This device shall neither unduly compress nor force apart the layers of the test assembly at the edges during cutting, and therefore a press knife is unsuitable.

4.12 Distilled or deionized water, if testing the wet adhesion strength, complying with grade 3 of ISO 3696.

4.13 Timer, capable of recording times up to 30 s to the nearest 0,5 s.

5 Sampling

5.1 For the dry tests, mark six rectangular boxes $(70 \pm 1) \text{ mm} \times (50 \pm 1) \text{ mm}$: two with their longer edges parallel to the along direction of sheet material (machine or backbone direction) or X-axis (as defined in ISO 17709) of the upper, and four with their longer edges perpendicular to this, on the reverse of the sheet material or uppers.

5.2 For the wet tests, mark either a further two rectangular boxes $(70 \pm 1) \text{ mm} \times (50 \pm 1) \text{ mm}$, putting the 50 mm edge in the direction with the lowest dry peel strength (if already known), or a further six boxes as described in [5.1](#) on the reverse of the material or uppers.

5.3 Make further marks on the material to divide each of the rectangles marked in [5.1](#) and [5.2](#) into two equal halves $(35 \pm 0,5) \text{ mm} \times (50 \pm 1) \text{ mm}$. Mark the along direction or X-axis in each of the smaller rectangles. Use an arrow and ensure that the arrow heads point in the same direction. For uppers, the arrow head shall point towards the toe.


5.4 For tests after humidity aging, mark a further two (70 ± 1) mm square boxes with their edges parallel to the along direction or X-axis. Mark the along direction or X-axis using an arrow as described in 5.3.

NOTE Since ink marks can be removed by the wetting or hydrolysis treatments, it is advisable to also use a code of cut off corners.

5.5 Cut from the sheet material or uppers the rectangular boxes marked in 5.1 and 5.2 and the squares marked in 5.4. Each piece of material is later cut to give two test specimens $(30 \pm 0,5)$ mm \times (50 ± 1) mm, see Figure 1. After bonding to resin rubber, each piece of material is later cut to give two peel test specimens. With some shoe styles, it will not be possible to cut the correct size pieces of material. In such cases, it will be necessary to reduce the size of the pieces to a minimum of (40 ± 1) mm \times (50 ± 1) mm. In all such cases, the pieces will give one test specimen only and shall not be further sub-divided as shown in 5.3.

5.6 Cut a rectangular piece of resin rubber (see 4.7) measuring (50 ± 1) mm \times (70 ± 1) mm for each piece of material cut as described in 5.5. If the setting of the radiant heater unit (see 4.5) needs to be checked, cut one or two additional pieces of rubber.

Dimensions in millimetres



Key

- 1 direction of peel
- 2 approximately 5 mm
- 3 staple
- 4 cut lines
- 5 paper strip

NOTE Specimens can be taken from materials likely to be used for uppers or from made-up uppers or finished footwear.

Figure 1 — Test specimen assembly

6 Test method

6.1 Principle

The coated surface of a test specimen is bonded to a piece of resin rubber using a strong adhesive. The force required to peel the test specimen from the resin rubber leaving the coating attached to the rubber is measured using a tensile testing machine. The test can also be carried out on wet and hydrolysed test specimens.

6.2 Procedure

6.2.1 Place a strip of paper (75 ± 5) mm \times (15 ± 3) mm to the coated side of each piece of material cut as described in [5.5](#) so that it is against one of the longer edges. Attach the paper strips with a staple (or similar) at each end so that the staples are positioned as shown in [Figure 1](#). With the four test specimens cut for the dry test where the arrow points toward a longer edge, two shall have the paper strip attached along the edge to which the arrow is pointing and two shall have the paper strip along the opposite edge.

6.2.2 If an adhesion primer (see [4.9](#)) is available, apply this in accordance with the supplier's instructions to the whole area of the reverse side of each piece of resin rubber cut as described in [5.6](#).

6.2.3 Allow the resin rubber pieces to dry full in accordance with the supplier's recommendations.

6.2.4 Apply the polyurethane adhesive (see [4.8](#)) in accordance with the supplier's instructions to the whole area of the reverse of each piece of resin rubber.

6.2.5 Similarly, apply adhesive to the coated surface of each piece of material under test so that it just overlaps the paper strip.

6.2.6 Allow the adhesive to dry for at least 1 h.

6.2.7 If the time required to heat the adhesive film to a temperature of between 80 °C and 90 °C using the radiant heater is not known, then measure this time using the extra pieces of rubber cut as described in [5.6](#) and the means of checking the temperature of the adhesive film (see [4.6](#)). If this time is found to be longer than 15 s, then either increase the temperature of the heating element or reduce the distance between the element and the resin rubber until the time is below 15 s. Record the time taken to heat the adhesive film to the desired temperature as T_a to the nearest 1 s.

6.2.8 The preparation of bonded assemblies is as follows.

6.2.8.1 Place a piece of adhesive coated resin rubber in the radiant heater with the adhesive surface facing the heater element so that it is subjected to heat for T_a (in seconds).

6.2.8.2 Carefully and quickly place the adhesive coated surface of a piece of upper material (see [5.5](#)) in contact with the adhesive coating on the piece of resin rubber so that the edges of both surfaces are aligned. This will subsequently be referred to as a test assembly.



6.2.8.3 Immediately place the test assembly into the platen press (see [4.3](#)) so that the resin rubber is lowermost and resting on the rubber pad (see [4.4](#)). Apply a pressure of (550 ± 50) kPa to the assembly for (15 ± 1) s.

It is important that the time between removing the resin rubber from the heater unit described in [6.2.8.1](#) to placing the assembly in the press and applying pressure as described in [6.2.8.3](#) shall be no more than 7 s.

6.2.9 Store the bonded assemblies in a conditioned standard atmosphere as specified in ISO 18454 for at least 24 h.

6.2.10 Use the cutting device (see [4.10](#) and [4.11](#)) to make three cuts in each test assembly parallel to the 50 mm edges so that the centre portions form two test specimens of width ($30,0 \pm 0,5$) mm and length (50 ± 1) mm and the two outer portions are waste strips of width approximately 5 mm, see [Figure 1](#).

6.2.11 Open the unbonded portion of each test specimen, taking care not to weaken the bond line, and centrally clamp it between the jaws of the tensile tester (see 4.1) so that the unbonded tab of resin rubber is in one jaw and the unbonded tab of upper material is in the other jaw (see Figure 2).



Key

- 1 delaminating force, in N
- 2 average
- 3 deformation

Figure 2 — Example of diagram force/deformation

6.2.12 Operate the tensile tester so that the jaws separate at a speed of (100 ± 10) mm/min and note the type of separation that occurs, such as the following:

- a) failure of adhesion of the coating to the base material;
- b) surface failure of the base material;
- c) deep failure of the base material;
- d) failure of adhesion of a top coating to a cellular coagulated coating;
- e) failure within the cellular or coagulated coating;
- f) separation between a cellular or coagulated layer and the base material.

If the separation is between the surface coating and the resin rubber, momentarily stop the test and without removing the test specimen from the tensile tester, using a sharp knife, carefully cut through the surface coating close to the point where it meets the resin rubber to encourage separation of the coating from the supporting material.

6.2.13 From the trace of force versus jaw movement produced by the tensile testing machine, measure the following:

6.2.13.1 Initial maximum force, in Newtons, required to break through the coating.

6.2.13.2 Average force (see [Figure 2](#)), in Newtons, required to peel the coating from its base (average of all force readings after the initial maximum peak).

6.2.14 Repeat the procedures in [6.2.11](#) to [6.2.13](#) for the remaining test specimens that are to be tested dry.

6.2.15 For the test specimens that are to be tested wet:

6.2.15.1 Select the test specimens corresponding to the lowest dry peel strength calculated according to the method described in [7.1.1](#) and wet the test specimens by immersing in water (see [4.12](#)) at $(23 \pm 2) ^\circ\text{C}$ for $(6,0 \pm 0,5)$ h.

6.2.15.2 Remove each test specimen from the water, blot the surfaces gently to remove surplus water and immediately carry out the test using the procedures in [6.2.11](#) to [6.2.13](#).

6.2.16 If testing test specimens after humidity aging:

6.2.16.1 Follow the procedure of humidity aging in ISO 20870 to produce two test specimens.

6.2.16.2 Cut a rectangular test specimen of material (70 ± 1) mm \times (50 ± 1) mm from each piece of humidity aged material so that the 50 mm edges are parallel to the direction of lowest dry peel strength calculated according to the method described in [7.1.2](#).

6.2.16.3 Repeat the procedures in [6.2.1](#) to [6.2.13](#) for the two test specimens of humidity aged material.

7 Expression of results

7.1 For each test specimen, calculate the following.

7.1.1 The initial maximum peel strength, in N/mm to the nearest 0,1 N/mm, by dividing the initial maximum force measured in [6.2.13.1](#), by the test specimen width.

7.1.2 The average peel strength, in N/mm to the nearest 0,1 N/mm, by dividing the average force measured in [6.2.13.2](#), by the test specimen width.

7.2 For each peel direction, calculate the following.

7.2.1 The arithmetic mean of the initial maximum peel strengths calculated in [7.1.1](#).

7.2.2 The arithmetic mean of the average peel strengths calculated in [7.1.2](#).

8 Test report

The test report shall include the following information:

- a) for each type of test specimen:
 - any pre-treatment, either wetting or humidity aging;
 - the peeling direction;
 - if required, the arithmetic mean of the initial maximum peel strengths calculated in accordance with [7.2.1](#);
 - the arithmetic mean of the average peel strengths calculated in accordance with [7.2.2](#);
- b) if testing finished footwear or uppers, a description of the style of shoe tested including commercial style codes;
- c) a description of the material, including commercial references if known;
- d) a reference to this International Standard, i.e. ISO 17698:2016;
- e) the date of testing;
- f) any deviations from this test method.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK