

BS EN ISO 17701:2016



BSI Standards Publication

**Footwear — Test methods
for uppers, lining and insoles
— Colour migration (ISO
17701:2016)**

National foreword

This British Standard is the UK implementation of EN ISO 17701:2016. It supersedes BS EN 13517:2002 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear, leather and coated fabrics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 80867 8

ICS 61.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2016.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN ISO 17701

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2016

ICS 61.060

Supersedes EN 13517:2001

English Version

Footwear - Test methods for uppers, lining and insoles - Colour migration (ISO 17701:2016)

Chaussures - Méthodes d'essai des tiges, de la doublure
et des premières de propreté - Migration de la couleur
(ISO 17701:2016)

Schuhe - Prüfverfahren für Obermaterialien, Futter und
Decksohlen - Farbmigration (ISO 17701:2016)

This European Standard was approved by CEN on 15 April 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 17701:2016) has been prepared by Technical Committee ISO/TC 216 “Footwear” in collaboration with Technical Committee CEN/TC 309 “Footwear” the secretariat of which is held by AENOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2016, and conflicting national standards shall be withdrawn at the latest by November 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13517:2001.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 17701:2016 has been approved by CEN as EN ISO 17701:2016 without any modification.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Apparatus and material	1
5 Sampling and conditioning	2
5.1 Testing for colour migration between materials.....	2
5.2 Testing for the effect of adhesives.....	2
5.3 Testing for the effect of adhesives in laminate.....	2
5.4 Testing components such as soling.....	3
6 Test method	3
6.1 Principle.....	3
6.2 Procedure.....	3
7 Test report	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

ISO 17701 was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 309, *Footwear*, in collaboration with ISO Technical Committee TC 216, *Footwear*, in accordance with the arrangement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 17701:2003), which has been technically revised.

Footwear — Test methods for uppers, lining and insoles — Colour migration

1 Scope

This International Standard specifies a test method for determining the propensity of a material to cause discolouration of another material when stored in close contact. This method is applicable to all materials which are used in intimate contact to adhesives which are used to bond them.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A01, *Textiles — Tests for colour fastness — Part A01: General principles of testing*

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 105-A03, *Textiles — Tests for colour fastness — Part A03: Grey scale for assessing staining*

ISO 18454, *Footwear — Standard atmospheres for conditioning and testing of footwear and components for footwear*

ISO 19952, *Footwear — Vocabulary*

CIE 15, *Colorimetry*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 19952 and the following apply.

3.1

colour migration

discolouration caused by movement of colour from one material to another

4 Apparatus and material

The following apparatus and material shall be used:

4.1 Knife to cut the test specimen.

4.2 Two smooth and even glass plates at least 70 mm × 70 mm and a mass of 50 g ± 5 g.

4.3 Mass of sufficient size that when combined with the mass of the glass plate will exert a pressure of 5,2 kPa ± 0,5 kPa.

NOTE The necessary mass depends of the area of the test specimen to get the same pressure.

EXAMPLE

Area of test specimen = 30 mm × 20 mm = 600 mm²

Mass = pressure × area

$$\text{Mass} = 5,2 \text{ kPa} \times 600 \text{ mm}^2 = 5\,200 \text{ Pa} \times 600 \text{ mm}^2 = 5\,200 \text{ kg} \times \text{m}^{-1} \times \text{s}^{-2} \times 6 \times 10^{-4} \text{ m}^{-2}$$

$$\text{Mass} = 3,12 \text{ kg} \times \text{m} \times \text{s}^{-2} = 3,12 \text{ N}$$

A mass of 3,12 N (these are 0,318 kg) is necessary to get a pressure of 5,2 kPa.

Please note that the mass of one glass plate has to be subtracted: $\text{mass} = 318 \text{ g} - 50 \text{ g} = 268 \text{ g}$.

If the area of the test specimen is 50 mm × 40 mm, a mass of 1,060 kg is necessary to get the same pressure. Please note that the mass of one glass plate has to be subtracted: $\text{mass} = 1\,060 \text{ g} - 50 \text{ g} = 1\,010 \text{ g}$.

4.4 Oven, without a door or glass window, heated to 60 °C ± 2 °C.

4.5 Colorimeter to measure the colour of the test specimen and the reference specimen to convert the results in CIE colour values and to calculate automatically the CIELAB colour differences in accordance with CIE 15.

The colorimeter has to be calibrated with a white standard (normal light D 65, normal observer 10°, measure geometry dl8°).

4.6 Grey scales with half step rating for assessing change in colour and degree of staining complying with ISO 105-A02 and ISO 105-A03, respectively.

4.7 Artificial lighting conditions as specified in ISO 105-A01 or north daylight.

5 Sampling and conditioning

Store the test materials in a conditioned standard atmosphere as specified in ISO 18454 for a minimum of 24 h prior to testing.

5.1 Testing for colour migration between materials

Cut two test specimens from each material, the dark-coloured material and the light-coloured material with a size of 30 mm × 20 mm (±2 mm) as minimum. One of each type of test specimen is the reference sample.

If there are insufficient materials, smaller samples may be used and a proportionally lower mass than 1 000 g ± 10 g to maintain the same contact pressure.

5.2 Testing for the effect of adhesives

Cut two samples of the test material with a size of (50 ± 2) mm × (50 ± 2) mm. One of the test specimens is the reference sample.

Coat the centre of the surface, to which the adhesive would be applied in production with the adhesive under test, so that the coating covers approximately 75 % of the area of the test specimen. Use a quantity of adhesive that is judged to be representative of that to be used in production. Allow the adhesive to dry at room temperature.

5.3 Testing for the effect of adhesives in laminate

Cut two samples from each material to be laminated together with a size of (50 ± 2) mm × (50 ± 2) mm, when testing for the effect of an adhesive within a laminate. One of each type of test specimen is the reference sample.

5.3.1 When testing for the effect of adhesives within a laminate, where a wet bond is used in production, place the two materials together and press by hand to form a bonded assembly and allow the adhesive to dry at room temperature.

5.3.2 When testing for the effect of adhesives within a laminate where the bond is formed with dry adhesive films, join the two materials using a technique similar to that used in production.

5.4 Testing components such as soling

5.4.1 Prepare by suitable means, a test specimen of uniform thickness from the sole or other component.

5.4.2 Cut a test specimen from the material and two pieces of the second test material ([5.1](#), one as reference sample).

NOTE Specimens can be taken either from materials likely to be used for uppers or from made up uppers or finished footwear.

6 Test method

6.1 Principle

Either two dissimilar materials are placed in intimate contact, or a single piece of material, coated with a product such as an adhesive, or laminated materials are placed between glass plates. The assembly is stored in the dark for a prescribed period at an elevated temperature. The test specimens are then examined for any discolouration compared with unexposed reference samples. Discolouration indicates that the materials are likely to discolour under normal service conditions.

6.2 Procedure

The CIE values of the colour of all test specimens have to be measured with the colorimeter (including the reference samples). Store the reference samples darkly in standard conditioned atmosphere as specified in ISO 18454.

6.2.1 For assemblies of two materials not joined together with adhesive.

6.2.1.1 Place the first test specimen centrally on a glass plate (see [4.2](#)) with its contact face uppermost.

6.2.1.2 Place the other test specimen with its contact face lowermost on the first specimen.

6.2.1.3 Place the remaining glass plate (see [4.2](#)) centrally on top of the specimens.

6.2.2 For adhesive coated single materials and laminates, place the test specimen between the two glass plates.

6.2.3 Place the mass (see [4.3](#)) symmetrically on the top glass plate (see [4.2](#)).

6.2.4 Place the assembly (see [6.2.1](#) or [6.2.2](#)) in the dark test environment at (60 ± 2) °C (see [4.4](#)).

6.2.5 After 24 h, remove the assembly from the test environment.

6.2.6 For assemblies of two not joined materials, separate the two materials and compare their contact faces to the reference samples. Assess in accordance with [6.2.8](#).

6.2.7 For adhesive coated single materials and laminates, remove the test specimen and compare the face not coated with adhesive to unexposed material. Assess in accordance with [6.2.8](#).

6.2.8 Measure the CIE values (in accordance with CIE 15) of the colour with the colorimeter (see 4.5). The use of the artificial lighting or north daylight is another method (4.7). Assess any loss of colour by comparing the contrast in colour between tested and non-tested material with the ratings on the grey scale.

6.2.8.1 Measure any loss of colour by comparing the colour between tested and non-tested material for assessing the change in colour.

6.2.8.2 Measure any transfer of colour by comparing the colour between tested and non-tested material for assessing the staining.

6.2.8.3 In all cases, assess the area showing the most marked contrast.

6.2.8.4 Record a description of the loss of colour or transfer of colour alongside the numerical ratings obtained in 6.2.8.1 and 6.2.8.2 in terms of colour, intensity and uniformity of the change.

6.2.9 Repeat the procedure from 6.2.1 to 6.2.8. Remove the assembly from the test environments after every $24 \text{ h} \pm 1 \text{ h}$ until a total exposure time of 7 d has been reached.

7 Test report

The test report shall include the following information:

- a) for each inspection carried out, a description of any loss of colour or transfer of colour of each test specimen as determined in 6.2.8 and the corresponding cumulative contact time;
- b) the method used for the measurement of colour changes;
- c) the description of the materials or samples that were tested, including commercial references (style codes, etc.);
- d) a reference to this International Standard, i.e. ISO 17701:2016;
- e) the date of testing;
- f) the date of analysis;
- g) any deviation from this test method.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK