

BS EN ISO 17730:2014



BSI Standards Publication

Dentistry — Fluoride varnishes

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 17730:2014.

The UK participation in its preparation was entrusted to Technical Committee CH/106/7, Oral hygiene products.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 78987 8

ICS 97.170

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2014.

Amendments issued since publication

Date	Text affected
------	---------------

ICS 97.170

English Version

Dentistry - Fluoride varnishes (ISO 17730:2014)

Médecine bucco-dentaire - Vernis fluorés (ISO 17730:2014)

Zahnheilkunde - Fluoridlacke (ISO 17730:2014)

This European Standard was approved by CEN on 23 August 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 17730:2014) has been prepared by Technical Committee ISO/TC 106 "Dentistry" in collaboration with Technical Committee CEN/TC 55 "Dentistry" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2015, and conflicting national standards shall be withdrawn at the latest by May 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 17730:2014 has been approved by CEN as EN ISO 17730:2014 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and Definitions	1
4 Requirements	2
4.1 Total fluoride content.....	2
5 Sampling	2
6 Test method	2
6.1 Test for total fluoride content.....	2
6.2 Test conditions.....	3
7 Test report	4
8 Instructions for use	4
9 Packaging, labelling, and marking	5
9.1 Packaging.....	5
9.2 Labelling.....	5
Bibliography	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 106, *Dentistry*, Subcommittee SC7, *Oral care products*.

Introduction

Fluoride varnishes are used in dentistry primarily for caries prevention and reduction of dentine hypersensitivity. Fluoride varnishes are applied in the oral cavity directly on the outer surfaces of teeth and fillings, and are intended to remain at least for several hours.

Specific qualitative and quantitative test methods for demonstrating freedom from unacceptable biological hazard are not included in this International Standard, but it is recommended that, for the assessment of possible biological or toxicological hazards, reference should be made to ISO 10993-1 and ISO 7405.

Dentistry — Fluoride varnishes

1 Scope

This International Standard specifies requirements and their test methods for total digestible fluoride content in dental varnishes containing fluoride, intended for use in the oral cavity directly on the outer surfaces of teeth and fillings. It also specifies the requirements for their packaging and labelling, including the instructions for use. This International Standard covers fluoride varnishes to be applied by dental health care workers.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1942, *Dentistry — Vocabulary*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 8601, *Data elements and interchange formats — Information interchange — Representation of dates and times*

3 Terms and Definitions

For the purposes of this document, the definitions given in ISO 1942 and the following apply.

3.1

consumer packaging

retail packaging

sales packaging

package, with labelling and contents as a sales unit to the user or consumer at the point of retail

Note 1 to entry: A consumer packaging can consist of a secondary packaging wrapping or container covering one or more primary packaging elements or, it can consist of a single primary packaging element containing the product.

Note 2 to entry: Adapted from ISO 21067:2007, definition 2.2.5.

3.2

fluoride varnish

dental product, in paintable liquid form containing fluoride compound for topical application to the outer surfaces of teeth and fillings, intended primarily to prevent tooth caries or reduce dentine hypersensitivity

3.3

total fluoride

mass percent of fluoride in the fluoride varnish

4 Requirements

4.1 Total fluoride content

The total fluoride content shall not deviate by more than 20 % from the stated amount on the package when tested in accordance with 6.1 or other validated methods for total fluoride content.

5 Sampling

Use packages prepared for retail sale from the same batch containing enough material to carry out the specified tests, plus an allowance for repeat tests, if necessary.

6 Test method

6.1 Test for total fluoride content

6.1.1 Chemicals and solutions

6.1.1.1 Total ionic strength adjusting buffer (TISAB) solution, described in ASTM D1179-10:2010 18.1 or alternative.

NOTE TISAB II: Sodium chloride 5,8 % (w/v), acetic acid 5,7 % (w/v), CDTA 0,4 % (w/v) adjust to pH 5 to pH 5,5 with sodium hydroxide (5 mol/L). Examples are TISAB II® (Orion Research). An acceptable product (TISAB II®) is available from Thermo Fisher Scientific, Beverly, MA 01915 USA. This information is given only for the convenience of users of this document and does not constitute an endorsement by ISO of this product.

6.1.1.2 50 % Diluted TISAB solution, dilute TISAB with deionized water 1:1 by volume.

6.1.1.3 Fluoride standard solution, commercially available or prepared with sodium fluoride at 0,10 mol/L.

6.1.1.4 Chloroform, reagent grade.

6.1.1.5 Deionized water, in accordance with ISO 3696:1987, grade 2.

6.1.1.6 Potassium hydroxide at 1 mol/L.

6.1.2 Apparatus

6.1.2.1 Chloroform resistant vials and caps, 25 mL or more capacity.

6.1.2.2 Balance accurate to 0,000 1 g.

6.1.2.3 Magnetic stir bar.

6.1.2.4 Magnetic stir plate.

6.1.2.5 Pipette, capable of measuring 1 mL to 0,01 mL.

6.1.2.6 Fluoride ion selective electrode (F-ISE), with reference electrode, or combination F-ISE/reference electrode pair.

6.1.2.7 Plastic vial (or beaker or small container), 25 mL or more capacity.

6.1.2.8 pH/mV electrometer (pH meter), with a sensitivity of $\pm 0,1$ mV.

Perform tests on “as received” samples.

6.2 Test conditions

Perform tests at room temperature with no more than 2 °C variation.

6.2.1 Preparation of standard solution

Make successive dilutions of the fluoride standard solution to obtain a set of working standard solutions that are 10^{-2} , 10^{-3} , 10^{-4} , 10^{-5} mol/L NaF.

6.2.2 Preparation of calibration curve

- a) Pipette 5,0 mL of each standard solution into a separate plastic vial (or beaker or small container).
- b) Add 5,0 mL of TISAB solution, add a magnetic stir bar to each plastic vial. Mix thoroughly.
- c) Insert the fluoride ion selective and reference electrodes into the liquid in the plastic vial containing the first standard solution.
- d) Record the millivolt reading to 0,1 mV at the steady potential difference with the mV electrometer.
- e) Conduct at least two measurements for millivolt readings until the difference between the two readings is less than 0,2 mV.
- f) Repeat steps (c) to (e) for each of the other standard solutions.
- g) Construct a calibration curve of millivolts versus the log of the fluoride ion concentration of the standard.

NOTE The slope of the calibration curve should be linear and no less than 55 mV per decade ($-\log_{10} [F]$), and the $l c$ coefficient of determination (r^2) should be greater than 0,98.

6.2.3 Sample preparation

- a) Place open chloroform resistant vial that can be capped, such as a scintillation vial, on balance and tare to zero.
- b) Dispense 1 to 3 drops (0,05 g to 0,15 g) of varnish product onto the bottom of the container.
- c) Determine and record the mass of the amount of varnish [$Varnish_{mass}$] added to $\pm 0,000$ 1 g.
- d) If the varnish sample contains fluorosilane, add 1,0 mL of 1 mol/L KOH to the varnish in the container and mix for 5 min. If the varnish sample does not contain fluorosilane then skip this step.
- e) Add ($4 \pm 0,5$) mL of chloroform into the container and stir.
- f) Add ($10,0 \pm 0,1$) mL of TISAB buffer to the chloroform + sample.
- g) Cap and vigorously shake the mixture to dissolve the resin into the chloroform and all the fluoride into the TISAB. Be careful to allow the pressure in the vial to escape by loosening the cap briefly and retightening.
- h) Add magnetic stir bar.
- i) Stir for at least 1,5 h at room temperature.

NOTE In some cases the TISAB/Chloroform/Varnish mixture does not mix well with magnetic stirring, it may be necessary to place the sample vial into a rotator or shaker to achieve better mixing.

- j) Turn off magnetic stir plate for at least 2 h (to allow the chloroform and the TISAB to separate);
- k) If the top (aqueous) layer is not uniform, gently homogenize (mix) just that layer prior to sampling for further dilution.

6.2.4 Sample Analysis

- a) Pipette 1,0 mL of aqueous (TISAB) layer (prevent to include parts of the lower chloroform layer) into a 25 mL container.
- b) Pipette 1,0 mL deionized water into the same container.
- c) Add 18,0 mL 50 % diluted TISAB solution to the container and stir.
- d) Insert the fluoride ion selective and reference electrodes into the sample liquid in the vial. Record the millivolt reading to the nearest 0,1 mV at the steady potential difference.
- e) Use the calibration curve of standard solutions to determine the fluoride ion concentration in the sample solution in mol/L.

6.2.5 Calculations

- a) Determine the apparent concentration $[F_{dil}]$ (mol/L) of the diluted sample from the standard curve.
- b) Multiply the $[F_{dil}]$ by 100 and divide by $[Varnish_{mass}] = [F]$ mmol/g product.

NOTE When calculating the $[F]$ mol/L of the standard, it is common practice to ignore the volume fraction of 50 % dilution caused by the addition of TISAB because the standards and samples all receive the same dilution. Should the standard curve be calculated with the actual $[F]$ mol/L (including the volume fraction of 50 % TISAB dilution) then the dilution factor to be used in the calculations 6.2.5.b) will be 200 in place of 100 when calculating the $[F]$ mmol/g product.

- c) Multiply $[F]$ mmol/g product by 19 000 = $[mg F/g]$.
- d) Multiply $[F]$ mmol/g product by 41 990 = $[mg NaF/g]$.
- e) Divide $[mg F/g]$ by 10 000 = $[mass \% F]$.
- f) Divide $[mg NaF/g]$ by 10 000 = $[mass \% NaF]$.

7 Test report

The test report shall include at least the following information:

- a) name and address of the institute responsible for the test report;
- b) a reference to this International Standard (i.e. ISO 17730);
- c) the manufacturer's tracking code;
- d) the test methods used and their results;
- e) any unusual features noted during the tests;
- f) whether the fluoride varnish passed or failed the test.

8 Instructions for use

Instructions shall indicate the method of application of the fluoride varnish to teeth.

9 Packaging, labelling, and marking

9.1 Packaging

The materials shall be supplied in containers or capsules that afford adequate protection and have no adverse effect on the quality of the contents.

9.2 Labelling

Each container shall be marked with at least the following information:

- a) the manufacturer's name and address and/or the authorized representative;
- b) the trade name of the material;
- c) the type of fluoride (for example: sodium fluoride);
- d) the total fluoride content (for example: micrograms per gram fluoride or mass % fluoride);
- e) the manufacturer's tracking code;
- f) recommended conditions of storage;
- g) the net mass, in grams, or net volume, in millilitres;
- h) the expiry date, expressed in accordance with ISO 8601, for the material if stored under the manufacturer's recommended conditions;
- i) any hazard warnings (flammable, etc.).

Bibliography

- [1] ISO 7405, *Dentistry — Evaluation of biocompatibility of medical devices used in dentistry*
- [2] ISO 10993-1, *Biological evaluation of medical devices — Part 1 Evaluation and testing within a risk management process*
- [3] SHEN C., & AUTIO-GOLD J. Assessing fluoride concentration uniformity and fluoride release from three varnishes. *J. Am. Dent. Assoc.* 2002, **133** pp. 176–182
- [4] American Society for Testing and Materials ASTM D1179-10: 2010, Standard test methods for fluoride ion in water
- [5] CAREY C.M., & COLEMAN S.S. Method for the analysis of total fluoride in fluoride-releasing dental varnishes. *Caries Res.* 2014, **48** pp. 306–311

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™