

BS EN ISO 18278-2:2016



BSI Standards Publication

Resistance welding — Weldability

Part 2: Evaluation procedures for weldability
in spot welding

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of EN ISO 18278-2:2016. It supersedes BS EN ISO 18278-2:2004 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee WEE/29, Resistance welding.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016. Published by BSI Standards Limited 2016

ISBN 978 0 580 83204 8

ICS 25.160.40

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2016.

Amendments issued since publication

Date	Text affected
------	---------------

English Version

Resistance welding - Weldability - Part 2: Evaluation
procedures for weldability in spot welding (ISO 18278-
2:2016)

Soudage par résistance - Soudabilité - Partie 2:
Méthodes d'évaluation de la soudabilité par points (ISO
18278-2:2016)

Widerstandsschweißen - Schweißeignung - Teil 2:
Verfahren zum Bewerten der Eignung für das
Widerstandspunktschweißen (ISO 18278-2:2016)

This European Standard was approved by CEN on 27 November 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 18278-2:2016) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2016, and conflicting national standards shall be withdrawn at the latest by August 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 18278-2:2004.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 18278-2:2016 has been approved by CEN as EN ISO 18278-2:2016 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Welding equipment	2
4.1 General.....	2
4.2 Electrodes.....	2
4.3 Welding current.....	2
4.4 Mechanical settings.....	2
4.5 Measurement of parameters.....	2
4.5.1 Welding current and electrode force.....	2
4.5.2 Electrode cooling water flow rate.....	2
4.6 Measurement of results.....	3
4.6.1 Weld diameter.....	3
4.6.2 Detection of expulsion.....	3
5 Preliminary adjustments	3
5.1 Electrode alignment.....	3
5.2 Electrode conditioning.....	3
6 Determination of the welding current range	3
6.1 Test specimens.....	3
6.2 Welding parameters.....	3
6.3 Test procedure.....	3
6.4 Current range criteria.....	4
6.5 Three sheet and multiple stack-ups.....	4
7 Estimation of electrode life	4
7.1 Test specimens.....	4
7.2 Welding parameters.....	4
7.3 Procedure.....	5
7.4 Test criteria, interpretation of results.....	5
8 Test report	6
8.1 General.....	6
8.2 Welding current range.....	6
8.3 Electrode life.....	6
Annex A (informative) Electrode alignment	7
Annex B (informative) Specific conditions for steel sheet customer qualification	9
Annex C (informative) Test specimens for mechanical characterization	12
Annex D (informative) Example of test report for welding current range	14
Annex E (informative) Example of test report for electrode life test	15
Bibliography	16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 44, *Welding and allied processes*, Subcommittee SC 6, *Resistance welding and allied mechanical joining*.

Requests for official interpretations of any aspect of this document should be directed to the Secretariat of ISO/TC 44/SC 6 via your national standards body. A complete listing of these bodies can be found at www.iso.org.

This second edition cancels and replaces the first edition (ISO 18278-2:2004), which has been technically revised.

ISO 18278 consists of the following parts, under the general title *Resistance welding — Weldability*:

- *Part 1: General requirements for the evaluation of weldability for resistance spot, seam and projection welding of metallic materials*
- *Part 2: Evaluation procedures for weldability in spot welding*

Introduction

This document describes procedures for evaluating the resistance spot welding weldability by determining the welding current range and electrode life.

These procedures can be used to evaluate the following:

- a) the effect of electrode material, shape, dimensions and electrode cooling;
- b) the effect of material types and thicknesses and coatings being welded;
- c) the effect of welding conditions;
- d) the effect of welding equipment.

Resistance welding — Weldability —

Part 2:

Evaluation procedures for weldability in spot welding

1 Scope

This part of ISO 18278 provides specific test procedures for the determination of the acceptable welding current range and the electrode life.

It is applicable for the evaluation of the weldability of assemblies of uncoated and coated sheets of individual thicknesses from 0,4 mm to 6,0 mm.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 669, *Resistance welding — Resistance welding equipment — Mechanical and electrical requirements*

ISO 5182, *Resistance welding — Materials for resistance welding electrodes and ancillary equipment*

ISO 5821, *Resistance welding — Spot welding electrode caps*

ISO 10447, *Resistance welding — Testing of welds — Peel and chisel testing of resistance spot and projection welds*

ISO 14270, *Resistance welding — Destructive testing of welds — Specimen dimensions and procedure for mechanized peel testing resistance spot, seam and embossed projection welds*

ISO 14272, *Resistance welding — Destructive testing of welds — Specimen dimensions and procedure for cross tension testing of resistance spot and embossed projection welds*

ISO 14273, *Resistance welding — Destructive testing of welds — Specimen dimensions and procedure for tensile shear testing resistance spot, seam and embossed projection welds*

ISO 14373, *Resistance welding — Procedure for spot welding of uncoated and coated low carbon steels*

ISO 15609-5, *Specification and qualification of welding procedures for metallic materials — Welding procedure specification — Part 5: Resistance welding*

ISO 17653, *Resistance welding — Destructive tests on welds in metallic materials — Torsion test of resistance spot welds*

ISO 17677-1, *Resistance welding — Vocabulary — Part 1: Spot, projection and seam welding*

ISO 18278-1, *Resistance welding — Weldability — Part 1: General requirements for the evaluation of weldability for resistance spot, seam and projection welding of metallic materials*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 669, ISO 14373, ISO 17677-1 and ISO 18278-1 apply.

4 Welding equipment

4.1 General

Methods to characterize resistance welding equipment can be found in ISO 669.

The mass and friction of the movable electrode assembly can be determined in accordance with ISO 18278-1.

4.2 Electrodes

The electrodes shall be of type A 2/2 material as defined in ISO 5182. Their geometry shall be defined according ISO 5821.

4.3 Welding current

The type of welding current used (AC or DC) shall be specified before testing. Constant current control settings shall be used.

When using AC resistance welding equipment, it shall be set so that welding current is not less than 30 % of R.M.S. value at full conduction angle.

4.4 Mechanical settings

The mechanical settings shall be chosen to limit the impact of the electrode meeting the sheet.

NOTE To limit the impact of the electrode an electrode approach speed of 0,15 m/s is recommended and/or the peak force should be less than 150 % of the nominal electrode force.

The machine squeeze time should be of sufficient duration to overcome electrode bounce effects and machine inertia so as to allow the electrode force to build up to the required value before the welding current is initiated.

4.5 Measurement of parameters

4.5.1 Welding current and electrode force

Measurement of welding current and electrode force requirements shall be in accordance with ISO 18278-1.

4.5.2 Electrode cooling water flow rate

Since water cooling significantly influences electrode life, the inlet water temperature should be maintained at 20 °C and shall not exceed 30 °C. A separate water supply should be used for each electrode, and the water flow rate for each electrode shall be a minimum of 4 l/min. The water cooling tube should be arranged to ensure that the water directly cools the electrode.

Dimensions of the water cooling holes and pipes shall comply with the relevant requirements of the appropriate ISO Standard for various electrode types. The distance between the back and working face of the electrode should not exceed the values given in ISO 5821 which specifies electrode dimensions.

Any deviations shall be recorded.

All machine and water cooling details shall be recorded in the format presented in [Clause 8](#).

4.6 Measurement of results

4.6.1 Weld diameter

After the destructive testing, the weld diameter shall be measured, see ISO 17677-1.

4.6.2 Detection of expulsion

Occurrence of expulsion shall be determined visually, by the electrode displacement curve, by the welding voltage signal or by the electrode force signal. For steel sheets, an expulsion is characterized by a very sharp deviation in the trace of an electrode displacement or welding voltage signal.

5 Preliminary adjustments

5.1 Electrode alignment

Electrode alignment shall be checked. This may be accomplished by the methods suggested in [Annex A](#).

Eccentricity (see ISO 669) should be less than 0,5 mm. This may be checked using the carbon imprint method where a sheet of paper is sandwiched between two carbon papers inserted between the two caps after which the electrode force is applied. Examples of carbon imprints obtained on the paper sheet after application of pressure are shown in [Figure A.1](#).

Angular deflection (see ISO 669) should not exceed 5°. A method using a tube is described in [Figure A.2](#).

5.2 Electrode conditioning

Electrodes shall not be conditioned.

6 Determination of the welding current range

6.1 Test specimens

Test specimens shall be single spot specimens, and their geometry shall be defined for a given welding current range test. Recommended geometries are those defined in ISO standards, especially cross-tension specimens (ISO 14272), tensile-shear specimens (ISO 14273), torsion specimens (ISO 17653), mechanized peel specimens (ISO 14270).

In the case of chisel/peel test (ISO 10447), the specimen shall have a minimum size of 40 mm × 40 mm with at least 35 mm overlap.

NOTE It is easier to accurately measure weld diameters after cross-tension, peel and chisel tests.

6.2 Welding parameters

Appropriate welding parameters shall be specified in the instructions or in the test order form. Proposed sets of welding parameters for steel assemblies are given in [Annex B](#).

6.3 Test procedure

Starting with a level sufficiently low to be under any welding or even bonding condition, the welding current is increased in 200 A steps, and never decreased. Three test specimens shall be prepared and welded for each current setting, two will be used for destructive testing and the third will be kept in reserve, for example for metallographic analysis.

When splashing occurs, the test shall be continued until the welding current reaches 10 % above the current after splashing first occurred.

Destructive testing and measurement of the weld diameter shall be performed according to [4.6.1](#) and the information supplied in [6.1](#).

In case of instrumented mechanical testing of the welds, it shall be performed at least 10 hours after welding.

6.4 Current range criteria

The minimum weld diameter shall be specified in the instructions.

NOTE This minimum weld diameter can be equal to $3,5\sqrt{t}$, t being the thickness of the thinnest sheet of the assembly.

The upper end of the welding current range I_{\max} is defined as the maximum current setting for which at least two out of three spot welds show no splash, and all current settings below satisfy the same condition.

The lower end of the welding current range I_{\min} is defined as the minimum current setting for which both spot weld specimens which are destructively tested will have a diameter equal or greater than the defined minimum, and all current settings above until I_{\max} satisfy the same condition.

6.5 Three sheet and multiple stack-ups

In such cases, each interface shall be considered individually. Therefore, the shape and number of test specimens shall be adapted to test each interface separately (i.e. in the case of instrumented testing, two specimens per interface and one in reserve for metallographic analysis).

The minimum weld diameters shall be defined for each interface of the stack-up, and the lower end of the welding current range is defined when every interface reaches its own minimum weld diameter condition.

The upper end of the welding current range is defined when every interface matches the no-splashing condition.

7 Estimation of electrode life

7.1 Test specimens

Two types of specimens are to be welded during this test:

- a) welding sheets (e.g. dimensions 300 mm × 400 mm) used to wear the electrodes through continuous spot welding;
- b) test strips for test welds. The size of these strips can be chosen depending on the means used for destructive testing, however, the overlap shall be at least 40 mm × 300 mm. [Annex C](#) gives examples of a test strip and a device for simultaneously separating 10 spot welds.

NOTE Single or double spot coupons can be specified by the contracting parties instead of test strips but the results may change.

7.2 Welding parameters

The welding current shall be set at I_{\max} as determined during a welding current range test on the same stack-up, the other parameters being defined in the instructions or in the test order form. New electrodes shall be installed before for this test.

NOTE Proposed sets of welding parameters for steel stack-ups are given in [Annex B](#).

7.3 Procedure

The test sequence is as follows.

a) First test strip: 10 welds.

If splashing occurs on three consecutive welds, the testing current shall be reduced by 100 A. If splashing still occurs on the three next welds then the test shall be restarted at I_{\max} minus 200 A.

b) 40 welds continuously on welding sheets.

c) 10 welds on subsequent test strips.

d) 40 welds continuously on welding sheets.

e) Repeat c) and d) until 400 welds.

f) 10 welds on a test strip.

g) 90 welds continuously on welding sheets.

h) Repeat f) and g) until ending conditions are reached.

The testing procedure shall be performed in a continuous mode, ideally in the same day.

For b), d) and g) a welding rate of 30 spots per minute is recommended for thin sheet material, see [Table B.1](#) for details in the case of steel sheets.

The test settings are given in [Table 1](#).

Table 1 — Settings for spot weld production

Weld pitch	30 mm
Edge distance	15 mm
Precision of weld positioning on the test strips	±5 mm

After welding, each test strip shall be tested destructively, and the weld diameters of the eight central spots shall be measured. The test shall be continued until at least four spots out of eight show a no-weld condition (weld diameter equal to zero). Other ending conditions may be defined.

The test shall be performed without tip dressing and current stepping control.

7.4 Test criteria, interpretation of results

Electrode life is defined as the last weld number of a test strip before reaching more than two welds out of eight below a minimum weld diameter defined by the contracting parties.

The electrode wear can be evaluated by

- the overall reduction in length of the electrodes, which can also be followed in-line by using displacement sensors,
- tip profile and diameter through carbon imprints or by using optical devices,
- the change of mass in the electrode.

NOTE This minimum weld diameter can be equal to $3,5\sqrt{t}$, t being the thickness of the thinnest sheet of the assembly.

8 Test report

8.1 General

The test report shall include data about stack up being welded (e.g. sheet thicknesses, materials, coatings) and welding parameters (e.g. machine type, machine reference, current type (AC or DC), electrode type, electrode force, welding cycle, inlet cooling water temperature and flow rate). See ISO 15609-5 for further details.

The test report shall also include all information that facilitates interpretation, especially anomalies such as sticking of the electrodes to the sheet, etc.

8.2 Welding current range

The test report shall include the minimum and maximum welding currents, defining the welding current range.

In addition, for each individual spot weld, the following information shall be recorded:

- welding current;
- diameter of the weld and failure type obtained as defined in ISO 17677-1;
- maximum load in case of instrumented mechanical testing;
- splashing and electrode sticking (if any);

An example of a typical data sheet is given in [Annex D](#).

8.3 Electrode life

The test report shall include the electrode life obtained and the welding current used for the test.

In addition, the following information shall be recorded:


- individual weld diameter as a function of the number of spot welds on test strips;
- splashing and electrode sticking (if any);
- change in weld current during the test (if applied).

An example of a typical data sheet is given in [Annex E](#).

Annex A (informative)

Electrode alignment

There are many methods to check the position of electrodes. [Annex A](#) shows two possibilities (see [Figure A.1](#) and [Figure A.2](#)).



Key



Carbon imprint on paper

The use of type C0 electrode caps (see ISO 5821) is recommended.

Figure A.1 — Acceptance criteria for the electrode alignment




Figure A.2 — Tube method

Annex B (informative)

Specific conditions for steel sheet customer qualification

B.1 Purpose

For the qualification of a new grade of steel or a new coating, the customer can ask the producer to characterize the weldability of its product. The general conditions of the method can be applied together with the following specific conditions.

B.2 Single-side coatings

In the case of single-side coated sheets, the coating position in the stack up should be reported (external coating; internal coating; alternating coating).

B.3 Welding parameters

Welding parameters for different steel sheet configurations are specified in [Table B.1](#). [Table B.2](#) gives maximum electrode diameter, electrode force, welding time and hold time which can be used for high strength steels (UTS ≥ 650 MPa) if nominal parameters from [Table B.1](#) give unsatisfactory results..

B.4 Minimum weld diameter

The minimum weld diameter is used to evaluate the lower end of the welding range and the end of electrode life. It can be defined as

$$x * \sqrt{t}$$

where

t is the thinner sheet thickness;

x is a coefficient to be defined (usually between 3 and 4,5).

Table B.1 — Welding parameters for steel sheets

Sheet thickness mm	Electrode type acc. ISO 5821 mm	Electrode force ^c kN		Number of impulses	Weld time ms		Hold time ms	Welding rate for electrode life test welds per min
		UTS < 380 MPa	UTS ≥ 380 MPa		Individual weld time ^{b,c} UTS < 380 MPa	Cool time UTS ≥ 380 MPa		
0,50 to 0,54	F1 - 16 - 20 - 50 - 6	1,70	2,10	1	100 + X	120 + X	120	30
0,55 to 0,64	F1 - 16 - 20 - 50 - 6	1,90	2,30	1	120 + X	140 + X	120	30
0,65 to 0,74	F1 - 16 - 20 - 50 - 6	2,10	2,60	1	140 + X	160 + X	140	30
0,75 to 0,84	F1 - 16 - 20 - 50 - 6	2,30	3,00	1	160 + X	180 + X	140	30
0,85 to 0,94	F1 - 16 - 20 - 50 - 6	2,50	3,50	1	180 + X	200 + X	160	30
0,95 to 1,09	F1 - 16 - 20 - 50 - 6	2,70	3,50	1	200 + X	220 + X	180	30
1,10 to 1,34	F1 - 16 - 20 - 50 - 6	3,00	4,00	1	240 + X	280 + X	200	30
1,35 to 1,64	F1 - 16 - 20 - 50 - 6	4,00	4,50	1	300 + X	340 + X	260	30
1,65 to 1,89	F1 - 20 - 22 - 50 - 8	4,50	5,00	3	140 + X	160 + X	320	20
1,90 to 2,24	F1 - 20 - 22 - 50 - 8	4,50	5,00	4	120 + X	140 + X	360	20
2,25 to 2,74	F1 - 20 - 22 - 50 - 8	5,00	6,00	5	120 + X	140 + X	460	20
2,75 to 3,00	F1 - 20 - 22 - 50 - 8	5,50	6,50	5	140 + X	160 + X	520	20

NOTE The table is compiled using 50 Hz.

^a When welding two sheets of unequal thickness, the thinner sheet determines the welding parameters. When welding a three sheets stack-up, the thinner of the two thicker sheets determines the welding parameters.

^b Add X = 40 ms to the individual weld time when at least one coating is present at one faying interface of the assembly.

^c When sheets with differing UTS are welded together, choose the highest UTS of the assembly to set weld time and electrode force.

Table B.2 — Optional maximum welding parameters for advanced high strength steel sheets (UTS ≥ 650 MPa)


Sheet thickness mm	Maximum electrode face diameter mm	Maximum electrode force kN	Maximum weld time ms	Maximum hold time ms
0,50 to 0,54	6	2,10	240	240
0,55 to 0,64	6	2,30	240	240
0,65 to 0,74	6	2,60	320	320
0,75 to 0,84	6	3,00	320	320
0,85 to 0,94	6	3,80	320	320
0,95 to 1,09	6	4,00	400	400
1,10 to 1,34	6	4,50	500	500
1,35 to 1,64	8	5,50	800	500
1,65 to 1,89	8	6,00	900	500
1,90 to 2,24	8	6,50	1100	500
2,25 to 2,74	10	7,00	1200	600
2,75 to 3,00	10	7,50	1400	700

These parameters are the maximum values that may be used in case of unsatisfactory results obtained for standard parameters given in [Table B.1](#).

Annex C (informative)

Test specimens for mechanical characterization

See [Figures C.1](#) and [C.2](#).



Key

a Cut centre.

Figure C.1 — Example of test strip

Dimensions in millimetres




Figure C.2 — Example of device for simultaneous separation of 5 or 10 weld spots

Annex D (informative)

Example of test report for welding current range

ISO 18278-2			Welding current range test					
<u>Date:</u> 2012-11-27 <u>Name:</u> Mr Smith								
<u>Material:</u> Sheet A Sheet B ... <u>Ident:</u> <u>Thickness:</u> <u>Coating</u>			<u>Welding parameters</u> <u>Machine reference:</u> Sciaky R125 <u>Current type:</u> AC <u>Electrodes:</u> G0-16-6 <u>Welding force:</u> 2,3 kN <u>heat time:</u> 200 ms <u>Hold time:</u> 200 ms <u>Impulses:</u> 1 <u>Cool time:</u> -					
<u>Stack-up arrangement</u> A + A <u>Specimen type</u> coupons <u>Minimum weld diameter</u> 3,6 mm								
No.	I_{RMS} [kA]	Splash	d_{w1} [mm]	d_{w2} [mm]	$\varnothing d_w$ [mm]	Failure mode	Estimated plug-% (PIF)	Notes
1	6,9		2,2	2,6	2,4	PF		
2	6,9		2,3	2,5	2,4	PF		
3	7,1		2,	3,8	3,3	PF		
4	7,1		7	3,7	3,2	PF		
5	7,3		2,7	3,9	3,4	PF		
...
20	8,7	x	5,3	5,3	5,3	PF		
21	8,9	x	5,1	5,3	5,2	PF		
22	8,9	x	5,0	5,3	5,2	PF		
23	8,8	x	5,1	5,2	5,2	PF		
24	8,7	x	5,2	5,2	5,2	PF		
25	8,6		5,4	5,6	5,5	PF		I_{max}

Annex E (informative)

Example of test report for electrode life test

ISO 18278-2		Electrode life test																																																																									
<u>Date:</u> 2012-11-28 <u>Name:</u> Mr Smith		<u>Test reference:</u> A 12-1568VA																																																																									
<u>Reference:</u> <u>Material:</u> <u>Thickness:</u> <u>Coating</u>	<u>Sheet A</u> <u>Sheet B</u> ...	<u>Welding parameters</u>																																																																									
<u>Stack-up arrangement</u> A + A <u>Specimen type</u> 10-weld strips		<u>Machine reference:</u> Sciaky R125 <u>Current type:</u> AC <u>Electrodes:</u> G0-16-6 <u>Welding force:</u> 2,3 kN <u>heat time:</u> 200 ms <u>Impulse number:</u> 1 <u>Cool time:</u>																																																																									
<u>Minimum weld diameter</u> 4 mm		<u>Welding current:</u> 9,4 kA <u>Hold time:</u> 120 ms																																																																									
<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th colspan="2" style="text-align: center;">Electrode life</th> <th style="text-align: center;">500</th> <th colspan="2" style="text-align: center;">welds</th> </tr> <tr> <th rowspan="2" style="text-align: center;">Weld number</th> <th rowspan="2" style="text-align: center;">Welding current (kA)</th> <th rowspan="2" style="text-align: center;">observations</th> <th colspan="2" style="text-align: center;">Weld diameter (mm)</th> </tr> <tr> <th style="text-align: center;">No expulsion</th> <th style="text-align: center;">Expulsion</th> </tr> </thead> <tbody> <tr><td style="text-align: center;">2</td><td style="text-align: center;">9,5</td><td style="text-align: center;">el. sticking</td><td></td><td style="text-align: center;">6,2</td></tr> <tr><td style="text-align: center;">3</td><td style="text-align: center;">9,5</td><td style="text-align: center;">el. sticking</td><td style="text-align: center;">6,3</td><td></td></tr> <tr><td style="text-align: center;">4</td><td style="text-align: center;">9,5</td><td style="text-align: center;">el. sticking</td><td></td><td style="text-align: center;">6,4</td></tr> <tr><td style="text-align: center;">5</td><td style="text-align: center;">9,5</td><td></td><td></td><td style="text-align: center;">6,1</td></tr> <tr><td style="text-align: center;">6</td><td style="text-align: center;">9,5</td><td style="text-align: center;">el. sticking</td><td></td><td style="text-align: center;">6,2</td></tr> <tr><td style="text-align: center;">7</td><td style="text-align: center;">9,4</td><td style="text-align: center;">el. sticking</td><td style="text-align: center;">6,3</td><td></td></tr> <tr><td style="text-align: center;">8</td><td style="text-align: center;">9,4</td><td></td><td></td><td style="text-align: center;">6,2</td></tr> <tr><td style="text-align: center;">9</td><td style="text-align: center;">9,4</td><td style="text-align: center;">el. sticking</td><td style="text-align: center;">6,4</td><td></td></tr> <tr><td style="text-align: center;">...</td><td style="text-align: center;">...</td><td style="text-align: center;">...</td><td style="text-align: center;">...</td><td style="text-align: center;">...</td></tr> <tr><td style="text-align: center;">52</td><td style="text-align: center;">9,4</td><td></td><td style="text-align: center;">6,1</td><td></td></tr> <tr><td style="text-align: center;">53</td><td style="text-align: center;">9,4</td><td style="text-align: center;">el. sticking</td><td style="text-align: center;">6,2</td><td></td></tr> <tr><td style="text-align: center;">54</td><td style="text-align: center;">9,4</td><td></td><td style="text-align: center;">5,9</td><td></td></tr> </tbody> </table>				Electrode life		500	welds		Weld number	Welding current (kA)	observations	Weld diameter (mm)		No expulsion	Expulsion	2	9,5	el. sticking		6,2	3	9,5	el. sticking	6,3		4	9,5	el. sticking		6,4	5	9,5			6,1	6	9,5	el. sticking		6,2	7	9,4	el. sticking	6,3		8	9,4			6,2	9	9,4	el. sticking	6,4		52	9,4		6,1		53	9,4	el. sticking	6,2		54	9,4		5,9	
Electrode life		500	welds																																																																								
Weld number	Welding current (kA)	observations	Weld diameter (mm)																																																																								
			No expulsion	Expulsion																																																																							
2	9,5	el. sticking		6,2																																																																							
3	9,5	el. sticking	6,3																																																																								
4	9,5	el. sticking		6,4																																																																							
5	9,5			6,1																																																																							
6	9,5	el. sticking		6,2																																																																							
7	9,4	el. sticking	6,3																																																																								
8	9,4			6,2																																																																							
9	9,4	el. sticking	6,4																																																																								
...																																																																							
52	9,4		6,1																																																																								
53	9,4	el. sticking	6,2																																																																								
54	9,4		5,9																																																																								

Bibliography

- [1] ISO 14271, *Resistance welding — Vickers hardness testing (low-force and microhardness) of resistance spot, projection, and seam welds*
- [2] ISO 14327, *Resistance welding — Procedures for determining the weldability lobe for resistance spot, projection and seam welding*
- [3] ISO 17657-1, *Resistance welding — Welding current measurement for resistance welding — Part 1: Guidelines for measurement*
- [4] ISO 17657-2, *Resistance welding — Welding current measurement for resistance welding — Part 2: Welding current meter with current sensing coil*
- [5] ISO 17657-5, *Resistance welding — Welding current measurement for resistance welding — Part 5: Verification of welding current measuring system*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK