

BS EN ISO 18846:2016



BSI Standards Publication

Solid biofuels — Determination of fines content in quantities of pellets (ISO 18846:2016)

National foreword

This British Standard is the UK implementation of EN ISO 18846:2016.

BSI, as a member of CEN, is obliged to publish EN ISO 18846 as a British Standard. However, attention is drawn to the fact that during the development of this European Standard, the UK committee voted against its approval as a European Standard.

The UK committee's main concerns are:

- some of the terminology used creates ambiguity;
- the supported methodology could result in incomplete separation of particle sizes;
- the standard is too prescriptive with regards to recommended equipment.

The UK participation in its preparation was entrusted to Technical Committee PTI/17, Solid biofuels.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 83583 4

ICS 27.190; 75.160.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2016.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN ISO 18846

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2016

ICS 27.190; 75.160.10

English Version

Solid biofuels - Determination of fines content in quantities of pellets (ISO 18846:2016)

Biocombustibles solides - Détermination de la teneur en fines dans des échantillons de granulés (ISO 18846:2016)

Biogene Festbrennstoffe - Bestimmung des Gehaltes an Feingut in Mengen von Pellets (ISO 18846:2016)

This European Standard was approved by CEN on 7 August 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 18846:2016) has been prepared by Technical Committee ISO/TC 238 "Solid biofuels" in collaboration with Technical Committee CEN/TC 335 "Solid biofuels" the secretariat of which is held by SIS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2017, and conflicting national standards shall be withdrawn at the latest by March 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 18846:2016 has been approved by CEN as EN ISO 18846:2016 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	1
6 Sample preparation	2
6.1 Sample reduction.....	2
6.2 Size of the test portion.....	2
7 Procedure	2
7.1 Sieving.....	2
7.2 Weighing.....	3
8 Calculations	3
8.1 Total mass of all fractions.....	3
8.2 Proportion of fines.....	3
8.3 Quality control.....	3
9 Performance characteristics	3
10 Test report	3
Bibliography	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 238, *Solid biofuels*.

Introduction

This International Standard describes a method for manual determination of the fines content in samples of pellets. The fines content is defined as the percentage in mass of material below 3,15 mm in size. The fines content is an important parameter since excessive amounts of fines in consignments of pellets increases the risk for dust explosions and is also a health problem if the dust is inhaled.

Solid biofuels — Determination of fines content in samples of pellets

1 Scope

This International Standard specifies a method for determining the amount of material passing through a sieve with 3,15 mm diameter round hole.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3310-2, *Test sieves — Technical requirements and testing — Part 2: Test sieves of perforated metal plate*

ISO 14780¹⁾, *Solid biofuels — Sample preparation*

ISO 16559, *Solid biofuels — Terminology, definitions and descriptions*

ISO 18135²⁾, *Solid biofuels — Sampling*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 16559 apply.

4 Principle

A test sample is subjected to sieving by means of manually shaking a sieve with 3,15 mm diameter round holes by horizontal movements and the mass of the material passing through is determined.

5 Apparatus

5.1 Sieve. The sieve shall have round holes with a diameter of 3,15 mm and aperture geometry in accordance with ISO 3310-2.

A sieve with a diameter of 400 mm is recommended. The frame of the sieve shall have a height that enable the sieves to contain a sample and allows a free movement of the sample during the sieving process. Other sizes of sieves may be used for practical reasons but it is important to make sure the sieve is not overloaded which may result in insufficient agitation of the test sample which may impact the flow of fines through the apertures of the sieve.

5.2 Collecting pan, for collection of material passing through the sieve, a collecting pan of adequate size is required.

5.3 Weighing container, for weighing of the fractions, the collecting pan or a separate container of adequate size is required.

1) To be published.

2) To be published. (Until ISO 18135 is published, EN 14778 should be used.)

5.4 Balance. The balance shall be capable of reading to the nearest 0,1 g.

The balance shall have a weighing capacity of 2 kg or a weighing capacity equal to the selected size of the sieve fractions and the mass of the weighing container.

6 Sample preparation

6.1 Sample reduction

The laboratory sample used for the determination of the fines content shall be obtained in accordance with ISO 18135. The sampling strategy shall be such that special provisions are taken regarding the tendency for stratification of the fines in a consignment of pellets. For example, the entire quantity of pellets in a bag shall be sampled in order to obtain a representative test sample. Due to the special provisions necessary regarding sampling for fines determination, the combined (raw) sample may end up being very large. The combined sample may be divided into one or more smaller test portions using a procedure for sample division in accordance with ISO 14780³⁾.

NOTE In bulk handling of large volumes of pellets, there is often a risk for stratification of materials in storage bins. There is also the risk of incremental variations of fines in volumes of pellets due to batch-wise operation during transportation with rail cars, trucks and ocean vessels.

6.2 Size of the test portion

The size of the test portion shall be selected in relation to pellets diameter as given in [Table 1](#).

NOTE A larger size of the test portion will yield a higher accuracy (e.g. 1 % according to ISO 17225-1, ISO 17225-2 and ISO 17225-6).

Table 1 — Minimum mass of test portion for pellet diameter classes in accordance with ISO 17225-1, ISO 17225-2 and ISO 17225-6

Pellet diameter mm	Sample size kg	
	Minimum	Recommended
<6	3	5 to 10
6 to 12	5	10 to 15
>12 (up to 25)	10	15 to 20

The total mass of the test portion shall be weighed to the nearest 0,1 g and recorded for the quality control calculation in [8.3](#).

7 Procedure

7.1 Sieving

The sieving shall be done in such a way that the fine particles are separated from the pellets but at the same time avoiding new fines being created. This is best achieved by 5 to 10 circular horizontal rotations of 0,5 kg of material in the sieve. If a sieve with a diameter other than 400 mm is used, the size of the sieved sub-portions (of the test portion) shall be adjusted to achieve the same degree of filling of the sieve.

After each sub-portion is sieved, the fines in the collecting pan shall be transferred to a weighing container or if practical the fines may be left in the collecting pan as fines from subsequent sub-portions

3) To be published. (Until ISO 14780 is published, EN 14780 should be used.)

collected. The coarse material retained on the sieve from each sub-portion shall be transferred to another container.

7.2 Weighing

After completing the sieving of all sub-portions of the test portion, weigh the total amount of material which passed through the sieve (the fines fraction) and weigh the total amount of material retained on the sieve (the coarse fraction).

The weighing of the fines fraction can be performed either by weighing the collecting pan with the fines fraction and subtracting the mass of the empty collecting pan, or the fines fraction can be transferred to a tared weighing container for determining the mass of the fraction.

8 Calculations

8.1 Total mass of all fractions

Calculate the total mass of all fractions as the sum of the mass of the fines fraction and the mass of the coarse fraction.

8.2 Proportion of fines

Calculate the w -% of fines by dividing the mass of the fraction by the mass of all fractions (as per [8.1](#)) and multiply by 100.

8.3 Quality control

Calculate the difference between the mass of the test portion (as per [8.2](#)) and the total mass of all fractions (as per [8.1](#)) and express the difference in percent of the mass of the test portion. If the difference is larger than 2 w -%, the causes for the deviation shall be investigated and the determination shall be repeated. If this is impractical or the difference after repeated determination still exceeds a mass fraction of 2 % of the mass of the test portion, the size of the difference in % mass fraction of the test portion shall be reported together with the fines content as per [8.2](#).

9 Performance characteristics

For the time being, not enough data are available for a precision statement regarding this test method.

10 Test report

The test report shall include at least the following information:

- a) the identification of the laboratory performing the test and the date of the test;
- b) the identification of product (or sample) tested;
- c) a reference to this International Standard, i.e. ISO 18846;
- d) the mass of the test portion (as per [6.2](#));
- e) the result of the test on an as-received basis;
- f) the difference between the mass of the test portion and the total mass of all fractions, in percent of the mass of the test portion if the difference exceeds a mass fraction of 2 %;
- g) any unusual features noted during the determination, which may affect the result;
- h) any deviation from this International Standard, or operations regarded as optional.

Bibliography

- [1] ISO 17225-1, *Solid biofuels — Fuel specifications and classes — Part 1: General requirements*
- [2] ISO 17225-2, *Solid biofuels — Fuel specifications and classes — Part 2: Graded wood pellets*
- [3] ISO 17225-6, *Solid biofuels — Fuel specifications and classes — Part 6: Graded non-woody pellets*
- [4] ISO 17225-8⁴⁾, *Solid biofuels — Fuel specifications and classes — Part 8: Graded thermally treated and densified biomass fuels*

4) To be published.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK