

BS EN ISO 26304:2011



BSI Standards Publication

# **Welding consumables — Solid wire electrodes, tubular cored electrodes and electrode-flux combinations for submerged arc welding of high strength steels — Classification (ISO 26304:2011)**

**bsi.**

...making excellence a habit.™

**National foreword**

This British Standard is the UK implementation of EN ISO 26304:2011. It supersedes BS EN ISO 26304:2009 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee WEE/39, Welding consumables.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2011

ISBN 978 0 580 72585 2

ICS 25.160.20

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 August 2011.

**Amendments issued since publication**

| Date | Text affected |
|------|---------------|
|------|---------------|

---

English Version

## Welding consumables - Solid wire electrodes, tubular cored electrodes and electrode-flux combinations for submerged arc welding of high strength steels - Classification (ISO 26304:2011)

Produits consommables pour le soudage - Fils-électrodes pleins, fils-électrodes fourrés et couples électrodes-flux pour le soudage à l'arc sous flux des aciers à haute résistance - Classification (ISO 26304:2011)

Schweißzusätze - Massivdrahtelektroden, Fülldrahtelektroden und Draht-Pulver-Kombinationen zum Unterpulverschweißen von hochfesten Stählen - Einteilung (ISO 26304:2011)

This European Standard was approved by CEN on 11 July 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

## Foreword

This document (EN ISO 26304:2011) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2012, and conflicting national standards shall be withdrawn at the latest by February 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 26304:2009.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

### Endorsement notice

The text of ISO 26304:2011 has been approved by CEN as a EN ISO 26304:2011 without any modification.

## Contents

Page

|                                                                                                                                                    |           |
|----------------------------------------------------------------------------------------------------------------------------------------------------|-----------|
| Foreword .....                                                                                                                                     | iv        |
| Introduction.....                                                                                                                                  | v         |
| <b>1 Scope .....</b>                                                                                                                               | <b>1</b>  |
| <b>2 Normative references .....</b>                                                                                                                | <b>1</b>  |
| <b>3 Classification .....</b>                                                                                                                      | <b>2</b>  |
| <b>4 Symbols and requirements .....</b>                                                                                                            | <b>3</b>  |
| 4.1 Symbol for the product or process .....                                                                                                        | 3         |
| 4.2 Symbols for the tensile properties of the all-weld metal deposit.....                                                                          | 3         |
| 4.3 Symbol for the impact properties of the all-weld metal .....                                                                                   | 4         |
| 4.4 Symbol for the type of welding flux.....                                                                                                       | 5         |
| 4.5 Symbol for the chemical composition of solid wire electrodes and of the all-weld metal<br>from tubular cored electrode-flux combinations ..... | 5         |
| 4.6 Symbol for the post-weld heat treatment.....                                                                                                   | 11        |
| 4.7 Symbol for hydrogen content of deposited metal .....                                                                                           | 12        |
| <b>5 Mechanical tests .....</b>                                                                                                                    | <b>13</b> |
| 5.1 Tensile and impact tests.....                                                                                                                  | 13        |
| 5.2 Preheating and interpass temperature.....                                                                                                      | 13        |
| 5.3 Welding conditions and pass sequence .....                                                                                                     | 13        |
| <b>6 Chemical analysis .....</b>                                                                                                                   | <b>14</b> |
| <b>7 Rounding procedure .....</b>                                                                                                                  | <b>14</b> |
| <b>8 Retests.....</b>                                                                                                                              | <b>15</b> |
| <b>9 Technical delivery conditions .....</b>                                                                                                       | <b>15</b> |
| <b>10 Examples of designation .....</b>                                                                                                            | <b>15</b> |
| <b>Annex A (informative) Possible risk of weld metal hydrogen cracking .....</b>                                                                   | <b>17</b> |
| <b>Bibliography.....</b>                                                                                                                           | <b>18</b> |

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 26304 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

This second edition cancels and replaces the first edition (ISO 26304:2008), of which it constitutes a minor revision. It also incorporates the Technical Corrigendum ISO 26304:2008/Cor.1:2009.

Requests for official interpretations of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 3 via your national standards body. A complete listing of these bodies can be found at [www.iso.org](http://www.iso.org).

## Introduction

This International Standard recognizes that there are two somewhat different approaches in the global market to classifying a given wire electrode, tubular cored electrode, and electrode-flux combination, and allows for either or both to be used, to suit a particular market need. Application of either type of classification designation (or of both where suitable) identifies a product as classified in accordance with this International Standard. The classification in accordance with system A is mainly based on EN 14295<sup>[3]</sup>. The classification in accordance with system B is mainly based upon standards used around the Pacific Rim. Future revisions aim to merge the two approaches into a single classification system.

This International Standard provides a classification for the designation of solid wire electrodes in terms of their chemical composition, tubular cored electrodes in terms of the deposit composition obtained with a particular submerged arc flux, and, where required, electrode-flux combinations in terms of the yield strength, tensile strength, elongation, and impact properties of the all-weld metal deposit. The ratio of yield to tensile strength of weld metal is generally higher than that of parent material. Users should note that matching weld metal yield strength to parent metal yield strength does not necessarily ensure that the weld metal tensile strength matches that of the parent material. Thus, where the application requires matching tensile strength, selection of the consumable should be made by reference to column 3 of Table 1A or Table 1B, as appropriate.

Although combinations of electrodes and fluxes supplied by individual companies may have the same classification, the combination of an electrode with a flux from one manufacturer versus the flux from another manufacturer, both fluxes having the same classification, may not be interchangeable unless verified in accordance with this International Standard. Two tubular cored wires of the same classification may likewise produce different results with the same flux.

The mechanical properties of the all-weld metal test specimens used to classify the electrode-flux combinations vary from those obtained in production joints because of differences in welding procedures such as electrode size, width of weave, welding position, and material composition.





# Welding consumables — Solid wire electrodes, tubular cored electrodes and electrode-flux combinations for submerged arc welding of high strength steels — Classification

## 1 Scope

This International Standard specifies requirements for classification of solid wire electrodes, tubular cored electrodes, and electrode-flux combinations (the all-weld metal deposits) in the as-welded condition and in the post-weld heat-treated condition for submerged arc welding of high strength steels with a minimum yield strength greater than 500 MPa or a minimum tensile strength greater than 570 MPa. One flux can be tested and classified with different electrodes. One electrode can be tested and classified with different fluxes. The solid wire electrode is also classified separately based on its chemical composition.

This International Standard is a combined specification providing for classification utilizing a system based upon the yield strength and average impact energy of 47 J for the all-weld metal, or utilizing a system based upon the tensile strength and average impact energy of 27 J for the all-weld metal.

- a) Clauses, subclauses and tables which carry the suffix letter “A” are applicable only to solid wire electrodes, tubular cored electrodes and the all-weld metal deposits classified to the system based upon the yield strength and the average impact energy of 47 J for the all-weld metal obtained with electrode-flux combinations in accordance with this International Standard.
- b) Clauses, subclauses and tables which carry the suffix letter “B” are applicable only to solid wire electrodes, tubular cored electrodes and the all-weld metal deposits classified to the system based upon the tensile strength and the average impact energy of 27 J for the all-weld metal obtained with electrode-flux combinations in accordance with this International Standard.
- c) Clauses, subclauses and tables which do not have either the suffix letter “A” or the suffix letter “B” are applicable to all solid wire electrodes, tubular cored electrodes and electrode-flux combinations classified in accordance with this International Standard.

For comparison purposes, some tables include requirements for electrodes classified in accordance with both systems, placing individual electrodes from the two systems, which are similar in composition and properties, on adjacent lines in the particular table. In a particular line of the table that is mandatory in one system, the symbol for the similar electrode from the other system is indicated in parentheses. By appropriate restriction of the formulation of a particular electrode, it is often, but not always, possible to produce an electrode that can be classified in both systems, in which case the electrode, or its packaging, may be marked with the classification in either or both systems.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 3690, *Welding and allied processes — Determination of hydrogen content in arc weld metal*

ISO 6847, *Welding consumables — Deposition of a weld metal pad for chemical analysis*

ISO 13916, *Welding — Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

ISO 14174, *Welding consumables — Fluxes for submerged arc welding and electroslag welding — Classification*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 15792-1:2000, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*

ISO 80000-1:2009, *Quantities and units — Part 1: General*

### 3 Classification

Classification designations are based upon two approaches to indicate the tensile properties and the impact properties of the all-weld metal obtained with a given electrode-flux combination. The two designation approaches include additional designators for the chemical composition of a solid wire electrode or the chemical composition of the all-weld metal deposit obtained with a tubular cored electrode and a particular flux. The two designation approaches include additional designators for some other classification requirements, but not all, as is clear from the following clauses. A given commercial product may be classified to the classification requirements in both systems; then either or both classification designations may be used for the product.

The classification includes the all-weld metal properties obtained with a specific electrode-flux combination as given in 3A and 3B. A solid wire electrode shall be classified in accordance with its chemical composition in Table 3.

A tubular cored electrode shall be classified in accordance with the all-weld metal deposit composition in Table 4, obtained with a particular flux.

When the solid wire electrode or tubular cored electrode is classified in combination with a flux for submerged arc welding, the classification shall be prefixed with a symbol in accordance with Clause 4 as appropriate.

#### 3A Classification by yield strength and 47 J impact energy

The classification is divided into seven parts:

- 1) the first part gives a symbol indicating the product or process to be identified;
- 2) the second part gives a symbol indicating the tensile properties of the all-weld metal (see Table 1A);
- 3) the third part gives a symbol indicating the impact properties of the all-weld metal (see Table 2);

#### 3B Classification by tensile strength and 27 J impact energy

The classification is divided into six parts:

- 1) the first part gives a symbol indicating the product or process to be identified;
- 2) the second part gives a symbol indicating the strength and elongation of the the all-weld metal in either the as-welded or the post-weld heat-treated condition (see Table 1B);
- 3) the third part gives a symbol indicating the impact properties of the all-weld metal in the same condition as specified for the tensile strength (see Table 2). The letter “U” after this designator indicates that the deposit meets an average optional requirement of 47 J at the designated impact test temperature;

- |                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                 |                                                                                                                                                                                                                                                                                                                                                                                                                                                             |
|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <p>4) the fourth part gives a symbol indicating the type of flux used (see 4.4);</p> <p>5) the fifth part gives a symbol indicating the chemical composition of the solid wire electrode used (see Table 3) or of the all-weld metal deposited by a tubular cored electrode-flux combination (see Table 4);</p> <p>6) the sixth part gives a symbol indicating the stress relief treatment if this is applied;</p> <p>7) the seventh part gives a symbol indicating the diffusible hydrogen content of the weld metal obtained in accordance with ISO 3690.</p> | <p>4) the fourth part gives a symbol indicating the type of flux used (see 4.4);</p> <p>5) the fifth part gives a symbol indicating the chemical composition of the solid wire electrode used (see Table 3), or of the all-weld metal deposited by a tubular cored electrode-flux combination (see Table 4);</p> <p>6) the sixth part gives a symbol indicating the diffusible hydrogen content of the weld metal obtained in accordance with ISO 3690.</p> |
|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|

## 4 Symbols and requirements

A solid wire electrode can be classified separately based upon its chemical composition, as specified in Table 3. The all-weld metal deposit composition and mechanical properties obtained with a particular solid wire electrode or tubular cored electrode vary somewhat depending upon the flux used. Accordingly, the classification of the all-weld metal deposit obtained with a particular solid wire electrode or tubular cored electrode may be different for different fluxes. However, deposit composition is only a classification requirement for tubular cored electrode-flux combinations.

### 4.1 Symbol for the product or process

The symbol for the electrode-flux combination or weld deposit produced by a solid wire electrode or by a tubular cored electrode using the submerged arc welding process with a particular flux, shall be the letter "S" placed at the beginning of the designation.

#### 4.1A Classification by yield strength and 47 J impact energy

The symbol for the solid wire electrode for use in the submerged arc welding process shall be the letter "S" placed at the beginning of the solid wire electrode designation.

The symbol for the tubular cored electrode for use in the submerged arc welding process shall be the letter "T" placed at the beginning of the tubular cored electrode designation.

#### 4.1B Classification by tensile strength and 27 J impact energy

The symbol for the solid wire electrode for use in the submerged arc welding process shall be the letters "SU" placed at the beginning of the solid wire electrode designation.

The symbol for the tubular cored electrode for use in the submerged arc welding process shall be the letters "TU" placed at the beginning of the tubular cored electrode designation.

### 4.2 Symbols for the tensile properties of the all-weld metal deposit

#### 4.2A Classification by yield strength and 47 J impact energy

The symbols in Table 1A indicate the yield strength, tensile strength, and elongation of the all-weld metal in the as-welded condition or after stress relief treatment in accordance with 4.6A, determined in accordance with Clause 5 (A-side).

#### 4.2B Classification by tensile strength and 27 J impact energy

The symbols in Table 1B indicate the tensile strength, yield strength, and elongation of the all-weld metal in the as-welded condition or in the post-weld heat-treated condition in accordance with 4.6B, determined in accordance with Clause 5 (B-side), with a particular flux.

**Table 1A — Symbol for the tensile properties**  
(Classification by yield strength and 47 J impact energy)

| Symbol | Minimum <sup>a</sup> yield strength<br>MPa | Tensile strength<br>MPa | Minimum <sup>b</sup> elongation<br>% |
|--------|--------------------------------------------|-------------------------|--------------------------------------|
| 55     | 550                                        | 640 to 820              | 18                                   |
| 62     | 620                                        | 700 to 890              | 18                                   |
| 69     | 690                                        | 770 to 940              | 17                                   |
| 79     | 790                                        | 880 to 1 080            | 16                                   |
| 89     | 890                                        | 940 to 1 180            | 15                                   |

<sup>a</sup> For yield strength, the lower yield strength,  $R_{eL}$ , is used when yielding occurs, otherwise the 0,2 % proof strength,  $R_{p0,2}$ , is used.

<sup>b</sup> Gauge length is equal to five times the test specimen diameter.

**Table 1B — Symbol for the tensile properties**  
(Classification by tensile strength and 27 J impact energy)

| Symbol <sup>a</sup> | Minimum yield strength <sup>b</sup><br>MPa | Tensile strength<br>MPa | Minimum elongation <sup>c</sup><br>% |
|---------------------|--------------------------------------------|-------------------------|--------------------------------------|
| 59X                 | 490                                        | 590 to 790              | 16                                   |
| 62X                 | 500                                        | 620 to 820              | 15                                   |
| 69X                 | 550                                        | 690 to 890              | 14                                   |
| 76X                 | 670                                        | 760 to 960              | 13                                   |
| 78X                 | 670                                        | 780 to 980              | 13                                   |
| 83X                 | 740                                        | 830 to 1 030            | 12                                   |

<sup>a</sup> X is "A" or "P", where "A" indicates testing in the as-welded condition and "P" indicates testing in the post-weld heat-treated condition

<sup>b</sup> For yield strength, the 0,2 % proof strength,  $R_{p0,2}$ , is used.

<sup>c</sup> Gauge length is equal to five times the test specimen diameter.

### 4.3 Symbol for the impact properties of the all-weld metal

The symbols in Table 2 indicate the temperature at which an average impact energy of 47 J or 27 J is achieved under the conditions given in Clause 5 in the as-welded condition or after post-weld heat treatment.

**Table 2 — Symbol for the impact properties of the all-weld metal**

| Symbol                           | Temperature for minimum average impact energy of 47 J <sup>a,b</sup> or 27 J <sup>b</sup><br>°C |
|----------------------------------|-------------------------------------------------------------------------------------------------|
| Z                                | No requirements                                                                                 |
| A <sup>a</sup> or Y <sup>b</sup> | +20                                                                                             |
| 0                                | 0                                                                                               |
| 2                                | -20                                                                                             |
| 3                                | -30                                                                                             |
| 4                                | -40                                                                                             |
| 5                                | -50                                                                                             |
| 6                                | -60                                                                                             |

<sup>a</sup> When classified in accordance with 4.3A.  
<sup>b</sup> When classified in accordance with 4.3B.

#### **4.3A Classification by yield strength and 47 J impact energy**

Three test specimens shall be tested. The average value shall be at least 47 J. Only one individual value may be lower than 47 J but not lower than 32 J.

#### **4.3B Classification by tensile strength and 27 J impact energy**

Five test specimens shall be tested. The lowest and highest values obtained shall be disregarded. Two of the three remaining values shall be greater than the specified 27 J level, one of the three may be lower but shall not be less than 20 J. The average of the three remaining values shall be at least 27 J.

The addition of the optional symbol U, immediately after the symbol for condition of heat treatment, indicates that the supplemental requirement of 47 J impact energy at the normal 27 J impact test temperature has also been satisfied. For the 47 J impact requirement, the number of specimens tested and values obtained shall meet the requirements of 4.3A.

#### **4.4 Symbol for the type of welding flux**

The symbols for welding flux shall be in accordance with ISO 14174.

#### **4.5 Symbol for the chemical composition of solid wire electrodes and of the all-weld metal from tubular cored electrode-flux combinations**

The symbols in Table 3 indicate the chemical composition of the solid wire electrode, determined under the conditions given in Clause 6.

The symbols in Table 4 indicate the chemical composition of the all-weld metal deposit obtained with the tubular cored electrode and a particular flux, determined under the conditions given in Clause 6.

Table 3 — Chemical composition requirements for solid wire electrodes

| Symbol for chemical composition                                      |                         | Chemical composition<br>% (by mass) <sup>a</sup> |              |              |       |       |      |              |              |                 |      |                                  |
|----------------------------------------------------------------------|-------------------------|--------------------------------------------------|--------------|--------------|-------|-------|------|--------------|--------------|-----------------|------|----------------------------------|
|                                                                      |                         | C                                                | Si           | Mn           | P     | S     | Cr   | Ni           | Mo           | Cu <sup>b</sup> | V    | Other                            |
| classification by yield strength and 47 J impact energy ISO 26304-A  | SUN1M3 <sup>cd</sup>    | 0,10 to 0,18                                     | 0,20         | 1,70 to 2,40 | 0,025 | 0,025 | —    | 0,40 to 0,80 | 0,40 to 0,65 | 0,35            | —    | —                                |
|                                                                      | SUN2M1 <sup>cd</sup>    | 0,12                                             | 0,05 to 0,30 | 1,20 to 1,60 | 0,020 | 0,020 | 0,20 | 0,75 to 1,25 | 0,10 to 0,30 | 0,35            | —    | —                                |
|                                                                      | SUN2M3 <sup>cd</sup>    | 0,15                                             | 0,25         | 0,80 to 1,40 | 0,020 | 0,020 | 0,20 | 0,80 to 1,20 | 0,40 to 0,65 | 0,40            | —    | —                                |
|                                                                      | SUN2M31 <sup>cd</sup>   | 0,15                                             | 0,25         | 1,30 to 1,90 | 0,020 | 0,020 | 0,20 | 0,80 to 1,20 | 0,40 to 0,65 | 0,40            | —    | —                                |
|                                                                      | SUN2M32 <sup>cd</sup>   | 0,15                                             | 0,25         | 1,60 to 2,30 | 0,020 | 0,020 | 0,20 | 0,80 to 1,20 | 0,40 to 0,65 | 0,40            | —    | —                                |
| classification by yield strength and 27 J impact energy ISO 26304-B  | SUN2M33 <sup>cd</sup>   | 0,10 to 0,18                                     | 0,30         | 1,70 to 2,40 | 0,025 | 0,025 | —    | 0,70 to 1,10 | 0,40 to 0,65 | 0,35            | —    | —                                |
|                                                                      | (SUN2M2)                | 0,07 to 0,15                                     | 0,05 to 0,25 | 0,80 to 1,30 | 0,020 | 0,020 | 0,20 | 0,80 to 1,20 | 0,45 to 0,65 | 0,30            | —    | 0,50                             |
|                                                                      | (SUN2M2)                | 0,07 to 0,15                                     | 0,05 to 0,35 | 1,30 to 1,80 | 0,020 | 0,020 | 0,20 | 0,80 to 1,20 | 0,45 to 0,65 | 0,30            | —    | 0,50                             |
|                                                                      | SUN2M2 <sup>c</sup>     | 0,07 to 0,15                                     | 0,15 to 0,35 | 0,90 to 1,70 | 0,025 | 0,025 | —    | 0,95 to 1,60 | 0,25 to 0,55 | 0,35            | —    | —                                |
|                                                                      | S3Ni1,5Mo <sup>de</sup> | 0,07 to 0,15                                     | 0,05 to 0,25 | 1,20 to 1,80 | 0,020 | 0,020 | 0,20 | 1,20 to 1,80 | 0,30 to 0,50 | 0,30            | —    | 0,50                             |
| classification by yield strength and 77 J impact energy ISO 26304-C  | SUN3M2 <sup>c</sup>     | 0,10                                             | 0,20 to 0,60 | 1,25 to 1,80 | 0,010 | 0,015 | 0,30 | 1,40 to 2,10 | 0,25 to 0,55 | 0,25            | 0,05 | Ti: 0,10<br>Zr: 0,10<br>Al: 0,10 |
|                                                                      | SUN3M3 <sup>cd</sup>    | 0,15                                             | 0,25         | 0,80 to 1,40 | 0,020 | 0,020 | 0,20 | 1,20 to 1,80 | 0,40 to 0,65 | 0,40            | —    | —                                |
|                                                                      | SUN3M31 <sup>cd</sup>   | 0,15                                             | 0,25         | 1,30 to 1,90 | 0,020 | 0,020 | 0,20 | 1,20 to 1,80 | 0,40 to 0,65 | —               | —    | —                                |
|                                                                      | SUN4M1 <sup>cd</sup>    | 0,12 to 0,19                                     | 0,10 to 0,30 | 0,60 to 1,00 | —     | —     | 0,20 | 1,60 to 2,10 | 0,10 to 0,30 | 0,35            | —    | —                                |
|                                                                      | SUN4M3 <sup>c</sup>     | 0,15                                             | 0,25         | 1,30 to 1,90 | —     | —     | —    | 1,80 to 2,40 | 0,40 to 0,65 | 0,40            | —    | —                                |
| classification by yield strength and 100 J impact energy ISO 26304-D | SUN4M31 <sup>c</sup>    | 0,15                                             | 0,25         | 1,60 to 2,30 | —     | —     | —    | 1,80 to 2,40 | 0,40 to 0,65 | 0,40            | —    | —                                |
|                                                                      | SUN4M2 <sup>c</sup>     | 0,10                                             | 0,20 to 0,60 | 1,40 to 1,80 | 0,010 | 0,015 | 0,55 | 1,90 to 2,60 | 0,25 to 0,65 | 0,25            | 0,04 | Ti: 0,10<br>Zr: 0,10<br>Al: 0,10 |

Table 3 (continued)

| Symbol for chemical composition                                     |                                                                       | Chemical composition<br>% (by mass) <sup>a</sup> |              |              |       |       |              |              |              |                 |      |                                  |
|---------------------------------------------------------------------|-----------------------------------------------------------------------|--------------------------------------------------|--------------|--------------|-------|-------|--------------|--------------|--------------|-----------------|------|----------------------------------|
| classification by yield strength and 47 J impact energy ISO 26304-A | classification by tensile strength and 27 J impact energy ISO 26304-B | C                                                | Si           | Mn           | P     | S     | Cr           | Ni           | Mo           | Cu <sup>b</sup> | V    | Other                            |
| S2Ni2Mo <sup>e</sup>                                                |                                                                       | 0,05 to 0,09                                     | 0,15         | 1,10 to 1,40 | 0,015 | 0,015 | 0,15         | 2,00 to 2,50 | 0,45 to 0,60 | 0,30            | —    | 0,50                             |
| SUN5M3 <sup>c</sup>                                                 |                                                                       | 0,10                                             | 0,20 to 0,60 | 1,40 to 1,80 | 0,010 | 0,015 | 0,60         | 2,00 to 2,80 | 0,30 to 0,65 | 0,25            | 0,03 | Ti: 0,10<br>Zr: 0,10<br>Al: 0,10 |
| SUN5M4 <sup>c</sup>                                                 |                                                                       | 0,15                                             | 0,25         | 1,60 to 2,30 | —     | —     | 0,20         | 2,20 to 3,00 | 0,40 to 0,90 | —               | —    | —                                |
| (S2Ni3Mo)                                                           |                                                                       | 0,15                                             | 0,25         | 0,80 to 1,40 | —     | —     | —            | 2,40 to 3,70 | 0,15 to 0,40 | —               | —    | —                                |
| S2Ni3Mo <sup>e</sup>                                                |                                                                       | 0,08 to 0,12                                     | 0,10 to 0,25 | 0,80 to 1,20 | 0,020 | 0,020 | 0,15         | 2,80 to 3,20 | 0,10 to 0,25 | 0,30            | —    | 0,50                             |
| SUN6M11 <sup>c</sup>                                                |                                                                       | 0,15                                             | 0,25         | 1,30 to 1,90 | —     | —     | —            | 2,40 to 3,70 | 0,15 to 0,40 | —               | —    | —                                |
| SUN6M3 <sup>c</sup>                                                 |                                                                       | 0,15                                             | 0,25         | 0,80 to 1,40 | —     | —     | —            | 2,40 to 3,70 | 0,40 to 0,65 | —               | —    | —                                |
| SUN6M31 <sup>c</sup>                                                |                                                                       | 0,15                                             | 0,25         | 1,30 to 1,90 | —     | —     | —            | 2,40 to 3,70 | 0,40 to 0,65 | —               | —    | —                                |
| SUN1C1M1 <sup>c</sup>                                               |                                                                       | 0,16 to 0,23                                     | 0,15 to 0,35 | 0,60 to 0,90 | 0,025 | 0,030 | 0,40 to 0,60 | 0,40 to 0,80 | 0,15 to 0,30 | 0,35            | —    | —                                |
| (S3Ni1,5CrMo)                                                       |                                                                       | 0,15                                             | 0,40         | 1,30 to 2,30 | —     | —     | 0,05 to 0,70 | 0,40 to 1,75 | 0,30 to 0,80 | —               | —    | —                                |
| S3Ni1,5CrMo <sup>e</sup>                                            |                                                                       | 0,07 to 0,14                                     | 0,05 to 0,15 | 1,30 to 1,50 | 0,020 | 0,020 | 0,15 to 0,35 | 1,50 to 1,70 | 0,30 to 0,50 | 0,30            | —    | 0,50                             |
| SUN2C2M3 <sup>c</sup>                                               |                                                                       | 0,15                                             | 0,40         | 1,00 to 2,30 | —     | —     | —            | 0,40 to 1,75 | 0,30 to 0,90 | —               | —    | —                                |
| SUN4C2M3 <sup>c</sup>                                               |                                                                       | 0,15                                             | 0,40         | 1,20 to 1,90 | —     | —     | 0,50 to 1,20 | 1,50 to 2,25 | 0,30 to 0,80 | —               | —    | —                                |
| (S3Ni2,5CrMo)                                                       |                                                                       | 0,15                                             | 0,40         | 1,20 to 1,90 | 0,018 | 0,018 | 0,20 to 0,65 | 1,50 to 2,25 | 0,30 to 0,80 | 0,40            | —    | —                                |
| S3Ni2,5CrMo <sup>e</sup>                                            |                                                                       | 0,07 to 0,15                                     | 0,10 to 0,25 | 1,20 to 1,80 | 0,020 | 0,020 | 0,30 to 0,85 | 2,00 to 2,60 | 0,40 to 0,70 | 0,30            | —    | 0,50                             |
| S1Ni2,5CrMo <sup>e</sup>                                            |                                                                       | 0,07 to 0,15                                     | 0,10 to 0,25 | 0,45 to 0,75 | 0,020 | 0,020 | 0,50 to 0,85 | 2,10 to 2,60 | 0,40 to 0,70 | 0,30            | —    | 0,50                             |
| (S4Ni2CrMo)                                                         |                                                                       | 0,10                                             | 0,40         | 1,30 to 2,30 | —     | —     | 0,60 to 1,20 | 2,10 to 3,10 | 0,30 to 0,70 | —               | —    | —                                |
| S4Ni2CrMo <sup>e</sup>                                              |                                                                       | 0,08 to 0,11                                     | 0,30 to 0,40 | 1,80 to 2,00 | 0,015 | 0,015 | 0,85 to 1,00 | 2,10 to 2,60 | 0,55 to 0,70 | 0,30            | —    | 0,50                             |
| SUN5C3M3 <sup>c</sup>                                               |                                                                       | 0,10 to 0,17                                     | 0,20         | 1,70 to 2,20 | 0,010 | 0,015 | 0,25 to 0,50 | 2,30 to 2,80 | 0,45 to 0,65 | 0,50            | —    | —                                |

Table 3 (continued)

| Symbol for chemical composition                                     |                                                                       | Chemical composition<br>% (by mass) <sup>a</sup> |      |              |   |   |              |              |              |                 |   |       |
|---------------------------------------------------------------------|-----------------------------------------------------------------------|--------------------------------------------------|------|--------------|---|---|--------------|--------------|--------------|-----------------|---|-------|
| classification by yield strength and 47 J impact energy ISO 26304-A | classification by tensile strength and 27 J impact energy ISO 26304-B | C                                                | Si   | Mn           | P | S | Cr           | Ni           | Mo           | Cu <sup>b</sup> | V | Other |
|                                                                     | SUN7C3M3 <sup>c</sup>                                                 | 0,08 to 0,18                                     | 0,40 | 0,20 to 1,20 | — | — | 1,00 to 2,00 | 3,00 to 4,00 | 0,30 to 0,70 | 0,40            | — | —     |
|                                                                     | SUN10C1M3 <sup>c</sup>                                                | 0,08 to 0,18                                     | 0,40 | 0,20 to 1,20 | — | — | 0,30 to 0,70 | 4,50 to 5,50 | 0,30 to 0,70 | 0,40            | — | —     |
| SZ                                                                  |                                                                       | Any other agreed composition <sup>f</sup>        |      |              |   |   |              |              |              |                 |   |       |

<sup>a</sup> Single values are maxima.

<sup>b</sup> The copper limit includes any copper coating that may be applied to the electrode.

<sup>c</sup> The electrode shall be analysed for the specific elements for which values are shown. If the presence of other elements is indicated in the course of this work, the amount of those elements shall be determined to ensure that their total (excluding iron) does not exceed 0,50 % (by mass).

<sup>d</sup> This solid wire electrode composition, with a lower strength requirement, is also found in ISO 14171<sup>[1]</sup>.

<sup>e</sup> If not specified: Al, Sn, As and Sb ≤0,02 % (by mass) each and Ti, Pb and N ≤0,01 % (by mass) each.

<sup>f</sup> Consumables for which the chemical composition is not listed shall be symbolized similarly and prefixed by the letters "SZ" or "SUG", as appropriate. The chemical composition ranges are not specified and it is possible that two electrodes with the same classification are not interchangeable.



Table 4 — Chemical composition requirements for the all-weld metal from tubular cored electrode-flux combinations

| Symbol for chemical composition                                                  |                                                                                    | Chemical composition<br>% (by mass) <sup>a</sup> |              |              |       |       |      |              |              |      |              |                      |
|----------------------------------------------------------------------------------|------------------------------------------------------------------------------------|--------------------------------------------------|--------------|--------------|-------|-------|------|--------------|--------------|------|--------------|----------------------|
| classification by<br>yield strength and<br>47 J impact<br>energy<br>ISO 26304-A, | classification by<br>tensile strength<br>and 27 J impact<br>energy<br>ISO 26304-B, | C                                                | Si           | Mn           | P     | S     | Cr   | Ni           | Mo           | Cu   | V            | Other                |
|                                                                                  | TUN1M3 <sup>bc</sup>                                                               | 0,17                                             | 0,80         | 1,25 to 2,25 | 0,030 | 0,030 | —    | 0,40 to 0,80 | 0,40 to 0,65 | 0,35 | —            | —                    |
| T3NiMod <sup>d</sup>                                                             |                                                                                    | 0,05 to 0,12                                     | 0,20 to 0,60 | 1,30 to 1,90 | 0,02  | 0,02  | —    | 0,60 to 1,00 | 0,15 to 0,45 | —    | —            | —                    |
|                                                                                  | TUN2M3 <sup>b</sup>                                                                | 0,17                                             | 0,80         | 1,25 to 2,25 | 0,030 | 0,030 | —    | 0,70 to 1,10 | 0,40 to 0,65 | 0,35 | —            | —                    |
| (T3Ni1Mo)                                                                        | TUN2M2 <sup>b</sup>                                                                | 0,12                                             | 0,80         | 0,70 to 1,50 | 0,030 | 0,030 | 0,15 | 0,90 to 1,70 | 0,55         | 0,35 | —            | —                    |
|                                                                                  | (TUN2M2)                                                                           | 0,03 to 0,09                                     | 0,10 to 0,50 | 1,30 to 1,80 | 0,02  | 0,02  | —    | 1,00 to 1,50 | 0,45 to 0,65 | —    | —            | —                    |
|                                                                                  | TUN3M1 <sup>b</sup>                                                                | 0,10                                             | 0,80         | 0,60 to 1,60 | 0,030 | 0,030 | 0,15 | 1,25 to 2,00 | 0,35         | 0,30 | 0,03         | Ti + V +<br>Zr: 0,03 |
|                                                                                  | TUN3M2 <sup>b</sup>                                                                | 0,10                                             | 0,80         | 0,90 to 1,80 | 0,020 | 0,020 | 0,35 | 1,40 to 2,10 | 0,25 to 0,65 | 0,30 | —            | Ti + V +<br>Zr: 0,03 |
|                                                                                  | TUN3M21 <sup>b</sup>                                                               | 0,12                                             | 0,50         | 1,60 to 2,50 | 0,015 | 0,015 | 0,40 | 1,40 to 2,10 | 0,20 to 0,50 | 0,30 | 0,02         | Ti: 0,03<br>Zr: 0,02 |
|                                                                                  | TUN3M4 <sup>b</sup>                                                                | 0,12                                             | 0,50         | 1,60 to 2,50 | 0,015 | 0,015 | 0,40 | 1,40 to 2,10 | 0,70 to 1,00 | 0,30 | 0,02         | Ti: 0,03<br>Zr: 0,02 |
| T3Ni2MoV <sup>d</sup>                                                            |                                                                                    | 0,03 to 0,09                                     | 0,20         | 1,20 to 1,70 | 0,02  | 0,02  | —    | 1,60 to 2,00 | 0,20 to 0,50 | —    | 0,05 to 0,15 | —                    |
| T3Ni2Mod <sup>d</sup>                                                            |                                                                                    | 0,03 to 0,09                                     | 0,40 to 0,80 | 1,30 to 1,80 | 0,02  | 0,02  | —    | 1,80 to 2,40 | 0,20 to 0,40 | —    | —            | —                    |
|                                                                                  | TUN4M2 <sup>b</sup>                                                                | 0,10                                             | 0,80         | 0,90 to 1,80 | 0,020 | 0,020 | 0,65 | 1,80 to 2,60 | 0,20 to 0,70 | 0,30 | 0,03         | Ti + V +<br>Zr: 0,03 |
|                                                                                  | TUN5M3 <sup>b</sup>                                                                | 0,10                                             | 0,80         | 1,30 to 2,25 | 0,020 | 0,020 | 0,80 | 2,00 to 2,80 | 0,30 to 0,80 | 0,30 | 0,03         | Ti + V +<br>Zr: 0,03 |
| T3Ni3Mod <sup>d</sup>                                                            |                                                                                    | 0,03 to 0,09                                     | 0,20 to 0,70 | 1,60 to 2,10 | 0,02  | 0,02  | —    | 2,70 to 3,20 | 0,20 to 0,40 | —    | —            | —                    |
|                                                                                  | TUN1C1M1 <sup>b</sup>                                                              | 0,17                                             | 0,80         | 1,60         | 0,030 | 0,035 | 0,60 | 0,40 to 0,80 | 0,25         | 0,35 | 0,03         | Ti + V +<br>Zr: 0,03 |

Table 4 (continued)

| Symbol for chemical composition                                      |                                                                        | Chemical composition<br>% (by mass) <sup>a</sup> |              |              |       |       |              |              |              |      |   |       |
|----------------------------------------------------------------------|------------------------------------------------------------------------|--------------------------------------------------|--------------|--------------|-------|-------|--------------|--------------|--------------|------|---|-------|
| classification by yield strength and 47 J impact energy ISO 26304-A, | classification by tensile strength and 27 J impact energy ISO 26304-B, | C                                                | Si           | Mn           | P     | S     | Cr           | Ni           | Mo           | Cu   | V | Other |
|                                                                      | TUN4C1M3 <sup>b</sup>                                                  | 0,14                                             | 0,80         | 0,80 to 1,85 | 0,030 | 0,020 | 0,65         | 1,50 to 2,25 | 0,60         | 0,40 | — | —     |
| (T3Ni2.5CrMo)                                                        | TUN5CM3 <sup>b</sup>                                                   | 0,17                                             | 0,80         | 1,20 to 1,80 | 0,020 | 0,020 | 0,65         | 2,00 to 2,80 | 0,30 to 0,80 | 0,50 | — | —     |
| T3Ni2.5CrMod <sup>d</sup>                                            | (TUN5CM3)                                                              | 0,03 to 0,09                                     | 0,10 to 0,50 | 1,20 to 1,70 | 0,02  | 0,02  | 0,40 to 0,70 | 2,20 to 2,60 | 0,30 to 0,60 | —    | — | —     |
| T3Ni2.5Cr1Mod <sup>d</sup>                                           |                                                                        | 0,04 to 0,10                                     | 0,20 to 0,70 | 1,20 to 1,70 | 0,02  | 0,02  | 0,70 to 1,20 | 2,20 to 2,60 | 0,40 to 0,70 | —    | — | —     |
| TZ <sup>d</sup>                                                      |                                                                        | Any other agreed composition <sup>e</sup>        |              |              |       |       |              |              |              |      |   |       |

<sup>a</sup> Single values are maxima.

<sup>b</sup> The weld metal shall be analysed for the specific elements for which values are shown. If the presence of other elements is indicated in the course of this work, the amount of those elements shall be determined to ensure that their total (excluding iron) does not exceed 0,50 % (by mass).

<sup>c</sup> This composition symbol, for a tubular cored electrode, with a lower strength requirement, is also found in ISO 14171<sup>[1]</sup>.

<sup>d</sup> Al, Sn, As, Sb and Ti shall be less than 0,02 % (by mass) each, and Pb and N shall be less than 0,01 % (by mass) each; total of other elements shall be 0,30 % (by mass) maximum.

<sup>e</sup> Consumables for which the chemical composition is not listed shall be symbolized similarly and prefixed by the letters "TZ" or "TUG", as appropriate. The chemical composition ranges are not specified and it is possible that two electrodes with the same classification are not interchangeable.

## 4.6 Symbol for the post-weld heat treatment

### 4.6A Classification by yield strength and 47 J impact energy

The letter “P” placed after the symbol for composition indicates that strength, elongation, and impact properties in the classification of the all-weld metal fulfil the classification criteria after a post-weld heat treatment at 560 °C to 600 °C for 1 h. The test piece shall be left in the furnace for cooling down to 300 °C.

### 4.6B Classification by tensile strength and 27 J impact energy

The symbol for the as-welded condition or for the post-weld heat-treated condition is included with the symbol for tensile properties (see Table 1B). The post-weld heat treatment conditions are specified in Table 5B.

NOTE Post-weld heat treatment can alter the impact properties of the weld metal from those obtained in the as-welded condition.

**Table 5B — Post-weld heat treatment conditions**  
(Classification by tensile strength and 27 J impact energy)

| Symbol for solid wire electrode composition or tubular cored electrode deposit composition | Post-weld heat treatment temperature <sup>a</sup> °C |
|--------------------------------------------------------------------------------------------|------------------------------------------------------|
| SUN1M3, TUN1M3                                                                             | 620 ± 15                                             |
| SUN2M1                                                                                     | 620 ± 15                                             |
| SUN2M3, TUN2M3                                                                             | 620 ± 15                                             |
| SUN2M31                                                                                    | 620 ± 15                                             |
| SUN2M32                                                                                    | 620 ± 15                                             |
| SUN2M33                                                                                    | 620 ± 15                                             |
| SUN2M2, TUN2M2                                                                             | 620 ± 15                                             |
| TUN3M1                                                                                     | 605 ± 15 <sup>b</sup>                                |
| SUN3M2, TUN3M2                                                                             | 605 ± 15 <sup>b</sup>                                |
| TUN3M21                                                                                    | 605 ± 15 <sup>b</sup>                                |
| SUN3M3                                                                                     | 620 ± 15                                             |
| SUN3M31                                                                                    | 620 ± 15                                             |
| TUN3M4                                                                                     | 605 ± 15 <sup>b</sup>                                |
| SUN4M1                                                                                     | 620 ± 15                                             |
| SUN4M3                                                                                     | 620 ± 15                                             |
| SUN4M31                                                                                    | 620 ± 15                                             |
| SUN4M2, TUN4M2                                                                             | 605 ± 15 <sup>b</sup>                                |
| SUN5M3, TUN5M3                                                                             | 605 ± 15 <sup>b</sup>                                |
| SUN5M4                                                                                     | 605 ± 15                                             |
| SUN6M1                                                                                     | 605 ± 15                                             |
| SUN6M11                                                                                    | 605 ± 15                                             |
| SUN6M3                                                                                     | 605 ± 15                                             |
| SUN6M31                                                                                    | 605 ± 15                                             |
| SUN1C1M1, TUN1C1M1                                                                         | 565 ± 15 <sup>b</sup>                                |
| SUN2C1M3                                                                                   | 565 ± 15                                             |
| SUN2C2M3                                                                                   | 565 ± 15                                             |

Table 5B (continued)

| Symbol for solid wire electrode composition or tubular cored electrode deposit composition | Post-weld heat treatment temperature <sup>a</sup> , °C |
|--------------------------------------------------------------------------------------------|--------------------------------------------------------|
| SUN4C2M3                                                                                   | 565 ± 15                                               |
| SUN4C1M3, TUN4C1M3                                                                         | 565 ± 15 <sup>b</sup>                                  |
| SUN5CM3, TUN5CM3                                                                           | 565 ± 15 <sup>b</sup>                                  |
| SUN5C2M3                                                                                   | 565 ± 15                                               |
| SUN7C3M3                                                                                   | 565 ± 15                                               |
| SUN10C1M3                                                                                  | 565 ± 15                                               |
| SUG, TUG                                                                                   | — <sup>c</sup>                                         |

<sup>a</sup> Post-weld heat treatment time shall be  $1\text{h}_0^{+15\text{min}}$  at the specified temperature. The furnace shall be at a temperature not higher than 315 °C when the test assembly is placed in it. The heating rate from that temperature to the specified post-weld heat treatment temperature shall not exceed 220 °C/h. When the time at the post-weld heat treatment temperature is completed, the assembly shall be allowed to cool in the furnace to a temperature below 315 °C at a rate not exceeding 195 °C/h. The assembly may be removed from the furnace at any temperature below 315 °C and allowed to cool in still air to room temperature.

<sup>b</sup> This classification is normally used in the as-welded condition.

<sup>c</sup> As agreed by user and supplier.

#### 4.7 Symbol for hydrogen content of deposited metal

The symbols in Table 6 indicate the deposited metal hydrogen content determined in accordance with the method given in ISO 3690.

Table 6 — Symbol for hydrogen content of deposited metal

| Symbol | Hydrogen content<br>ml/100 g deposited metal, max. |
|--------|----------------------------------------------------|
| H5     | 5                                                  |
| H10    | 10                                                 |
| H15    | 15                                                 |

When a hydrogen symbol in accordance with Table 6 is included in the classification, the manufacturer shall state in their literature what restrictions need to be placed on the conditions of storage and redrying, and on current, arc voltage, electrode extension, and polarity to remain within the limit for that symbol.

## 5 Mechanical tests

### 5.1 Tensile and impact tests

#### 5.1A Classification by yield strength and 47 J impact energy

Tensile and impact tests shall be carried out on weld metal in the as-welded condition using an all-weld metal test assembly type 1.3 in accordance with ISO 15792-1:2000 using 4,0 mm or nearest commercially available diameter wire electrodes.

#### 5.1B Classification by tensile strength and 27 J impact energy

Tensile and impact tests shall be carried out on weld metal in the as-welded condition or in the post-weld heat-treated condition using an all-weld metal test assembly type 1.4 in accordance with ISO 15792-1:2000 using 4,0 mm or nearest commercially available diameter wire electrodes.

### 5.2 Preheating and interpass temperature

#### 5.2A Classification by yield strength and 47 J impact energy

Welding of the all-weld metal test piece shall be executed in a temperature range from 120 °C to 180 °C with the exception of the first layer in the test assembly, which may be welded without preheating.

#### 5.2B Classification by tensile strength and 27 J impact energy

Welding of the all-weld metal test piece shall be executed in a temperature range from 135 °C to 165 °C.

The interpass temperature shall be measured using temperature indicator crayons, surface thermometers or thermocouples (see ISO 13916).

### 5.3 Welding conditions and pass sequence

The test assembly weld shall be completed in two passes per layer, except that the top layer may be completed in three passes if necessary. Welding shall be performed by machine or automatic welding with straight progression (no weaving), in the flat position. Each pass shall be completed without interruption.

#### 5.3A Classification by yield strength and 47 J impact energy

The weld test assembly shall be produced using a 4,0 mm, 3,2 mm, 3,0 mm or 2,8 mm electrode, whichever is the largest size being produced. Welding conditions for solid wire electrodes shall be as given in Table 7A. The length of the weld deposit shall be 200 mm minimum. Welding conditions for tubular cored electrodes shall be in accordance with the manufacturer's recommendations except that the interpass temperature specified in 5.2A is required.

#### 5.3B Classification by tensile strength and 27 J impact energy

Classification is based on the properties of weld metal produced from 4,0 mm electrodes, or the closest size to 4,0 mm if 4,0 mm is not produced. Welding conditions for solid wire electrodes shall be as given in Table 7B. Welding conditions for tubular cored electrodes shall be in accordance with the manufacturer's recommendations.

**Table 7A — Welding conditions for solid wire electrodes** (classification by chemical composition)

| Electrode diameter                                                                                                                                                                                                                                                                                                                                         | Welding current <sup>a</sup> | Welding voltage <sup>b</sup> | Contact-tip-to-work distance | Travel speed |
|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------|------------------------------|------------------------------|--------------|
| mm                                                                                                                                                                                                                                                                                                                                                         | A<br>±20                     | V<br>±1                      | mm                           | mm/min       |
| No corresponding values                                                                                                                                                                                                                                                                                                                                    |                              |                              |                              |              |
| 2,8                                                                                                                                                                                                                                                                                                                                                        | 440                          | 27                           | 25 to 35                     | 350 to 450   |
| 3,0                                                                                                                                                                                                                                                                                                                                                        | 440                          | 27                           | 25 to 35                     | 350 to 450   |
| 3,2                                                                                                                                                                                                                                                                                                                                                        | 440                          | 27                           | 25 to 35                     | 350 to 450   |
| 4,0                                                                                                                                                                                                                                                                                                                                                        | 580                          | 29                           | 25 to 35                     | 500 to 600   |
| No corresponding values                                                                                                                                                                                                                                                                                                                                    |                              |                              |                              |              |
| <sup>a</sup> If a.c. and d.c. operation are claimed, test welding shall be carried out using a.c. only; a.c. means alternating current; d.c. means direct current. The stated current range applies to the average value, not to instantaneous values.<br><sup>b</sup> The stated voltage range applies to the average value, not to instantaneous values. |                              |                              |                              |              |

**Table 7B — Welding conditions for solid wire electrodes** (classification by tensile strength and chemical composition)

| Electrode diameter                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                   | Welding current <sup>a</sup> | Welding voltage <sup>b</sup> | Contact-tip-to-work distance <sup>c</sup> | Travel speed |
|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------|------------------------------|-------------------------------------------|--------------|
| mm                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                   | A<br>±50                     | V                            | mm                                        | mm/min       |
| 1,6                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | 300                          | 25 to 29                     | 13 to 19                                  | 280 to 320   |
| 2,0                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | 350                          | 25 to 29                     | 13 to 19                                  | 310 to 350   |
| 2,5 or 2,4                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                           | 400                          | 26 to 30                     | 19 to 32                                  | 340 to 380   |
| 2,8                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | 450                          | 26 to 30                     | 19 to 32                                  | 340 to 380   |
| 3,0                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | 450                          | 26 to 30                     | 25 to 38                                  | 360 to 400   |
| 3,2                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | 475                          | 26 to 30                     | 25 to 38                                  | 360 to 400   |
| 4,0                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | 525                          | 27 to 31                     | 25 to 38                                  | 380 to 420   |
| 4,8                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | 575                          | 27 to 31                     | 25 to 38                                  | 400 to 440   |
| 5,0                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | 600                          | 27 to 31                     | 25 to 38                                  | 400 to 440   |
| 5,6                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | 625                          | 27 to 31                     | 32 to 44                                  | 430 to 470   |
| 6,0                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | 675                          | 27 to 31                     | 32 to 44                                  | 460 to 500   |
| 6,4                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | 750                          | 28 to 32                     | 38 to 50                                  | 490 to 530   |
| <sup>a</sup> A lower current may be used for the first layer. The stated current range applies to the average value, not to instantaneous values.<br><sup>b</sup> A.c. or d.c., either polarity, may be used. The reference method shall be d.c. electrode positive. The stated voltage range applies to the average value, not to instantaneous values.<br><sup>c</sup> If the electrode manufacturer recommends a contact-tip-to-work distance outside the specified range, that recommendation shall be followed to within ±6 mm. |                              |                              |                                           |              |

## 6 Chemical analysis

Chemical analysis may be performed on any suitable test piece. In cases of dispute, specimens in accordance with ISO 6847 shall be used.

Any analytical technique can be used, but in cases of dispute, reference shall be made to established published methods

## 7 Rounding procedure

For purposes of determining compliance with the requirements of this International Standard, the actual test values obtained shall be subject to the rounding rules of ISO 80000-1:2009, B.3, Rule A. If the measured values are obtained by equipment calibrated in units other than those of this International Standard, the measured values shall be converted to the units of this International Standard before rounding. If an arithmetic average value is to be compared to the requirements of this International Standard, rounding shall be done only after calculating the arithmetic average. If the test method cited in Clause 2 contains instructions for rounding that conflict with the instructions of this International Standard, the rounding-requirements of the test method standard shall apply. The rounded results shall fulfil the requirements of the appropriate table for the classification under test.

## 8 Retests

If any test fails to meet the requirement, that test shall be repeated twice. The results of both retests shall meet the requirement. Specimens for the retest may be taken from the original test assembly or from a new test assembly. For chemical analysis, retests need be only for those specific elements that failed to meet their test requirement. If the results of one or both retests fail to meet the requirement, the material under test shall be considered as not meeting the requirements of this specification for that classification.

In the event that, during preparation or after completion of any test, it is clearly determined that prescribed or proper procedures were not followed in preparing the weld test assembly or test specimen(s), or in conducting the tests, the test shall be considered invalid, without regard to whether the test was actually completed, or whether the test results met or failed to meet the requirement. That test shall be repeated, following proper prescribed procedures. In this case, the requirement for doubling the number of test specimens does not apply.

## 9 Technical delivery conditions

Technical delivery conditions shall meet the requirements of ISO 544 and ISO 14344.

## 10 Examples of designation

The designation of the solid wire electrode, the solid wire electrode-flux combination, and the tubular cored electrode-flux combination, shall follow the principles given in the examples below.

### 10A Classification by yield strength and 47 J impact energy

EXAMPLE 1A:

A solid wire electrode-flux combination for submerged arc welding (S) deposits weld metal with a minimum yield strength of 620 MPa (62) and a minimum average impact energy of 47 J at  $-40\text{ }^{\circ}\text{C}$  (4) produced with an aluminate-basic flux (AB) and a wire S2Ni2Mo. Hydrogen is determined in accordance with ISO 3690 and does not exceed 5 ml/100 g deposited metal (H5). The solid wire electrode-flux combination is designated:

**ISO 26304-A - S 62 4 AB S2Ni2Mo H5**

where

- ISO 26304-A is the number of this International Standard, with classification by yield strength and 47 J impact energy;
- S indicates submerged arc welding (see 4.1);
- 62 indicates the tensile properties (see Table 1A);
- 4 indicates the impact properties (see Table 2);
- AB is the type of welding flux (see 4.4);

### 10B Classification by tensile strength and 27 J impact energy

EXAMPLE 1B:

A solid wire electrode-flux combination for submerged arc welding (SU) deposits weld metal with a tensile strength of 690 MPa to 830 MPa in the as-welded condition (69A) and a minimum average impact energy of 27 J at  $-40\text{ }^{\circ}\text{C}$  (4) produced with an aluminate-basic flux (AB) and a solid wire electrode SUN2M2. Hydrogen is determined in accordance with ISO 3690 and does not exceed 5 ml/100 g deposited metal (H5). The solid wire electrode-flux combination is designated:

**ISO 26304-B - SU 69A 4 AB SUN2M2 H5**

where

- ISO 26304-B is the number of this International Standard, with classification by tensile strength and 27 J impact energy;
- SU indicates submerged arc welding (see 4.1);
- 69A indicates the tensile properties in the as-welded condition (see Table 1B);
- 4 indicates the impact properties (see Table 2);

- S2Ni2Mo is the chemical composition of the solid wire electrode (see Table 3);
- H5 indicates the maximum diffusible hydrogen content (see Table 6).

EXAMPLE 2A:

A solid wire electrode-flux combination for submerged arc welding (S) deposits weld metal with a minimum yield strength in the post-weld heat-treated condition of 550 MPa (55) and a minimum average impact energy of 47 J at -40 °C (4) produced with an aluminate-basic flux (AB) and a wire S2Ni2Mo, with mechanical tests performed after post-weld heat treatment (P). Hydrogen is not specified. The solid wire electrode-flux combination is designated:

**ISO 26304-A - S 55 4 AB S2Ni2Mo P**

EXAMPLE 3A:

A solid wire electrode complying with the chemical requirement of S2Ni2Mo in Table 4 is designated:

**ISO 26304-A - S2Ni2Mo**

EXAMPLE 4A:

A tubular cored electrode-flux combination for submerged arc welding (S) deposits weld metal with a minimum yield strength of 620 MPa (62) and a minimum average impact energy of 47 J at -40 °C (4) produced with an aluminate-basic flux (AB) and the all-weld metal chemical composition T3Ni2Mo. Hydrogen is determined in accordance with ISO 3690 and does not exceed 5 ml/100 g deposited metal (H5). The tubular cored electrode-flux combination is designated:

**ISO 26304-A - S 62 4 AB T3Ni2Mo H5**

where

- ISO 26304-A is the number of this International Standard, with classification by yield strength and 47 J impact energy;
- S indicates submerged arc welding (see 4.1);
- 62 indicates the tensile properties (see Table 1A);
- 4 indicates the impact properties (see Table 2);
- AB is the type of welding flux (see 4.4);
- T3Ni2Mo is the chemical composition of the all-weld metal deposited with the tubular cored electrode-flux combination (see Table 4);
- H5 indicates the maximum diffusible hydrogen content (see Table 6).

- AB is the type of welding flux (see 4.4);
- SUN2M2 indicates a solid wire electrode of chemical composition N2M2 (see Table 3) for submerged arc welding;
- H5 indicates the maximum diffusible hydrogen content (see Table 6).

EXAMPLE 2B:

A solid wire electrode-flux combination for submerged arc welding (SU) deposits weld metal with a tensile strength in the post-weld heat-treated condition of 620 MPa to 760 MPa (62P) and a minimum average impact energy of 27 J at -40 °C (4) produced with an aluminate-basic flux (AB) and a solid wire electrode SUN2M2. Hydrogen is not specified. The solid wire electrode-flux combination is designated:

**ISO 26304-B - SU 62P4 AB SUN2M2**

EXAMPLE 3B:

A solid wire electrode complying with the chemical requirement of N2M2 in Table 4 is designated:

**ISO 26304-B - SUN2M2**

EXAMPLE 4B:

A tubular cored electrode-flux combination for submerged arc welding (SU) deposits weld metal with a tensile strength of 690 MPa to 830 MPa in the as-welded condition (69A) and a minimum average impact energy of 27 J at -40 °C (4) produced with an aluminate-basic flux (AB) and the all-weld metal chemical composition N3M2. Hydrogen is determined in accordance with ISO 3690 and does not exceed 5 ml/100 g deposited metal (H5). The solid wire electrode-flux combination is designated:

**ISO 26304-B - SU 69A4 AB TUN3M2 H5**

where

- ISO 26304-B is the number of this International Standard, with classification by tensile strength and 27 J impact energy;
- S indicates submerged arc welding (see 4.1);
- 69A indicates the tensile properties in the as-welded condition (see Table 1B);
- 4 indicates the impact properties (see Table 2);
- AB is the type of welding flux (see 4.4);
- TUN3M2 indicates the chemical composition of the all-weld metal deposited with the tubular cored electrode-flux combination (see Table 4);
- H5 indicates the maximum diffusible hydrogen content (see Table 6).



## **Annex A** (informative)

### **Possible risk of weld metal hydrogen cracking**

The user should note that, in modern high-strength steels, the risk of hydrogen cracking tends to be greater in the weld metal than in the parent steel heat-affected zone (HAZ). Procedures developed to minimize the risk of hydrogen cracking in the HAZ may not be sufficient to avoid cracking in the weld metal. In particular, steels with yield strengths of about 700 MPa and above are particularly at risk and require special safe welding procedures to be developed and qualified. Research work has shown that weld metal hydrogen contents significantly less than 5 ml/100 g of weld metal may be required to help ensure crack-free deposits.

Manufacturers and suppliers of submerged arc welding consumables designed for these steels should be consulted to establish the necessary working practices for storage, handling, and use of consumables to produce the lowest possible weld metal hydrogen contents. It should be noted that welding conditions outside the manufacturer's recommended ranges may produce significantly higher diffusible hydrogen levels than the symbol indicates.

There are other approaches to lessening the likelihood of hydrogen cracking, such as increasing interpass temperature, increasing the time between weld runs, and post-weld soaking to remove hydrogen before cooling from the interpass temperature. As the weld metal strength increases, the need for these other approaches increases. Also, it needs to be appreciated that zero hydrogen is unobtainable.

Since there is a real risk of cracking in weld metals, users are strongly recommended to review suitable non-destructive crack detection methods and carry out "fitness for purpose" assessments using a fracture mechanics methodology. This is particularly important for thicker walled, safety critical structures.

## Bibliography

- [1] ISO 14171, *Welding consumables — Solid wire electrodes, tubular cored electrodes and electrode/flux combinations for submerged arc welding of non alloy and fine grain steels — Classification*
- [2] EN 14295, *Welding consumables — Wire and tubular cored electrodes and electrode-flux combinations for submerged arc welding of high strength steels — Classification*<sup>1)</sup>

---

1) Superseded by this International Standard.







# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™