

Non-destructive testing — Ultrasonic examination

Part 3. Transmission technique

The European Standard EN 583-3 : 1997 has the status of a
British Standard

ICS 19.100

National foreword

This British Standard is the English language version of EN 583-3 : 1997. There has previously been no direct British Standard equivalent to this standard.

The UK participation in its preparation was entrusted to Technical Committee WEE/46, Non-destructive testing, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled 'International Standards Correspondence Index', or by using the 'Find' facility of the BSI Standards Electronic Catalogue.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 8, an inside back cover and a back cover.

Amendments issued since publication

Amd. No.	Date	Text affected

This British Standard, having been prepared under the direction of the Engineering Sector Board, was published under the authority of the Standards Board and comes into effect on 15 September 1997

© BSI 1997

ISBN 0 580 28308 9

ICS 19.100

Descriptors: Non-destructive tests, ultrasonic frequencies, ultrasonic tests, transmission, generalities, inspection methods, measurements, comparison analysis

English version

Non-destructive testing — Ultrasonic examination — Part 3: Transmission technique

Essais non destructifs — Contrôle ultrasonore —
Partie 3: Technique par transmission

Zerstörungsfreie Prüfung — Ultraschallprüfung —
Teil 3: Durchschallungstechnik

This European Standard was approved by CEN on 1997-04-10. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 138 Non-destructive testing, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1997, and conflicting national standards shall be withdrawn at the latest by November 1997.

This standard consists of the following Parts:

- | | |
|-----------|--|
| EN 583-1 | <i>Non-destructive testing — Ultrasonic examination — Part 1: General principles</i> |
| EN 583-2 | <i>Non-destructive testing — Ultrasonic examination — Part 2: Sensitivity and range setting</i> |
| EN 583-3 | <i>Non-destructive testing — Ultrasonic examination — Part 3: Transmission technique</i> |
| EN 583-4 | <i>Non-destructive testing — Ultrasonic examination — Part 4: Examination for imperfections perpendicular to the surface</i> |
| EN 583-5 | <i>Non-destructive testing — Ultrasonic examination — Part 5: Characterization and sizing of imperfections</i> |
| ENV 583-6 | <i>Non-destructive testing — Ultrasonic examination — Part 6: Time-of-flight diffraction technique as a method for detection and sizing of imperfections</i> |

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Contents

	Page
Foreword	2
1 Scope	3
2 Normative references	3
3 Definitions	3
4 Principles of the examination	3
4.1 Basic techniques and set-up	3
4.2 Capability of detection of imperfections	3
4.3 Requirements for geometry and access	5
4.4 Effects of variation in coupling, angulation and alignment of probe	5
5 Examination technique	5
5.1 General	5
5.2 Sensitivity setting	5
5.3 Scanning	5
5.4 Evaluation of imperfections	5
5.5 Determination of attenuation coefficient	5

1 Scope

This part of the standard specifies the principles of transmission techniques.

Transmission techniques can be used for:

- detection of imperfections;
- determination of attenuation.

The general principles required for the use of ultrasonic examination of industrial products are described in part 1 of this standard.

The transmission technique is used for examination of flat products, e.g. plates and sheets.

Further, it is used for examinations, e.g:

- where the shape, dimensions or orientation of possible imperfections are unfavourable for direct reflection;
- in materials with high attenuation;
- in thin products.

2 Normative references

This European Standard incorporates, by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

- EN 583-1 *Non-destructive testing — Ultrasonic examination — Part 1: General principles*
- EN 1330-4 *Non-destructive testing — Terminology — Part 4: Terms used in ultrasonic testing*

3 Definitions

For the purposes of this standard the definitions in EN 1330-4 apply.

4 Principles of the examination

4.1 Basic techniques and set-up

In its simplest application two probes, one emitting and the second receiving, are placed so that the receiving probe receives the sound transmitted through the object. This can be achieved with straight beam probes or angle beam probes. See figures 5 to 8.

Alternatively, the examination can be carried out using a single probe where the sound is reflected on a surface of an object on the opposite side of the examination object or on the opposite surface of the examination object (back wall). See figures 1 to 4. See also table 1.

Table 1. Techniques and typical set-ups used in transmission technique

wave mode	continuous waves	pulsed waves
wave type	longitudinal or transverse	longitudinal or transverse
number of transducers	2	1 or 2
angle of incidence	normal	normal or oblique
evaluation of	amplitude of transmitted sound	amplitude or time of flight of transmitted pulse or echo

The decrease in amplitude of the transmitted signal can be used to indicate the presence of a discontinuity located in the sound path, or to indicate material attenuation. In addition, the position of the transmitted signal along the timebase of the instrument can be used to indicate material thickness.

Examination can be carried out with either continuous or pulsed ultrasonic waves, except when the technique is used for thickness measurement where only pulsed ultrasonic waves apply.









Straight beam or angle beam probes can be used depending on the scope of the examination.

A probe can be coupled to the product by means of a couplant, a squirter, by immersing the product, or by applying a wheel probe.

4.2 Capability of detection of imperfections

When used for the detection of imperfections, any imperfection (or group of imperfections) shall intercept a significant proportion (i.e. 25 % to 50 %) of the cross-sectional area of the ultrasonic beam before an unambiguous change in signal amplitude is observed. This technique can only be used for detecting imperfections or groups of imperfections which are relatively large compared to the ultrasonic beam area, e.g. laminations in plate material.

Within the limitations mentioned above, the technique provides positive proof of the absence of an imperfection at any position along the sound path. However, it does not indicate the position in depth of a detected imperfection.

Table 2. Possible configurations for transmission techniques		
	One probe	Two probes
Straight beam contact	 <p>Figure 1</p>	 <p>Figure 5</p>
Angle beam contact	 <p>Figure 2</p>	 <p>Figure 6</p>
Total immersion	 <p>Figure 3</p>	 <p>Figure 7</p>
Local immersion (squirter)	 <p>Figure 4</p>	 <p>Figure 8</p>

4.3 Requirements for geometry and access

The technique requires that the geometry of the object under examination and access to its surfaces allow the transmitting and receiving probes to be so positioned that their beam axes are coincident, either with or without intermediate reflection from a surface of the object.

4.4 Effects of variations in coupling, angulation and alignment of probe

The technique is particularly sensitive to variations in probe coupling and misangulation due to surface irregularities, since these factors also cause a marked reduction in transmitted signal amplitude. To improve the uniformity of coupling immersion or squirter scanning is most frequently used. Dressing of the surface to improve coupling uniformity can be necessary, especially for contact scanning.

When using separate transmitting and receiving probes and/or a reflecting object on the opposite side of the object to be examined their positions in relation to each other are also critical, and wherever possible they should be maintained in alignment by permanent orientation.

5 Examination technique

5.1 General

The technique described under this clause refers to the detection of imperfections, and where applicable their size determination, and to the measurement of sound attenuation in the material.

5.2 Sensitivity setting

The test sensitivity shall be set on either a reference block of the same relevant dimensions, surface finish and similar ultrasonic properties as the object to be examined or on an area of the latter known to be free from imperfections and of known or previously determined attenuation in accordance with 5.5. The probes shall be maintained in alignment in ultrasonic contact with the block or object and the gain adjusted to set the transmitted signal to a specified level. For manual examination a level of 80 % full screen height is recommended.

5.3 Scanning

Scanning shall be carried out in accordance with the requirements of the applicable test procedure, at all times keeping the probes in correct alignment to each other and to the object under examination.

5.4 Evaluation of imperfections

The evaluation of imperfections shall be done in accordance with the relevant standard¹⁾. For imperfections whose transmitted signal amplitude during scanning is reduced to below the evaluation level, the evaluation criteria and requirements can be summarized as follows:

- a) confirm that the reduction in signal amplitude is not due to loss of coupling or to a normal geometrical feature of the object;
- b) measure the maximum reduction in transmitted signal amplitude. When the zone causing the signal reduction to fall below the evaluation level is smaller than the beam width, it is possible to relate the reduction in amplitude to the area of an imperfection, perpendicular to the ultrasonic beam, placed at a given depth;
- c) determine as accurately as possible the volume of the object through which the ultrasonic beam is being attenuated;
- d) determine if an imperfection is continuous or intermittent;
- e) if either a complete or a partial loss of the transmitted signal amplitude is observed, due to a single large imperfection, the extent of the imperfection may be plotted by noting those positions of the sound beam at which the transmitted signal amplitude has fallen by a given value (most frequently 6 dB) below its value in a zone of the object free of imperfections.

5.5 Determination of attenuation coefficient

5.5.1 General

The energy loss, usually called attenuation, is normally expressed as an attenuation coefficient determined in dB/m of sound path in the examination object.

The value depends on the type of wave, i.e. longitudinal, transverse and on the ultrasonic frequency etc.

Two techniques for determining the attenuation coefficient are described in 5.5.2 and 5.5.3.

5.5.2 Comparative technique using a reference block

This technique is based on determining the difference in amplitude between 2 echoes. The first echo is that transmitted through a sample of material whose attenuation coefficient, α_1 , is to be determined. The second echo is that transmitted through a sample whose attenuation coefficient, α_2 , is known.

It is important to use the same determination conditions: ultrasonic probes, equipment and settings for each amplitude determination and coupling medium, and the samples shall be of the same thickness and surface finish.

The technique can employ either one probe acting as both transmitter and receiver, or two separate transmitting and receiving probes positioned on opposite faces of the sample. Either the first transmitted echo, or any subsequent multiple echo may be used.

¹⁾ Prior to the publication of the EN Standard related to this subject the corresponding national standards can be used.

The attenuation coefficient (α_1) in the material to be determined is given by:

$$\alpha_1 = \alpha_2 + \frac{20 \log \left(\frac{A_1}{A_2} \right)}{B} \text{ dB/m} \quad (1)$$

or equivalent

$$\alpha_1 = \alpha_2 + \left(\frac{V_2 - V_1}{B} \right) \text{ dB/m} \quad (2)$$

where:

- α_1 is the attenuation coefficient of the object to be determined;
- α_2 is the known attenuation coefficient of the reference sample;
- B is the total sound path length in the examination object (m);
- A_1 is the signal amplitude in the object to be determined;
- A_2 is the signal amplitude in the reference sample with known attenuation coefficient;
- V_1 is the amplification in decibel for signal amplitude A_1 ;
- V_2 is the amplification in decibel for signal amplitude A_2 .

5.5.3 Direct immersion technique

This technique is based on comparing the amplitude of one echo (A_m) of a series of multiple echoes, from within a sample of material to be determined, with the amplitude of a subsequent echo (A_n) within the same series. See figure 9.

The technique can employ any of the probe configurations described under 5.5.2, but the following additional requirements apply:

- a) the sound path of the echoes used for the measurement shall be longer than three near field lengths. Equations (3) and (4) apply for non-focusing probes;
- b) allowance should be made for the loss each time the pulse is reflected at a material water interface.

The attenuation coefficient (α) is given by:

$$\alpha = \frac{20 \log \left(\frac{A_m}{A_n} \right) + 20 \log \left(\frac{B_m}{B_n} \right) + 40(n - m) \log(R)}{2(n - m)d} \text{ dB/m} \quad (3)$$

or equivalent

$$\alpha = \frac{(V_n - V_m) + 20 \log \left(\frac{B_m}{B_n} \right) + 40(n - m) \log(R)}{2(n - m)d} \text{ dB/m} \quad (4)$$

where:

- α is the attenuation coefficient in the test object;
- B_m = $2[g + md(c_s/c_w)]$ is the equivalent water path of the m th echo;
- B_n = $2[g + nd(c_s/c_w)]$ is the equivalent water path of the n th echo;
- c_s is the longitudinal sound velocity in the test object (m/s);
- c_w is the sound velocity in water (1480 m/s);
- d is the thickness of the test object (m);
- g is the water delay between probe and test object (m);
- m, n are the number of evaluated echoes ($n > m$);
- A_m is the amplitude of m th echo;
- A_n is the amplitude of n th echo;
- $R = \frac{|Z_s - Z_w|}{Z_s + Z_w}$ is the modulus of reflection coefficient water/sample respectively sample/water;
- V_m is the amplification in decibel for the amplitude A_m of the m th echo (dB);
- V_n is the amplification in decibel for the amplitude A_n of the n th echo (dB);
- Z_s is the acoustical impedance of the test object (Pa·s/m);
- Z_w is the acoustical impedance of water ($1,480 \times 10^6$ Pa·s/m).




Figure 1. Measurement of attenuation by direction techniques

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.