

**Paper and board
intended to come
into contact with
foodstuffs —
Determination of
colour fastness of dyed
paper and board**

The European Standard EN 646:2006 has the status of a
British Standard

ICS 67.250; 85.060

National foreword

This British Standard is the official English language version of EN 646:2006. It supersedes BS EN 646:2001 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PAI/11, Methods of test for paper, board and pulps, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 8, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2006

© BSI 2006

ISBN 0 580 48809 8

Amendments issued since publication

Amd. No.	Date	Comments

English Version

Paper and board intended to come into contact with foodstuffs -
Determination of colour fastness of dyed paper and board

Papiers et cartons destinés à entrer en contact avec les
denrées alimentaires - Détermination de la solidité de la
couleur des papiers et cartons colorés

Papier und Pappe vorgesehen für den Kontakt mit
Lebensmitteln - Bestimmung der Farbechtheit von
gefärbtem Papier und Pappe

This European Standard was approved by CEN on 28 March 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents		Page
Foreword		3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4
4	Principle.....	4
5	Materials and equipment	4
6	Reagents.....	5
7	Sampling.....	5
8	Preparation of sample	6
9	Procedure A (long duration contact).....	6
10	Procedure B (short time contact).....	6
11	Evaluation.....	6
12	Report	7
Bibliography.....		8

Foreword

This document (EN 646:2006) has been prepared by Technical Committee CEN/TC 172 "Pulp, paper and board", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2006, and conflicting national standards shall be withdrawn at the latest by October 2006.

This document supersedes EN 646:2000.

With regard to EN 646:2000 the following changes have been made:

- a) the test fluid "sodium carbonate solution" has been omitted and the test fluid "saliva simulant" has been introduced to cover a demand;
- b) editorial changes.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This document describes procedures for the testing of dyed paper and board intended to come into contact with foodstuffs. Two procedures are given. Procedure A for contact of long duration (e. g. food packaging) and procedure B for contact of short duration (e. g. napkins, kitchen papers, household papers).

Visual evaluation against a blank is used only in order to detect any bleeding (yes/no) while evaluation against a grey scale provides grading of the bleeding.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 8787, *Paper and board — Determination of capillary rise — Klemm method*

3 Terms and definitions

For the purposes of this document, the following term and definition applies.

colour fastness

lack of transfer of colour from a paper to a non stained glass-fibre paper, saturated with a test fluid and evaluated visually for staining against a grey scale or a blank

4 Principle

A sample is brought into contact with glass fibre papers which have been saturated with a test fluid and placed under load for a given time. The staining of the glass fibre paper is evaluated with the grey scale. The staining of the glass fibre paper is evaluated against a blank or grey scale. The test fluids used are distilled or deionised water, dilute acetic acid, saliva simulant and olive oil depending on the type of contact expected.

5 Materials and equipment

5.1 Unstained glass fibre papers of 60 mm × 90 mm. The glass fibre papers shall meet the following conditions:

- a) grammage 70 g/m²;
- b) capillary rise of 190 mm to 210 mm in 10 min in accordance with ISO 8787;
- c) free from fluorescent whitened and wet strength agents;
- d) free from cellulosic fibres.

5.2 Glass plates, 60 mm × 90 mm.

5.3 Polyethylene film, uncoloured and transparent.

5.4 Mass, 1 kg.

5.5 Grey scale in accordance with EN 20105 A03. This is only needed when grading is required.

6 Reagents

6.1 Distilled or deionised water

6.2 Aqueous acetic acid 3,0 % (m/v)

6.3 Saliva simulant 5 g/l

6.3.1 Composition of the simulated saliva with a pH of 6.8 ± 0.1

Reagents	Mass fraction g/l
Magnesium chloride ($\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$)	0.17
Calcium chloride ($\text{CaCl}_2 \cdot 2\text{H}_2\text{O}$)	0.15
Dipotassium hydrogen phosphate ($\text{K}_2\text{HPO}_4 \cdot 2\text{H}_2\text{O}$)	0.76
Potassium carbonate (K_2CO_3)	0.53
Sodium chloride (NaCl)	0.33
Potassium chloride (KCl)	0.75
Hydrochloric acid (1%, mass fraction)	Added until pH value equals 6.8 ± 0.1

6.3.2 Production of simulated saliva

Dissolve the potassium and sodium salts in approx. 900 ml water. Then add the calcium chloride and magnesium chloride and stir until all added reagents have dissolved completely. Calibrate the pH meter with a buffer solution as stipulated by the manufacturer. Then immerse the pH electrode into the solution, stir briefly and add hydrochloric acid until a constant pH of 6.8 ± 0.1 has been obtained. Transfer the solution to a 1000 ml volumetric flask and fill to the mark with water. Store protected from light and make sure that the pH of the simulated saliva is in the 6.8 ± 0.1 range prior to use.

NOTE If the simulated saliva is to be kept longer than 2 weeks, it is advisable to use water that has been boiled for 10 minutes.

6.4 Iso-octane (2,2,4-trimethylpentan)

6.5 Rectified olive oil, characterized as follows:

— iodine value (Wijs)	80 to 88
— refractive index at 25 °C	1,4665 to 1,4679
— acidity (expressed as % oleic acid)	max. 0,5 %
— peroxide number (expressed as oxygen milli-equivalents per kg oil)	max. 10

7 Sampling

If a lot is tested then sampling is carried out in accordance with EN ISO 186.

8 Preparation of sample

Cut or punch several test pieces of 50 mm × 20 mm from the sample under investigation. Smooth edges shall be obtained.

9 Procedure A (long duration contact)

9.1 Immerse two sheets of unstained glass fibre paper (5.1) in a test fluid (6.1, 6.2, 6.3, 6.4 or 6.5). Remove the sheets after saturation and free the sheets from excess fluid by wiping on the rim of the container.

9.2 Place one sheet of unstained glass fibre paper with its smooth side upwards on the glass plate (5.2). Place the test piece (Clause 8) immediately on the unstained glass fibre paper. Cover it with the second saturated sheet of unstained glass fibre paper, so that the smooth side of the unstained glass fibre paper is in contact with the test piece again. Place a second glass plate (5.2) on top of the second unstained glass fibre paper and wrap the total assembly in polyethylene film (5.3) to prevent the edges from drying out, load it with a mass of 1 kg (5.4) and allow it to stand for 24 h at $(23 \pm 2) ^\circ\text{C}$ with protection against direct light penetration.

9.3 If test pieces of a grammage of $> 140 \text{ g/m}^2$ are to be investigated, an appropriate even number of unstained glass fibre paper layers (5.1) is used so that the total of their grammages just exceeds the grammage of the test piece.

Construct the assembly as described in 9.2, with each unstained glass fibre paper being individually saturated and wiped, and arranged in such a way that the same number of unstained glass fibre papers are in contact with both sides of the test piece.

9.4 After 24 h open the assembly. Place the unstained glass fibre papers on 3 adjacent glass rods, $\varnothing 8 \text{ mm}$ to $\varnothing 10 \text{ mm}$, with the side which was in contact with the test piece upwards, cover them without contact to prevent light penetration and air-dry at ambient temperature. Unstained glass fibre papers saturated with olive oil are not dried.

10 Procedure B (short time contact)

10.1 Immerse two sheets of unstained glass fibre paper (5.1) in a test fluid (6.1, 6.2, 6.3, 6.4 or 6.5). Remove the sheets after saturation and free the sheets from excess fluid by wiping on the rim of the container.

10.2 Place one sheet of unstained glass fibre paper with its smooth side upwards on the glass plate (5.2). Place the test piece (Clause 8) immediately on the unstained glass fibre paper. Cover it with the second saturated sheet of unstained glass fibre paper, so that the smooth side of the unstained glass fibre paper is in contact with the test piece again. Place a second glass plate (5.2) on top of the second unstained glass fibre paper and wrap the total assembly in polyethylene film (5.3) to prevent the edges from drying out, load it with a mass of 1 kg (5.4) and allow it to stand for 10 min at $(23 \pm 2) ^\circ\text{C}$ with protection against direct light penetration.

10.3 After 10 min open the assembly. Place the unstained glass fibre papers on three adjacent glass rods, $\varnothing 8 \text{ mm}$ to $\varnothing 10 \text{ mm}$, with the side which was in contact with the test piece upwards, cover them without contact to prevent light penetration and air-dry at ambient temperature. Unstained glass fibre papers saturated with olive oil are not dried.

11 Evaluation

Evaluate the staining of the glass fibre papers on the side with which they were in contact with the sample, using a blank or the grey scale (5.5). If grading is required use the grey scale in accordance with EN 20103 A03. When several layers of unstained glass fibre papers are used, evaluate only the layer that was in contact with the test piece. If the two sides of the sample produce different results, the test report shall state to which side of the sample the data relates.

If the evaluation is done against a blank in order to detect any bleeding, the result is given as "yes" or "no". If a grading is provided a distinction is drawn between five different evaluation grades: Grade one signifies poor fastness; grade five signifies good fastness. The grade of the grey scale which is the most similar to the stained glass fibre paper is given as the evaluation grade of the tested paper.

NOTE 1 In the case that paper or board is coming into contact with foodstuffs only with one side (e. g. food packaging) and it is known which side is facing the food, only this side will be evaluated.

NOTE 2 As iso-octane is more severe than olive oil it is possible to show compliance using olive oil, if the test fails with iso-octane.

12 Report

The test report shall include the following information:

- a) Reference to this European Standard;
- b) test result;
- c) designation of the paper or board and identification of the sample tested; side tested if applicable;
- d) procedure A or B; evaluation yes/no or grading;
- e) test fluids and associated evaluation notes;
- f) date of test;
- g) any deviation from this European Standard.

Bibliography

- [1] EN ISO 186, *Paper and board - Sampling to determine average quality (ISO 186:2002)*
- [2] EN 20105 A03, *Textiles — Test for colour fastness — Part A03: Grey scale for assessing staining (ISO 105-A03:1993)*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.