



BSI Standards Publication

**Resilient floor coverings
— Polyvinyl chloride floor
coverings on jute backing
or on polyester felt backing
or on a polyester felt with
a polyvinyl chloride backing
— Specification**

National foreword

This British Standard is the UK implementation of EN 650:2012. It supersedes BS EN 650:1997, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/3/60, Textile & Resilient Floor Coverings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012.
Published by BSI Standards Limited 2012.

ISBN 978 0 580 71692 8

ICS 97.150

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2012.

Amendments issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN 650

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2012

ICS 97.150

Supersedes EN 650:1996

English Version

Resilient floor coverings - Polyvinyl chloride floor coverings on jute backing or on polyester felt backing or on a polyester felt with a polyvinyl chloride backing - Specification

Revêtements de sol résilients - Revêtements de sol à base de polychlorure de vinyle sur support de jute ou de polyester avec envers en polychlorure de vinyle - Spécifications

Elastische Bodenbeläge - Bodenbeläge aus Polyvinylchlorid mit einem Rücken aus Jute oder Polyestervlies oder auf Polyestervlies mit einem Rücken aus Polyvinylchlorid - Spezifikation

This European Standard was approved by CEN on 10 August 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	5
4 Requirements and testing.....	5
4.1 General requirements.....	5
4.2 Classification requirements.....	5
4.2.1 Wear group classification	5
4.2.2 Homogeneous products and wear layers	5
4.2.3 Level of use classification	5
5 Marking	11
Annex A (informative) Optional properties	12
Bibliography	13

Foreword

This document (EN 650:2012) has been prepared by Technical Committee CEN/TC 134 "Resilient, textile and laminate floor coverings", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2013, and conflicting national standards shall be withdrawn at the latest by March 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 650:1996.

The following technical changes were introduced in this version:

- Wear group classification is based on one method (EN 660-2) instead of two (EN 660-1 and -2)
- A requirement on "wear layers" has been added
- A new table 3 was included. The original table 3 is now table 4.
- Annexes A and B were merged and new characteristics added (staining, cigarette resistance, curling when wet)

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies the characteristics of floor coverings based on polyvinyl chloride and modifications thereof, on jute or polyester backing or on polyester felt with polyvinyl chloride backing, supplied in either tile or roll form.

To encourage the consumer to make an informed choice the standard includes a classification system (see EN 685) based on intensity of use, which shows where these floor coverings should give satisfactory service. It also specifies requirements for marking.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 424, *Resilient floor coverings — Determination of the effect of simulated movement of a furniture leg*

EN 425, *Resilient and laminate floor coverings — Castor chair test*

EN 426, *Resilient floor coverings — Determination of width, length, straightness and flatness of sheet material*

EN 427, *Resilient floor coverings — Determination of the side length, squareness and straightness of tiles*

EN 428, *Resilient floor coverings — Determination of overall thickness*

EN 429, *Resilient floor coverings — Determination of the thickness of layers*

EN 430, *Resilient floor coverings — Determination of mass per unit area*

EN 431, *Resilient floor coverings — Determination of peel resistance*

EN 432, *Resilient floor coverings — Determination of shear force*

EN 433, *Resilient floor coverings — Determination of residual indentation after static loading*

EN 434, *Resilient floor coverings — Determination of dimensional stability and curling after exposure to heat*

EN 436, *Resilient floor coverings — Determination of density*

EN 660-2, *Resilient floor coverings — Determination of wear resistance — Part 2: Frick-Taber test*

EN 661, *Resilient floor coverings — Determination of the spreading of water*

EN 663, *Resilient floor coverings — Determination of conventional pattern depth*

EN 684, *Resilient floor coverings — Determination of seam strength*

EN 685, *Resilient, textile and laminate floor coverings — Classification*

EN 718, *Resilient floor coverings — Determination of mass per unit area of a reinforcement or a backing of polyvinyl chloride floor coverings*

EN ISO 105-B02:1999, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test (ISO 105-B02:1994, including amendment 1:1998)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

polyvinyl chloride floor covering on jute backing

floor covering consisting of a polyvinyl chloride surface layer applied to jute felt backing

3.2

polyvinyl chloride floor covering on polyester felt backing

floor covering consisting of a polyvinyl chloride surface layer applied to polyester felt backing

3.3

polyvinyl chloride floor covering on polyester felt with polyvinyl chloride backing

floor covering consisting of a polyvinyl chloride surface layer applied to polyester felt with a polyvinyl chloride backing

4 Requirements and testing

4.1 General requirements

Floor coverings described in this European Standard shall conform to the appropriate general requirements as specified in Table 1 when tested in accordance with the methods given therein.

4.2 Classification requirements

4.2.1 Wear group classification

Polyvinyl chloride floor coverings are classified in the appropriate wear group specified in EN 660-2.

Floor coverings described in this standard shall be classified in wear group T or P.

Floor coverings with a transparent wear layer are a priori group T and need not be tested

4.2.2 Wear layers

A homogeneous product shall retain its wear group classification throughout the thickness of the product if tested.

A wear layer shall retain its wear group classification throughout its thickness if tested.

4.2.3 Level of use classification

Floor coverings described in this European Standard shall be classified as suitable for different levels of use in accordance with the performance requirements specified in Table 3 and 4, when tested with the methods given therein. Classification shall conform to the scheme specified in EN 685.

Table 1 (2 of 2)

Curling after exposure to heat: Floor coverings on jute or polyester felt	mm	≤ 8	EN 434
Floor coverings on polyester felt with polyvinyl chloride backing: sheets and tiles intended for welding tiles intended for dry-joint laying		≤ 8 ≤ 2	
Colour fastness to artificial light		6 minimum	EN ISO 105-B02:1999 Method 3 ^a
Peel resistance average individual results	N/50 mm	≥ 50 ≥ 40	EN 431
Shear force of backing (for jute backing only) average individual results		≥ 360 ≥ 280	EN 432
Spreading of water ^b		The time for water to spread to one edge of a test specimen shall be greater than 16 h	EN 661
^a Expose a full size of test specimen. Store a further test specimen in the dark, which will constitute the reference standard for assessment of colour change.			
^b For floor coverings, other than those on jute backing, intended for use under moist conditions.			

Table 2 — Classification requirements for wear groups

Characteristic	Requirements for wear group				Test method
	T	P	M	F	
volume loss F_v mm ³	$F_v \leq 2,0$ ^a	$2,0 < F_v \leq 4,0$	$4,0 < F_v \leq 7,5$	$7,5 < F_v \leq 15,0$	EN 660-2
^a If tested for verification.					

Table 3 — Classification requirements for level of use (1 of 2)







Class	Symbol ^d	Level of use	Thickness of wear layer. Nominal value ^c , mm		Conventional pattern of depth. Nominal value (minimum), mm		Effect of castor chair	Simulated movement of a furniture leg	Seam strength when welded in accordance with manufacturer's instructions N/50 mm	
			T	P	T	P				
21		domestic moderate	0,15	0,20	0,13	0,15	No requirement	No requirement	No requirement	
22		domestic general	0,20	0,30	0,15	0,18				No damage shall be visible after testing with a type 3 foot
22+		domestic general	0,20	0,30	0,15	0,18				
23		domestic heavy	0,25	0,40	0,18	0,20				
31		commercial moderate	0,25	0,40	0,18	0,20		No disturbance to the surface other than slight change in appearance and no delamination shall occur		No damage shall be visible after testing with a type 2 foot
32 ^{a b}		commercial general	0,35	0,50	0,30	-				

Table 3 (2 of 2)















41 ^b		light industrial moderate	0,35	0,50	0,30	-	No disturbance to the surface other than slight change in appearance and no delamination shall occur	No damage shall be visible after testing with a type 2 foot	Average value ≥ 240 Individual values ≥ 180
33 ^b		commercial heavy	0,50	0,65	-	-			
42 ^b		light industrial general	0,50	0,65	-	-			
34 ^b		commercial very heavy	0,65	1,00	-	-			
Test method			EN 429		EN 663		EN 425	EN 424	EN 684
<p>^a Floor coverings on polyester felt backing.</p> <p>^b Floor coverings on polyester felt with polyvinyl chloride backing.</p> <p>^c The average value shall be the nominal value with a tolerance of + 13 % / - 10 % but not more than 0,1 mm. Individual values shall not vary more than 0,05 mm or 15 % below the average, whichever is the greater. Where this requirement is not met by only one individual value, however, the test shall be repeated once more.</p> <p>^d The floor symbols can be found at http://www.floorsymbols.com</p>									

Table 4 - Classification requirements for level of use

Class	Symbol	Level of use	Underfoot comfort Indentation after static loading (average), mm	Residual indentation after static loading (average), mm		
				Floor coverings on jute backing	Floor coverings on polyester felt	Floor coverings on polyester felt with polyvinyl chloride backing
21		domestic moderate	≥ 0,40 when measured after 15 s under load	≤ 0,50	≤ 0,40	≤ 0,35
22		domestic general				
22+		domestic general				
23		domestic heavy				
31		commercial moderate				
32		commercial general	No requirement	Not suitable	≤ 0,20	
41		light industrial moderate				Not suitable
33		commercial heavy		No requirement	Not suitable	
42		light industrial general				
34		commercial very heavy	No requirement	Not suitable	Not suitable	
Test method			EN 433			

5 Marking

Floor coverings covered by this standard and/or their packaging shall bear the following marking:

- a) number and date of this European Standard, i.e. EN 650:2012;
- b) manufacturer's or supplier's identification;
- c) product name;
- d) colour/pattern, and batch number and, if applicable, roll number;
- e) classes/symbols appropriate for the product;
- f) for rolls: the length, width and thickness;
- g) for tiles: the dimensions of a tile and the area in square metres contained in a package.

Annex A (informative)

Optional properties

Where the following properties are required for specific applications, the floor covering should be tested in accordance with the appropriate methods:

- electrical resistance (EN 1081);
- electrostatic propensity (EN 1815);
- effect of stains (EN 423);
- cigarette resistance (EN 1399);
- curling on exposure to moisture (EN 662);
- volatile loss (EN 664);
- exudation of plasticizers (EN 665);
- gelling (EN 666).

Bibliography

- [1] EN 423, *Resilient floor coverings — Determination of resistance to staining*
- [2] EN 662, *Resilient floor coverings — Determination of curling on exposure to moisture*
- [3] EN 664, *Resilient floor coverings — Determination of volatile loss*
- [4] EN 665, *Resilient floor coverings — Determination of exudation of plasticizers*
- [5] EN 666, *Resilient floor coverings — Determination of gelling*
- [6] EN 1081, *Resilient floor coverings — Determination of the electrical resistance*
- [7] EN 1815, *Resilient and textile floor coverings — Assessment of static electrical propensity*
- [8] EN 1399, *Resilient floor coverings — Determination of resistance to stubbed and burning cigarettes*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™