BS EN 686:2011



BSI Standards Publication

Resilient floor coverings — Specification for plain and decorative linoleum on a foam backing



BS EN 686:2011 BRITISH STANDARD

National foreword

This British Standard is the UK implementation of EN 686:2011. It supersedes BS EN 686:1997, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/60, Resilient floor coverings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2011

ISBN 978 0 580 71955 4

ICS 97.150

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2011.

Amendments issued since publication

Date Text affected

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 686

April 2011

ICS 97.150 Supersedes EN 686:1997

English Version

Resilient floor coverings - Specification for plain and decorative linoleum on a foam backing

Revêtements de sol résilients - Spécifications pour le linoléum uni et décoratif sur sous-couche de mousse

Elastische Bodenbeläge - Spezifikation für Linoleum mit und ohne Muster mit Schaumrücken

This European Standard was approved by CEN on 10 March 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		
Fore	eword	3
1	Scope	4
2	Normative references	4
3	Terms and definitions	5
4	Identification	5
5 5.1	RequirementsGeneral requirementsClassification requirements	5
5.1	General requirements	5
5.2		
6	• 5	
Anne	ex A (informative) Optional properties	10
Riblia	iography	11

Foreword

This document (EN 686:2011) has been prepared by Technical Committee CEN/TC 134 "Resilient, textile and laminate floor coverings", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2011, and conflicting national standards shall be withdrawn at the latest by October 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 686:1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies the characteristics of plain and decorated linoleum on a foam backing as a compound floor covering, supplied in roll form.

To encourage the consumer to make an informed choice, this European Standard includes a classification system based on intensity of use, which shows where resilient floor coverings should give satisfactory service (see EN 685). It also includes requirements for marking.

The term 'linoleum' is frequently incorrectly applied to a range of floor coverings, often to those based on polyvinyl chloride or rubber. Such materials are not included in this standard.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

- EN 425, Resilient and laminate floor coverings Castor chair test
- EN 426, Resilient floor coverings Determination of width, length, straightness and flatness of sheet material
- EN 428, Resilient floor coverings Determination of overall thickness
- EN 429, Resilient floor coverings Determination of the thickness of layers
- EN 430, Resilient floor coverings Determination of mass per unit area
- EN 431, Resilient floor coverings Determination of peel resistance
- EN 433, Resilient floor coverings Determination of residual indentation after static loading
- EN 435, Resilient floor coverings Determination of flexibility
- EN 670, Resilient floor coverings Identification of linoleum and determination of cement content and ash residue
- EN 685, Resilient, textile and laminate floor coverings Classification
- EN ISO 105-B02, Textiles Tests for colour fastness Part B02: Colour fastness to artificial light: Xenon arc fading lamp test (ISO 105-B02:1994, including amendment 1:1998)

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

linoleum cement

binder in linoleum, consisting of a mixture of linseed oil and/or other vegetable drying oils, rosin and drying oil catalysts, which is converted to a semi-elastic mass by an oxidative curing process

3.2

linoleum

product produced by calendering a homogeneous mixture of linoleum cement, cork and/or wood flour, pigments and inorganic filler onto a fibrous backing; the product is then converted into its final form by an oxidative curing process.

NOTE The only chemical cross-linking bondings in linoleum will be those which are formed during the oxidation process.

3.3

linoleum on a foam backing

product formed by laminating linoleum on to a foam layer

4 Identification

Linoleum shall be identified by its ability to be disintegrated in 0,5 mol/l potassium hydroxide/methanol solution and by the determination of cement content and ash residue.

The minimum amount of linoleum cement shall be 30 % when tested in accordance with EN 670.

The maximum amount of inorganic filler (ash residue) shall be 50 % when tested in accordance with EN 670.

5 Requirements

5.1 General requirements

All classes of linoleum on foam backing shall comply with the appropriate general requirements specified in Table 1, when tested in accordance with the methods given therein.

Table 1 — General requirements

Property	Requirement	Test method
Rolls		EN 426
length m	Not less than the nominal values	
width mm		
Overall thickness mm		EN 428
average	Nominal value ± 0,20	
individual values	Nominal value ± 0,25	
Thickness of linoleum mm		EN 429
average	Nominal value ± 0,15	
individual values	Nominal value ± 0,20	
Thickness of fibrous backing		
average mm	≤ 0,80	
Thickness of foam backing mm		
average	Nominal value ± 0,10	
Mass per unit area g/m²		EN 430
average	nominal value ± 10 %	
Residual indentation after static		EN 433
loading mm		
average	± 0,30	
Flexibility		EN 435
		Method A
Thickness Mandrel		
of linoleum diameter		
(nominal)		
2,0 mm 30 mm	Shall show no signs of cracking when bent around the appropriate mandrel	
2,5 mm 40 mm		

Table 1 (continued)

Property	Requirement	Test method
Colour fastness to artificial light	6 minimum	EN ISO 105-B02 Method 3 ¹⁾
Effect of a castor chair	No damage shall be apparent.	EN 425
Peel resistance between foam backing and fibrous backing		EN 431
average N/50mm	≥10	

Before comparing the test piece, expose the reference sample together with the Blue Wool cloth to the xenon arc lamp, until a contrast is produced on Blue Wool Reference 2 equal to the contrast illustrated by Grey Scale 3. This step is necessary to remove the inherent 'stove yellowing' of linoleum before the stable colouration is achieved.

5.2 Classification requirements

The classification scheme for resilient floor coverings is described in EN 685. The requirements for floor coverings described in this standard sold as a compound floor covering, in accordance with this scheme, are related to the nominal thickness of the linoleum, as shown in Table 2.

Table 2 — Classification

Class	Symbol	Level of use	Nominal thickness of the linoleum, mm
21		domestic moderate	2,0
22		domestic general	
22+		domestic general	
23		domestic heavy	
31		commercial moderate	2,0
32		commercial general	
33		commercial heavy	2,5
41		light industrial moderate	2,0

6 Marking

Floor coverings of plain and decorative linoleum on a foam backing and/or their packaging shall bear the following marking:

- a) number and date of this European Standard, i.e. EN 686:2011;
- b) manufacturer's or supplier's identification;
- c) product name;
- d) colour/pattern, and batch and roll number;
- e) classes/symbols appropriate for the product;
- f) type of foam backing;
- g) length, width and thickness of rolls.

Annex A (informative)

Optional properties

Where the following properties are required for specific applications, the floor covering should be tested in accordance with the appropriate methods.

—	electrical resistance (see EN 1081);
—	electrostatic propensity (see EN 1815);
_	effect of stains (see EN 423);
_	cigarette resistance (see EN 1399):
	In general use, a linoleum floor covering, depending on the colour and/or pattern, is expected to have the following rating when tested in accordance with EN 1399: Method A, stubbed cigarettes; rating 4 or higher Method B, burning cigarettes; rating 3 or higher

— sound insulation (see EN ISO 10140-3 and EN ISO 717-2).

Bibliography

- [1] EN 423, Resilient floor coverings Determination of resistance to staining
- [2] EN 1081, Resilient floor coverings Determination of electrical resistance
- [3] EN 1399, Resilient floor coverings Determination of resistance to stubbed and burning cigarettes
- [4] EN 1815, Resilient and textile floor coverings Assessment of static electrical propensity
- [5] EN ISO 10140-3, Acoustics Laboratory measurement of sound insulation of building elements Part 3: Measurement of impact sound insulation (ISO 10140-3:2010)
- [6] EN ISO 717-2, Acoustics Rating of sound insulation in buildings and of building elements Part 2: Impact sound insulation (ISO 717-2:1996)





British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards -based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com
Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070 Email: copyright@bsigroup.com

