

Materials and articles in contact with foodstuffs — Plastics —

Part 5: Test methods for overall migration into aqueous food simulants by cell

The European Standard EN 1186-5:2002 has the status of a
British Standard

ICS 67.250

National foreword

This British Standard is the official English language version of EN 1186-5:2002. It supersedes DD ENV 1186-5:1994 which is withdrawn.

The UK participation in its preparation was entrusted by Technical Committee CW/47, Materials in contact with food, to Subcommittee CW/47/1, Migration from plastics, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled “International Standards Correspondence Index”, or by using the “Find” facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard, having been prepared under the direction of the Consumer Products and Services Sector Policy and Strategy Committee, was published under the authority of the Standards Policy and Strategy Committee on 21 May 2002

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 13 and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

English version

Materials and articles in contact with foodstuffs - Plastics - Part 5: Test methods for overall migration into aqueous food simulants by cell

Matériaux et objets en contact avec les denrées
alimentaires - Matière plastique - Partie 5: Méthodes
d'essai pour la migration globale dans les liquides
simulateurs aqueux en cellule

Werkstoffe und Gegenstände in Kontakt mit Lebensmitteln
- Kunststoffe - Teil 5: Prüfverfahren für die
Gesamtmigration in wässrigen Prüflebensmitteln mittels
Zellen

This European Standard was approved by CEN on 4 January 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword.....	3
1 Scope	5
2 Normative references	5
3 Principle	5
4 Reagents	5
5 Apparatus	6
6 Preparation of test specimens.....	7
7 Number of test specimens	7
8 Procedure	7
9 Expression of results	9
10 Test report	9
Annex A (informative) Precision data.....	10
Annex ZA (informative) Relationship of this European Standard with Council Directive 89/109/EEC and Commission Directive 90/128/EEC and associated Directives.....	11
Bibliography	13

Foreword

This document EN 1186-5:2002 has been prepared by Technical Committee CEN/TC 194 "Utensils in contact with food", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2002, and conflicting national standards shall be withdrawn at the latest by October 2002.

This document supersedes ENV 1186-5:1994.

This European Standard is one of a series of methods of test for plastics materials and articles in contact with foodstuffs.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EC Directive(s).

For relationship with EC Directive(s), see informative annex ZA, which is an integral part of this document.

At the time of preparation and publication of this standard the European Union legislation relating to plastics materials and articles intended to come into contact with foodstuffs is incomplete. Further Directives and amendments to existing Directives are expected which could change the legislative requirements which this standard supports. It is therefore strongly recommended that users of this standard refer to the latest relevant published Directive(s) before commencement of any of the test or tests described in this standard.

EN 1186-5 should be read in conjunction with EN 1186-1.

Further Parts of this standard have been prepared concerned with the determination of overall migration from plastics materials into food simulants. Their titles are as follows:

EN 1186 - Materials and articles in contact with foodstuffs – Plastics

Part 1	Guide to the selection of conditions and test methods for overall migration
Part 2	Test methods for overall migration into olive oil by total immersion
Part 3	Test methods for overall migration into aqueous food simulants by total immersion
Part 4	Test methods for overall migration into olive oil by cell
Part 6	Test methods for overall migration into olive oil using a pouch
Part 7	Test methods for overall migration into aqueous food simulants using a pouch
Part 8	Test methods for overall migration into olive oil by article filling
Part 9	Test methods for overall migration into aqueous food simulants by article filling
Part 10	Test methods for overall migration into olive oil modified method for use in cases where incomplete extraction of olive oil occurs)
Part 11	Test methods for overall migration into mixtures of ¹⁴ C-labelled synthetic triglyceride
Part 12	Test methods for overall migration at low temperatures

EN 1186-5:2002 (E)

- Part 13 Test methods for overall migration at high temperatures
- Part 14 Test methods for 'substitute tests' for overall migration from plastics intended to come into contact with fatty foodstuffs using test media iso-octane and 95 % ethanol
- Part 15 Alternative test methods to migration into fatty food simulants by rapid extraction into iso-octane and/or 95 % ethanol

Annex A is informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This Part of this European Standard specifies test methods for the determination of the overall migration into aqueous based food simulants from one surface only of plastics, which are intended to come into contact with foodstuffs, by exposing the food contact surface, using a cell, to the selected food simulant at temperatures up to and including 70 °C for selected test times.

This method is most suitable for plastics in the form of films and sheets, but is particularly applicable to those materials consisting of more than one layer or of surfaces that differ in their migration characteristics, which should be tested with the food simulant in contact only with the surface which is intended to come into contact with foodstuffs.

2 Normative references

This European Standard incorporates by dated and undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to and revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 1186-1:2002, *Materials and articles in contact with foodstuffs – Plastics – Part 1: Guide to the selection of conditions and test methods for overall migration.*

ISO 648, *Laboratory glassware - One mark pipettes.*

ISO 4788, *Laboratory glassware - Graduated measuring cylinders.*

3 Principle

The overall migration of non-volatile substances from a sample of the plastics is determined as the mass of non-volatile residue after evaporation of the food simulant.

The selection of the conditions of test and the food simulant(s) will be determined by the conditions of use, see clauses 4, 5 and 6 of EN 1186-1:2002.

Test specimens of approximately 2,5 dm² are exposed in a cell to the food simulant for the exposure time at temperatures up to and including 70 °C. At the end of the test period, each test specimen is removed from the cell. The food simulant from each test specimen is evaporated to dryness, the mass of the non-volatile residue is determined gravimetrically and expressed as milligrams per square decimetre of surface area of test specimen.

NOTE In some circumstances the procedure described in this standard can be used for exposure at temperatures above 70 °C.

Overall migration is reported as the mean of three determinations on separate test specimens.

4 Reagents

NOTE For details of the preparation and purity of these reagents see clause 4 of EN 1186-1:2002.

4.1 Distilled water or water of equivalent quality (simulant A)

4.2 Acetic acid 3 % (w/v) in aqueous solution (simulant B)

4.3 Ethanol 10 % (v/v) in aqueous solution (simulant C)

4.4 Alcoholic simulants for liquids or beverages of an alcoholic strength exceeding 10 % (v/v).

NOTE In the case of materials and articles intended to come into contact with liquids or beverages of an alcoholic strength exceeding 10 % (v/v) the test is carried out with aqueous solutions of ethanol of a similar strength.

5 Apparatus

5.1 Cutting slab, clean smooth glass, metal or plastics slab of suitable area to prepare test specimens, 250 mm × 250 mm is suitable.

5.2 Tweezers, stainless steel, blunt nosed.

5.3 Cutting implement, scalpel, scissors or sharp knife or other suitable device.

5.4 Rule, graduated in millimetres, and with an accuracy of 0,1 mm.

5.5 Analytical balance capable of determining a change in mass of 0,1 mg.

5.6 Cells, type A as shown in Figure C.3 of EN 1186-1:2002, either the all aluminium (anodized) cells or the cells with the stainless steel (316 grade) lids and rings, are suitable for the water and aqueous ethanol food simulants. For the aqueous acetic acid food simulant the cells with the stainless steel lids and rings are used. The internal diameter of the rim of the sealing ring shall be 178,4 mm ± 0,1 mm, to give an area of the test specimen exposed to the food simulant of 2,5 dm².

NOTE The cells, type A, are constructed with a rubber mat in the base plate. When using the cells with either the water or aqueous ethanol food simulants it is advised that a disc of aluminium foil is placed on the mat before inserting the test specimen. For the aqueous acetic acid food simulant a disc of polytetrafluoroethylene or other suitable material which is inert to acetic acid can be used. The use of these discs will prevent any substances from the mat influencing the migration result.

For details of equivalent cells see 7.3 of EN 1186-1:2002.

5.7 Pipettes, complying with the minimum requirements of ISO 648, 50 ml and 100 ml.

5.8 Glass tubes, ground neck, and stoppers, for retaining the food simulant. Tubes with an internal diameter of approximately 35 mm and length of approximately 100 mm to 200 mm, excluding the ground neck (see 7.2 of EN 1186-1:2002), have been found to be satisfactory.

5.9 Thermostatically controlled oven or incubator or refrigerator capable of maintaining a set temperature within the tolerances specified in Table B.2 of EN 1186-1:2002.

5.10 Dishes, stainless steel, nickel, platinum, platinum alloy, gold, 50 mm to 90 mm diameter and maximum mass 100 g, for evaporation of food simulants and weighing of residues. Glass, glass ceramic or ceramic dishes may be used, provided that the surface characteristics are such that the masses of the dishes after evaporation of any specified food simulants followed by conditioning in the desiccator used achieves a constancy of ± 0,5 mg. Stainless steel and nickel dishes are suitable only for distilled water and ethanol solutions. Glass, glass ceramic, glazed ceramic, platinum, platinum alloy or gold dishes are suitable for all three simulants.

5.11 Steam bath, hot plate, distillation apparatus or rotary evaporator for evaporation of food simulant at the end of test period.

5.12 Desiccator with anhydrous calcium chloride or self indicating silica gel.

5.13 Measuring cylinders, 250 ml, complying with the minimum requirements of ISO 4788.

6 Preparation of test specimens

6.1 General

It is essential that test specimens are clean and free from surface contamination (many plastics can readily attract dust due to static charges). Before preparing test specimens, remove any surface contamination from the sample by gently wiping it with a lint free cloth, or by brushing with a soft brush. Under no circumstances wash the sample with water or solvent. If it is specified in the instructions for use of the article that it should be washed or cleaned before use, see 8.1 of EN 1186-1:2002. Minimize handling of the samples and where necessary, wear cotton gloves.

7 Number of test specimens

Three test specimens are required for samples, in the form of thin films, sheets, and flat sections cut from containers or similar articles.

7.1 Cutting test specimens

Lay the sample on the cutting slab (5.1) with the surface to be in contact with the food simulant uppermost. Take the ring from the standard cell (5.6) and place on the surface of the sample. Cut out the test specimen by cutting round the outer edge of the ring, using the cutting implement (5.3).

8 Procedure

8.1 Exposure to food simulant

Take three cells (5.6), mark these for identification purposes. Place in the thermostatically controlled oven or incubator or refrigerator (5.9), which is set at the selected test temperature and leave until the test temperature has been attained.

Take three glass tubes (5.8), for the simulant for contact with the test specimens and a further two to provide blanks, measure by measuring cylinder 125 ml \pm 2 ml of the food simulant into each tube. Insert a thermometer or thermocouple, if applicable, see NOTE 2, in one of the tubes and stopper the tubes.

Mark the liquid level on the outside of each tube with a suitable marker.

Place the five tubes in the thermostatically controlled oven or incubator or refrigerator, set at the test temperature and leave until the simulant has attained the test temperature.

Remove the cells from the thermostatically controlled oven or incubator or refrigerator, dismantle and place on the base of each cell one of the test specimens. Reassemble the cells, ensuring that the clamping screw wheel is well tightened down.

Remove three tubes containing 125 ml of the food simulant from the thermostatically controlled oven or incubator or refrigerator and transfer the food simulant from each tube to each of the cells through the filler hole. Remove the thermometer or thermocouple from the tube and insert, if applicable see NOTE 2, in one of the cells and replace the filler plugs. This part of the operation should be carried out in the minimum time to prevent undue heat loss from the cells and simulants.

Replace the test cells in the thermostatically controlled oven or incubator or refrigerator, set at the test temperature. Observe the temperature, leave the cells and the blank tubes for the selected period of time after the temperature of the simulant in the cell has reached a temperature within the permitted tolerance for the test temperature, see Tables B.1 and B.2 of EN 1186-1:2002 for permitted tolerances on test times and temperature.

EN 1186-5:2002 (E)

NOTE 1 Annex B of EN 1186-1:2002 includes tolerances on a wide range of contact times and contact temperatures. All of these contact times and contact temperatures are not necessarily relevant to this Part of the standard.

Take the cells and the two tubes containing the blank simulants from the thermostatically controlled oven or incubator or refrigerator.

Recover at least 90 % of the original volume of simulant or repeat the test.

Rinse each cell twice with $20 \text{ ml} \pm 2 \text{ ml}$ of unused simulant, add these rinses to the respective tubes. Add twice $20 \text{ ml} \pm 2 \text{ ml}$ of simulant to each of the two tubes containing blank simulant.

NOTE 2 For exposure times of 24 h or more it is acceptable to monitor the temperature of the airbath of the thermostatically controlled oven or incubator or refrigerator, instead of the temperature of the simulant.

8.2 Determination of migrating substances

8.2.1 Preparation of dishes

Take five dishes (5.10), marked for identification, place the dishes in an oven maintained at $105 \text{ }^{\circ}\text{C}$ to $110 \text{ }^{\circ}\text{C}$, for a period of $30 \text{ min} \pm 5 \text{ min}$, to dry.

Remove the dishes from the oven, place in a desiccator (5.12) and allow to cool to ambient temperature. Weigh and record the individual masses of each dish.

Replace the dishes in the oven and repeat the cycle of heating, cooling and weighing until individual consecutive masses differ by not more than 0,5 mg, record their final masses.

8.2.2 Evaporation method

Take the tubes containing the simulant and pour 40 ml to 50 ml from each into separate dishes. By means of a steam bath, hot plate or other form of heating (5.11) evaporate to a low volume, taking care to avoid loss, in particular by sputtering or overheating of the residues.

NOTE 1 The evaporation of acetic acid and ethanol should be carried out in a fume cupboard.

When most of the simulant has evaporated, pour the remaining simulant from each of the tubes into the respective dishes and continue the evaporation. Wash out each of the tubes, including the blank tubes, with two lots of $10 \text{ ml} \pm 1 \text{ ml}$ of unused simulant and pour these washings into the respective dishes. Continue the evaporation.

NOTE 2 A stream of nitrogen can be used to facilitate evaporation.

When the simulant has almost completely evaporated, place the dish in an oven maintained at $105 \text{ }^{\circ}\text{C}$ to $110 \text{ }^{\circ}\text{C}$, for a period of $30 \text{ min} \pm 5 \text{ min}$, to complete the evaporation and dry the residue.

Remove the dishes from the oven, place in a desiccator (5.12) and allow to cool to ambient temperature. Weigh and record the individual masses of a dish and residue.

Replace the dishes in the oven and repeat the cycle of heating, cooling and weighing until individual consecutive masses differ by not more than 0,5 mg.

Determine the mass of the residue by subtracting the original stable mass of the dish from the stable mass of the dish and residue.

8.2.3 Distillation method

Transfer the simulants to individual round bottom flasks (250 ml are suitable). Wash out each tube twice, including the blank tubes, with two lots of $10 \text{ ml} \pm 1 \text{ ml}$ of unused simulant, add these rinses to the respective flasks. Place the flasks in an electric heating mantle and connect to a side arm distillation arrangement or rotary evaporator.

Distil off the simulants until approximately 30 ml to 50 ml remains in each flask. Transfer the remaining simulant in each flask to individual evaporating dishes (5.10). Rinse each flask with 10 ml ± 1 ml of fresh simulant and add the rinses to the appropriate dishes. Continue the evaporation of the simulant by means of a steam bath, hot plate or other form of heating, proceeding as in 8.2.1.

NOTE The evaporation of acetic acid and ethanol should be carried out in a fume cupboard.

9 Expression of results

9.1 Method of calculation

Express the overall migration as milligrams of residue per square decimetre of the surface of the sample which is intended to come into contact with foodstuffs, calculated for each test specimen using the following formula:

$$M = \frac{(m_a - m_b) \times 1000}{S}$$

where

- M is the overall migration into the simulant, in milligrams per square decimetre of the surface area of sample intended come into contact with the foodstuff;
- m_a is the mass of the residue from the test specimen after evaporation of the simulant which had filled the cell, in grams;
- m_b is the mass of residue from the blank simulant, in grams;
- S is the surface area of the test specimen in contact with the food simulant in the cell, that is 2,5 dm² in the standard cell.

Calculate the result for each test specimen to the nearest 0,1 mg/dm² and the mean of the individual test results, to the nearest 0,1 mg/dm².

See 11.3 of EN 1186-1:2002 for the directions to determine whether the results are valid.

9.2 Precision

See annex A.

10 Test report

The test report shall include the following (see clause 11 of EN 1186-1:2002):

- a) reference to this European Standard and to the Part used for the test procedure;
- b) all information necessary for complete identification of the sample such as chemical type, supplier, trade mark, grade, batch number, thicknesses;
- c) conditions of time and temperature of exposure to simulants;
- d) departures from the specified procedure, and reasons for these;
- e) individual test results, and the mean of these, expressed as milligrams of residue per square decimetre of sample;
- f) relevant comments on the test results.

Annex A (informative)

Precision data

The precision data were determined for a polyamide sample under the test conditions of total immersion for 24 h at 40 °C with simulants A, B and C.

As such they are intended to be indicative of the results to be expected using the other methods, for which the precision data are at present unavailable.

NOTE It is anticipated that more complete precision data, for all of the methods will be incorporated in a future revision of EN 1186-1.

The precision data for simulant A were determined from the BSI/DTI trial conducted in 1991 (Pira Report No.SP91/2- January 1992) involving 13 laboratories and one sample.

The precision data for simulant B were determined from the BSI/DTI trial conducted in 1991 (Pira Report No.SP91/2- January 1992) involving 10 laboratories and one sample.

The precision data for simulant C were determined from the BSI/DTI trial conducted in 1991 (Pira Report No.SP91/2- January 1992) involving 13 laboratories and one sample.

Table A.1 — Precision data

Level	Repeatability (<i>r</i>)	Reproducibility (<i>R</i>)
Simulant A 6,9 mg/dm ²	1,3 mg/dm ²	2,6 mg/dm ²
Simulant B 10,7 mg/dm ²	1,1 mg/dm ²	2,3 mg/dm ²
Simulant C 11,9 mg/dm ²	1,1 mg/dm ²	2,9 mg/dm ²

The difference between two single results found on identical test material by one operator using the same apparatus within the shortest feasible time interval will exceed the repeatability value *r* on average not more than once in 20 cases in the normal and correct operation of the method.

Single results on identical test material reported by two laboratories will differ by more than the reproducibility value *R* on average not more than once in 20 cases in the normal and correct operation of the method.

Annex ZA (informative)

Relationship of this European Standard with Council Directive 89/109/EEC and Commission Directive 90/128/EEC and associated Directives

This European Standard has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association (EFTA).

NOTE Other requirements and other EU Directives may be applicable to products falling within the scope of this standard.

The clauses of this standard are likely to support Directives 89/109/EEC [1], 90/128/EEC [2], 82/711/EEC [3] and its amendments 93/8/EEC [4] and 97/48/EC [5], and 85/572/EEC [6].

Compliance with this standard provides one means of conforming to the overall migration requirements of the Directive concerned and associated EFTA regulations.

European Commission Directive 90/128/EEC relating to plastics materials and articles intended to come into contact with foodstuffs, [3], specifies in article 2.

Plastics materials and articles shall not transfer their constituents to foodstuffs in quantities exceeding 10 milligrams per square decimetre of surface area of materials or articles (overall migration limit). However this limit shall be 60 milligrams of constituents released per kilogram of foodstuff in the following cases :

- a) articles which are containers or are comparable to containers or which can be filled, with a capacity of not less than 500 ml and not more than 10 l;
- b) articles which can be filled and for which it is impracticable to estimate the surface area in contact with foodstuffs;
- c) caps, gaskets, stoppers or similar devices for sealing.

European Council Directive 82/711/EEC laying down the basic rules necessary for testing migration of the constituents of plastics materials and articles intended to come into contact with foodstuffs [3], and the subsequent amendments (Directives 93/8/EEC [4] and 97/48/EC [5]), recognizes that there are difficulties in the determination of the migration in food products and allows use of food simulants with conventional test conditions, which reproduce, as far as possible, the migration phenomena which may occur with contact between the article and foodstuffs. There are four food simulants:

- simulant A, distilled water or water of equivalent quality;
- simulant B, 3% acetic acid (w/v) in aqueous solution;
- simulant C, 10% ethanol (v/v) in aqueous solution;
- simulant D, rectified olive oil, or other fatty food simulants.

European Directive 82/711/EEC and the subsequent amendments also contain the conventional test conditions (time and temperature) for migration tests with food simulants. European Commission Directive 97/48/EC, the second amendment to European Council Directive 82/711/EEC, also contains test media and conventional test conditions for 'substitute tests'. Substitute tests may be performed in place of migration tests with simulant D, if it has been shown that for technical reasons connected with the method of analysis it is not feasible to obtain a valid test result in a migration test with simulant D.

European Council Directive 85/572/EEC laying down the list of simulants to be used for testing of constituents of plastics materials and articles intended to come into contact with foodstuffs [6] has a Table in the Annex which contains a non-exhaustive list of foodstuffs and which identify the simulants to be used in migration tests on those plastic materials and articles intended to come into contact with a particular foodstuff or group of foodstuffs.

This standard contains the test methods for the measurement of overall migration from plastics materials to food simulants, or test media, using conventional contact test conditions of time and temperature, to determine compliance with the legislative overall migration limit specified in article 2 of European Commission Directive 90/128/EEC.

These test methods may also be used for the verification of compliance with the specific migration limits provided for in paragraph 1 of Commission Directive 90/128/EEC, if it can be established that compliance with the overall migration limit laid down in Article 2 of Commission Directive 90/128/EEC implies that the specific migration limits are not exceeded.

Commission Directive also specifies that the migration tests using rectified olive oil or substitutes shall not be carried out to check compliance with the overall migration limit in cases where there is conclusive proof that the specified analytical method is inadequate from the technical standpoint.

In any such case, substances exempt from specific migration limits or other restrictions in the list provided in Annex II of Commission Directive 90/128/EEC, a generic specific migration limit of 60 mg/kg or 10 mg/dm², according to the case, is applied. However, Commission Directive 90/128/EEC requires that the sum of all specific migrations determined shall not exceed the overall migration limit.

Bibliography

[1] Commission of the European Communities, Council Directive of 21 December 1988 on the approximation of the laws of the Member States relating to materials and articles intended to come into contact with foodstuff (89/109/EEC), Official Journal of the European Communities, 11 February 1989, no. L 40, p 38.

[2] Commission of the European Communities, Commission Directive of 23 February 1990 relating to plastics materials and articles intended to come into contact with foodstuffs (90/128/EEC), Official Journal of the European Communities, 13 December 1990, no. L 349, p 26. Corrigendum of the previous publication, Official Journal of the European Communities, 21 March 1990, no. 75. p 19.

[3] Commission of the European Communities, Council Directive of 18 October 1982 laying down the basic rules necessary for testing migration of the constituents of plastics materials and articles intended to come into contact with foodstuffs (82/711/EEC), Official Journal of the European Communities, 23 October 1982, no. L 297, p 26.

[4] Commission of the European Communities, Commission Directive of 15 March 1993 amending Council Directive 82/711/EEC laying down the basic rules necessary for testing migration of the constituents of plastics materials and articles intended to come into contact with foodstuffs (93/8/EEC), Official Journal of the European Communities, 14 April 1993, no. L 90, p 22.

[5] Commission of the European Communities, Commission Directive of 97/48/EC of 29 July 1997 amending Council Directive 82/711/EEC laying down the basic rules necessary for testing migration of the constituents of plastics materials and articles intended to come into contact with foodstuffs , Official Journal of the European Communities, 12 August 1997, no. L 222, p 10

[6] Commission of the European Communities, Council Directive of 19 December 1985 laying down the list of simulants to be used for testing migration of constituents of plastics materials and articles intended to come into contact with foodstuffs (85/572/EEC), Official Journal of the European Communities, 31 December 1985, no. L 372, p 14.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.