

# **Glass in building — Determination of the bending strength of glass —**

## **Part 2: Coaxial double ring test on flat specimens with large test surface areas**

The European Standard EN 1288-2:2000 has the status of a  
British Standard

ICS 81.040.20

## National foreword

This British Standard is the official English language version of EN 1288-2:2000.

The UK participation in its preparation was entrusted by Technical Committee B/520, Glass and glazing in building, to Subcommittee B/520/4, Properties and glazing methods, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

### Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled “International Standards Correspondence Index”, or by using the “Find” facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

### Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 20, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

### Amendments issued since publication

Amd. No.	Date	Comments

This British Standard, having been prepared under the direction of the Sector Committee for Building and Civil Engineering, was published under the authority of the Standards Committee and comes into effect on 15 August 2000

© BSI 08-2000

ISBN 0 580 36154 3

---

ICS 81.040.20

English version

## Glass in building - Determination of the bending strength of glass - Part 2: Coaxial double ring test on flat specimens with large test surface areas

Verre dans la construction - Détermination de la résistance du verre à la flexion - Partie 2: Essais avec doubles anneaux concentriques sur éprouvettes planes, avec de grandes surfaces de sollicitation

Glas im Bauwesen - Bestimmung der Biegefestigkeit von Glas - Teil 2: Doppelring-Biegeversuch an plattenförmigen Proben mit großen Prüfflächen

This European Standard was approved by CEN on 5 September 1999.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

<b>Contents</b>		Page
<b>Foreword</b>		<b>3</b>
<b>1</b>	<b>Scope</b>	<b>4</b>
<b>2</b>	<b>Normative references</b>	<b>4</b>
<b>3</b>	<b>Definitions</b>	<b>4</b>
<b>4</b>	<b>Symbols</b>	<b>5</b>
<b>5</b>	<b>Principle of test method</b>	<b>6</b>
<b>6</b>	<b>Apparatus</b>	<b>7</b>
<b>7</b>	<b>Sample</b>	<b>9</b>
<b>8</b>	<b>Procedure</b>	<b>11</b>
<b>9</b>	<b>Evaluation</b>	<b>13</b>
<b>10</b>	<b>Test report</b>	<b>15</b>
<b>Annex A (informative) Example of a device for keeping the gas pressure, <math>p</math>, in line with the piston force, <math>F</math></b>		<b>17</b>
<b>Annex B (informative) Bibliography</b>		<b>20</b>

## Foreword

This European Standard has been prepared by Technical Committee CEN/TC 129, Glass in building, the Secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2000, and conflicting national standards shall be withdrawn at the latest by December 2000.

CEN/TC 129/WG8, Mechanical Strength, prepared the draft, Glass in building - Determination of the bending strength of glass - Part 2: Coaxial double ring test on flat specimens with large test surface areas.

There are four other parts to this standard:

- Part 1: Fundamentals of testing glass;
- Part 3: Test with specimen supported at two points (four point bending);
- Part 4: Testing of channel shaped glass;
- Part 5: Coaxial double ring test on flat specimens with small test surface areas.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

## 1 Scope

This European Standard specifies a method for determining the bending strength of glass for use in buildings, excluding the effects of the edges.

The limitations of this standard are described in EN 1288-1.

EN 1288-1 should be read in conjunction with this standard.

## 2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references, the latest edition of the publication referred to applies.

EN 1288-1	Glass in building - Determination of the bending strength of glass – Part 1: Fundamentals of testing glass.
EN 572-1	Glass in building - Basic soda lime silicate glass products - Part 1: Definitions and general physical and mechanical properties.
ISO 48	Rubber, vulcanized or thermoplastic - Determination of hardness (hardness between 10 IRHD and 100 IRHD).

## 3 Definitions

For the purposes of this standard, the following definitions apply.

**3.1 bending stress:** the tensile bending stress induced in the surface of a specimen

NOTE: For testing purposes, the bending stress should be uniform over a specified part of the surface.

**3.2 effective bending stress:** a weighted average of the tensile bending stresses, calculated by applying a factor to take into account non-uniformity of the stress field

**3.3 bending strength:** the bending stress or effective bending stress which leads to breakage of the specimen

**3.4 equivalent bending strength:** the apparent bending strength of patterned glass, for which the irregularities in the thickness do not allow precise calculation of the bending stress

## 4 Symbols

$A$	Effective surface area of quasi-uniform stress
$E$	Modulus of elasticity (Young's modulus) of the specimen.

NOTE: For soda lime silicate glass (see EN 572-1), a value of  $70 \times 10^3 \text{ N/mm}^2$  is used.

$F$	Piston force
$F_{\max}$	Piston force upon breakage, "breaking force"
$F_{\text{ring}}$	Force transmitted by the loading ring to the specimen, "ring load"
$h$	Thickness or average thickness of specimen
$L$	Side length of the square specimens
$\mu$	Poisson number of specimen

NOTE: For soda lime silicate glass (see EN 572-1), a value of 0,23 is used.

$p$	Gas pressure on the surface area defined by the loading ring
$p(F)$	Nominal gas pressure as a function of the piston force
$p_{\max}(F_{\max})$	Nominal gas pressure upon breakage
$r$	Location co-ordinate
$r_1$	Radius of loading ring
$r_2$	Radius of supporting ring
$r_{3m}$	Average specimen radius (for evaluation)
$\sigma$	Stress
$\sigma_{\text{bB}}$	Bending strength
$\sigma_{\text{beqB}}$	Equivalent bending strength
$t$	Time
$\Delta F/\Delta t$	Rate at which piston force rises
$F^*, p^*, \sigma^*$	Non-dimensional quantities corresponding to $F$ , $p$ and $\sigma$ [see equations (1) to (5)]

## 5 Principle of test method

The square specimen, of side length,  $L$ , and having virtually plain parallel surfaces, is placed loosely on a supporting ring (a circular ring with a radius  $r_2$ ). The specimen is subjected to a load,  $F_{\text{ring}}$ , by means of a loading ring (radius  $r_1$ ), which is arranged concentrically to the supporting ring. In addition, the area,  $A$ , defined by the loading ring  $0 < r < r_1$  is placed under gas pressure,  $p$ , which has a specific relationship with the ring load,  $F_{\text{ring}}$  (see Figure 1).

When the specimen is subjected to the ring load and the associated gas pressure, depending upon the dimensions  $r_1$ ,  $r_2$ ,  $L$ , and  $h$ , a radial tensile stress field, which is sufficiently homogeneous for the test purpose, is developed on the convexly bent surface over the area defined by the loading ring (see [1], [2], [3] of annex B). The tangential tensile stress is equal to the radial tensile stress at the central point ( $r = 0$ ) of the specimen, but decreases as the radius,  $r$ , increases.

Outside the loading ring, the radial and tangential stresses fall sharply towards the edge of the specimen, so that the risk of breakage outside the loading ring is low. On the edge of the specimen itself, the radial stress is zero and the tangential stress is a compressive stress, this being the case on both the concavely and the convexly bent sides of the specimen. The edge of the specimen is thus always under tangential compressive stress (see EN 1288-1).

By increasing the force,  $F$ , and the gas pressure,  $p$ , the tensile stress in the central part of the specimen is increased at a constant rate [see (6.1b)] until breakage, so the origin of the break can be expected to occur in the surface area subjected to maximum tensile stress within the loading ring.

NOTE: With the test apparatus as shown in Figure 1, a force,  $pA$ , acts against the piston force,  $F$ , due to the gas pressure,  $p$ . The force transferred by the loading ring is  $F_{\text{ring}} = F - pA$ . Thus a distinction should be made between the piston force and the ring load.

The bending strength,  $\sigma_{\text{bB}}$ , or equivalent bending strength,  $\sigma_{\text{beqB}}$ , is calculated from the maximum value,  $F_{\text{max}}$ , of the piston force, measured at the time of breakage, and the thickness,  $h$ , of the specimen, taking into account the prescribed dimensions of the specimen and various characteristic material values. This assumes that the gas pressure,  $p$ , follows the piston force,  $F$ , according to the nominal function  $p(F)$ , (see Figure 3).




## 6 Apparatus

### 6.1 Testing machine


The bending test shall be carried out using a suitable bending testing machine, which shall incorporate the following features.

- a) The stressing of the specimen shall be capable of being applied from zero up to a maximum value in a manner which minimizes shock and is stepless.
- b) The stressing device shall be capable of the specified rate of stressing.
- c) The testing machine shall incorporate a load measuring device with a limit of error of  $\pm 2,0$  % within the measuring range.



- 1 Loading ring
- 2 Specimen
- 3 Supporting ring

Figure 1: Basic diagram of test apparatus



- 1 Specimen
- 2 Rigid base plate, preferably made of steel, with supporting ring (radius  $r_2$ )<sup>(1)</sup>
- 3 Rubber profile, adapted to the supporting ring, 3 mm thick, with a hardness ( $40 \pm 10$ ) IRHD (in accordance with ISO 48)
- 4 Rigid loading ring (radius  $r_1$ ), preferably made of steel<sup>(1)</sup>
- 5 Force transmitting component, with a ball mechanism to ensure the force is centred in the loading ring
- 6 Rubber profile, adapted to the loading ring, 3 mm thick with a hardness ( $40 \pm 10$ ) IRHD (in accordance with ISO 48)<sup>(2)</sup>
- 7 Adjustment jaws for centring the specimen<sup>(3)</sup>
- 8 Contact circle of the loading ring
- 9 Contact circle of the supporting ring

NOTE:

- (1) The radius of curvature of the bearing surface of the ring is 5 mm.
- (2) In the case of specimens which are patterned on the loading ring side, a sponge rubber profile approximately 5 mm thick should also be used to ensure an adequate seal for the gas pressure.
- (3) The jaws are removed before the bending test is started, in order that the edge of the specimen is not clamped.

Figure 2: Loading device

## 6.2 Loading device

### 6.2.1 Ring load

The ring load shall be applied using a loading device as shown in Figure 2. The dimensions of the loading device are given in Table 1.

**Table 1: Dimensions for the loading ring and supporting ring**

Loading ring $r_1$ mm	Supporting ring $r_2$ mm	Effective surface area $A$ mm <sup>2</sup>
300 ± 1	400 ± 1	240 000

### 6.2.2 Surface pressure regulator

The loading device for the surface pressure is shown in Figure 2.

The regulator shall be chosen with regard to accuracy and flow rate in such a way that the nominal function,  $p(F)$ , as shown in Figure 3 or Table 3, can be met (see annex A).

### 6.3 Measuring instruments

The following measuring instruments are required:

- a measuring instrument enabling the width of the specimen to be measured to the nearest millimetre;
- a measuring instrument allowing the thickness of the specimen to be measured to the nearest 0,01 mm.

## 7 Sample

### 7.1 Shape and dimensions of the specimens

Square specimens of the dimensions shown in Table 2 shall be used.

The minimum thickness given for the specimens has been calculated in such a way that the effect of the self-weight of the specimen upon the stress distribution can be ignored.

**Table 2: Dimensions of specimens**

Specimen side length $L$ mm	Minimum nominal specimen thickness mm	Average specimen radius (for evaluation) $r_{3m}$ mm
1 000 ± 4	3	600

The following tolerances for the specimens shall be observed.

In the case of specimens with flat surfaces:

- the evenness tolerance shall be 0,3 mm;
- the parallelism tolerance shall be 2 % of the specimen thickness.

In the case of specimens with one or two patterned surfaces:

- the fluctuations of the plate thickness (see 8.3) shall not be more than 4 % and the local deviations from the average thickness (due to the depth of the pattern) shall be a maximum 30 % or 2 mm, whichever is the lower.

## **7.2 Sampling and preparation of specimens**

### **7.2.1 Cutting and handling**

The greatest care shall be taken that the test surface, which will be subsequently subjected to tensile stress, does not come into contact with tools, grinding agents, glass splinters, etc. and also is not damaged during storage.

NOTE 1: In order to preserve specific surface conditions, the test surface can be provided with a protective coating (glued down) during specimen preparation.

NOTE 2: The method of cutting specimens is not significant and no edge processing is necessary.

### **7.2.2 Conditioning**

Protective coatings shall be removed 24 h before the test (see EN 1288-1). The specimen shall be stored in the test environment (see 8.1 and 8.2) for at least 4 h before testing.

### **7.2.3 Examination**

Before the bending strength test, all specimens shall be examined over the test surface area for any faults which are not representative of the quality characteristics of the material tested.

### **7.2.4 Adhesive film**

To hold together the fragments, an adhesive film shall be fixed to the side of the specimen facing the loading ring. This facilitates location of the fracture origin and measurement of the specimen thickness.

## **7.3 Number of specimens**

The number of specimens to be tested shall be determined depending on the confidence limits required, especially with regard to estimating the extremes of the strength distribution (see EN 1288-1 for a discussion of numbers of specimens).

## 8 Procedure

### 8.1 Temperature

The coaxial ring bending test shall be carried out at a temperature of  $(23 \pm 5)$  °C. During the test, the temperature of the specimen shall be kept constant to 1 °C, in order to avoid the development of thermal stresses.

### 8.2 Humidity

The coaxial ring bending test shall be carried out at a relative humidity between 40 % and 70 %.

### 8.3 Thickness measurement

Since the nominal pressure function,  $p(F)$ , in accordance with Figure 3 or Table 3, is dependent upon the specimen thickness,  $h$ , this shall be determined before starting the test.

For this purpose, the thickness shall be measured at a minimum of eight points on the edge of the specimen. For specimens with one or two ornamental surfaces, both the plate thickness and the core thickness shall be measured. The average is taken from all these measured values.

The value obtained in this way for the specimen thickness or the equivalent specimen thickness,  $h$ , is used to determine the nominal pressure function,  $p(F)$ . By measuring the thickness on the edge of the specimen, undesirable damage to the surface caused by measuring tools does not affect the fracture behaviour.

### 8.4 Base plate

The base plate is centred by moving down the force transmitting cone (without the loading ring and specimen) into the adjusting cone (see Figure 2). The base plate shall be fixed in this position. Glass splinters and other hard and sharp-edged particles shall be cleaned from the supporting ring. Damage to the supporting ring shall be eliminated.

### 8.5 Positioning of specimen and loading ring

The specimen is positioned with the surface to be tested downwards. The loading ring, from which glass splinters and other hard and sharp-edged particles have been removed, is placed on the upper side of the specimen and centred. The rubber connection attached to the loading ring shall be checked for its sealing effect and if necessary replaced. Damage to the loading ring shall be eliminated.

## 8.6 Load application

The piston force,  $F$ , and the gas pressure,  $p$ , shall be increased continuously until the specimen breaks. The inter-relationship,  $p(F)$ , to be maintained during the loading, shall be determined from the non-dimensional representation in Figure 3 (curve  $p^*$ ) or Table 3. The following relationships exist between the non-dimensional parameters,  $p^*$  and  $F^*$ , and the values  $p$  and  $F$ .

$$p = p^* \frac{Eh^4}{r_{3m}^4 (1 - \mu^2)} \quad (1)$$

$$F = F^* \frac{Eh^4}{r_{3m}^2 (1 - \mu^2)} \quad (2)$$

The piston force,  $F$ , and the gas pressure,  $p$ , shall be monitored up to breakage of the specimen, to check whether the nominal function,  $p(F)$ , meets that shown in Figure 3 or Table 3.

NOTE: Only if the nominal pressure function,  $p(F)$ , is followed, is a uniform radial tensile stress distribution developed on the convexly bent surface in that area of the specimen defined by the loading ring. Keeping the gas pressure,  $p$ , in line with the piston force,  $F$ , may be carried out manually by means of a control valve, but it is recommended that the gas pressure,  $p$ , be controlled automatically as a function of the piston force,  $F$ . It is permissible to linearize the function  $p^*(F^*)$  given in Figure 3 for loads close to fracture. A suitable arrangement is described in annex A.

The maximum force,  $F_{\max}$ , and the associated gas pressure,  $p_{\max}$ , shall be measured.

From these two values, the stress at break,  $\sigma_{\text{bB}}$  or  $\sigma_{\text{beqB}}$ , in  $\text{N/mm}^2$ , shall be determined in accordance with Figure 3 or Table 3 (see 9.2).

## 8.7 Loading rate

The increase with time of the piston force and the associated gas pressure shall be chosen in such a way that the radial tensile stress in the centre of the specimen increases at a rate of  $(2 \pm 0,4) \text{ N/mm}^2 \cdot \text{s}$  until the specimen breaks. Since there is no linear relationship between the stress and the piston force, the permissible loading rate shall be determined in accordance with Figure 3 or Table 3.

NOTE 1: A preliminary test is recommended in order to determine the rate of loading.

NOTE 2: Since the breakage stress is most dependent on the loading rate in the few seconds before fracture, it is permissible to set that loading rate required at loads close to fracture constant over the entire test.

## 8.8 Location of the origin

The location of the origin of the fracture (see [4] of annex B) shall be determined from the fragments. The position of the origin of the fracture “inside or outside the contact circle of the loading ring” shall be determined for every specimen.

NOTE: After fracture, further thickness measurements, for control purposes, can be made on fragments from the centre of the specimen bounded by the loading ring contact circle, preferably as close to the fracture origin as possible.

## 8.9 Assessment of residual stresses

If the specimens are considered to be free from inherent stresses, (that is, they are of annealed glass), this condition shall be examined photo-elastically, in the case of transparent glasses, on specimens or suitable fragments. Stress-free specimens placed between cross-polarized polarizing filters shall not show any significant brightness variations when viewed through the cross-section over an optical path length of 5 mm.

## 9 Evaluation

### 9.1 Limitation of the evaluation

For evaluation purposes, only those specimens shall be considered in which the origin of the fracture lies within the area defined by the loading ring.

### 9.2 Calculation of bending strength

The bending strength,  $\sigma_{bB}$ , or equivalent bending strength,  $\sigma_{beqB}$ , associated with the fracture force,  $F_{max}$ , and the associated gas pressure,  $p_{max}(F_{max})$ , is determined from the non-dimensional representation in Figure 3 (curve  $\sigma^*$ ) or Table 3 taking into account the specimen thickness,  $h$ . For this purpose, the measured variables,  $F_{max}$  and  $p_{max}(F_{max})$ , are converted with the aid of the equations (3) and (4) into the corresponding non-dimensional factors  $F_{max}^*$  and  $p_{max}^*$ .

$$F_{max}^* = F_{max} \frac{r_{3m}^2 (1 - \mu^2)}{Eh^4} \quad (3)$$

$$p_{max}^* = p_{max}(F_{max}) \frac{r_{3m}^4 (1 - \mu^2)}{Eh^4} \quad (4)$$

The non-dimensional fracture stress,  $\sigma_{bB}^*$ , shall be determined from these values using Figure 3 (curve  $\sigma^*$ ) or Table 3 and then converted into the bending strength,  $\sigma_{bB}$ , in accordance with equation (5).

$$\sigma_{bB} = \sigma_{bB}^* \frac{Eh^2}{r_{3m}^2 (1-\mu^2)} \quad (5)$$




Figure 3: Relationship between the virtually uniform radial tensile stress,  $\sigma_{rad}^*$ , the nominal gas pressure,  $p^*(F^*)$ , and the piston force,  $F^*$ , in a non-dimensional representation, (where  $r_1:r_2 = 1:1,33$  and  $r_2:r_{3m} = 1:1,5$ )



**Table 3: Relationship between the virtually uniform radial tensile stress,  $\sigma^*_{\text{rad}}$ , the nominal gas pressure,  $p^*(F^*)$ , and the piston force,  $F^*$ , in a non-dimensional representation, (where  $r_1:r_2 = 1:1,33$  and  $r_2:r_{3m} = 1:1,5$ )**

$F^*$	$p^*(F^*)$	$\sigma^*_{\text{rad}}$	$F^*$	$p^*(F^*)$	$\sigma^*_{\text{rad}}$
5	0	1,00	210	205,0	16,55
10	0,5	2,05	220	219,0	16,95
15	1,8	3,05	230	231,0	17,40
20	3,5	3,85	240	245,0	17,80
25	6,0	4,60	250	259,0	18,20
30	9,0	5,25	260	272,0	18,60
35	12,5	5,85	270	285,0	19,00
40	16,5	6,40	280	299,0	19,35
45	20,0	6,90	290	312,0	19,75
50	24,0	7,35	300	326,0	20,15
60	32,5	8,20	320	351,0	20,85
70	41,2	8,90	340	377,0	21,55
80	51,0	9,55	360	404,0	22,20
90	61,5	10,15	380	430,0	22,85
100	72,5	10,80	400	456,0	23,55
110	83,5	11,45	420	484,0	24,25
120	94,7	12,05	440	510,0	24,95
130	106,0	12,60	460	536,0	25,65
140	117,0	13,15	480	563,0	26,35
150	129,0	13,70	500	589,0	27,00
160	141,0	14,20			
170	153,0	14,65			
180	166,0	15,15			
190	178,0	15,60			
200	191,0	16,05			

## 10 Test report

With reference to this standard, the test report shall contain the following information:

- a) Type and name of glass;
- b) Pre-treatment and surface condition of the tested specimen surface including the sequence of treatment stages. In the case of specimens with one patterned surface, the surface which is placed under tensile stress (flat or patterned side) shall be indicated;
- c) Inherent stress of the specimen, annealed or prestressed glass, including nature and if possible degree of prestressing;
- d) Number of specimens;

e) For each specimen, the following information:

- 1) Thickness,  $h$ , in mm, to the nearest 0,05 mm, in the case of specimens with flat surfaces; maximum thickness (plate thickness), minimum thickness (core thickness) and average thickness,  $h$ , in mm, to the nearest 0,05 mm, in the case of specimens with one or two patterned surfaces;
- 2) Bending strength,  $\sigma_{bB}$  or  $\sigma_{beqB}$ , in  $\text{N/mm}^2$ , rounded off to 0,1  $\text{N/mm}^2$ , of each specimen broken in accordance with 9.1;
- 3) Time to breakage in seconds to the nearest 1 s;

No average for the measured results shall be given;

f) Number of specimens not broken in accordance with 9.1;


g) Any deviation from this standard which may have affected the results.

## Annex A (informative)

### Example of a device for keeping the gas pressure, $p$ , in line with the piston force, $F$

If the gas pressure within the loading ring is applied in accordance with the relevant loading specification (taking the plate and ring geometries into account), the testing procedure corresponds to that of conventional bending tests, where knowledge of the force triggering off the fracture is sufficient for determining fracture stress. When designing the gas pressure control system (the gas pressure depends on the piston force applied), it was the major concern to develop a device which ensured that it was easy to apply in spite of varying loading specifications.

If a typical plot of the nominal gas pressure against piston force is considered (see Figure A.1), it is apparent that the curve runs almost linearly in the middle and upper regions, and it can be approximated by a straight line without any great error. The slope of a straight line and its zero point displacement can be set with simple electrical devices, whilst copying a non-linear function is more complicated and costly. As far as ease of operation is concerned, a linear approximation function brings considerable advantages for control of the system. A linearized loading specification obtained in this way, however, no longer leads to optimized stress distributions in the lower region of the curve, where the deviation from the nominal loading specification becomes greater. As long as the stresses generated in this region of the curve do not reach values which are critical for the initiation of fracture, this disadvantage is insignificant.



**Figure A.1: Typical plot of force against pressure**


In cases where the values,  $p(F)$ , necessary for a series of measurements, lie in the bent part of the curve (see Figure A.1), linearization on the basis of the least square method using the values in Table 3 can be carried out. This assumes that estimated values for the maximum and minimum fracture stresses, which occur in the series of measurements, are known. Linearization is only permissible in a region in which the deviation between the linearized function and the nominal function remains less than 5 % of the respective

nominal value.

Given these considerations, the electrical part of the control unit (see Figure A.2) was developed and tested. An input voltage proportional to the piston force is sent from the load cell to an amplifier. The output of this amplifier is connected to the input of a function generator which supplies a current proportional to the respective piston force to control a current-pressure transmitter. The electrical signal is changed by the transmitter into a pneumatic signal, which is subsequently converted into the pressure range necessary for the test according to the linearized function,  $p(F)$ .

In principle, it is also possible to copy the exact nominal function,  $p(F)$ , by means of a microprocessor-controlled gas pressure regulator. By this means a higher degree of accuracy can be achieved, particularly in the case of specimens with very low fracture stresses, but at a considerably higher expenditure.

In theory, any gas available may be chosen as the medium. For cost and safety reasons, however, the use of compressed air is recommended.



- 1 Application of piston force
- 2 Load cell
- 3 Pressure recorder
- 4 Measuring amplifier (pressure)
- 5 X-Y recorder or memory units
- 6 Measuring amplifier (force)
- 7 Force-current converter or microprocessor controlled gas pressure regulator
- 8 Quick-fitting coupling
- 9 Filter reducing valve
- 10 Reducing valve
- 11 Gas pressure memory
- 12 Current-pressure transmitter with pressure transducer
- 13 Measuring and control system

**Figure A.2: Schematic diagram of the control system**

## Annex B (informative)

### Bibliography

- [1] Schmitt, R. W.: Die Doppelringmethode mit überlagertem Gasdruck als Prüfverfahren zur Bestimmung der Bruchspannungen von großformatigen ebenen Glasplatten kleiner Dicke. (The double ring method with super-imposed gas pressure as a testing procedure for determining the stress at break of large-sized flat sheets of glass of a small thickness.)

Diplomarbeit am Institut für Maschinenelemente und Maschinengestaltung (Thesis at the Institute for Machinery Components and Machine Design), Leiter: Professor Dr. H. Peeken, RWTH Aachen, 1982.

- [2] Schmitt, R. W.: Entwicklung eines Prüfverfahrens zur Ermittlung der Biegefestigkeit von Glas und Aspekte der statistischen Behandlung der gewonnenen Messwerte. (Development of a testing procedure for the determination of the bending strength of glass and some aspects of the statistical evaluation of test results.)

Diss. RWTH Aachen, 1987.

- [3] Blank, K.; Schmitt, R. W.; Troeder, Chr.: Ein modifiziertes Doppelringverfahren zur Bestimmung der Biegezugfestigkeit grossformatiger Glasplatten. (A modified coaxial-ring-bending method for testing the bending strength of large glass plates.)

Glastechn. Ber. 56K (1983), volume 1, pp. 414-419 (Vortrag auf dem 13 Internationalen Glas-Kongress, Hamburg 1983)

- [4] Kerkhof, F.: Bruchvorgänge in Gläsern. (Fracture Processes in Glass.)

Deutsche Glastechnische Gesellschaft, Frankfurt/Main 1970, p. 209 ff.



---

## BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

### Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.