

Adhesives for tiles — Determination of wetting capability

The European Standard EN 1347:2007 has the status of a
British Standard

ICS 83.180; 91.100.10

National foreword

This British Standard is the UK implementation of EN 1347:2007. It supersedes BS EN 1347:1999 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee B/539, Ceramic tiles and other rigid tiling.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 December 2007

© BSI 2007

ISBN 978 0 580 57397 2

Amendments issued since publication

Amd. No.	Date	Comments

English Version

Adhesives for tiles - Determination of wetting capability

Colles à carrelage - Détermination du pouvoir mouillant

Mörtel und Klebstoffe für Fliesen und Platten - Bestimmung der Benetzungsfähigkeit

This European Standard was approved by CEN on 11 June 2007.

CEN members are bound to comply with the CEN/GENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Sampling	4
4 Test conditions	4
5 Test materials and apparatus	4
5.1 General.....	4
5.2 Glass plates	4
5.3 Concrete slab	4
5.4 Notched trowel	5
5.5 Weight	5
6 Mixing of adhesive.....	5
7 Procedure	5
8 Test report	6

Foreword

This document (EN 1347:2007) has been prepared by Technical Committee CEN/TC 67 “Ceramic tiles”, the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2008, and conflicting national standards shall be withdrawn at the latest by February 2008.

This document supersedes EN 1347:1996.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This European Standard specifies the method for the determination of the wetting capability of ceramic tile adhesives.

This European Standard is applicable to all ceramic tile adhesives for internal or external tile installations on walls and floors.

This European Standard does not contain performance requirements or recommendations for the design and installation of ceramic tiles.

NOTE Ceramic tile adhesives can also be used for other types of tiles (natural and agglomerated stones etc.), if they do not adversely affect the stones.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 196-1:2005, *Method of testing cement — Part 1: Determination of strength*

EN 1067, *Adhesives — Examination and preparation of samples for testing*

EN 1323, *Adhesives for tiles — Concrete slabs for test*

EN ISO 15605, *Adhesives — Sampling (ISO 15605:2000)*

3 Sampling

Take a sample of at least 2 kg of the adhesive in accordance with EN ISO 15605 and EN 1067.

4 Test conditions

Standard conditions shall be (23 ± 2) °C and (50 ± 5) % R.H. and a speed of air in the testing area less than 0,2 m/s.

5 Test materials and apparatus

5.1 General

Condition all test materials (adhesive etc.) for at least 24 h under standard conditions. The adhesive to be tested shall be within its shelf life, where this is specified.

5.2 Glass plates

Clean, dry glass plates of dimensions (100 ± 1) mm \times (100 ± 1) mm \times $(6 \pm 0,5)$ mm, with ground edges.

5.3 Concrete slab

The concrete slab shall comply with EN 1323.

5.4 Notched trowel

A notched trowel having 6 mm × 6 mm notches at 12 mm centres.

5.5 Weight

A mass capable of exerting a force of $(50 \pm 0,5)$ N with a cross sectional area of less than (100 ± 1) mm × (100 ± 1) mm.

6 Mixing of adhesive

The amounts of water and/or liquid admix required for preparing the adhesive shall be as stated by the manufacturer in parts by mass (i.e. liquid to dry powder). If a range of values is given, the average shall be used.

Prepare a minimum quantity of 2 kg of the adhesive in a mixer of the type described in 4.4 of EN 196-1:2005, using the slow speed settings, (140 ± 5) rpm and (62 ± 5) rpm planetary movement.

Carry out the following procedure:

- pour the liquid into the pan;
- scatter the dry powder over the liquid;
- mix for 30 s;
- take out the mixing paddle;
- scrape down the paddle and pan within 1 min;
- replace the paddle and mix for 1 min.

If required, let the adhesive mature in accordance with the manufacturer's instructions, followed by a further mixing for 15 s.

In the case of ready-to-use dispersion adhesives or reaction resin adhesives follow the manufacturer's instructions.

7 Procedure

Apply a thin layer of the adhesive, mixed in accordance with Clause 6, to the concrete slab (5.3) with a straight edge trowel. Then apply a thicker layer and comb with a notched trowel (5.4).

Hold the trowel at an angle of approximately 60° to the substrate at a right angle to one edge of the slab and drawn across the slab parallel to that edge (in a straight line).

Place the glass plates on the adhesive immediately and, after 10 min, 20 min and 30 min, load each plate with $(50 \pm 0,5)$ N for 30 s. Care shall be taken to align the adhesive ribs parallel with the edge of the glass plate, ensuring that the outer rib is flush with one edge of the glass plate.

Determine the contact surface between the combed adhesive layer and the glass plate in terms of the percentage of the total area of the glass plate (e.g. by planimetry).

Each test requires three glass plates.

EN 1347:2007 (E)

Report the results in percent.

8 Test report

The test report shall provide the following information:

- a) title, number and date of this European Standard, i.e. EN 1347:2007;
- b) place, date and time of sampling;
- c) type of adhesive, commercial designation and manufacturer;
- d) identification of the test sample;
- e) handling and storage of samples before testing;
- f) test conditions;
- g) date of testing;
- h) amount of water or liquid used for preparing the adhesive;
- i) wetting capability (%) for each time interval (individual and mean values);
- j) any other factor that could have influenced the result.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.